Glass 8229

Technical Data

Glass Type/Application	Intermediate sealing glass. Sealing to glass 8228 and glass 8230.		
Physical Data (approx. value)	Coefficient of mean linear thermal expansion α(20°C; 300°C) (ISO 7991)	2.0	$10^{-6}K^{-1}$
	Transformation temperature T_g (ISO 7884-8)	600	°C
	Glass temperature at viscosity η in dPa·s		
	10^{13} (annealing point) (ISO 7884-4)	637	°C
	$10^{7.6}$ (softening point) (ISO 7884-3)	930	°C
	10^{4} (working point) (ISO 7884-2)	1440	°C
	Stress-optical coefficient K (DIN 52314)	-	$10^{-6}mm^2 \cdot N^{-1}$
	Density ρ at 25°C	2.17	$g \cdot cm^{-3}$
	Modulus of elasticity E (Young's modulus)	-	$10^3 N \cdot mm^{-2}$
	Poisson's ratio μ	-	
	Thermal conductivity λ_w at 90°C	-	$W \cdot m^{-1} \cdot K^{-1}$
	Log of the electric volume resistivity (Ω·cm)		
	at 250°C	-	
	at 350°C	-	
	t_{k100} (DIN 52326)	350	°C
	Dielectric constant ε for 1 MHz at 25°C	-	
	Dielectric loss factor tan d for 1 MHz at 25°C	-	10^{-4}
	Refractive index n_d (λ = 587.6 nm)	-	
Chemical Resistance	Hydrolytic resistance (ISO 719)	Class	-
	Acid resistance (DIN 12116)	Class	-
	Alkali resistance (ISO 695)	Class	-

The heavy metal content for the elements lead, cadmium, mercury and hexavalent chromium is below 100 ppm.

SCHOTT