

**SCHOTT**  
glass made of ideas



# Optical Glass

Datasheets

# Table of Content

Glass type	Glass type	Glass type	Glass type
<b>FK</b>	<b>SK</b>	<b>F</b>	<b>SF</b>
FK5HTi	N-SK2	F2	N-SF1
N-FK5 <sup>1)</sup>	N-SK2HT	F2HT	N-SF2
N-FK51A <sup>1)</sup>	N-SK4	F2HTi	N-SF4
N-FK58	N-SK5	F5	N-SF5
	N-SK5HTi	N-F2	N-SF6
<b>PK</b>	N-SK11		N-SF6HT
N-PK51 <sup>1)</sup>	N-SK14	<b>BASF</b>	N-SF6HTultra
N-PK52A <sup>1)</sup>	N-SK16	N-BASF2	N-SF8
	P-SK57 <sup>1)</sup>	N-BASF64	N-SF10
<b>PSK</b>	P-SK57Q1 <sup>1)</sup>		N-SF11
N-PSK3	P-SK58A <sup>1)</sup>	<b>LAF</b>	N-SF14
N-PSK53A	P-SK60 <sup>1)</sup>	N-LAF2	N-SF15
		N-LAF7	N-SF57
<b>BK</b>	<b>KF</b>	N-LAF21	N-SF57HT
SCHOTT N-BK7 <sup>®</sup>	N-KF9	N-LAF33 <sup>1)</sup>	N-SF57HTultra
N-BK7HT		N-LAF34	N-SF66
N-BK7HTi	<b>SSK</b>	N-LAF35	P-SF8 <sup>1)</sup>
N-BK10	N-SSK2	P-LAF37 <sup>1)</sup>	P-SF68 <sup>1)</sup>
P-BK7 <sup>1)</sup>	N-SSK5		P-SF69 <sup>1)</sup>
	N-SSK8		SF1
<b>K</b>		<b>LASF</b>	SF2
K7	<b>LAK</b>	LASF35	SF3
K10	N-LAK7	N-LASF9	SF4
N-K5	N-LAK8	N-LASF9HT	SF5
N-ZK7	N-LAK9	N-LASF31A	SF6
N-ZK7A	N-LAK10	N-LASF40	SF6HT
	N-LAK12	N-LASF41	SF10
<b>BAK</b>	N-LAK14	N-LASF43	SF11
N-BAK1	N-LAK21	N-LASF44	SF56A
N-BAK2	N-LAK22	N-LASF45	SF57 <sup>1)</sup>
N-BAK4	N-LAK28	N-LASF45HT	SF57HTultra <sup>1)</sup>
N-BAK4HT	N-LAK33B	N-LASF46A	
	N-LAK34	N-LASF46B <sup>1)</sup>	<b>KZFS</b>
<b>BAF</b>	P-LAK35 <sup>1)</sup>	N-LASF55	N-KZFS11 <sup>1)</sup>
N-BAF4		P-LASF47 <sup>1)</sup>	N-KZFS2 <sup>1)</sup>
N-BAF10	<b>LLF</b>	P-LASF50 <sup>1)</sup>	N-KZFS4 <sup>1)</sup>
N-BAF51	LLF1	P-LASF51 <sup>1)</sup>	N-KZFS4HT <sup>1)</sup>
N-BAF52	LLF1HTi		N-KZFS5 <sup>1)</sup>
			N-KZFS8 <sup>1)</sup>
<b>BALF</b>	<b>LF</b>		<b>Radiation resistant</b>
N-BALF4	LF5		BK7G18
N-BALF5	LF5HTi		F2G12
			K5G20
			LAK9G15
			LF5G19
			SF6G05

<sup>1)</sup> Glass suitable for Precision Molding

## Explanations

### Refractive indices

The refractive indices  $n$  are listed for a maximum of 23 wavelengths in the range between 248.2 nm and 2325.4 nm.

### Constants of the dispersion formula

From the Sellmeier dispersion formula

$$n^2(\lambda) - 1 = \frac{B_1 \lambda^2}{\lambda^2 - C_1} + \frac{B_2 \lambda^2}{\lambda^2 - C_2} + \frac{B_3 \lambda^2}{\lambda^2 - C_3}$$

the refractive indices for any wavelength within the range from the near UV to 2.3  $\mu\text{m}$  can be calculated with the help of the constants  $B_1, B_2, B_3,$  and  $C_1, C_2, C_3$ .

When calculating the refractive index using the Sellmeier coefficients from the SCHOTT data sheets, the wavelength  $\lambda$  needs to be entered in units of  $\mu\text{m}$ .

### Constants of the formula $dn/dT$

The temperature dependence of the refractive index can be calculated using the following formula:

$$\frac{dn_{\text{abs}}(\lambda, T)}{dT} = \frac{n^2(\lambda, T_0) - 1}{2 n(\lambda, T_0)} \left( D_0 + 2 D_1 \Delta T + 3 D_2 \Delta T^2 + \frac{E_0 + 2 E_1 \Delta T}{\lambda^2 - \lambda_{\text{TK}}^2} \right)$$

The constants are valid for a temperature range from  $-100^\circ\text{C}$  to  $+140^\circ\text{C}$  and a wavelength range from 0.365  $\mu\text{m}$  to 1.014  $\mu\text{m}$ . The temperature coefficients in the data sheets are guideline values.

### Temperature coefficient of refraction

$\Delta n_{\text{rel}} / \Delta T$  referring to air at normal pressure 1013.3 mbar

$\Delta n_{\text{abs}} / \Delta T$  referring to vacuum

### Internal transmittance $\tau_i$

The internal transmittance in the wavelength range between 250 nm and 2500 nm is listed for thickness of 10 and 25 mm. The internal transmittance and color code listed in the data sheet represent median values from several melts of one glass type. For HT and HTultra grade, the internal transmittance in the visible spectrum includes guaranteed minimum values.

### Color code

The color code lists the wavelength  $\lambda_{80}$  and  $\lambda_5$  at which the transmittance is 0.80 and 0.05 at 10 mm thickness. The values are rounded off to 10 nm and denoted by eliminating the first digit. For high index glass types with  $nd > 1.83$ , the data of the color codes (marked by \*) refers to the transmittance values 0.70 and 0.05 ( $\lambda_{70}$  and  $\lambda_5$ ).

### Relative partial dispersion

The relative partial dispersions  $P_{xy}$  and  $P'_{xy}$  for the wavelengths  $x$  and  $y$  are derived from the equations.

$$P_{xy} = \frac{n_x - n_y}{n_F - n_C} \quad \text{und} \quad P'_{xy} = \frac{n_x - n_y}{n_{F'} - n_{C'}}$$

### Deviation of the relative partial dispersion from the "normal line" $\Delta P$

The term  $\Delta P_{xy}$  quantitatively describes a deviation relation of the dispersion from the "normal glasses".

## Other characteristics

$\alpha_{-30/+70}$	= The coefficient of thermal expansion in the temperature range between $-30^{\circ}\text{C}$ und $+70^{\circ}\text{C}$ in $10^{-6}/\text{K}$
$\alpha_{20/300}$	= The coefficient of linear thermal expansion in the temperature range between $+20^{\circ}\text{C}$ und $+300^{\circ}\text{C}$ in $10^{-6}/\text{K}$
Tg	= Transformation temperature in $^{\circ}\text{C}$
$T_{10^{13.0}}$	= Temperature of the glass in $^{\circ}\text{C}$ at a viscosity of $10^{13}$ dPa·s
$T_{10^{7.6}}$	= Temperature of the glass in $^{\circ}\text{C}$ at a viscosity of $10^{7.6}$ dPa·s
$c_p$	= average specific heat capacity in $\text{J}/(\text{g}\cdot\text{K})$
$\lambda$	= Thermal conductivity in $\text{W}/(\text{m}\cdot\text{K})$
AT*	= Yield point/sag temperature in $^{\circ}\text{C}$
$\rho$	= Density in $\text{g}/\text{cm}^3$
E	= Elasticity modulus in $10^3$ N/mm <sup>2</sup>
$\mu$	= Poisson's ratio
K	= Stress optical coefficient in $10^{-6}$ mm <sup>2</sup> /N
HK	= Knoop hardness
HG	= Grindability class (ISO 12844)
Abrasion Aa*	= Grindability according to JOGIS**
CR	= Climatic resistance Resistance to moisture in the air expressed in CR classes 1 (high) to 4 (low).
FR	= Stain resistance Resistance to stain formation expressed in FR classes 0 (high) to 5 (low).
SR	= Acid resistance Resistance to acid solutions expressed in SR classes 1 (high) to 4 (low) and 51 to 53 (very low).
AR	= Alkali resistance Resistance to alkaline solutions expressed in AR classes 1 (high) to 4 (low).
PR	= Phosphate resistance Resistance to alkaline phosphate containing solutions expressed in PR classes 1 (high) to 4 (low).
SR-J*	= Acid resistance class according to JOGIS**
WR-J*	= Water resistance class according to JOGIS**

\* only precision molding glasses

\*\* JOGIS = Japanese Optical Glass Industrial Standards

## FK5HTi 487705.245

$n_d = 1.48748$   
 $n_e = 1.48913$

$v_d = 70.47$   
 $v_e = 70.29$

$n_F - n_C = 0.006918$   
 $n_{F'} - n_{C'} = 0.006959$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.46180
$n_{1970.1}$	1970.1	1.46738
$n_{1529.6}$	1529.6	1.47312
$n_{1060.0}$	1060.0	1.47855
$n_t$	1014.0	1.47912
$n_s$	852.1	1.48137
$n_r$	706.5	1.48409
$n_C$	656.3	1.48534
$n_{C'}$	643.8	1.48568
$n_{632.8}$	632.8	1.48600
$n_D$	589.3	1.48742
$n_d$	587.6	1.48748
$n_e$	546.1	1.48913
$n_F$	486.1	1.49225
$n_{F'}$	480.0	1.49264
$n_g$	435.8	1.49591
$n_h$	404.7	1.49892
$n_i$	365.0	1.50398
$n_{334.1}$	334.1	1.50935
$n_{312.6}$	312.6	1.51423
$n_{296.7}$	296.7	1.51861
$n_{280.4}$	280.4	1.52409
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	0.909362180
$B_2$	0.279077054
$B_3$	0.891813298
$C_1$	0.005201425
$C_2$	0.0158938446
$C_3$	95.91094480

### Constants of Formula for $dn/dT$

$D_0$	-7.47E-06
$D_1$	1.58E-08
$D_2$	-1.23E-11
$E_0$	3.58E-07
$E_1$	4.03E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.164

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-1.6	-1.2	-0.9	-3.6	-3.3	-3.0
+20/+40	-1.5	-1.1	-0.7	-2.7	-2.4	-2.0
+60/+80	-1.3	-0.8	-0.4	-2.3	-1.8	-1.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.680	0.390
2325	0.830	0.630
1970	0.971	0.930
1530	0.986	0.965
1060	0.999	0.998
700	0.999	0.997
660	0.998	0.995
620	0.998	0.994
580	0.998	0.995
546	0.998	0.995
500	0.998	0.994
460	0.998	0.995
436	0.998	0.996
420	0.999	0.997
405	0.999	0.997
400	0.999	0.997
390	0.999	0.997
380	0.998	0.996
370	0.999	0.996
365	0.998	0.996
350	0.998	0.994
334	0.996	0.989
320	0.992	0.979
310	0.983	0.958
300	0.959	0.900
290	0.900	0.760
280	0.760	0.510
270	0.550	0.220
260	0.300	0.050
250	0.120	0.000

### Color Code

$\lambda_{80} / \lambda_5$  29/25

### Remarks

i-line glass

### Relative Partial Dispersion P

$P_{s,t}$	0.3253
$P_{C,s}$	0.5742
$P_{d,C}$	0.3098
$P_{e,d}$	0.2388
$P_{g,F}$	0.5288
$P_{i,h}$	0.7315

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3234
$P'_{C,s}$	0.6203
$P'_{d,C'}$	0.2584
$P'_{e,d}$	0.2374
$P'_{g,F'}$	0.4703
$P'_{i,h}$	0.7271

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0202
$\Delta P_{C,s}$	0.0070
$\Delta P_{F,e}$	0.0001
$\Delta P_{g,F}$	0.0036
$\Delta P_{i,g}$	0.0321

### Chemical Properties

CR	2
FR	1
SR	4
AR	2
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.0
$T_g$ [°C]	466
$T_{10}^{13}$ [°C]	469
$T_{10}^{7.6}$ [°C]	672
$c_p$ [J/(g·K)]	0.808
$\lambda$ [W/(m·K)]	0.925
$\rho$ [g/cm <sup>3</sup> ]	2.45
$E$ [ $10^3$ N/mm <sup>2</sup> ]	62
$\mu$	0.232
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.91
$HK_{0.1/20}$	520

## N-FK5 487704.245

$n_d = 1.48749$   
 $n_e = 1.48914$

$v_d = 70.41$   
 $v_e = 70.23$

$n_F - n_C = 0.006924$   
 $n_{F'} - n_{C'} = 0.006965$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.46181
$n_{1970.1}$	1970.1	1.46738
$n_{1529.6}$	1529.6	1.47312
$n_{1060.0}$	1060.0	1.47855
$n_t$	1014.0	1.47912
$n_s$	852.1	1.48137
$n_r$	706.5	1.48410
$n_C$	656.3	1.48535
$n_{C'}$	643.8	1.48569
$n_{632.8}$	632.8	1.48601
$n_D$	589.3	1.48743
$n_d$	587.6	1.48749
$n_e$	546.1	1.48914
$n_F$	486.1	1.49227
$n_{F'}$	480.0	1.49266
$n_g$	435.8	1.49593
$n_h$	404.7	1.49894
$n_i$	365.0	1.50401
$n_{334.1}$	334.1	1.50939
$n_{312.6}$	312.6	1.51428
$n_{296.7}$	296.7	1.51867
$n_{280.4}$	280.4	1.52415
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	0.844309338
$B_2$	0.344147824
$B_3$	0.910790213
$C_1$	0.004751120
$C_2$	0.0149814849
$C_3$	97.86002930

### Constants of Formula for $dn/dT$

$D_0$	-7.24E-06
$D_1$	1.58E-08
$D_2$	-9.51E-12
$E_0$	3.51E-07
$E_1$	4.61E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.156

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-1.5	-1.2	-0.9	-3.5	-3.2	-2.9
+20/+40	-1.4	-1.0	-0.6	-2.6	-2.3	-2.0
+60/+80	-1.2	-0.7	-0.3	-2.2	-1.8	-1.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.680	0.380
2325	0.830	0.630
1970	0.971	0.930
1530	0.986	0.965
1060	0.999	0.998
700	0.998	0.995
660	0.996	0.991
620	0.996	0.990
580	0.996	0.991
546	0.996	0.991
500	0.996	0.989
460	0.996	0.990
436	0.997	0.992
420	0.997	0.993
405	0.998	0.994
400	0.998	0.994
390	0.998	0.994
380	0.996	0.991
370	0.997	0.992
365	0.997	0.992
350	0.995	0.988
334	0.991	0.977
320	0.980	0.950
310	0.954	0.890
300	0.900	0.760
290	0.760	0.500
280	0.500	0.180
270	0.220	0.020
260	0.060	0.000
250	0.000	

### Color Code

$\lambda_{80} / \lambda_5$  30/26

### Remarks

suitable for precision molding

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.3252
$P_{C,s}$	0.5740
$P_{d,C}$	0.3097
$P_{e,d}$	0.2388
$P_{g,F}$	0.5290
$P_{i,h}$	0.7319

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3232
$P'_{C,s}$	0.6201
$P'_{d,C'}$	0.2584
$P'_{e,d}$	0.2374
$P'_{g,F'}$	0.4704
$P'_{i,h}$	0.7276

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0202
$\Delta P_{C,s}$	0.0070
$\Delta P_{F,e}$	0.0001
$\Delta P_{g,F}$	0.0036
$\Delta P_{i,g}$	0.0322

### Chemical Properties

CR	2
FR	1
SR	4
AR	2
PR	2.3
SR-J	5
WR-J	4

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.0
$T_g$ [°C]	466
$T_{10}^{13}$ [°C]	469
$T_{10}^{7.6}$ [°C]	672
$c_p$ [J/(g·K)]	0.808
$\lambda$ [W/(m·K)]	0.925
AT [°C]	557
$\rho$ [g/cm <sup>3</sup> ]	2.45
E [ $10^3$ N/mm <sup>2</sup> ]	62
$\mu$	0.232
K [ $10^{-6}$ mm <sup>2</sup> /N]	2.91
HK <sub>0.1/20</sub>	520
HG	3
Abrasion Aa	109

## N-FK51A 487845.368

$n_d = 1.48656$

$v_d = 84.47$

$n_F - n_C = 0.005760$

$n_e = 1.48794$

$v_e = 84.07$

$n_F - n_C = 0.005804$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.46958
$n_{1970.1}$	1970.1	1.47271
$n_{1529.6}$	1529.6	1.47608
$n_{1060.0}$	1060.0	1.47959
$n_t$	1014.0	1.47999
$n_s$	852.1	1.48165
$n_r$	706.5	1.48379
$n_C$	656.3	1.48480
$n_{C'}$	643.8	1.48508
$n_{632.8}$	632.8	1.48534
$n_D$	589.3	1.48651
$n_d$	587.6	1.48656
$n_e$	546.1	1.48794
$n_F$	486.1	1.49056
$n_{F'}$	480.0	1.49088
$n_g$	435.8	1.49364
$n_h$	404.7	1.49618
$n_i$	365.0	1.50046
$n_{334.1}$	334.1	1.50501
$n_{312.6}$	312.6	1.50911
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	0.971247817
$B_2$	0.216901417
$B_3$	0.904651666
$C_1$	0.004723020
$C_2$	0.0153575612
$C_3$	168.68133000

### Constants of Formula for $dn/dT$

$D_0$	-1.83E-05
$D_1$	-7.89E-09
$D_2$	-1.63E-12
$E_0$	3.74E-07
$E_1$	3.46E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.150

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-4.9	-4.6	-4.3	-6.9	-6.6	-6.4
+20/+40	-6.0	-5.7	-5.3	-7.3	-7.0	-6.7
+60/+80	-6.5	-6.2	-5.8	-7.5	-7.2	-6.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.89	0.75
2325	0.93	0.84
1970	0.996	0.989
1530	0.996	0.990
1060	0.998	0.994
700	0.998	0.995
660	0.998	0.995
620	0.998	0.996
580	0.999	0.997
546	0.999	0.997
500	0.998	0.996
460	0.997	0.993
436	0.997	0.992
420	0.997	0.992
405	0.997	0.993
400	0.997	0.993
390	0.997	0.992
380	0.995	0.988
370	0.990	0.976
365	0.985	0.963
350	0.95	0.88
334	0.83	0.63
320	0.62	0.30
310	0.43	0.12
300	0.26	0.04
290	0.14	0.01
280	0.06	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  34/28

### Remarks

suitable for precision molding

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2879
$P_{C,s}$	0.5465
$P_{d,C}$	0.3062
$P_{e,d}$	0.2388
$P_{g,F}$	0.5359
$P_{i,h}$	0.7429

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2858
$P'_{C,s}$	0.5909
$P'_{d,C'}$	0.2554
$P'_{e,d}$	0.2370
$P'_{g,F'}$	0.4759
$P'_{i,h}$	0.7373

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.1112
$\Delta P_{C,s}$	-0.0533
$\Delta P_{F,e}$	0.0110
$\Delta P_{g,F}$	0.0342
$\Delta P_{i,g}$	0.1675

### Chemical Properties

CR	1
FR	0
SR	52.3
AR	2.2
PR	4.3
SR-J	3
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	12.7
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	14.8
$T_g$ [°C]	464
$T_{10}^{13}$ [°C]	463
$T_{10}^{7.6}$ [°C]	527
$c_p$ [J/(g·K)]	0.690
$\lambda$ [W/(m·K)]	0.760
AT [°C]	503
$\rho$ [g/cm <sup>3</sup> ]	3.68
$E$ [ $10^3$ N/mm <sup>2</sup> ]	73
$\mu$	0.302
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	0.63
HK <sub>0.1/20</sub>	345
HG	6
Abrasion Aa	528

## N-FK58 456909.365

$n_d = 1.45600$   
 $n_e = 1.45720$

$v_d = 90.90$   
 $v_e = 90.47$

$n_F - n_C = 0.005017$   
 $n_{F'} - n_{C'} = 0.005053$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.44114
$n_{1970.1}$	1970.1	1.44388
$n_{1529.6}$	1529.6	1.44683
$n_{1060.0}$	1060.0	1.44991
$n_t$	1014.0	1.45026
$n_s$	852.1	1.45171
$n_r$	706.5	1.45358
$n_C$	656.3	1.45446
$n_{C'}$	643.8	1.45471
$n_{632.8}$	632.8	1.45494
$n_D$	589.3	1.45596
$n_d$	587.6	1.45600
$n_e$	546.1	1.45720
$n_F$	486.1	1.45948
$n_{F'}$	480.0	1.45976
$n_g$	435.8	1.46216
$n_h$	404.7	1.46436
$n_i$	365.0	1.46807
$n_{334.1}$	334.1	1.47199
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	0.738042712
$B_2$	0.363371967
$B_3$	0.989296264
$C_1$	0.003390656
$C_2$	0.0117551189
$C_3$	212.84214500

### Constants of Formula for $dn/dT$

$D_0$	-2.05E-05
$D_1$	-6.33E-09
$D_2$	4.13E-11
$E_0$	3.84E-07
$E_1$	1.63E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.073

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-5.4	-5.1	-4.8	-7.3	-7.1	-6.8
+20/+40	-6.5	-6.2	-5.9	-7.7	-7.4	-7.2
+60/+80	-6.8	-6.5	-6.2	-7.8	-7.5	-7.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.997	0.993
2325	0.998	0.996
1970	0.999	0.998
1530	0.999	0.998
1060	0.998	0.995
700	0.997	0.993
660	0.997	0.993
620	0.997	0.994
580	0.998	0.994
546	0.998	0.995
500	0.998	0.994
460	0.997	0.992
436	0.996	0.991
420	0.996	0.991
405	0.996	0.991
400	0.996	0.991
390	0.996	0.990
380	0.995	0.987
370	0.992	0.980
365	0.990	0.975
350	0.976	0.940
334	0.930	0.830
320	0.820	0.610
310	0.690	0.400
300	0.530	0.200
290	0.360	0.080
280	0.240	0.030
270	0.150	0.010
260	0.110	0.010
250	0.090	0.000

### Color Code

$\lambda_{80} / \lambda_5$  33/--

### Remarks

XLS glass

### Relative Partial Dispersion P

$P_{s,t}$	0.2894
$P_{C,s}$	0.5481
$P_{d,C}$	0.3066
$P_{e,d}$	0.2388
$P_{g,F}$	0.5347
$P_{i,h}$	0.7387

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2873
$P'_{C,s}$	0.5927
$P'_{d,C'}$	0.2557
$P'_{e,d}$	0.2371
$P'_{g,F'}$	0.4749
$P'_{i,h}$	0.7334

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.1386
$\Delta P_{C,s}$	-0.0667
$\Delta P_{F,e}$	0.0140
$\Delta P_{g,F}$	0.0438
$\Delta P_{i,g}$	0.2157

### Chemical Properties

CR	1
FR	1
SR	52.3
AR	3.3
PR	4.3
SR-J	4
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	13.7
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	15.7
$T_g$ [°C]	445
$T_{10}^{13}$ [°C]	448
$T_{10}^{7.6}$ [°C]	508
$c_p$ [J/(g·K)]	0.710
$\lambda$ [W/(m·K)]	0.760
AT [°C]	475
$\rho$ [g/cm <sup>3</sup> ]	3.65
E [ $10^3$ N/mm <sup>2</sup> ]	70
$\mu$	0.301
K [ $10^{-6}$ mm <sup>2</sup> /N]	0.54
HK <sub>0.1/20</sub>	372
HG	6



## N-PK51 529770.386

$n_d = 1.52855$   
 $n_e = 1.53019$

$v_d = 76.98$   
 $v_e = 76.58$

$n_F - n_C = 0.006867$   
 $n_{F'} - n_{C'} = 0.006923$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.50987
$n_{1970.1}$	1970.1	1.51312
$n_{1529.6}$	1529.6	1.51665
$n_{1060.0}$	1060.0	1.52045
$n_t$	1014.0	1.52089
$n_s$	852.1	1.52278
$n_r$	706.5	1.52527
$n_C$	656.3	1.52646
$n_{C'}$	643.8	1.52680
$n_{632.8}$	632.8	1.52711
$n_D$	589.3	1.52849
$n_d$	587.6	1.52855
$n_e$	546.1	1.53019
$n_F$	486.1	1.53333
$n_{F'}$	480.0	1.53372
$n_g$	435.8	1.53704
$n_h$	404.7	1.54010
$n_i$	365.0	1.54527
$n_{334.1}$	334.1	1.55079
$n_{312.6}$	312.6	1.55579
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.156107750
$B_2$	0.153229344
$B_3$	0.785618966
$C_1$	0.005855974
$C_2$	0.0194072416
$C_3$	140.53704600

### Constants of Formula for $dn/dT$

$D_0$	-1.98E-05
$D_1$	-6.06E-09
$D_2$	1.60E-11
$E_0$	4.16E-07
$E_1$	5.01E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.134

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-6.0	-5.7	-5.4	-8.1	-7.8	-7.5
+20/+40	-7.1	-6.7	-6.4	-8.4	-8.1	-7.7
+60/+80	-7.5	-7.1	-6.7	-8.6	-8.2	-7.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.920	0.810
2325	0.940	0.860
1970	0.986	0.966
1530	0.994	0.985
1060	0.998	0.994
700	0.997	0.992
660	0.996	0.991
620	0.997	0.992
580	0.998	0.995
546	0.998	0.996
500	0.997	0.993
460	0.995	0.988
436	0.994	0.984
420	0.994	0.984
405	0.994	0.986
400	0.994	0.986
390	0.994	0.984
380	0.989	0.973
370	0.982	0.955
365	0.976	0.940
350	0.930	0.840
334	0.820	0.600
320	0.600	0.280
310	0.400	0.100
300	0.210	0.020
290	0.060	0.000
280	0.010	
270	0.000	
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  34/29

### Remarks

suitable for precision molding  
step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2750
$P_{C,s}$	0.5360
$P_{d,C}$	0.3046
$P_{e,d}$	0.2387
$P_{g,F}$	0.5401
$P_{i,h}$	0.7535

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2727
$P'_{C,s}$	0.5797
$P'_{d,C'}$	0.2540
$P'_{e,d}$	0.2367
$P'_{g,F'}$	0.4794
$P'_{i,h}$	0.7473

### Deviation of Rel. Partial Disp. $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0991
$\Delta P_{C,s}$	-0.0463
$\Delta P_{F,e}$	0.0088
$\Delta P_{g,F}$	0.0258
$\Delta P_{i,g}$	0.1203

### Chemical Properties

CR	1
FR	0
SR	52.3
AR	3.3
PR	4.3
SR-J	3
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	12.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	14.1
$T_g$ [°C]	487
$T_{10}^{13}$ [°C]	488
$T_{10}^{7.6}$ [°C]	568
$c_p$ [J/(g·K)]	0.620
$\lambda$ [W/(m·K)]	0.650
AT [°C]	528
$\rho$ [g/cm <sup>3</sup> ]	3.86
E [ $10^3$ N/mm <sup>2</sup> ]	74
$\mu$	0.295
K [ $10^{-6}$ mm <sup>2</sup> /N]	0.54
HK <sub>0.1/20</sub>	415
HG	6
Abrasion Aa	592

## N-PK52A 497816.370

$n_d = 1.49700$

$v_d = 81.61$

$n_F - n_C = 0.006090$

$n_e = 1.49845$

$v_e = 81.21$

$n_F - n_C = 0.006138$

Refractive Indices		
	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.47966
$n_{1970.1}$	1970.1	1.48279
$n_{1529.6}$	1529.6	1.48616
$n_{1060.0}$	1060.0	1.48971
$n_t$	1014.0	1.49012
$n_s$	852.1	1.49184
$n_r$	706.5	1.49408
$n_C$	656.3	1.49514
$n_{C'}$	643.8	1.49544
$n_{632.8}$	632.8	1.49571
$n_D$	589.3	1.49695
$n_d$	587.6	1.49700
$n_e$	546.1	1.49845
$n_F$	486.1	1.50123
$n_{F'}$	480.0	1.50157
$n_g$	435.8	1.50450
$n_h$	404.7	1.50720
$n_i$	365.0	1.51175
$n_{334.1}$	334.1	1.51658
$n_{312.6}$	312.6	1.52096
$n_{296.7}$	296.7	1.52489
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

Constants of Dispersion Formula	
$B_1$	1.029607000
$B_2$	0.188050600
$B_3$	0.736488165
$C_1$	0.005168002
$C_2$	0.0166658798
$C_3$	138.96412900

Constants of Formula for $dn/dT$	
$D_0$	-1.97E-05
$D_1$	-5.50E-09
$D_2$	5.28E-12
$E_0$	3.60E-07
$E_1$	2.45E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.172

Temperature Coefficients of the Refractive Index						
[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/+20	-5.7	-5.4	-5.1	-7.7	-7.4	-7.1
+20/+40	-6.7	-6.4	-6.0	-8.0	-7.7	-7.4
+60/+80	-7.1	-6.8	-6.4	-8.1	-7.8	-7.5

Internal Transmittance $\tau_i$		
$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.987	0.967
2325	0.991	0.978
1970	0.996	0.990
1530	0.998	0.994
1060	0.998	0.994
700	0.997	0.993
660	0.997	0.993
620	0.998	0.995
580	0.999	0.997
546	0.999	0.997
500	0.998	0.996
460	0.997	0.992
436	0.996	0.990
420	0.996	0.990
405	0.997	0.992
400	0.997	0.992
390	0.997	0.992
380	0.996	0.989
370	0.992	0.980
365	0.988	0.970
350	0.950	0.88
334	0.83	0.63
320	0.62	0.30
310	0.43	0.12
300	0.25	0.04
290	0.12	0.01
280	0.04	
270	0.01	
260		
250		

Color Code	
$\lambda_{80} / \lambda_5$	34/28

Remarks
suitable for precision molding

Relative Partial Dispersion P	
$P_{s,t}$	0.2819
$P_{C,s}$	0.5417
$P_{d,C}$	0.3055
$P_{e,d}$	0.2388
$P_{g,F}$	0.5377
$P_{i,h}$	0.7470

Relative Partial Dispersion P'	
$P'_{s,t}$	0.2797
$P'_{C,s}$	0.5858
$P'_{d,C'}$	0.2548
$P'_{e,d}$	0.2369
$P'_{g,F'}$	0.4774
$P'_{i,h}$	0.7412

Deviation of Rel. Partial Disp. $\Delta P$ from the normal line	
$\Delta P_{C,t}$	-0.1084
$\Delta P_{C,s}$	-0.0514
$\Delta P_{F,e}$	0.0103
$\Delta P_{g,F}$	0.0311
$\Delta P_{i,g}$	0.1497

Chemical Properties	
CR	1
FR	0
SR	52.3
AR	3.3
PR	4.3
SR-J	4
WR-J	1

Other Properties	
$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	13.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	15.0
$T_g$ [°C]	467
$T_{10}^{13}$ [°C]	467
$T_{10}^{7.6}$ [°C]	538
$c_p$ [J/(g·K)]	0.670
$\lambda$ [W/(m·K)]	0.730
AT [°C]	520
$\rho$ [g/cm <sup>3</sup> ]	3.70
E [ $10^3$ N/mm <sup>2</sup> ]	71
$\mu$	0.298
K [ $10^{-6}$ mm <sup>2</sup> /N]	0.65
HK <sub>0.1/20</sub>	355
HG	6
Abrasion Aa	526

## N-PSK3 552635.291

$n_d = 1.55232$   
 $n_e = 1.55440$

$v_d = 63.46$   
 $v_e = 63.23$

$n_F - n_C = 0.008704$   
 $n_{F'} - n_{C'} = 0.008767$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.52375
$n_{1970.1}$	1970.1	1.52954
$n_{1529.6}$	1529.6	1.53558
$n_{1060.0}$	1060.0	1.54154
$n_t$	1014.0	1.54218
$n_s$	852.1	1.54482
$n_r$	706.5	1.54811
$n_C$	656.3	1.54965
$n_{C'}$	643.8	1.55008
$n_{632.8}$	632.8	1.55048
$n_D$	589.3	1.55224
$n_d$	587.6	1.55232
$n_e$	546.1	1.55440
$n_F$	486.1	1.55835
$n_{F'}$	480.0	1.55885
$n_g$	435.8	1.56302
$n_h$	404.7	1.56688
$n_i$	365.0	1.57342
$n_{334.1}$	334.1	1.58041
$n_{312.6}$	312.6	1.58679
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	0.887272110
$B_2$	0.489592425
$B_3$	1.048652960
$C_1$	0.004698241
$C_2$	0.0161818463
$C_3$	104.37497500

### Constants of Formula for $dn/dT$

$D_0$	2.03E-06
$D_1$	1.19E-08
$D_2$	2.46E-11
$E_0$	3.14E-07
$E_1$	2.45E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.235

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.6	3.1	3.6	0.6	1.0	1.5
+20/+40	2.5	3.0	3.5	1.2	1.6	2.1
+60/+80	2.7	3.2	3.8	1.7	2.2	2.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.650	0.340
2325	0.810	0.590
1970	0.950	0.880
1530	0.991	0.978
1060	0.999	0.997
700	0.998	0.995
660	0.997	0.993
620	0.997	0.992
580	0.997	0.993
546	0.997	0.993
500	0.996	0.990
460	0.995	0.987
436	0.994	0.986
420	0.994	0.986
405	0.995	0.987
400	0.994	0.986
390	0.993	0.983
380	0.991	0.977
370	0.988	0.971
365	0.985	0.964
350	0.967	0.920
334	0.910	0.800
320	0.770	0.520
310	0.580	0.260
300	0.320	0.060
290	0.120	
280	0.030	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  33/28

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.3023
$P_{C,s}$	0.5555
$P_{d,C}$	0.3069
$P_{e,d}$	0.2386
$P_{g,F}$	0.5365
$P_{i,h}$	0.7509

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3001
$P'_{C,s}$	0.6002
$P'_{d,C'}$	0.2559
$P'_{e,d}$	0.2369
$P'_{g,F'}$	0.4767
$P'_{i,h}$	0.7454

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0118
$\Delta P_{C,s}$	0.0047
$\Delta P_{F,e}$	-0.0005
$\Delta P_{g,F}$	-0.0005
$\Delta P_{i,g}$	0.0016

### Chemical Properties

CR	3
FR	0
SR	2.2
AR	2
PR	2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$T_g$ [°C]	599
$T_{10}^{13}$ [°C]	597
$T_{10}^{7.6}$ [°C]	736
$c_p$ [J/(g·K)]	0.682
$\lambda$ [W/(m·K)]	0.990
$\rho$ [g/cm <sup>3</sup> ]	2.91
$E$ [ $10^3$ N/mm <sup>2</sup> ]	84
$\mu$	0.226
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.48
$HK_{0.1/20}$	630
HG	2

## N-PSK53A 618634.357

$n_d = 1.61800$

$v_d = 63.39$

$n_F - n_C = 0.009749$

$n_e = 1.62033$

$v_e = 63.10$

$n_F - n_C = 0.009831$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.59015
$n_{1970.1}$	1970.1	1.59528
$n_{1529.6}$	1529.6	1.60073
$n_{1060.0}$	1060.0	1.60641
$n_t$	1014.0	1.60706
$n_s$	852.1	1.60979
$n_r$	706.5	1.61334
$n_C$	656.3	1.61503
$n_{C'}$	643.8	1.61550
$n_{632.8}$	632.8	1.61595
$n_D$	589.3	1.61791
$n_d$	587.6	1.61800
$n_e$	546.1	1.62033
$n_F$	486.1	1.62478
$n_{F'}$	480.0	1.62534
$n_g$	435.8	1.63007
$n_h$	404.7	1.63445
$n_i$	365.0	1.64190
$n_{334.1}$	334.1	1.64991
$n_{312.6}$	312.6	1.65724
$n_{296.7}$	296.7	1.66390
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.381218360
$B_2$	0.196745645
$B_3$	0.886089205
$C_1$	0.007064163
$C_2$	0.0233251345
$C_3$	97.48473450

### Constants of Formula for $dn/dT$

$D_0$	-9.28E-06
$D_1$	7.19E-09
$D_2$	1.45E-12
$E_0$	4.06E-07
$E_1$	3.17E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.190

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-2.6	-2.1	-1.6	-4.7	-4.3	-3.8
+20/+40	-2.9	-2.4	-1.8	-4.3	-3.8	-3.3
+60/+80	-2.9	-2.3	-1.8	-4.0	-3.5	-2.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.610	0.290
2325	0.760	0.510
1970	0.920	0.800
1530	0.982	0.956
1060	0.998	0.994
700	0.998	0.994
660	0.997	0.993
620	0.997	0.992
580	0.998	0.994
546	0.998	0.995
500	0.997	0.992
460	0.994	0.986
436	0.993	0.982
420	0.992	0.979
405	0.988	0.970
400	0.985	0.964
390	0.976	0.940
380	0.959	0.900
370	0.930	0.830
365	0.910	0.780
350	0.780	0.530
334	0.530	0.200
320	0.230	0.030
310	0.060	0.000
300	0.000	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  36/31

### Remarks

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2797
$P_{C,s}$	0.5380
$P_{d,C}$	0.3044
$P_{e,d}$	0.2385
$P_{g,F}$	0.5424
$P_{i,h}$	0.7642

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2774
$P'_{C,s}$	0.5816
$P'_{d,C'}$	0.2538
$P'_{e,d}$	0.2365
$P'_{g,F'}$	0.4815
$P'_{i,h}$	0.7578

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0279
$\Delta P_{C,s}$	-0.0127
$\Delta P_{F,e}$	0.0020
$\Delta P_{g,F}$	0.0052
$\Delta P_{i,g}$	0.0208

### Chemical Properties

CR	1
FR	1
SR	53.3
AR	2.3
PR	4.3
SR-J	5
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.8
$T_g$ [°C]	606
$T_{10}^{13}$ [°C]	609
$T_{10}^{7.6}$ [°C]	699
$c_p$ [J/(g·K)]	0.590
$\lambda$ [W/(m·K)]	0.640
AT [°C]	647
$\rho$ [g/cm <sup>3</sup> ]	3.57
E [ $10^3$ N/mm <sup>2</sup> ]	76
$\mu$	0.288
K [ $10^{-6}$ mm <sup>2</sup> /N]	1.16
HK <sub>0.1/20</sub>	415
HG	6
Abrasion Aa	284

## SCHOTT N-BK7® 517642.251

$n_d = 1.51680$

$v_d = 64.17$

$n_F - n_C = 0.008054$

$n_e = 1.51872$

$v_e = 63.96$

$n_F - n_C = 0.008110$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.48921
$n_{1970.1}$	1970.1	1.49495
$n_{1529.6}$	1529.6	1.50091
$n_{1060.0}$	1060.0	1.50669
$n_t$	1014.0	1.50731
$n_s$	852.1	1.50980
$n_r$	706.5	1.51289
$n_C$	656.3	1.51432
$n_{C'}$	643.8	1.51472
$n_{632.8}$	632.8	1.51509
$n_D$	589.3	1.51673
$n_d$	587.6	1.51680
$n_e$	546.1	1.51872
$n_F$	486.1	1.52238
$n_{F'}$	480.0	1.52283
$n_g$	435.8	1.52668
$n_h$	404.7	1.53024
$n_i$	365.0	1.53627
$n_{334.1}$	334.1	1.54272
$n_{312.6}$	312.6	1.54862
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.039612120
$B_2$	0.231792344
$B_3$	1.010469450
$C_1$	0.006000699
$C_2$	0.0200179144
$C_3$	103.56065300

### Constants of Formula for $dn/dT$

$D_0$	1.86E-06
$D_1$	1.31E-08
$D_2$	-1.37E-11
$E_0$	4.34E-07
$E_1$	6.27E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.170

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.4	2.9	3.3	0.3	0.8	1.2
+20/+40	2.4	3.0	3.5	1.1	1.6	2.1
+60/+80	2.5	3.1	3.7	1.5	2.1	2.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.67	0.36
2325	0.79	0.56
1970	0.93	0.84
1530	0.992	0.980
1060	0.999	0.997
700	0.998	0.996
660	0.998	0.994
620	0.998	0.994
580	0.998	0.995
546	0.998	0.996
500	0.998	0.994
460	0.997	0.993
436	0.997	0.992
420	0.997	0.993
405	0.997	0.993
400	0.997	0.992
390	0.996	0.989
380	0.993	0.983
370	0.991	0.977
365	0.988	0.971
350	0.967	0.92
334	0.91	0.78
320	0.77	0.52
310	0.57	0.25
300	0.29	0.05
290	0.06	
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  33/29

### Remarks

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.3098
$P_{C,s}$	0.5612
$P_{d,C}$	0.3076
$P_{e,d}$	0.2386
$P_{g,F}$	0.5349
$P_{i,h}$	0.7483

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3076
$P'_{C,s}$	0.6062
$P'_{d,C'}$	0.2566
$P'_{e,d}$	0.2370
$P'_{g,F'}$	0.4754
$P'_{i,h}$	0.7432

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0216
$\Delta P_{C,s}$	0.0087
$\Delta P_{F,e}$	-0.0009
$\Delta P_{g,F}$	-0.0009
$\Delta P_{i,g}$	0.0035

### Chemical Properties

CR	1
FR	0
SR	1
AR	2.3
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.3
$T_g$ [°C]	557
$T_{10}^{13}$ [°C]	557
$T_{10}^{7.6}$ [°C]	719
$c_p$ [J/(g·K)]	0.858
$\lambda$ [W/(m·K)]	1.114
AT [°C]	609
$\rho$ [g/cm <sup>3</sup> ]	2.51
E [10 <sup>3</sup> N/mm <sup>2</sup> ]	82
$\mu$	0.206
K [10 <sup>-6</sup> mm <sup>2</sup> /N]	2.76
HK <sub>0.1/20</sub>	610
HG	3

## N-BK7HT 517642.251

$n_d = 1.51680$

$v_d = 64.17$

$n_F - n_C = 0.008054$

$n_e = 1.51872$

$v_e = 63.96$

$n_F - n_C = 0.008110$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.48921
$n_{1970.1}$	1970.1	1.49495
$n_{1529.6}$	1529.6	1.50091
$n_{1060.0}$	1060.0	1.50669
$n_t$	1014.0	1.50731
$n_s$	852.1	1.50980
$n_r$	706.5	1.51289
$n_C$	656.3	1.51432
$n_{C'}$	643.8	1.51472
$n_{632.8}$	632.8	1.51509
$n_D$	589.3	1.51673
$n_d$	587.6	1.51680
$n_e$	546.1	1.51872
$n_F$	486.1	1.52238
$n_{F'}$	480.0	1.52283
$n_g$	435.8	1.52668
$n_h$	404.7	1.53024
$n_i$	365.0	1.53627
$n_{334.1}$	334.1	1.54272
$n_{312.6}$	312.6	1.54862
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.039612120
$B_2$	0.231792344
$B_3$	1.010469450
$C_1$	0.006000699
$C_2$	0.0200179144
$C_3$	103.56065300

### Constants of Formula for $dn/dT$

$D_0$	1.86E-06
$D_1$	1.31E-08
$D_2$	-1.37E-11
$E_0$	4.34E-07
$E_1$	6.27E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.170

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.4	2.9	3.3	0.3	0.8	1.2
+20/+40	2.4	3.0	3.5	1.1	1.6	2.1
+60/+80	2.5	3.1	3.7	1.5	2.1	2.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.750	0.490
2325	0.850	0.660
1970	0.954	0.890
1530	0.995	0.987
1060	0.999	0.999
700	0.999	0.998
660	0.999	0.997
620	0.999	0.997
580	0.999	0.998
546	0.999	0.998
500	0.999	0.997
460	0.998	0.996
436	0.998	0.996
420	0.998	0.996
405	0.998	0.996
400	0.998	0.996
390	0.998	0.994
380	0.997	0.992
370	0.996	0.989
365	0.994	0.985
350	0.985	0.964
334	0.950	0.880
320	0.820	0.600
310	0.570	0.240
300	0.220	0.020
290	0.040	
280	0.000	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  33/29

### Remarks

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.3098
$P_{C,s}$	0.5612
$P_{d,C}$	0.3076
$P_{e,d}$	0.2386
$P_{g,F}$	0.5349
$P_{i,h}$	0.7483

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3076
$P'_{C,s}$	0.6062
$P'_{d,C'}$	0.2566
$P'_{e,d}$	0.2370
$P'_{g,F'}$	0.4754
$P'_{i,h}$	0.7432

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0216
$\Delta P_{C,s}$	0.0087
$\Delta P_{F,e}$	-0.0009
$\Delta P_{g,F}$	-0.0009
$\Delta P_{i,g}$	0.0035

### Chemical Properties

CR	1
FR	0
SR	1
AR	2.3
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.3
$T_g$ [°C]	557
$T_{10}^{13}$ [°C]	557
$T_{10}^{7.6}$ [°C]	719
$c_p$ [J/(g·K)]	0.858
$\lambda$ [W/(m·K)]	1.114
$\rho$ [g/cm <sup>3</sup> ]	2.51
$E$ [ $10^3$ N/mm <sup>2</sup> ]	82
$\mu$	0.206
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.77
$HK_{0.1/20}$	610
HG	3

## N-BK7HTi 517642.251

$n_d = 1.51680$

$v_d = 64.17$

$n_F - n_C = 0.008054$

$n_e = 1.51872$

$v_e = 63.96$

$n_F - n_C = 0.008110$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.48921
$n_{1970.1}$	1970.1	1.49495
$n_{1529.6}$	1529.6	1.50091
$n_{1060.0}$	1060.0	1.50669
$n_t$	1014.0	1.50731
$n_s$	852.1	1.50980
$n_r$	706.5	1.51289
$n_C$	656.3	1.51432
$n_{C'}$	643.8	1.51472
$n_{632.8}$	632.8	1.51509
$n_D$	589.3	1.51673
$n_d$	587.6	1.51680
$n_e$	546.1	1.51872
$n_F$	486.1	1.52238
$n_{F'}$	480.0	1.52283
$n_g$	435.8	1.52668
$n_h$	404.7	1.53024
$n_i$	365.0	1.53627
$n_{334.1}$	334.1	1.54272
$n_{312.6}$	312.6	1.54862
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.039612120
$B_2$	0.231792344
$B_3$	1.010469450
$C_1$	0.006000699
$C_2$	0.0200179144
$C_3$	103.56065300

### Constants of Formula for $dn/dT$

$D_0$	1.86E-06
$D_1$	1.31E-08
$D_2$	-1.37E-11
$E_0$	4.34E-07
$E_1$	6.27E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.170

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.4	2.9	3.3	0.3	0.8	1.2
+20/+40	2.4	3.0	3.5	1.1	1.6	2.1
+60/+80	2.5	3.1	3.7	1.5	2.1	2.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.75	0.49
2325	0.85	0.66
1970	0.954	0.89
1530	0.995	0.987
1060	0.999	0.999
700	0.999	0.998
660	0.999	0.997
620	0.999	0.997
580	0.999	0.998
546	0.999	0.998
500	0.999	0.997
460	0.998	0.996
436	0.998	0.996
420	0.998	0.996
405	0.998	0.996
400	0.998	0.996
390	0.998	0.994
380	0.997	0.992
370	0.996	0.989
365	0.994	0.985
350	0.985	0.964
334	0.95	0.88
320	0.82	0.60
310	0.57	0.24
300	0.22	0.02
290	0.04	
280	0.00	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  33/29

### Remarks

i-line glass

### Relative Partial Dispersion P

$P_{s,t}$	0.3098
$P_{C,s}$	0.5612
$P_{d,C}$	0.3076
$P_{e,d}$	0.2386
$P_{g,F}$	0.5349
$P_{i,h}$	0.7483

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3076
$P'_{C,s}$	0.6062
$P'_{d,C'}$	0.2566
$P'_{e,d}$	0.2370
$P'_{g,F'}$	0.4754
$P'_{i,h}$	0.7432

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0216
$\Delta P_{C,s}$	0.0087
$\Delta P_{F,e}$	-0.0009
$\Delta P_{g,F}$	-0.0009
$\Delta P_{i,g}$	0.0035

### Chemical Properties

CR	1
FR	0
SR	1
AR	2.3
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.3
$T_g$ [°C]	557
$T_{10}^{13}$ [°C]	557
$T_{10}^{7.6}$ [°C]	719
$c_p$ [J/(g·K)]	0.858
$\lambda$ [W/(m·K)]	1.114
$\rho$ [g/cm <sup>3</sup> ]	2.51
$E$ [ $10^3$ N/mm <sup>2</sup> ]	82
$\mu$	0.206
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.76
$HK_{0.1/20}$	610
HG	3

## N-BK10 498670.239

$n_d = 1.49782$   
 $n_e = 1.49960$

$v_d = 66.95$   
 $v_e = 66.78$

$n_F - n_C = 0.007435$   
 $n_F - n_C = 0.007481$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.47060
$n_{1970.1}$	1970.1	1.47647
$n_{1529.6}$	1529.6	1.48252
$n_{1060.0}$	1060.0	1.48827
$n_t$	1014.0	1.48887
$n_s$	852.1	1.49127
$n_r$	706.5	1.49419
$n_C$	656.3	1.49552
$n_{C'}$	643.8	1.49589
$n_{632.8}$	632.8	1.49623
$n_D$	589.3	1.49775
$n_d$	587.6	1.49782
$n_e$	546.1	1.49960
$n_F$	486.1	1.50296
$n_{F'}$	480.0	1.50337
$n_g$	435.8	1.50690
$n_h$	404.7	1.51014
$n_i$	365.0	1.51561
$n_{334.1}$	334.1	1.52144
$n_{312.6}$	312.6	1.52674
$n_{296.7}$	296.7	1.53151
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	0.888308131
$B_2$	0.328964475
$B_3$	0.984610769
$C_1$	0.005169008
$C_2$	0.0161190045
$C_3$	99.75753310

### Constants of Formula for $dn/dT$

$D_0$	3.32E-06
$D_1$	1.72E-08
$D_2$	-2.05E-11
$E_0$	3.57E-07
$E_1$	3.90E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.169

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.7	3.1	3.5	0.7	1.1	1.4
+20/+40	2.9	3.4	3.8	1.6	2.1	2.5
+60/+80	3.1	3.7	4.1	2.1	2.6	3.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.740	0.470
2325	0.870	0.710
1970	0.980	0.950
1530	0.992	0.980
1060	0.998	0.996
700	0.998	0.995
660	0.997	0.993
620	0.997	0.992
580	0.997	0.993
546	0.997	0.993
500	0.996	0.991
460	0.996	0.990
436	0.996	0.989
420	0.996	0.989
405	0.996	0.990
400	0.996	0.990
390	0.996	0.989
380	0.994	0.985
370	0.994	0.986
365	0.994	0.986
350	0.991	0.978
334	0.978	0.950
320	0.940	0.860
310	0.870	0.710
300	0.710	0.420
290	0.410	0.110
280	0.120	
270	0.010	
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  31/27

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.3224
$P_{C,s}$	0.5716
$P_{d,C}$	0.3093
$P_{e,d}$	0.2387
$P_{g,F}$	0.5303
$P_{i,h}$	0.7360

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3204
$P'_{C,s}$	0.6174
$P'_{d,C'}$	0.2580
$P'_{e,d}$	0.2373
$P'_{g,F'}$	0.4716
$P'_{i,h}$	0.7315

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0314
$\Delta P_{C,s}$	0.0126
$\Delta P_{F,e}$	-0.0012
$\Delta P_{g,F}$	-0.0008
$\Delta P_{i,g}$	0.0091

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.6
$T_g$ [°C]	551
$T_{10}^{13}$ [°C]	
$T_{10}^{7.6}$ [°C]	753
$c_p$ [J/(g·K)]	0.810
$\lambda$ [W/(m·K)]	1.320
$\rho$ [g/cm <sup>3</sup> ]	2.39
$E$ [ $10^3$ N/mm <sup>2</sup> ]	71
$\mu$	0.203
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.21
$HK_{0.1/20}$	560
HG	4



## P-BK7 516641.243

$n_d = 1.51640$

$v_d = 64.06$

$n_F - n_C = 0.008061$

$n_e = 1.51832$

$v_e = 63.87$

$n_F - n_C = 0.008115$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.48811
$n_{1970.1}$	1970.1	1.49407
$n_{1529.6}$	1529.6	1.50025
$n_{1060.0}$	1060.0	1.50620
$n_t$	1014.0	1.50683
$n_s$	852.1	1.50936
$n_r$	706.5	1.51248
$n_C$	656.3	1.51392
$n_{C'}$	643.8	1.51431
$n_{632.8}$	632.8	1.51469
$n_D$	589.3	1.51633
$n_d$	587.6	1.51640
$n_e$	546.1	1.51832
$n_F$	486.1	1.52198
$n_{F'}$	480.0	1.52243
$n_g$	435.8	1.52628
$n_h$	404.7	1.52982
$n_i$	365.0	1.53583
$n_{334.1}$	334.1	1.54227
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.183185030
$B_2$	0.087175643
$B_3$	1.031337010
$C_1$	0.007221420
$C_2$	0.0268216805
$C_3$	101.70236200

### Constants of Formula for $dn/dT$

$D_0$	5.96E-06
$D_1$	1.36E-08
$D_2$	1.04E-12
$E_0$	5.00E-07
$E_1$	6.97E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.125

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.1	4.7	5.2	2.1	2.6	3.1
+20/+40	4.1	4.8	5.3	2.8	3.5	4.0
+60/+80	4.3	5.1	5.7	3.3	4.0	4.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.730	0.460
2325	0.870	0.700
1970	0.967	0.920
1530	0.992	0.979
1060	0.999	0.999
700	0.999	0.997
660	0.999	0.997
620	0.999	0.997
580	0.999	0.997
546	0.999	0.997
500	0.998	0.996
460	0.998	0.995
436	0.998	0.994
420	0.997	0.994
405	0.997	0.993
400	0.997	0.992
390	0.996	0.990
380	0.994	0.986
370	0.992	0.979
365	0.989	0.973
350	0.971	0.930
334	0.880	0.730
320	0.570	0.240
310	0.180	0.020
300	0.000	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  33/30

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.3143
$P_{C,s}$	0.5649
$P_{d,C}$	0.3082
$P_{e,d}$	0.2387
$P_{g,F}$	0.5335
$P_{i,h}$	0.7455

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3122
$P'_{C,s}$	0.6102
$P'_{d,C'}$	0.2571
$P'_{e,d}$	0.2371
$P'_{g,F'}$	0.4742
$P'_{i,h}$	0.7405

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0303
$\Delta P_{C,s}$	0.0126
$\Delta P_{F,e}$	-0.0016
$\Delta P_{g,F}$	-0.0025
$\Delta P_{i,g}$	-0.0017

### Chemical Properties

CR	1
FR	0
SR	1
AR	2.3
PR	2.3
SR-J	1
WR-J	4

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$T_g$ [°C]	498
$T_{10}^{13}$ [°C]	498
$T_{10}^{7.6}$ [°C]	657
$c_p$ [J/(g·K)]	0.870
$\lambda$ [W/(m·K)]	1.130
AT [°C]	546
$\rho$ [g/cm <sup>3</sup> ]	2.43
E [ $10^3$ N/mm <sup>2</sup> ]	85
$\mu$	0.202
K [ $10^{-6}$ mm <sup>2</sup> /N]	2.77
HK <sub>0.1/20</sub>	627
Abrasion Aa	66

## K7 511604.253

$n_d = 1.51112$

$v_d = 60.41$

$n_F - n_C = 0.008461$

$n_e = 1.51314$

$v_e = 60.15$

$n_F - n_C = 0.008531$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.48553
$n_{1970.1}$	1970.1	1.49046
$n_{1529.6}$	1529.6	1.49565
$n_{1060.0}$	1060.0	1.50091
$n_t$	1014.0	1.50150
$n_s$	852.1	1.50394
$n_r$	706.5	1.50707
$n_C$	656.3	1.50854
$n_{C'}$	643.8	1.50895
$n_{632.8}$	632.8	1.50934
$n_D$	589.3	1.51105
$n_d$	587.6	1.51112
$n_e$	546.1	1.51314
$n_F$	486.1	1.51700
$n_{F'}$	480.0	1.51748
$n_g$	435.8	1.52159
$n_h$	404.7	1.52540
$n_i$	365.0	1.53189
$n_{334.1}$	334.1	1.53891
$n_{312.6}$	312.6	1.54537
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.127355500
$B_2$	0.124412303
$B_3$	0.827100531
$C_1$	0.007203417
$C_2$	0.0269835916
$C_3$	100.38458800

### Constants of Formula for $dn/dT$

$D_0$	-1.67E-06
$D_1$	8.80E-09
$D_2$	-2.86E-11
$E_0$	5.42E-07
$E_1$	7.81E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.172

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.0	1.6	2.1	-1.0	-0.4	0.1
+20/+40	0.9	1.6	2.2	-0.4	0.2	0.9
+60/+80	0.8	1.6	2.3	-0.2	0.6	1.2

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.650	0.340
2325	0.760	0.500
1970	0.910	0.790
1530	0.992	0.980
1060	0.998	0.994
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.994
546	0.998	0.994
500	0.997	0.993
460	0.996	0.990
436	0.996	0.990
420	0.996	0.990
405	0.996	0.990
400	0.996	0.990
390	0.995	0.988
380	0.993	0.983
370	0.990	0.976
365	0.988	0.971
350	0.976	0.940
334	0.910	0.780
320	0.710	0.420
310	0.400	0.100
300	0.090	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  33/30

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2880
$P_{C,s}$	0.5436
$P_{d,C}$	0.3049
$P_{e,d}$	0.2385
$P_{g,F}$	0.5422
$P_{i,h}$	0.7677

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2857
$P'_{C,s}$	0.5874
$P'_{d,C'}$	0.2542
$P'_{e,d}$	0.2365
$P'_{g,F'}$	0.4814
$P'_{i,h}$	0.7614

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0001
$\Delta P_{C,s}$	-0.0001
$\Delta P_{F,e}$	0.0000
$\Delta P_{g,F}$	0.0000
$\Delta P_{i,g}$	-0.0001

### Chemical Properties

CR	3
FR	0
SR	2
AR	1
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.7
$T_g$ [°C]	513
$T_{10}^{13}$ [°C]	
$T_{10}^{7.6}$ [°C]	712
$c_p$ [J/(g·K)]	
$\lambda$ [W/(m·K)]	
$\rho$ [g/cm <sup>3</sup> ]	2.53
$E$ [ $10^3$ N/mm <sup>2</sup> ]	69
$\mu$	0.214
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.95
$HK_{0.1/20}$	520
HG	3

## K10 501564.252

$n_d = 1.50137$

$v_d = 56.41$

$n_F - n_C = 0.008888$

$n_e = 1.50349$

$v_e = 56.15$

$n_F - n_C = 0.008967$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.47507
$n_{1970.1}$	1970.1	1.48008
$n_{1529.6}$	1529.6	1.48536
$n_{1060.0}$	1060.0	1.49076
$n_t$	1014.0	1.49137
$n_s$	852.1	1.49389
$n_r$	706.5	1.49713
$n_C$	656.3	1.49867
$n_{C'}$	643.8	1.49910
$n_{632.8}$	632.8	1.49950
$n_D$	589.3	1.50129
$n_d$	587.6	1.50137
$n_e$	546.1	1.50349
$n_F$	486.1	1.50756
$n_{F'}$	480.0	1.50807
$n_g$	435.8	1.51243
$n_h$	404.7	1.51649
$n_i$	365.0	1.52350
$n_{334.1}$	334.1	1.53120
$n_{312.6}$	312.6	1.53844
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.156870820
$B_2$	0.064262544
$B_3$	0.872376139
$C_1$	0.008094243
$C_2$	0.0386051284
$C_3$	104.74773000

### Constants of Formula for $dn/dT$

$D_0$	4.86E-06
$D_1$	1.72E-08
$D_2$	-3.02E-11
$E_0$	3.82E-07
$E_1$	4.53E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.260

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.3	3.9	4.5	1.3	1.8	2.4
+20/+40	3.6	4.2	4.9	2.3	2.9	3.6
+60/+80	3.8	4.5	5.2	2.8	3.4	4.2

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.770	0.520
2325	0.830	0.630
1970	0.940	0.850
1530	0.993	0.983
1060	0.998	0.996
700	0.999	0.997
660	0.998	0.994
620	0.997	0.993
580	0.997	0.993
546	0.997	0.992
500	0.996	0.991
460	0.996	0.990
436	0.995	0.988
420	0.995	0.988
405	0.995	0.987
400	0.994	0.986
390	0.993	0.982
380	0.989	0.973
370	0.986	0.966
365	0.983	0.958
350	0.963	0.910
334	0.880	0.720
320	0.630	0.310
310	0.370	0.130
300	0.140	0.020
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  33/30

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2835
$P_{C,s}$	0.5385
$P_{d,C}$	0.3037
$P_{e,d}$	0.2382
$P_{g,F}$	0.5475
$P_{i,h}$	0.7888

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2810
$P'_{C,s}$	0.5817
$P'_{d,C'}$	0.2531
$P'_{e,d}$	0.2362
$P'_{g,F'}$	0.4860
$P'_{i,h}$	0.7819

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0094
$\Delta P_{C,s}$	0.0041
$\Delta P_{F,e}$	-0.0007
$\Delta P_{g,F}$	-0.0015
$\Delta P_{i,g}$	-0.0048

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1.2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$T_g$ [°C]	459
$T_{10}^{13}$ [°C]	453
$T_{10}^{7.6}$ [°C]	691
$c_p$ [J/(g·K)]	0.770
$\lambda$ [W/(m·K)]	1.120
$\rho$ [g/cm <sup>3</sup> ]	2.52
$E$ [ $10^3$ N/mm <sup>2</sup> ]	65
$\mu$	0.190
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.12
$HK_{0.1/20}$	470
HG	4

## N-K5 522595.259

$n_d = 1.52249$

$v_d = 59.48$

$n_F - n_C = 0.008784$

$n_e = 1.52458$

$v_e = 59.22$

$n_F - n_C = 0.008858$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.49656
$n_{1970.1}$	1970.1	1.50146
$n_{1529.6}$	1529.6	1.50664
$n_{1060.0}$	1060.0	1.51197
$n_t$	1014.0	1.51257
$n_s$	852.1	1.51507
$n_r$	706.5	1.51829
$n_C$	656.3	1.51982
$n_{C'}$	643.8	1.52024
$n_{632.8}$	632.8	1.52064
$n_D$	589.3	1.52241
$n_d$	587.6	1.52249
$n_e$	546.1	1.52458
$n_F$	486.1	1.52860
$n_{F'}$	480.0	1.52910
$n_g$	435.8	1.53338
$n_h$	404.7	1.53734
$n_i$	365.0	1.54412
$n_{334.1}$	334.1	1.55145
$n_{312.6}$	312.6	1.55821
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.085118330
$B_2$	0.199562005
$B_3$	0.930511663
$C_1$	0.006610995
$C_2$	0.0241108660
$C_3$	111.98277700

### Constants of Formula for $dn/dT$

$D_0$	-4.13E-07
$D_1$	1.03E-08
$D_2$	-3.40E-11
$E_0$	4.73E-07
$E_1$	5.19E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.213

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.5	2.1	2.6	-0.6	0.0	0.5
+20/+40	1.4	2.1	2.7	0.1	0.7	1.4
+60/+80	1.4	2.1	2.8	0.4	1.1	1.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.780	0.530
2325	0.850	0.660
1970	0.950	0.870
1530	0.994	0.986
1060	0.998	0.995
700	0.998	0.994
660	0.997	0.992
620	0.997	0.993
580	0.998	0.995
546	0.998	0.995
500	0.997	0.993
460	0.996	0.991
436	0.996	0.991
420	0.996	0.991
405	0.996	0.989
400	0.995	0.988
390	0.994	0.984
380	0.991	0.977
370	0.985	0.962
365	0.982	0.956
350	0.950	0.880
334	0.830	0.630
320	0.540	0.210
310	0.220	0.020
300	0.060	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  34/30

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2843
$P_{C,s}$	0.5404
$P_{d,C}$	0.3044
$P_{e,d}$	0.2384
$P_{g,F}$	0.5438
$P_{i,h}$	0.7717

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2819
$P'_{C,s}$	0.5839
$P'_{d,C'}$	0.2538
$P'_{e,d}$	0.2364
$P'_{g,F'}$	0.4828
$P'_{i,h}$	0.7653

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0025
$\Delta P_{C,s}$	-0.0012
$\Delta P_{F,e}$	0.0001
$\Delta P_{g,F}$	0.0000
$\Delta P_{i,g}$	-0.0019

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.6
$T_g$ [°C]	546
$T_{10}^{13}$ [°C]	540
$T_{10}^{7.6}$ [°C]	720
$c_p$ [J/(g·K)]	0.783
$\lambda$ [W/(m·K)]	0.950
$\rho$ [g/cm <sup>3</sup> ]	2.59
$E$ [ $10^3$ N/mm <sup>2</sup> ]	71
$\mu$	0.224
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.03
$HK_{0.1/20}$	530
HG	3

## N-ZK7 508612.249

$n_d = 1.50847$   
 $n_e = 1.51045$

$v_d = 61.19$   
 $v_e = 60.98$

$n_F - n_C = 0.008310$   
 $n_F - n_C = 0.008370$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.48062
$n_{1970.1}$	1970.1	1.48637
$n_{1529.6}$	1529.6	1.49233
$n_{1060.0}$	1060.0	1.49813
$n_t$	1014.0	1.49876
$n_s$	852.1	1.50129
$n_r$	706.5	1.50445
$n_C$	656.3	1.50592
$n_{C'}$	643.8	1.50633
$n_{632.8}$	632.8	1.50671
$n_D$	589.3	1.50840
$n_d$	587.6	1.50847
$n_e$	546.1	1.51045
$n_F$	486.1	1.51423
$n_{F'}$	480.0	1.51470
$n_g$	435.8	1.51869
$n_h$	404.7	1.52238
$n_i$	365.0	1.52865
$n_{334.1}$	334.1	1.53538
$n_{312.6}$	312.6	1.54155
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.077150320
$B_2$	0.168079109
$B_3$	0.851889892
$C_1$	0.006766017
$C_2$	0.0230642817
$C_3$	89.04987780

### Constants of Formula for $dn/dT$

$D_0$	1.15E-05
$D_1$	1.73E-08
$D_2$	-8.06E-11
$E_0$	4.32E-07
$E_1$	7.05E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.179

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	5.9	6.5	7.0	3.9	4.5	4.9
+20/+40	6.4	7.0	7.6	5.1	5.7	6.3
+60/+80	6.4	7.2	7.8	5.4	6.2	6.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.660	0.350
2325	0.850	0.660
1970	0.971	0.930
1530	0.990	0.976
1060	0.998	0.994
700	0.998	0.996
660	0.998	0.994
620	0.998	0.994
580	0.998	0.995
546	0.998	0.995
500	0.997	0.993
460	0.995	0.988
436	0.994	0.984
420	0.992	0.981
405	0.991	0.977
400	0.990	0.975
390	0.987	0.969
380	0.982	0.956
370	0.976	0.940
365	0.971	0.930
350	0.940	0.860
334	0.850	0.670
320	0.690	0.390
310	0.490	0.170
300	0.220	0.030
290	0.030	
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  34/29

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.3049
$P_{C,s}$	0.5570
$P_{d,C}$	0.3069
$P_{e,d}$	0.2386
$P_{g,F}$	0.5370
$P_{i,h}$	0.7543

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3027
$P'_{C,s}$	0.6017
$P'_{d,C'}$	0.2560
$P'_{e,d}$	0.2369
$P'_{g,F'}$	0.4771
$P'_{i,h}$	0.7488

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0267
$\Delta P_{C,s}$	0.0115
$\Delta P_{F,e}$	-0.0017
$\Delta P_{g,F}$	-0.0039
$\Delta P_{i,g}$	-0.0129

### Chemical Properties

CR	1
FR	0
SR	2
AR	1.2
PR	2.2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	4.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.2
$T_g$ [°C]	539
$T_{10}^{13}$ [°C]	
$T_{10}^{7.6}$ [°C]	721
$c_p$ [J/(g·K)]	0.770
$\lambda$ [W/(m·K)]	1.042
$\rho$ [g/cm <sup>3</sup> ]	2.49
$E$ [ $10^3$ N/mm <sup>2</sup> ]	70
$\mu$	0.214
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.63
$HK_{0.1/20}$	530
HG	4

## N-ZK7A 508610.247

$n_d = 1.50805$   
 $n_e = 1.51004$

$v_d = 61.04$   
 $v_e = 60.84$

$n_F - n_C = 0.008323$   
 $n_{F'} - n_{C'} = 0.008384$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.48001
$n_{1970.1}$	1970.1	1.48582
$n_{1529.6}$	1529.6	1.49184
$n_{1060.0}$	1060.0	1.49768
$n_t$	1014.0	1.49831
$n_s$	852.1	1.50086
$n_r$	706.5	1.50403
$n_C$	656.3	1.50550
$n_{C'}$	643.8	1.50591
$n_{632.8}$	632.8	1.50629
$n_D$	589.3	1.50798
$n_d$	587.6	1.50805
$n_e$	546.1	1.51004
$n_F$	486.1	1.51382
$n_{F'}$	480.0	1.51429
$n_g$	435.8	1.51829
$n_h$	404.7	1.52198
$n_i$	365.0	1.52826
$n_{334.1}$	334.1	1.53500
$n_{312.6}$	312.6	1.54118
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.075098910
$B_2$	0.168895044
$B_3$	0.860503983
$C_1$	0.006766017
$C_2$	0.0230642817
$C_3$	89.04987780

### Constants of Formula for $dn/dT$

$D_0$	1.09E-05
$D_1$	1.98E-08
$D_2$	-1.49E-11
$E_0$	4.48E-07
$E_1$	3.26E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.183

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	5.8	6.5	7.0	3.8	4.4	4.9
+20/+40	6.1	6.8	7.4	4.9	5.5	6.1
+60/+80	6.5	7.2	7.9	5.5	6.2	6.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.660	0.350
2325	0.850	0.660
1970	0.971	0.930
1530	0.990	0.976
1060	0.998	0.994
700	0.998	0.996
660	0.998	0.994
620	0.998	0.994
580	0.998	0.995
546	0.998	0.995
500	0.997	0.993
460	0.995	0.988
436	0.994	0.984
420	0.992	0.981
405	0.991	0.977
400	0.990	0.975
390	0.987	0.969
380	0.982	0.956
370	0.976	0.940
365	0.971	0.930
350	0.940	0.860
334	0.850	0.670
320	0.690	0.390
310	0.490	0.170
300	0.220	0.030
290	0.030	
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  34/29

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.3058
$P_{C,s}$	0.5576
$P_{d,C}$	0.3070
$P_{e,d}$	0.2386
$P_{g,F}$	0.5368
$P_{i,h}$	0.7540

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3036
$P'_{C,s}$	0.6024
$P'_{d,C'}$	0.2560
$P'_{e,d}$	0.2369
$P'_{g,F'}$	0.4770
$P'_{i,h}$	0.7486

### Deviation of Rel. Partial Disp. $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0289
$\Delta P_{C,s}$	0.0125
$\Delta P_{F,e}$	-0.0019
$\Delta P_{g,F}$	-0.0043
$\Delta P_{i,g}$	-0.0146

### Chemical Properties

CR	1
FR	0
SR	2
AR	1.2
PR	2.2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	4.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.2
$T_g$ [°C]	519
$T_{10}^{13}$ [°C]	547
$T_{10}^{7.6}$ [°C]	729
$c_p$ [J/(g·K)]	0.770
$\lambda$ [W/(m·K)]	1.042
$\rho$ [g/cm <sup>3</sup> ]	2.47
$E$ [ $10^3$ N/mm <sup>2</sup> ]	70
$\mu$	0.214
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.63
HK <sub>0.1/20</sub>	530

## N-BAK1 573576.319

$n_d = 1.57250$   
 $n_e = 1.57487$

$v_d = 57.55$   
 $v_e = 57.27$

$n_F - n_C = 0.009948$   
 $n_{F'} - n_{C'} = 0.010039$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.54556
$n_{1970.1}$	1970.1	1.55032
$n_{1529.6}$	1529.6	1.55543
$n_{1060.0}$	1060.0	1.56088
$n_t$	1014.0	1.56152
$n_s$	852.1	1.56421
$n_r$	706.5	1.56778
$n_C$	656.3	1.56949
$n_{C'}$	643.8	1.56997
$n_{632.8}$	632.8	1.57041
$n_D$	589.3	1.57241
$n_d$	587.6	1.57250
$n_e$	546.1	1.57487
$n_F$	486.1	1.57943
$n_{F'}$	480.0	1.58000
$n_g$	435.8	1.58488
$n_h$	404.7	1.58941
$n_i$	365.0	1.59716
$n_{334.1}$	334.1	1.60554
$n_{312.6}$	312.6	1.61326
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.123656620
$B_2$	0.309276848
$B_3$	0.881511957
$C_1$	0.006447428
$C_2$	0.0222284402
$C_3$	107.29775100

### Constants of Formula for $dn/dT$

$D_0$	1.86E-07
$D_1$	1.29E-08
$D_2$	-1.87E-11
$E_0$	5.25E-07
$E_1$	5.46E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.182

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.7	2.4	3.0	-0.4	0.2	0.8
+20/+40	1.8	2.5	3.2	0.4	1.2	1.8
+60/+80	1.9	2.7	3.5	0.9	1.7	2.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.810	0.580
2325	0.880	0.720
1970	0.960	0.900
1530	0.994	0.986
1060	0.998	0.996
700	0.999	0.997
660	0.998	0.995
620	0.998	0.995
580	0.998	0.995
546	0.998	0.995
500	0.997	0.992
460	0.996	0.990
436	0.996	0.989
420	0.996	0.990
405	0.996	0.990
400	0.996	0.990
390	0.995	0.988
380	0.993	0.983
370	0.991	0.977
365	0.987	0.969
350	0.971	0.930
334	0.920	0.820
320	0.800	0.570
310	0.610	0.290
300	0.350	0.070
290	0.100	
280	0.010	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  33/29

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2712
$P_{C,s}$	0.5301
$P_{d,C}$	0.3029
$P_{e,d}$	0.2384
$P_{g,F}$	0.5472
$P_{i,h}$	0.7788

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2687
$P'_{C,s}$	0.5730
$P'_{d,C'}$	0.2525
$P'_{e,d}$	0.2362
$P'_{g,F'}$	0.4855
$P'_{i,h}$	0.7717

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0167
$\Delta P_{C,s}$	-0.0069
$\Delta P_{F,e}$	0.0006
$\Delta P_{g,F}$	0.0002
$\Delta P_{i,g}$	-0.0075

### Chemical Properties

CR	2
FR	1
SR	3.3
AR	1.2
PR	2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.6
$T_g$ [°C]	592
$T_{10}^{13}$ [°C]	592
$T_{10}^{7.6}$ [°C]	746
$c_p$ [J/(g·K)]	0.687
$\lambda$ [W/(m·K)]	0.795
$\rho$ [g/cm <sup>3</sup> ]	3.19
$E$ [ $10^3$ N/mm <sup>2</sup> ]	73
$\mu$	0.252
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.62
$HK_{0.1/20}$	530
HG	2

## N-BAK2 540597.286

$n_d = 1.53996$   
 $n_e = 1.54212$

$v_d = 59.71$   
 $v_e = 59.44$

$n_F - n_C = 0.009043$   
 $n_{F'} - n_{C'} = 0.009120$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.51387
$n_{1970.1}$	1970.1	1.51871
$n_{1529.6}$	1529.6	1.52385
$n_{1060.0}$	1060.0	1.52919
$n_t$	1014.0	1.52980
$n_s$	852.1	1.53234
$n_r$	706.5	1.53564
$n_C$	656.3	1.53721
$n_{C'}$	643.8	1.53765
$n_{632.8}$	632.8	1.53806
$n_D$	589.3	1.53988
$n_d$	587.6	1.53996
$n_e$	546.1	1.54212
$n_F$	486.1	1.54625
$n_{F'}$	480.0	1.54677
$n_g$	435.8	1.55117
$n_h$	404.7	1.55525
$n_i$	365.0	1.56221
$n_{334.1}$	334.1	1.56971
$n_{312.6}$	312.6	1.57660
$n_{296.7}$	296.7	1.58287
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.016621540
$B_2$	0.319903051
$B_3$	0.937232995
$C_1$	0.005923838
$C_2$	0.0203828415
$C_3$	113.11841700

### Constants of Formula for $dn/dT$

$D_0$	-1.45E-06
$D_1$	1.10E-08
$D_2$	4.89E-12
$E_0$	5.16E-07
$E_1$	3.05E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.164

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.1	1.8	2.3	-0.9	-0.3	0.2
+20/+40	1.0	1.7	2.3	-0.3	0.3	0.9
+60/+80	1.1	1.8	2.4	0.1	0.8	1.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.760	0.500
2325	0.830	0.630
1970	0.940	0.850
1530	0.994	0.984
1060	0.999	0.997
700	0.998	0.996
660	0.998	0.995
620	0.998	0.994
580	0.998	0.995
546	0.998	0.995
500	0.998	0.994
460	0.997	0.992
436	0.997	0.992
420	0.997	0.993
405	0.997	0.993
400	0.997	0.993
390	0.997	0.992
380	0.996	0.990
370	0.996	0.989
365	0.994	0.986
350	0.988	0.971
334	0.963	0.910
320	0.870	0.700
310	0.690	0.400
300	0.400	0.100
290	0.160	
280	0.040	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  32/28

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2810
$P_{C,s}$	0.5382
$P_{d,C}$	0.3042
$P_{e,d}$	0.2385
$P_{g,F}$	0.5437
$P_{i,h}$	0.7695

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2787
$P'_{C,s}$	0.5817
$P'_{d,C'}$	0.2536
$P'_{e,d}$	0.2364
$P'_{g,F'}$	0.4826
$P'_{i,h}$	0.7630

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	-0.0089
$\Delta P_{C,s}$	-0.0039
$\Delta P_{F,e}$	0.0004
$\Delta P_{g,F}$	0.0004
$\Delta P_{i,g}$	-0.0027

### Chemical Properties

CR	2
FR	0
SR	1
AR	1
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.0
$T_g$ [°C]	554
$T_{10}^{13}$ [°C]	550
$T_{10}^{7.6}$ [°C]	727
$c_p$ [J/(g·K)]	0.690
$\lambda$ [W/(m·K)]	0.920
$\rho$ [g/cm <sup>3</sup> ]	2.86
$E$ [ $10^3$ N/mm <sup>2</sup> ]	71
$\mu$	0.233
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.60
$HK_{0.1/20}$	530
HG	2



## N-BAK4 569560.305

$n_d = 1.56883$

$v_d = 55.98$

$n_F - n_C = 0.010162$

$n_e = 1.57125$

$v_e = 55.70$

$n_F - n_C = 0.010255$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.54044
$n_{1970.1}$	1970.1	1.54561
$n_{1529.6}$	1529.6	1.55111
$n_{1060.0}$	1060.0	1.55688
$n_t$	1014.0	1.55755
$n_s$	852.1	1.56034
$n_r$	706.5	1.56400
$n_C$	656.3	1.56575
$n_{C'}$	643.8	1.56624
$n_{632.8}$	632.8	1.56670
$n_D$	589.3	1.56874
$n_d$	587.6	1.56883
$n_e$	546.1	1.57125
$n_F$	486.1	1.57591
$n_{F'}$	480.0	1.57649
$n_g$	435.8	1.58149
$n_h$	404.7	1.58614
$n_i$	365.0	1.59415
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.288346420
$B_2$	0.132817724
$B_3$	0.945395373
$C_1$	0.007799806
$C_2$	0.0315631177
$C_3$	105.96587500

### Constants of Formula for $dn/dT$

$D_0$	3.06E-06
$D_1$	1.44E-08
$D_2$	-2.23E-11
$E_0$	5.46E-07
$E_1$	6.05E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.189

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.0	3.7	4.4	0.9	1.5	2.2
+20/+40	3.1	3.9	4.7	1.8	2.6	3.3
+60/+80	3.3	4.2	5.0	2.2	3.1	3.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.780	0.540
2325	0.870	0.710
1970	0.959	0.900
1530	0.993	0.982
1060	0.998	0.995
700	0.999	0.997
660	0.998	0.995
620	0.998	0.995
580	0.998	0.996
546	0.998	0.996
500	0.998	0.994
460	0.996	0.989
436	0.995	0.988
420	0.995	0.987
405	0.993	0.983
400	0.992	0.980
390	0.987	0.967
380	0.976	0.940
370	0.954	0.890
365	0.930	0.840
350	0.790	0.550
334	0.350	0.070
320	0.010	
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  36/33

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2749
$P_{C,s}$	0.5321
$P_{d,C}$	0.3029
$P_{e,d}$	0.2383
$P_{g,F}$	0.5487
$P_{i,h}$	0.7879

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2724
$P'_{C,s}$	0.5750
$P'_{d,C'}$	0.2524
$P'_{e,d}$	0.2361
$P'_{g,F'}$	0.4869
$P'_{i,h}$	0.7807

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0034
$\Delta P_{C,s}$	-0.0013
$\Delta P_{F,e}$	-0.0001
$\Delta P_{g,F}$	-0.0010
$\Delta P_{i,g}$	-0.0087

### Chemical Properties

CR	1
FR	0
SR	1.2
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.9
$T_g$ [°C]	581
$T_{10}^{13}$ [°C]	569
$T_{10}^{7.6}$ [°C]	725
$c_p$ [J/(g·K)]	0.680
$\lambda$ [W/(m·K)]	0.880
$\rho$ [g/cm <sup>3</sup> ]	3.05
$E$ [ $10^3$ N/mm <sup>2</sup> ]	77
$\mu$	0.240
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.90
$HK_{0.1/20}$	550
HG	2

## N-BAK4HT 569560.305

$n_d = 1.56883$

$v_d = 55.98$

$n_F - n_C = 0.010162$

$n_e = 1.57125$

$v_e = 55.70$

$n_F - n_C = 0.010255$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.54044
$n_{1970.1}$	1970.1	1.54561
$n_{1529.6}$	1529.6	1.55111
$n_{1060.0}$	1060.0	1.55688
$n_t$	1014.0	1.55755
$n_s$	852.1	1.56034
$n_r$	706.5	1.56400
$n_C$	656.3	1.56575
$n_{C'}$	643.8	1.56624
$n_{632.8}$	632.8	1.56670
$n_D$	589.3	1.56874
$n_d$	587.6	1.56883
$n_e$	546.1	1.57125
$n_F$	486.1	1.57591
$n_{F'}$	480.0	1.57649
$n_g$	435.8	1.58149
$n_h$	404.7	1.58614
$n_i$	365.0	1.59415
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.288346420
$B_2$	0.132817724
$B_3$	0.945395373
$C_1$	0.007799806
$C_2$	0.0315631177
$C_3$	105.96587500

### Constants of Formula for $dn/dT$

$D_0$	3.06E-06
$D_1$	1.44E-08
$D_2$	-2.23E-11
$E_0$	5.46E-07
$E_1$	6.05E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.189

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.0	3.7	4.4	0.9	1.5	2.2
+20/+40	3.1	3.9	4.7	1.8	2.6	3.3
+60/+80	3.3	4.2	5.0	2.2	3.1	3.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.850	0.670
2325	0.920	0.810
1970	0.979	0.950
1530	0.996	0.991
1060	0.999	0.998
700	0.998	0.996
660	0.998	0.996
620	0.998	0.996
580	0.998	0.996
546	0.998	0.996
500	0.998	0.995
460	0.997	0.993
436	0.997	0.992
420	0.996	0.991
405	0.994	0.985
400	0.993	0.983
390	0.989	0.972
380	0.979	0.950
370	0.959	0.900
365	0.940	0.860
350	0.810	0.600
334	0.390	0.100
320	0.020	0.000
310	0.000	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  36/32

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2749
$P_{C,s}$	0.5321
$P_{d,C}$	0.3029
$P_{e,d}$	0.2383
$P_{g,F}$	0.5487
$P_{i,h}$	0.7879

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2724
$P'_{C,s}$	0.5750
$P'_{d,C'}$	0.2524
$P'_{e,d}$	0.2361
$P'_{g,F'}$	0.4869
$P'_{i,h}$	0.7807

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0034
$\Delta P_{C,s}$	-0.0013
$\Delta P_{F,e}$	-0.0001
$\Delta P_{g,F}$	-0.0010
$\Delta P_{i,g}$	-0.0087

### Chemical Properties

CR	1
FR	0
SR	1.2
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.9
$T_g$ [°C]	581
$T_{10}^{13}$ [°C]	569
$T_{10}^{7.6}$ [°C]	725
$c_p$ [J/(g·K)]	0.680
$\lambda$ [W/(m·K)]	0.880
$\rho$ [g/cm <sup>3</sup> ]	3.05
$E$ [ $10^3$ N/mm <sup>2</sup> ]	77
$\mu$	0.240
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.90
$HK_{0.1/20}$	550
HG	2

## N-BAF4 606437.289

$n_d = 1.60568$   
 $n_e = 1.60897$

$v_d = 43.72$   
 $v_e = 43.43$

$n_F - n_C = 0.013853$   
 $n_P - n_C = 0.014021$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.57092
$n_{1970.1}$	1970.1	1.57685
$n_{1529.6}$	1529.6	1.58323
$n_{1060.0}$	1060.0	1.59016
$n_t$	1014.0	1.59099
$n_s$	852.1	1.59452
$n_r$	706.5	1.59926
$n_C$	656.3	1.60157
$n_{C'}$	643.8	1.60222
$n_{632.8}$	632.8	1.60282
$n_D$	589.3	1.60556
$n_d$	587.6	1.60568
$n_e$	546.1	1.60897
$n_F$	486.1	1.61542
$n_{F'}$	480.0	1.61624
$n_g$	435.8	1.62336
$n_h$	404.7	1.63022
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.420563280
$B_2$	0.102721269
$B_3$	1.143809760
$C_1$	0.009420154
$C_2$	0.0531087291
$C_3$	110.27885600

### Constants of Formula for $dn/dT$

$D_0$	9.39E-07
$D_1$	1.24E-08
$D_2$	-9.00E-12
$E_0$	6.17E-07
$E_1$	8.42E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.242

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.2	3.1	4.1	0.1	0.9	1.9
+20/+40	2.2	3.3	4.5	0.9	1.9	3.0
+60/+80	2.4	3.6	4.9	1.3	2.5	3.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.710	0.420
2325	0.840	0.640
1970	0.954	0.890
1530	0.991	0.977
1060	0.998	0.994
700	0.998	0.994
660	0.996	0.991
620	0.996	0.990
580	0.997	0.992
546	0.997	0.992
500	0.994	0.985
460	0.988	0.971
436	0.983	0.959
420	0.976	0.940
405	0.959	0.900
400	0.950	0.870
390	0.900	0.770
380	0.800	0.580
370	0.600	0.280
365	0.440	0.130
350	0.010	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  39/35

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2545
$P_{C,s}$	0.5089
$P_{d,C}$	0.2972
$P_{e,d}$	0.2372
$P_{g,F}$	0.5733
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2515
$P'_{C,s}$	0.5491
$P'_{d,C'}$	0.2473
$P'_{e,d}$	0.2344
$P'_{g,F'}$	0.5081
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0110
$\Delta P_{C,s}$	0.0041
$\Delta P_{F,e}$	0.0002
$\Delta P_{g,F}$	0.0030
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1.2
PR	1.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.3
$T_g$ [°C]	580
$T_{10}^{13}$ [°C]	580
$T_{10}^{7.6}$ [°C]	709
$c_p$ [J/(g·K)]	0.740
$\lambda$ [W/(m·K)]	1.020
$\rho$ [g/cm <sup>3</sup> ]	2.89
$E$ [ $10^3$ N/mm <sup>2</sup> ]	85
$\mu$	0.231
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.58
$HK_{0.1/20}$	610
HG	3

## N-BAF10 670471.375

$n_d = 1.67003$   
 $n_e = 1.67341$

$v_d = 47.11$   
 $v_e = 46.83$

$n_F - n_C = 0.014222$   
 $n_{F'} - n_{C'} = 0.014380$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.63524
$n_{1970.1}$	1970.1	1.64094
$n_{1529.6}$	1529.6	1.64714
$n_{1060.0}$	1060.0	1.65404
$n_t$	1014.0	1.65488
$n_s$	852.1	1.65849
$n_r$	706.5	1.66339
$n_C$	656.3	1.66578
$n_{C'}$	643.8	1.66645
$n_{632.8}$	632.8	1.66708
$n_D$	589.3	1.66990
$n_d$	587.6	1.67003
$n_e$	546.1	1.67341
$n_F$	486.1	1.68000
$n_{F'}$	480.0	1.68083
$n_g$	435.8	1.68801
$n_h$	404.7	1.69480
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.585149500
$B_2$	0.143559385
$B_3$	1.085212690
$C_1$	0.009266813
$C_2$	0.0424489805
$C_3$	105.61357300

### Constants of Formula for $dn/dT$

$D_0$	3.79E-06
$D_1$	1.28E-08
$D_2$	-1.42E-11
$E_0$	5.84E-07
$E_1$	7.60E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.220

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.7	4.7	5.6	1.5	2.4	3.3
+20/+40	3.8	4.9	6.0	2.4	3.5	4.5
+60/+80	4.0	5.2	6.4	2.9	4.1	5.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.730	0.450
2325	0.860	0.680
1970	0.967	0.920
1530	0.992	0.980
1060	0.998	0.994
700	0.998	0.994
660	0.996	0.990
620	0.996	0.991
580	0.996	0.990
546	0.996	0.990
500	0.992	0.981
460	0.987	0.967
436	0.981	0.954
420	0.976	0.940
405	0.959	0.900
400	0.950	0.880
390	0.920	0.800
380	0.850	0.660
370	0.720	0.440
365	0.630	0.310
350	0.180	0.010
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  39/35

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2539
$P_{C,s}$	0.5122
$P_{d,C}$	0.2989
$P_{e,d}$	0.2377
$P_{g,F}$	0.5629
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2511
$P'_{C,s}$	0.5533
$P'_{d,C'}$	0.2489
$P'_{e,d}$	0.2351
$P'_{g,F'}$	0.4990
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	-0.0024
$\Delta P_{C,s}$	-0.0005
$\Delta P_{F,e}$	-0.0003
$\Delta P_{g,F}$	-0.0016
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	4.3
AR	1.3
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.0
$T_g$ [°C]	660
$T_{10}^{13}$ [°C]	652
$T_{10}^{7.6}$ [°C]	790
$c_p$ [J/(g·K)]	0.560
$\lambda$ [W/(m·K)]	0.780
$\rho$ [g/cm <sup>3</sup> ]	3.75
$E$ [ $10^3$ N/mm <sup>2</sup> ]	89
$\mu$	0.271
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.37
$HK_{0.1/20}$	620
HG	4

## N-BAF51 652450.333

$n_d = 1.65224$

$v_d = 44.96$

$n_F - n_C = 0.014507$

$n_e = 1.65569$

$v_e = 44.67$

$n_F - n_C = 0.014677$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.61873
$n_{1970.1}$	1970.1	1.62390
$n_{1529.6}$	1529.6	1.62961
$n_{1060.0}$	1060.0	1.63619
$n_t$	1014.0	1.63701
$n_s$	852.1	1.64059
$n_r$	706.5	1.64551
$n_C$	656.3	1.64792
$n_{C'}$	643.8	1.64860
$n_{632.8}$	632.8	1.64924
$n_D$	589.3	1.65211
$n_d$	587.6	1.65224
$n_e$	546.1	1.65569
$n_F$	486.1	1.66243
$n_{F'}$	480.0	1.66328
$n_g$	435.8	1.67065
$n_h$	404.7	1.67766
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.515036230
$B_2$	0.153621958
$B_3$	1.154279090
$C_1$	0.009427347
$C_2$	0.0430826500
$C_3$	124.88986800

### Constants of Formula for $dn/dT$

$D_0$	-2.84E-07
$D_1$	1.04E-08
$D_2$	-1.80E-11
$E_0$	7.01E-07
$E_1$	8.47E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.219

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.7	2.8	3.8	-0.5	0.5	1.5
+20/+40	1.7	2.9	4.1	0.3	1.5	2.7
+60/+80	1.8	3.1	4.4	0.7	2.0	3.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.750	0.480
2325	0.830	0.630
1970	0.950	0.870
1530	0.992	0.980
1060	0.997	0.993
700	0.997	0.993
660	0.996	0.990
620	0.996	0.990
580	0.997	0.992
546	0.996	0.991
500	0.994	0.985
460	0.988	0.970
436	0.982	0.956
420	0.976	0.940
405	0.963	0.910
400	0.954	0.890
390	0.920	0.820
380	0.860	0.690
370	0.740	0.470
365	0.640	0.330
350	0.210	0.020
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  39/34

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2463
$P_{C,s}$	0.5055
$P_{d,C}$	0.2977
$P_{e,d}$	0.2376
$P_{g,F}$	0.5670
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2435
$P'_{C,s}$	0.5460
$P'_{d,C'}$	0.2479
$P'_{e,d}$	0.2349
$P'_{g,F'}$	0.5024
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0064
$\Delta P_{C,s}$	-0.0022
$\Delta P_{F,e}$	-0.0001
$\Delta P_{g,F}$	-0.0012
$\Delta P_{i,g}$	

### Chemical Properties

CR	2
FR	0
SR	5.4
AR	1.3
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.5
$T_g$ [°C]	569
$T_{10}^{13}$ [°C]	574
$T_{10}^{7.6}$ [°C]	712
$c_p$ [J/(g·K)]	0.840
$\lambda$ [W/(m·K)]	0.670
$\rho$ [g/cm <sup>3</sup> ]	3.33
$E$ [ $10^3$ N/mm <sup>2</sup> ]	91
$\mu$	0.262
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.22
$HK_{0.1/20}$	560
HG	5

## N-BAF52 609466.305

$n_d = 1.60863$

$v_d = 46.60$

$n_F - n_C = 0.013061$

$n_e = 1.61173$

$v_e = 46.30$

$n_F - n_C = 0.013211$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.57475
$n_{1970.1}$	1970.1	1.58067
$n_{1529.6}$	1529.6	1.58702
$n_{1060.0}$	1060.0	1.59381
$n_t$	1014.0	1.59461
$n_s$	852.1	1.59801
$n_r$	706.5	1.60254
$n_C$	656.3	1.60473
$n_{C'}$	643.8	1.60535
$n_{632.8}$	632.8	1.60593
$n_D$	589.3	1.60852
$n_d$	587.6	1.60863
$n_e$	546.1	1.61173
$n_F$	486.1	1.61779
$n_{F'}$	480.0	1.61856
$n_g$	435.8	1.62521
$n_h$	404.7	1.63157
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.439034330
$B_2$	0.096704605
$B_3$	1.098758180
$C_1$	0.009078001
$C_2$	0.0508212080
$C_3$	105.69185600

### Constants of Formula for $dn/dT$

$D_0$	1.15E-06
$D_1$	1.27E-08
$D_2$	-5.08E-12
$E_0$	5.64E-07
$E_1$	6.38E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.238

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.3	3.1	4.0	0.2	0.9	1.8
+20/+40	2.3	3.3	4.3	0.9	1.9	2.9
+60/+80	2.5	3.6	4.7	1.4	2.5	3.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.690	0.390
2325	0.830	0.630
1970	0.954	0.890
1530	0.990	0.975
1060	0.998	0.994
700	0.997	0.993
660	0.996	0.990
620	0.996	0.989
580	0.996	0.990
546	0.996	0.989
500	0.992	0.980
460	0.987	0.967
436	0.981	0.954
420	0.975	0.940
405	0.959	0.900
400	0.950	0.880
390	0.910	0.800
380	0.840	0.650
370	0.670	0.370
365	0.540	0.210
350	0.050	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  39/35

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2600
$P_{C,s}$	0.5147
$P_{d,C}$	0.2985
$P_{e,d}$	0.2374
$P_{g,F}$	0.5678
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2571
$P'_{C,s}$	0.5555
$P'_{d,C'}$	0.2485
$P'_{e,d}$	0.2348
$P'_{g,F'}$	0.5035
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0087
$\Delta P_{C,s}$	0.0031
$\Delta P_{F,e}$	0.0002
$\Delta P_{g,F}$	0.0024
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1.3
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.9
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.8
$T_g$ [°C]	594
$T_{10}^{13}$ [°C]	596
$T_{10}^{7.6}$ [°C]	716
$c_p$ [J/(g·K)]	0.680
$\lambda$ [W/(m·K)]	0.960
$\rho$ [g/cm <sup>3</sup> ]	3.05
$E$ [ $10^3$ N/mm <sup>2</sup> ]	86
$\mu$	0.237
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.42
$HK_{0.1/20}$	600
HG	3

## N-BALF4 580539.311

$n_d = 1.57956$

$v_d = 53.87$

$n_F - n_C = 0.010759$

$n_e = 1.58212$

$v_e = 53.59$

$n_F - n_C = 0.010863$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.55068
$n_{1970.1}$	1970.1	1.55577
$n_{1529.6}$	1529.6	1.56124
$n_{1060.0}$	1060.0	1.56707
$n_t$	1014.0	1.56776
$n_s$	852.1	1.57065
$n_r$	706.5	1.57447
$n_C$	656.3	1.57631
$n_{C'}$	643.8	1.57683
$n_{632.8}$	632.8	1.57731
$n_D$	589.3	1.57946
$n_d$	587.6	1.57956
$n_e$	546.1	1.58212
$n_F$	486.1	1.58707
$n_{F'}$	480.0	1.58769
$n_g$	435.8	1.59301
$n_h$	404.7	1.59799
$n_i$	365.0	1.60658
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.310041280
$B_2$	0.142038259
$B_3$	0.964929351
$C_1$	0.007965965
$C_2$	0.0330672072
$C_3$	109.19732000

### Constants of Formula for $dn/dT$

$D_0$	5.33E-06
$D_1$	1.47E-08
$D_2$	-1.58E-11
$E_0$	5.75E-07
$E_1$	6.58E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.195

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.1	4.9	5.6	2.0	2.7	3.4
+20/+40	4.2	5.1	6.0	2.9	3.7	4.6
+60/+80	4.4	5.4	6.4	3.4	4.3	5.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.800	0.580
2325	0.890	0.740
1970	0.967	0.920
1530	0.994	0.984
1060	0.997	0.993
700	0.999	0.997
660	0.998	0.995
620	0.998	0.995
580	0.998	0.996
546	0.998	0.995
500	0.997	0.993
460	0.994	0.986
436	0.993	0.983
420	0.992	0.981
405	0.988	0.970
400	0.985	0.964
390	0.976	0.940
380	0.959	0.900
370	0.920	0.820
365	0.890	0.750
350	0.680	0.380
334	0.160	
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  37/33

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2687
$P_{C,s}$	0.5265
$P_{d,C}$	0.3019
$P_{e,d}$	0.2382
$P_{g,F}$	0.5520
$P_{i,h}$	0.7986
<b>Relative Partial Dispersion P'</b>	
$P'_{s,t}$	0.2661
$P'_{C,s}$	0.5689
$P'_{d,C'}$	0.2515
$P'_{e,d}$	0.2359
$P'_{g,F'}$	0.4897
$P'_{i,h}$	0.7909

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0053
$\Delta P_{C,s}$	-0.0019
$\Delta P_{F,e}$	-0.0001
$\Delta P_{g,F}$	-0.0012
$\Delta P_{i,g}$	-0.0114

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$T_g$ [°C]	578
$T_{10}^{13}$ [°C]	584
$T_{10}^{7.6}$ [°C]	661
$c_p$ [J/(g·K)]	0.690
$\lambda$ [W/(m·K)]	0.850
$\rho$ [g/cm <sup>3</sup> ]	3.11
$E$ [ $10^3$ N/mm <sup>2</sup> ]	77
$\mu$	0.245
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.01
$HK_{0.1/20}$	540
HG	2

## N-BALF5 547536.261

$n_d = 1.54739$

$v_d = 53.63$

$n_F - n_C = 0.010207$

$n_e = 1.54982$

$v_e = 53.36$

$n_F - n_C = 0.010303$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	
$n_{1970.1}$	1970.1	
$n_{1529.6}$	1529.6	
$n_{1060.0}$	1060.0	1.53529
$n_t$	1014.0	1.53598
$n_s$	852.1	1.53885
$n_r$	706.5	1.54255
$n_C$	656.3	1.54430
$n_{C'}$	643.8	1.54479
$n_{632.8}$	632.8	1.54525
$n_D$	589.3	1.54730
$n_d$	587.6	1.54739
$n_e$	546.1	1.54982
$n_F$	486.1	1.55451
$n_{F'}$	480.0	1.55510
$n_g$	435.8	1.56016
$n_h$	404.7	1.56491
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.283859650
$B_2$	0.071930094
$B_3$	1.050489270
$C_1$	0.008258160
$C_2$	0.0441920027
$C_3$	107.09732400

### Constants of Formula for $dn/dT$

$D_0$	1.14E-06
$D_1$	1.29E-08
$D_2$	-1.46E-11
$E_0$	5.02E-07
$E_1$	5.87E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.219

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.1	2.8	3.5	0.1	0.7	1.3
+20/+40	2.1	2.9	3.7	0.8	1.6	2.3
+60/+80	2.3	3.1	3.9	1.3	2.1	2.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.620	0.300
2325	0.760	0.500
1970	0.920	0.810
1530	0.989	0.973
1060	0.996	0.991
700	0.998	0.995
660	0.997	0.993
620	0.997	0.993
580	0.998	0.995
546	0.998	0.995
500	0.997	0.992
460	0.995	0.988
436	0.994	0.984
420	0.991	0.978
405	0.986	0.965
400	0.983	0.957
390	0.967	0.920
380	0.940	0.850
370	0.870	0.710
365	0.820	0.600
350	0.440	0.130
334	0.010	
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  37/34

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2810
$P_{C,s}$	0.5345
$P_{d,C}$	0.3025
$P_{e,d}$	0.2380
$P_{g,F}$	0.5532
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2783
$P'_{C,s}$	0.5771
$P'_{d,C'}$	0.2520
$P'_{e,d}$	0.2357
$P'_{g,F'}$	0.4909
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0161
$\Delta P_{C,s}$	0.0066
$\Delta P_{F,e}$	-0.0007
$\Delta P_{g,F}$	-0.0004
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	2
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$T_g$ [°C]	558
$T_{10}^{13}$ [°C]	559
$T_{10}^{7.6}$ [°C]	711
$c_p$ [J/(g·K)]	0.810
$\lambda$ [W/(m·K)]	1.050
$\rho$ [g/cm <sup>3</sup> ]	2.61
$E$ [ $10^3$ N/mm <sup>2</sup> ]	81
$\mu$	0.214
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.76
$HK_{0.1/20}$	600
HG	2



## N-SK2 607567.355

$n_d = 1.60738$   
 $n_e = 1.60994$

$v_d = 56.65$   
 $v_e = 56.37$

$n_F - n_C = 0.010722$   
 $n_{F'} - n_{C'} = 0.010821$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.57881
$n_{1970.1}$	1970.1	1.58378
$n_{1529.6}$	1529.6	1.58914
$n_{1060.0}$	1060.0	1.59490
$n_t$	1014.0	1.59558
$n_s$	852.1	1.59847
$n_r$	706.5	1.60230
$n_C$	656.3	1.60414
$n_{C'}$	643.8	1.60465
$n_{632.8}$	632.8	1.60513
$n_D$	589.3	1.60729
$n_d$	587.6	1.60738
$n_e$	546.1	1.60994
$n_F$	486.1	1.61486
$n_{F'}$	480.0	1.61547
$n_g$	435.8	1.62073
$n_h$	404.7	1.62562
$n_i$	365.0	1.63398
$n_{334.1}$	334.1	1.64304
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.281890120
$B_2$	0.257738258
$B_3$	0.968186040
$C_1$	0.007271916
$C_2$	0.0242823527
$C_3$	110.37777300

### Constants of Formula for $dn/dT$

$D_0$	3.80E-06
$D_1$	1.41E-08
$D_2$	2.28E-11
$E_0$	6.44E-07
$E_1$	8.03E-11
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.108

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.7	4.6	5.3	1.5	2.4	3.1
+20/+40	3.6	4.5	5.3	2.3	3.1	3.9
+60/+80	4.0	4.9	5.7	2.9	3.8	4.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.820	0.600
2325	0.900	0.760
1970	0.971	0.930
1530	0.995	0.988
1060	0.998	0.995
700	0.998	0.995
660	0.998	0.994
620	0.998	0.994
580	0.998	0.995
546	0.998	0.995
500	0.996	0.990
460	0.993	0.983
436	0.993	0.982
420	0.994	0.984
405	0.994	0.985
400	0.994	0.984
390	0.992	0.979
380	0.988	0.970
370	0.976	0.940
365	0.967	0.920
350	0.910	0.780
334	0.750	0.490
320	0.500	0.180
310	0.280	0.040
300	0.100	
290	0.020	
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  33/28

### Remarks

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2690
$P_{C,s}$	0.5285
$P_{d,C}$	0.3027
$P_{e,d}$	0.2384
$P_{g,F}$	0.5477
$P_{i,h}$	0.7802

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2666
$P'_{C,s}$	0.5713
$P'_{d,C'}$	0.2523
$P'_{e,d}$	0.2362
$P'_{g,F'}$	0.4860
$P'_{i,h}$	0.7730

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0162
$\Delta P_{C,s}$	-0.0064
$\Delta P_{F,e}$	0.0003
$\Delta P_{g,F}$	-0.0008
$\Delta P_{i,g}$	-0.0130

### Chemical Properties

CR	2
FR	0
SR	2.2
AR	1
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$T_g$ [°C]	659
$T_{10}^{13}$ [°C]	659
$T_{10}^{7.6}$ [°C]	823
$c_p$ [J/(g·K)]	0.595
$\lambda$ [W/(m·K)]	0.776
$\rho$ [g/cm <sup>3</sup> ]	3.55
$E$ [ $10^3$ N/mm <sup>2</sup> ]	78
$\mu$	0.263
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.31
$HK_{0.1/20}$	550
HG	2

## N-SK2HT 607567.355

$n_d = 1.60738$   
 $n_e = 1.60994$

$v_d = 56.65$   
 $v_e = 56.37$

$n_F - n_C = 0.010722$   
 $n_P - n_C = 0.010821$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.57881
$n_{1970.1}$	1970.1	1.58378
$n_{1529.6}$	1529.6	1.58914
$n_{1060.0}$	1060.0	1.59490
$n_t$	1014.0	1.59558
$n_s$	852.1	1.59847
$n_r$	706.5	1.60230
$n_C$	656.3	1.60414
$n_{C'}$	643.8	1.60465
$n_{632.8}$	632.8	1.60513
$n_D$	589.3	1.60729
$n_d$	587.6	1.60738
$n_e$	546.1	1.60994
$n_F$	486.1	1.61486
$n_{F'}$	480.0	1.61547
$n_g$	435.8	1.62073
$n_h$	404.7	1.62562
$n_i$	365.0	1.63398
$n_{334.1}$	334.1	1.64304
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.281890120
$B_2$	0.257738258
$B_3$	0.968186040
$C_1$	0.007271916
$C_2$	0.0242823527
$C_3$	110.37777300

### Constants of Formula for $dn/dT$

$D_0$	3.80E-06
$D_1$	1.41E-08
$D_2$	2.28E-11
$E_0$	6.44E-07
$E_1$	8.03E-11
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.108

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.7	4.6	5.3	1.5	2.4	3.1
+20/+40	3.6	4.5	5.3	2.3	3.1	3.9
+60/+80	4.0	4.9	5.7	2.9	3.8	4.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.810	0.590
2325	0.890	0.750
1970	0.976	0.940
1530	0.995	0.987
1060	0.998	0.996
700	0.999	0.997
660	0.998	0.996
620	0.998	0.996
580	0.999	0.997
546	0.999	0.997
500	0.998	0.995
460	0.997	0.992
436	0.996	0.991
420	0.997	0.992
405	0.996	0.991
400	0.996	0.990
390	0.994	0.986
380	0.992	0.980
370	0.987	0.968
365	0.983	0.957
350	0.955	0.890
334	0.870	0.700
320	0.650	0.350
310	0.390	0.090
300	0.130	0.000
290	0.010	
280	0.000	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  33/28

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2690
$P_{C,s}$	0.5285
$P_{d,C}$	0.3027
$P_{e,d}$	0.2384
$P_{g,F}$	0.5477
$P_{i,h}$	0.7802

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2666
$P'_{C,s}$	0.5713
$P'_{d,C'}$	0.2523
$P'_{e,d}$	0.2362
$P'_{g,F'}$	0.4860
$P'_{i,h}$	0.7730

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0162
$\Delta P_{C,s}$	-0.0064
$\Delta P_{F,e}$	0.0003
$\Delta P_{g,F}$	-0.0008
$\Delta P_{i,g}$	-0.0130

### Chemical Properties

CR	2
FR	0
SR	2.2
AR	1
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$T_g$ [°C]	659
$T_{10}^{13}$ [°C]	659
$T_{10}^{7.6}$ [°C]	823
$c_p$ [J/(g·K)]	0.595
$\lambda$ [W/(m·K)]	0.776
$\rho$ [g/cm <sup>3</sup> ]	3.55
$E$ [ $10^3$ N/mm <sup>2</sup> ]	78
$\mu$	0.263
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.31
$HK_{0.1/20}$	550
HG	2

## N-SK4 613586.354

$n_d = 1.61272$

$v_d = 58.63$

$n_F - n_C = 0.010450$

$n_e = 1.61521$

$v_e = 58.37$

$n_F - n_C = 0.010541$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.58282
$n_{1970.1}$	1970.1	1.58835
$n_{1529.6}$	1529.6	1.59422
$n_{1060.0}$	1060.0	1.60032
$n_t$	1014.0	1.60102
$n_s$	852.1	1.60393
$n_r$	706.5	1.60774
$n_C$	656.3	1.60954
$n_{C'}$	643.8	1.61005
$n_{632.8}$	632.8	1.61052
$n_D$	589.3	1.61262
$n_d$	587.6	1.61272
$n_e$	546.1	1.61521
$n_F$	486.1	1.61999
$n_{F'}$	480.0	1.62059
$n_g$	435.8	1.62568
$n_h$	404.7	1.63042
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.329937410
$B_2$	0.228542996
$B_3$	0.988465211
$C_1$	0.007168741
$C_2$	0.0246455892
$C_3$	100.88636400

### Constants of Formula for $dn/dT$

$D_0$	7.96E-07
$D_1$	1.30E-08
$D_2$	-1.31E-11
$E_0$	4.36E-07
$E_1$	6.01E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.179

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.0	2.6	3.1	-0.1	0.4	0.9
+20/+40	2.1	2.8	3.4	0.7	1.4	2.0
+60/+80	2.3	3.0	3.7	1.2	1.9	2.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.690	0.390
2325	0.830	0.620
1970	0.959	0.900
1530	0.991	0.977
1060	0.997	0.993
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.995
546	0.998	0.995
500	0.997	0.992
460	0.994	0.985
436	0.993	0.983
420	0.993	0.983
405	0.992	0.979
400	0.990	0.975
390	0.984	0.960
380	0.971	0.930
370	0.950	0.870
365	0.930	0.830
350	0.820	0.610
334	0.530	0.200
320	0.100	
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  36/32

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2792
$P_{C,s}$	0.5366
$P_{d,C}$	0.3039
$P_{e,d}$	0.2384
$P_{g,F}$	0.5448
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2768
$P'_{C,s}$	0.5799
$P'_{d,C'}$	0.2533
$P'_{e,d}$	0.2364
$P'_{g,F'}$	0.4835
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0073
$\Delta P_{C,s}$	-0.0030
$\Delta P_{F,e}$	0.0001
$\Delta P_{g,F}$	-0.0004
$\Delta P_{i,g}$	

### Chemical Properties

CR	3
FR	1
SR	51.2
AR	2
PR	2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$T_g$ [°C]	658
$T_{10}^{13}$ [°C]	646
$T_{10}^{7.6}$ [°C]	769
$c_p$ [J/(g·K)]	0.570
$\lambda$ [W/(m·K)]	0.830
$\rho$ [g/cm <sup>3</sup> ]	3.54
$E$ [ $10^3$ N/mm <sup>2</sup> ]	84
$\mu$	0.261
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.92
$HK_{0.1/20}$	580
HG	3

## N-SK5 589613.330

$n_d = 1.58913$

$v_d = 61.27$

$n_F - n_C = 0.009616$

$n_e = 1.59142$

$v_e = 61.02$

$n_F - n_C = 0.009692$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.55966
$n_{1970.1}$	1970.1	1.56539
$n_{1529.6}$	1529.6	1.57140
$n_{1060.0}$	1060.0	1.57747
$n_t$	1014.0	1.57815
$n_s$	852.1	1.58094
$n_r$	706.5	1.58451
$n_C$	656.3	1.58619
$n_{C'}$	643.8	1.58666
$n_{632.8}$	632.8	1.58710
$n_D$	589.3	1.58904
$n_d$	587.6	1.58913
$n_e$	546.1	1.59142
$n_F$	486.1	1.59581
$n_{F'}$	480.0	1.59635
$n_g$	435.8	1.60100
$n_h$	404.7	1.60530
$n_i$	365.0	1.61260
$n_{334.1}$	334.1	1.62043
$n_{312.6}$	312.6	1.62759
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	0.991463823
$B_2$	0.495982121
$B_3$	0.987393925
$C_1$	0.005227305
$C_2$	0.0172733646
$C_3$	98.35945790

### Constants of Formula for $dn/dT$

$D_0$	3.50E-06
$D_1$	1.22E-08
$D_2$	6.38E-11
$E_0$	2.46E-07
$E_1$	-3.34E-11
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.278

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.5	4.0	4.6	1.4	1.9	2.4
+20/+40	3.2	3.7	4.3	1.9	2.3	2.9
+60/+80	3.6	4.1	4.7	2.6	3.0	3.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.680	0.380
2325	0.840	0.640
1970	0.963	0.910
1530	0.992	0.980
1060	0.999	0.997
700	0.998	0.995
660	0.998	0.994
620	0.997	0.993
580	0.998	0.995
546	0.998	0.996
500	0.998	0.994
460	0.996	0.989
436	0.995	0.987
420	0.994	0.986
405	0.993	0.983
400	0.992	0.981
390	0.988	0.971
380	0.984	0.960
370	0.976	0.940
365	0.971	0.930
350	0.920	0.820
334	0.800	0.580
320	0.590	0.270
310	0.400	0.100
300	0.210	0.020
290	0.090	
280	0.030	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  34/29

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2904
$P_{C,s}$	0.5460
$P_{d,C}$	0.3055
$P_{e,d}$	0.2386
$P_{g,F}$	0.5400
$P_{i,h}$	0.7591

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2881
$P'_{C,s}$	0.5901
$P'_{d,C'}$	0.2547
$P'_{e,d}$	0.2367
$P'_{g,F'}$	0.4796
$P'_{i,h}$	0.7531

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0008
$\Delta P_{C,s}$	0.0003
$\Delta P_{F,e}$	-0.0002
$\Delta P_{g,F}$	-0.0007
$\Delta P_{i,g}$	-0.0045

### Chemical Properties

CR	3
FR	1
SR	4.4
AR	2
PR	1.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.5
$T_g$ [°C]	660
$T_{10}^{13}$ [°C]	657
$T_{10}^{7.6}$ [°C]	791
$c_p$ [J/(g·K)]	0.560
$\lambda$ [W/(m·K)]	0.990
$\rho$ [g/cm <sup>3</sup> ]	3.30
$E$ [ $10^3$ N/mm <sup>2</sup> ]	84
$\mu$	0.256
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.16
$HK_{0.1/20}$	590
HG	3

## N-SK5HTi 589613.330

$n_d = 1.58913$

$v_d = 61.27$

$n_F - n_C = 0.009616$

$n_e = 1.59142$

$v_e = 61.02$

$n_F - n_C = 0.009692$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.55966
$n_{1970.1}$	1970.1	1.56539
$n_{1529.6}$	1529.6	1.57140
$n_{1060.0}$	1060.0	1.57747
$n_t$	1014.0	1.57815
$n_s$	852.1	1.58094
$n_r$	706.5	1.58451
$n_C$	656.3	1.58619
$n_{C'}$	643.8	1.58666
$n_{632.8}$	632.8	1.58710
$n_D$	589.3	1.58904
$n_d$	587.6	1.58913
$n_e$	546.1	1.59142
$n_F$	486.1	1.59581
$n_{F'}$	480.0	1.59635
$n_g$	435.8	1.60100
$n_h$	404.7	1.60530
$n_i$	365.0	1.61260
$n_{334.1}$	334.1	1.62043
$n_{312.6}$	312.6	1.62759
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	0.991463823
$B_2$	0.495982121
$B_3$	0.987393925
$C_1$	0.005227305
$C_2$	0.0172733646
$C_3$	98.35945790

### Constants of Formula for $dn/dT$

$D_0$	3.50E-06
$D_1$	1.22E-08
$D_2$	6.38E-11
$E_0$	2.46E-07
$E_1$	-3.34E-11
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.278

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.5	4.0	4.6	1.4	1.9	2.4
+20/+40	3.2	3.7	4.3	1.9	2.3	2.9
+60/+80	3.6	4.1	4.7	2.6	3.0	3.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.957	0.900
2325	0.989	0.973
1970	0.990	0.976
1530	0.995	0.987
1060	1.000	0.999
700	0.999	0.998
660	0.999	0.998
620	0.998	0.995
580	0.998	0.995
546	0.998	0.996
500	0.998	0.994
460	0.997	0.993
436	0.997	0.992
420	0.997	0.992
405	0.997	0.993
400	0.997	0.992
390	0.997	0.992
380	0.996	0.989
370	0.993	0.983
365	0.991	0.978
350	0.981	0.952
334	0.940	0.870
320	0.840	0.650
310	0.720	0.440
300	0.540	0.220
290	0.320	0.060
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  0,000000

### Remarks

i-line glass

### Relative Partial Dispersion P

$P_{s,t}$	0.2904
$P_{C,s}$	0.5460
$P_{d,C}$	0.3055
$P_{e,d}$	0.2386
$P_{g,F}$	0.5400
$P_{i,h}$	0.7591

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2881
$P'_{C,s}$	0.5901
$P'_{d,C'}$	0.2547
$P'_{e,d}$	0.2367
$P'_{g,F'}$	0.4796
$P'_{i,h}$	0.7531

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0008
$\Delta P_{C,s}$	0.0003
$\Delta P_{F,e}$	-0.0002
$\Delta P_{g,F}$	-0.0007
$\Delta P_{i,g}$	-0.0045

### Chemical Properties

CR	3
FR	1
SR	4.4
AR	2
PR	1.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.5
$T_g$ [°C]	660
$T_{10}^{13}$ [°C]	657
$T_{10}^{7.6}$ [°C]	791
$c_p$ [J/(g·K)]	0.560
$\lambda$ [W/(m·K)]	0.990
$\rho$ [g/cm <sup>3</sup> ]	3.30
$E$ [ $10^3$ N/mm <sup>2</sup> ]	84
$\mu$	0.256
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.16
HK <sub>0.1/20</sub>	590
HG	3

## N-SK11 564608.308

$n_d = 1.56384$

$v_d = 60.80$

$n_F - n_C = 0.009274$

$n_e = 1.56605$

$v_e = 60.55$

$n_F - n_C = 0.009349$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.53598
$n_{1970.1}$	1970.1	1.54131
$n_{1529.6}$	1529.6	1.54693
$n_{1060.0}$	1060.0	1.55266
$n_t$	1014.0	1.55330
$n_s$	852.1	1.55597
$n_r$	706.5	1.55939
$n_C$	656.3	1.56101
$n_{C'}$	643.8	1.56146
$n_{632.8}$	632.8	1.56188
$n_D$	589.3	1.56376
$n_d$	587.6	1.56384
$n_e$	546.1	1.56605
$n_F$	486.1	1.57028
$n_{F'}$	480.0	1.57081
$n_g$	435.8	1.57530
$n_h$	404.7	1.57946
$n_i$	365.0	1.58653
$n_{334.1}$	334.1	1.59414
$n_{312.6}$	312.6	1.60110
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.179636310
$B_2$	0.229817295
$B_3$	0.935789652
$C_1$	0.006802821
$C_2$	0.0219737205
$C_3$	101.51323200

### Constants of Formula for $dn/dT$

$D_0$	2.14E-06
$D_1$	1.27E-08
$D_2$	-7.21E-11
$E_0$	3.51E-07
$E_1$	5.41E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.238

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.4	2.8	3.4	0.3	0.7	1.2
+20/+40	2.6	3.2	3.8	1.2	1.8	2.4
+60/+80	2.5	3.2	3.9	1.5	2.1	2.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.78	0.54
2325	0.88	0.73
1970	0.967	0.92
1530	0.994	0.984
1060	0.998	0.995
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.996
546	0.999	0.997
500	0.998	0.994
460	0.996	0.990
436	0.995	0.988
420	0.994	0.985
405	0.992	0.980
400	0.990	0.975
390	0.988	0.970
380	0.985	0.963
370	0.980	0.950
365	0.976	0.94
350	0.950	0.88
334	0.87	0.71
320	0.70	0.41
310	0.48	0.16
300	0.21	0.02
290	0.06	
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  34/29

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2874
$P_{C,s}$	0.5436
$P_{d,C}$	0.3051
$P_{e,d}$	0.2385
$P_{g,F}$	0.5411
$P_{i,h}$	0.7626

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2850
$P'_{C,s}$	0.5875
$P'_{d,C'}$	0.2544
$P'_{e,d}$	0.2366
$P'_{g,F'}$	0.4805
$P'_{i,h}$	0.7564

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0024
$\Delta P_{C,s}$	-0.0011
$\Delta P_{F,e}$	0.0000
$\Delta P_{g,F}$	-0.0004
$\Delta P_{i,g}$	-0.0037

### Chemical Properties

CR	2
FR	0
SR	2
AR	1
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.6
$T_g$ [°C]	610
$T_{10}^{13}$ [°C]	601
$T_{10}^{7.6}$ [°C]	760
$c_p$ [J/(g·K)]	0.650
$\lambda$ [W/(m·K)]	0.920
$\rho$ [g/cm <sup>3</sup> ]	3.08
$E$ [ $10^3$ N/mm <sup>2</sup> ]	79
$\mu$	0.239
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.45
$HK_{0.1/20}$	570
HG	2

## N-SK14 603606.343

$n_d = 1.60311$

$v_d = 60.60$

$n_F - n_C = 0.009953$

$n_e = 1.60548$

$v_e = 60.34$

$n_F - n_C = 0.010034$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.57336
$n_{1970.1}$	1970.1	1.57903
$n_{1529.6}$	1529.6	1.58502
$n_{1060.0}$	1060.0	1.59113
$n_t$	1014.0	1.59182
$n_s$	852.1	1.59467
$n_r$	706.5	1.59834
$n_C$	656.3	1.60008
$n_{C'}$	643.8	1.60056
$n_{632.8}$	632.8	1.60101
$n_D$	589.3	1.60302
$n_d$	587.6	1.60311
$n_e$	546.1	1.60548
$n_F$	486.1	1.61003
$n_{F'}$	480.0	1.61059
$n_g$	435.8	1.61542
$n_h$	404.7	1.61988
$n_i$	365.0	1.62748
$n_{334.1}$	334.1	1.63564
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	0.936155374
$B_2$	0.594052018
$B_3$	1.043745830
$C_1$	0.004617165
$C_2$	0.0168859270
$C_3$	103.73626500

### Constants of Formula for $dn/dT$

$D_0$	1.58E-06
$D_1$	1.22E-08
$D_2$	-8.04E-12
$E_0$	4.46E-07
$E_1$	5.22E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.150

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.5	3.0	3.5	0.3	0.8	1.3
+20/+40	2.4	3.1	3.7	1.1	1.7	2.3
+60/+80	2.6	3.3	4.0	1.5	2.2	2.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.68	0.38
2325	0.83	0.63
1970	0.959	0.90
1530	0.992	0.980
1060	0.998	0.994
700	0.998	0.995
660	0.998	0.995
620	0.998	0.995
580	0.998	0.995
546	0.998	0.995
500	0.997	0.993
460	0.995	0.988
436	0.994	0.985
420	0.993	0.983
405	0.991	0.978
400	0.990	0.975
390	0.988	0.970
380	0.981	0.952
370	0.971	0.93
365	0.963	0.91
350	0.91	0.79
334	0.77	0.52
320	0.55	0.22
310	0.35	0.07
300	0.16	
290	0.04	
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  35/29

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2864
$P_{C,s}$	0.5427
$P_{d,C}$	0.3049
$P_{e,d}$	0.2385
$P_{g,F}$	0.5415
$P_{i,h}$	0.7631

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2841
$P'_{C,s}$	0.5865
$P'_{d,C'}$	0.2542
$P'_{e,d}$	0.2366
$P'_{g,F'}$	0.4808
$P'_{i,h}$	0.7569

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	-0.0033
$\Delta P_{C,s}$	-0.0015
$\Delta P_{F,e}$	0.0000
$\Delta P_{g,F}$	-0.0003
$\Delta P_{i,g}$	-0.0044

### Chemical Properties

CR	4
FR	2
SR	51.3
AR	2
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.0
$T_g$ [°C]	654
$T_{10}^{13}$ [°C]	638
$T_{10}^{7.6}$ [°C]	773
$c_p$ [J/(g·K)]	0.636
$\lambda$ [W/(m·K)]	0.851
$\rho$ [g/cm <sup>3</sup> ]	3.43
$E$ [ $10^3$ N/mm <sup>2</sup> ]	86
$\mu$	0.261
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.00
$HK_{0.1/20}$	600
HG	3

## N-SK16 620603.358

$n_d = 1.62041$

$v_d = 60.32$

$n_F - n_C = 0.010285$

$n_e = 1.62286$

$v_e = 60.08$

$n_{F'} - n_{C'} = 0.010368$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.58919
$n_{1970.1}$	1970.1	1.59523
$n_{1529.6}$	1529.6	1.60157
$n_{1060.0}$	1060.0	1.60799
$n_t$	1014.0	1.60871
$n_s$	852.1	1.61167
$n_r$	706.5	1.61548
$n_C$	656.3	1.61727
$n_{C'}$	643.8	1.61777
$n_{632.8}$	632.8	1.61824
$n_D$	589.3	1.62032
$n_d$	587.6	1.62041
$n_e$	546.1	1.62286
$n_F$	486.1	1.62756
$n_{F'}$	480.0	1.62814
$n_g$	435.8	1.63312
$n_h$	404.7	1.63773
$n_i$	365.0	1.64559
$n_{334.1}$	334.1	1.65403
$n_{312.6}$	312.6	1.66178
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.343177740
$B_2$	0.241144399
$B_3$	0.994317969
$C_1$	0.007046873
$C_2$	0.0229005000
$C_3$	92.75085260

### Constants of Formula for $dn/dT$

$D_0$	-2.37E-08
$D_1$	1.32E-08
$D_2$	-1.29E-11
$E_0$	4.09E-07
$E_1$	5.17E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.170

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.6	2.2	2.6	-0.5	-0.1	0.4
+20/+40	1.7	2.3	2.9	0.3	0.9	1.4
+60/+80	1.9	2.6	3.2	0.8	1.5	2.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.580	0.260
2325	0.780	0.540
1970	0.950	0.880
1530	0.989	0.973
1060	0.998	0.995
700	0.998	0.996
660	0.998	0.994
620	0.997	0.993
580	0.998	0.994
546	0.998	0.994
500	0.996	0.991
460	0.994	0.984
436	0.992	0.981
420	0.992	0.979
405	0.990	0.974
400	0.988	0.970
390	0.982	0.956
380	0.971	0.930
370	0.954	0.890
365	0.940	0.860
350	0.870	0.700
334	0.690	0.400
320	0.410	0.110
310	0.210	0.020
300	0.060	
290	0.010	
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  36/30

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2885
$P_{C,s}$	0.5443
$P_{d,C}$	0.3051
$P_{e,d}$	0.2385
$P_{g,F}$	0.5412
$P_{i,h}$	0.7633

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2861
$P'_{C,s}$	0.5882
$P'_{d,C'}$	0.2544
$P'_{e,d}$	0.2366
$P'_{g,F'}$	0.4805
$P'_{i,h}$	0.7572

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0016
$\Delta P_{C,s}$	0.0007
$\Delta P_{F,e}$	-0.0003
$\Delta P_{g,F}$	-0.0011
$\Delta P_{i,g}$	-0.0067

### Chemical Properties

CR	4
FR	4
SR	53.3
AR	3.3
PR	3.2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$T_g$ [°C]	636
$T_{10}^{13}$ [°C]	633
$T_{10}^{7.6}$ [°C]	750
$c_p$ [J/(g·K)]	0.578
$\lambda$ [W/(m·K)]	0.818
$\rho$ [g/cm <sup>3</sup> ]	3.58
$E$ [ $10^3$ N/mm <sup>2</sup> ]	89
$\mu$	0.264
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.90
$HK_{0.1/20}$	600
HG	4



## P-SK57 587596.301

$n_d = 1.58700$

$v_d = 59.60$

$n_F - n_C = 0.009849$

$n_e = 1.58935$

$v_e = 59.36$

$n_{F'} - n_{C'} = 0.009928$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.55688
$n_{1970.1}$	1970.1	1.56271
$n_{1529.6}$	1529.6	1.56885
$n_{1060.0}$	1060.0	1.57507
$n_t$	1014.0	1.57576
$n_s$	852.1	1.57862
$n_r$	706.5	1.58227
$n_C$	656.3	1.58399
$n_{C'}$	643.8	1.58447
$n_{632.8}$	632.8	1.58492
$n_D$	589.3	1.58691
$n_d$	587.6	1.58700
$n_e$	546.1	1.58935
$n_F$	486.1	1.59384
$n_{F'}$	480.0	1.59440
$n_g$	435.8	1.59917
$n_h$	404.7	1.60359
$n_i$	365.0	1.61112
$n_{334.1}$	334.1	1.61923
$n_{312.6}$	312.6	1.62669
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.310534140
$B_2$	0.169376189
$B_3$	1.109877140
$C_1$	0.007408772
$C_2$	0.0254563489
$C_3$	107.75108700

### Constants of Formula for $dn/dT$

$D_0$	2.60E-06
$D_1$	9.40E-09
$D_2$	-2.30E-11
$E_0$	4.90E-07
$E_1$	5.96E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.178

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.0	3.7	4.2	0.9	1.5	2.0
+20/+40	2.9	3.6	4.3	1.5	2.2	2.9
+60/+80	2.9	3.7	4.4	1.8	2.6	3.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.690	0.400
2325	0.830	0.630
1970	0.954	0.890
1530	0.991	0.978
1060	0.999	0.997
700	0.999	0.997
660	0.999	0.997
620	0.999	0.997
580	0.999	0.997
546	0.999	0.997
500	0.998	0.995
460	0.996	0.991
436	0.996	0.989
420	0.995	0.987
405	0.994	0.985
400	0.994	0.984
390	0.992	0.980
380	0.989	0.973
370	0.984	0.960
365	0.980	0.950
350	0.950	0.870
334	0.820	0.610
320	0.480	0.160
310	0.120	0.000
300	0.000	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  34/31

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2902
$P_{C,s}$	0.5454
$P_{d,C}$	0.3053
$P_{e,d}$	0.2385
$P_{g,F}$	0.5412
$P_{i,h}$	0.7644

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2878
$P'_{C,s}$	0.5894
$P'_{d,C'}$	0.2545
$P'_{e,d}$	0.2366
$P'_{g,F'}$	0.4806
$P'_{i,h}$	0.7583

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0079
$\Delta P_{C,s}$	0.0036
$\Delta P_{F,e}$	-0.0008
$\Delta P_{g,F}$	-0.0024
$\Delta P_{i,g}$	-0.0115

### Chemical Properties

CR	4
FR	3
SR	52.3
AR	2
PR	3
SR-J	4
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.9
$T_g$ [°C]	493
$T_{10}^{13}$ [°C]	494
$T_{10}^{7.6}$ [°C]	593
$c_p$ [J/(g·K)]	0.760
$\lambda$ [W/(m·K)]	1.010
AT [°C]	522
$\rho$ [g/cm <sup>3</sup> ]	3.01
E [ $10^3$ N/mm <sup>2</sup> ]	93
$\mu$	0.249
K [ $10^{-6}$ mm <sup>2</sup> /N]	2.17
HK <sub>0.1/20</sub>	535
HG	3
Abrasion Aa	124

## P-SK57Q1 586595.301

$n_d = 1.58600$

$v_d = 59.50$

$n_F - n_C = 0.009849$

$n_e = 1.58835$

$v_e = 59.26$

$n_{F'} - n_{C'} = 0.009928$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.55583
$n_{1970.1}$	1970.1	1.56169
$n_{1529.6}$	1529.6	1.56784
$n_{1060.0}$	1060.0	1.57407
$n_t$	1014.0	1.57476
$n_s$	852.1	1.57762
$n_r$	706.5	1.58127
$n_C$	656.3	1.58299
$n_{C'}$	643.8	1.58347
$n_{632.8}$	632.8	1.58392
$n_D$	589.3	1.58591
$n_d$	587.6	1.58600
$n_e$	546.1	1.58835
$n_F$	486.1	1.59284
$n_{F'}$	480.0	1.59340
$n_g$	435.8	1.59817
$n_h$	404.7	1.60260
$n_i$	365.0	1.61013
$n_{334.1}$	334.1	1.61826
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.305364830
$B_2$	0.171434328
$B_3$	1.101172190
$C_1$	0.007364088
$C_2$	0.0255786047
$C_3$	106.72606000

### Constants of Formula for $dn/dT$

$D_0$	0.00E00
$D_1$	0.00E00
$D_2$	0.00E00
$E_0$	0.00E00
$E_1$	0.00E00
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.000

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	0.0	0.0	0.0	0.0	0.0	0.0
+20/+40	0.0	0.0	0.0	0.0	0.0	0.0
+60/+80	0.0	0.0	0.0	0.0	0.0	0.0

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.690	0.400
2325	0.830	0.630
1970	0.954	0.890
1530	0.991	0.978
1060	0.999	0.997
700	0.999	0.997
660	0.999	0.997
620	0.999	0.997
580	0.999	0.997
546	0.999	0.997
500	0.998	0.995
460	0.996	0.991
436	0.996	0.989
420	0.995	0.987
405	0.994	0.985
400	0.994	0.984
390	0.992	0.980
380	0.989	0.973
370	0.984	0.960
365	0.980	0.950
350	0.950	0.870
334	0.820	0.610
320	0.480	0.160
310	0.120	0.000
300	0.000	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  34/31

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2903
$P_{C,s}$	0.5454
$P_{d,C}$	0.3052
$P_{e,d}$	0.2385
$P_{g,F}$	0.5414
$P_{i,h}$	0.7652

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2880
$P'_{C,s}$	0.5894
$P'_{d,C'}$	0.2545
$P'_{e,d}$	0.2366
$P'_{g,F'}$	0.4807
$P'_{i,h}$	0.7590

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0085
$\Delta P_{C,s}$	0.0038
$\Delta P_{F,e}$	-0.0008
$\Delta P_{g,F}$	-0.0024
$\Delta P_{i,g}$	-0.0113

### Chemical Properties

CR	4
FR	3
SR	52.3
AR	2
PR	3
SR-J	4
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.9
$T_g$ [°C]	493
$T_{10}^{13}$ [°C]	494
$T_{10}^{7.6}$ [°C]	593
$c_p$ [J/(g·K)]	0.760
$\lambda$ [W/(m·K)]	1.010
AT [°C]	522
$\rho$ [g/cm <sup>3</sup> ]	3.01
$E$ [ $10^3$ N/mm <sup>2</sup> ]	93
$\mu$	0.249
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.17
HK <sub>0.1/20</sub>	535
HG	3
Abrasion Aa	124

## P-SK58A 589612.297

$n_d = 1.58913$

$v_d = 61.15$

$n_F - n_C = 0.009634$

$n_e = 1.59143$

$v_e = 60.93$

$n_{F'} - n_{C'} = 0.009707$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.55820
$n_{1970.1}$	1970.1	1.56439
$n_{1529.6}$	1529.6	1.57086
$n_{1060.0}$	1060.0	1.57728
$n_t$	1014.0	1.57799
$n_s$	852.1	1.58086
$n_r$	706.5	1.58449
$n_C$	656.3	1.58618
$n_{C'}$	643.8	1.58665
$n_{632.8}$	632.8	1.58709
$n_D$	589.3	1.58904
$n_d$	587.6	1.58913
$n_e$	546.1	1.59143
$n_F$	486.1	1.59581
$n_{F'}$	480.0	1.59636
$n_g$	435.8	1.60100
$n_h$	404.7	1.60530
$n_i$	365.0	1.61260
$n_{334.1}$	334.1	1.62045
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.316784100
$B_2$	0.171154756
$B_3$	1.125014730
$C_1$	0.007207175
$C_2$	0.0245659595
$C_3$	102.73972800

### Constants of Formula for $dn/dT$

$D_0$	3.16E-06
$D_1$	1.23E-08
$D_2$	-1.08E-11
$E_0$	4.41E-07
$E_1$	3.20E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.176

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.2	3.8	4.4	1.0	1.6	2.2
+20/+40	3.2	3.8	4.4	1.8	2.4	3.0
+60/+80	3.3	4.0	4.7	2.2	2.9	3.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.550	0.220
2325	0.750	0.480
1970	0.920	0.820
1530	0.984	0.961
1060	0.996	0.991
700	0.995	0.988
660	0.995	0.988
620	0.996	0.989
580	0.997	0.992
546	0.998	0.994
500	0.997	0.993
460	0.996	0.989
436	0.995	0.987
420	0.994	0.986
405	0.994	0.985
400	0.994	0.984
390	0.991	0.977
380	0.986	0.965
370	0.980	0.950
365	0.971	0.930
350	0.920	0.820
334	0.750	0.490
320	0.360	0.080
310	0.070	0.000
300	0.000	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  35/31

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2982
$P_{C,s}$	0.5519
$P_{d,C}$	0.3062
$P_{e,d}$	0.2386
$P_{g,F}$	0.5386
$P_{i,h}$	0.7578
Relative Partial Dispersion P'	
$P'_{s,t}$	0.2959
$P'_{C,s}$	0.5963
$P'_{d,C'}$	0.2554
$P'_{e,d}$	0.2368
$P'_{g,F'}$	0.4784
$P'_{i,h}$	0.7521

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0150
$\Delta P_{C,s}$	0.0065
$\Delta P_{F,e}$	-0.0010
$\Delta P_{g,F}$	-0.0023
$\Delta P_{i,g}$	-0.0080

### Chemical Properties

CR	
FR	
SR	
AR	
PR	
SR-J	4
WR-J	2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$T_g$ [°C]	510
$T_{10}^{13}$ [°C]	510
$T_{10}^{7.6}$ [°C]	608
$c_p$ [J/(g·K)]	0.770
$\lambda$ [W/(m·K)]	1.020
AT [°C]	551
$\rho$ [g/cm <sup>3</sup> ]	2.97
$E$ [ $10^3$ N/mm <sup>2</sup> ]	97
$\mu$	0.245
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.12
HK <sub>0.1/20</sub>	662
Abrasion Aa	102

## P-SK60 610579.308

$n_d = 1.61035$

$v_d = 57.90$

$n_F - n_C = 0.010541$

$n_e = 1.61286$

$v_e = 57.66$

$n_F - n_C = 0.010628$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.57831
$n_{1970.1}$	1970.1	1.58450
$n_{1529.6}$	1529.6	1.59102
$n_{1060.0}$	1060.0	1.59762
$n_t$	1014.0	1.59836
$n_s$	852.1	1.60140
$n_r$	706.5	1.60530
$n_C$	656.3	1.60714
$n_{C'}$	643.8	1.60765
$n_{632.8}$	632.8	1.60813
$n_D$	589.3	1.61026
$n_d$	587.6	1.61035
$n_e$	546.1	1.61286
$n_F$	486.1	1.61768
$n_{F'}$	480.0	1.61828
$n_g$	435.8	1.62340
$n_h$	404.7	1.62815
$n_i$	365.0	1.63627
$n_{334.1}$	334.1	1.64506
$n_{312.6}$	312.6	1.65317
$n_{296.7}$	296.7	1.66061
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.407904420
$B_2$	0.143381417
$B_3$	1.165139470
$C_1$	0.007843824
$C_2$	0.0287769365
$C_3$	105.37339700

### Constants of Formula for $dn/dT$

$D_0$	2.41E-06
$D_1$	9.52E-09
$D_2$	-8.08E-12
$E_0$	4.72E-07
$E_1$	6.22E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.193

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.0	3.7	4.3	0.9	1.5	2.1
+20/+40	2.9	3.6	4.3	1.5	2.3	2.9
+60/+80	2.9	3.8	4.5	1.8	2.7	3.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.690	0.400
2325	0.830	0.630
1970	0.959	0.900
1530	0.993	0.983
1060	0.999	0.998
700	0.999	0.997
660	0.998	0.996
620	0.998	0.996
580	0.999	0.998
546	0.999	0.998
500	0.999	0.997
460	0.998	0.995
436	0.998	0.994
420	0.998	0.994
405	0.997	0.993
400	0.997	0.992
390	0.995	0.988
380	0.993	0.983
370	0.990	0.974
365	0.987	0.967
350	0.967	0.920
334	0.910	0.780
320	0.750	0.480
310	0.480	0.160
300	0.150	0.010
290	0.010	0.000
280	0.000	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  33/29

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2887
$P_{C,s}$	0.5438
$P_{d,C}$	0.3049
$P_{e,d}$	0.2384
$P_{g,F}$	0.5427
$P_{i,h}$	0.7702

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2863
$P'_{C,s}$	0.5876
$P'_{d,C'}$	0.2542
$P'_{e,d}$	0.2365
$P'_{g,F'}$	0.4819
$P'_{i,h}$	0.7639

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0128
$\Delta P_{C,s}$	0.0059
$\Delta P_{F,e}$	-0.0012
$\Delta P_{g,F}$	-0.0037
$\Delta P_{i,g}$	-0.0177

### Chemical Properties

CR	3
FR	5
SR	53.4
AR	2.3
PR	3.3
SR-J	4
WR-J	3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.9
$T_g$ [°C]	507
$T_{10}^{13}$ [°C]	509
$T_{10}^{7.6}$ [°C]	606
$c_p$ [J/(g·K)]	0.760
$\lambda$ [W/(m·K)]	1.130
AT [°C]	547
$\rho$ [g/cm <sup>3</sup> ]	3.08
$E$ [ $10^3$ N/mm <sup>2</sup> ]	99
$\mu$	0.253
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.04
HK <sub>0.1/20</sub>	601
Abrasion Aa	86

## N-KF9 523515.250

$n_d = 1.52346$   
 $n_e = 1.52588$

$v_d = 51.54$   
 $v_e = 51.26$

$n_F - n_C = 0.010156$   
 $n_{F'} - n_{C'} = 0.010258$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.49608
$n_{1970.1}$	1970.1	1.50095
$n_{1529.6}$	1529.6	1.50616
$n_{1060.0}$	1060.0	1.51170
$n_t$	1014.0	1.51234
$n_s$	852.1	1.51507
$n_r$	706.5	1.51867
$n_C$	656.3	1.52040
$n_{C'}$	643.8	1.52089
$n_{632.8}$	632.8	1.52134
$n_D$	589.3	1.52337
$n_d$	587.6	1.52346
$n_e$	546.1	1.52588
$n_F$	486.1	1.53056
$n_{F'}$	480.0	1.53114
$n_g$	435.8	1.53620
$n_h$	404.7	1.54096
$n_i$	365.0	1.54925
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.192867780
$B_2$	0.089334657
$B_3$	0.920819805
$C_1$	0.008391547
$C_2$	0.0404010786
$C_3$	112.57244600

### Constants of Formula for $dn/dT$

$D_0$	-1.66E-06
$D_1$	8.44E-09
$D_2$	-1.01E-11
$E_0$	6.10E-07
$E_1$	6.96E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.217

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.1	1.9	2.6	-0.9	-0.2	0.5
+20/+40	0.9	1.8	2.6	-0.4	0.4	1.3
+60/+80	0.9	1.8	2.8	-0.1	0.8	1.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.620	0.300
2325	0.710	0.430
1970	0.890	0.740
1530	0.992	0.981
1060	0.998	0.995
700	0.999	0.997
660	0.998	0.995
620	0.998	0.994
580	0.998	0.996
546	0.998	0.996
500	0.998	0.994
460	0.996	0.990
436	0.995	0.988
420	0.994	0.985
405	0.990	0.975
400	0.986	0.965
390	0.976	0.940
380	0.950	0.880
370	0.900	0.770
365	0.860	0.680
350	0.540	0.210
334	0.030	
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  37/34

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2683
$P_{C,s}$	0.5249
$P_{d,C}$	0.3012
$P_{e,d}$	0.2380
$P_{g,F}$	0.5558
$P_{i,h}$	0.8161

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2657
$P'_{C,s}$	0.5669
$P'_{d,C'}$	0.2509
$P'_{e,d}$	0.2356
$P'_{g,F'}$	0.4930
$P'_{i,h}$	0.8080

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0038
$\Delta P_{C,s}$	0.0018
$\Delta P_{F,e}$	-0.0004
$\Delta P_{g,F}$	-0.0014
$\Delta P_{i,g}$	-0.0075

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	11.0
$T_g$ [°C]	476
$T_{10}^{13}$ [°C]	476
$T_{10}^{7.6}$ [°C]	640
$c_p$ [J/(g*K)]	0.860
$\lambda$ [W/(m*K)]	1.040
$\rho$ [g/cm <sup>3</sup> ]	2.50
$E$ [ $10^3$ N/mm <sup>2</sup> ]	66
$\mu$	0.225
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.74
$HK_{0.1/20}$	480
HG	1

## N-SSK2 622533.353

$n_d = 1.62229$   
 $n_e = 1.62508$

$v_d = 53.27$   
 $v_e = 52.99$

$n_F - n_C = 0.011681$   
 $n_{F'} - n_{C'} = 0.011795$

Refractive Indices		
	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.59149
$n_{1970.1}$	1970.1	1.59685
$n_{1529.6}$	1529.6	1.60260
$n_{1060.0}$	1060.0	1.60880
$n_t$	1014.0	1.60953
$n_s$	852.1	1.61264
$n_r$	706.5	1.61678
$n_C$	656.3	1.61877
$n_{C'}$	643.8	1.61933
$n_{632.8}$	632.8	1.61985
$n_D$	589.3	1.62219
$n_d$	587.6	1.62229
$n_e$	546.1	1.62508
$n_F$	486.1	1.63045
$n_{F'}$	480.0	1.63112
$n_g$	435.8	1.63691
$n_h$	404.7	1.64232
$n_i$	365.0	1.65166
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

Constants of Dispersion Formula	
$B_1$	1.430602700
$B_2$	0.153150554
$B_3$	1.013909040
$C_1$	0.008239830
$C_2$	0.0333736841
$C_3$	106.87082200

Constants of Formula for $dn/dT$	
$D_0$	5.21E-06
$D_1$	1.34E-08
$D_2$	-1.01E-11
$E_0$	5.21E-07
$E_1$	5.87E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.199

Temperature Coefficients of the Refractive Index						
[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.2	5.0	5.8	2.1	2.8	3.5
+20/+40	4.3	5.2	6.1	2.9	3.8	4.6
+60/+80	4.5	5.5	6.4	3.5	4.4	5.3

Internal Transmittance $\tau_i$		
$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.760	0.500
2325	0.880	0.720
1970	0.971	0.930
1530	0.992	0.981
1060	0.997	0.992
700	0.998	0.996
660	0.998	0.994
620	0.997	0.993
580	0.998	0.995
546	0.998	0.995
500	0.997	0.992
460	0.994	0.985
436	0.992	0.980
420	0.990	0.975
405	0.985	0.963
400	0.981	0.954
390	0.967	0.920
380	0.940	0.860
370	0.890	0.750
365	0.850	0.670
350	0.570	0.250
334	0.080	
320		
310		
300		
290		
280		
270		
260		
250		

Color Code	
$\lambda_{80} / \lambda_{5}$	37/33

Remarks
i-line glass

Relative Partial Dispersion P	
$P_{s,t}$	0.2661
$P_{C,s}$	0.5246
$P_{d,C}$	0.3016
$P_{e,d}$	0.2381
$P_{g,F}$	0.5526
$P_{i,h}$	0.7997

Relative Partial Dispersion P'	
$P'_{s,t}$	0.2636
$P'_{C,s}$	0.5669
$P'_{d,C'}$	0.2513
$P'_{e,d}$	0.2358
$P'_{g,F'}$	0.4902
$P'_{i,h}$	0.7920

Deviation of Rel. Partial Disp. $\Delta P$ from the normal line	
$\Delta P_{C,t}$	-0.0069
$\Delta P_{C,s}$	-0.0025
$\Delta P_{F,e}$	-0.0001
$\Delta P_{g,F}$	-0.0016
$\Delta P_{i,g}$	-0.0146

Chemical Properties	
CR	1
FR	0
SR	1.2
AR	1
PR	1

Other Properties	
$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.7
$T_g$ [°C]	653
$T_{10}^{13}$ [°C]	655
$T_{10}^{7.6}$ [°C]	801
$c_p$ [J/(g·K)]	0.580
$\lambda$ [W/(m·K)]	0.810
$\rho$ [g/cm <sup>3</sup> ]	3.53
$E$ [ $10^3$ N/mm <sup>2</sup> ]	82
$\mu$	0.261
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.51
$HK_{0.1/20}$	570
HG	3

## N-SSK5 658509.371

$n_d = 1.65844$

$v_d = 50.88$

$n_F - n_C = 0.012940$

$n_e = 1.66152$

$v_e = 50.59$

$n_F - n_C = 0.013075$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.62581
$n_{1970.1}$	1970.1	1.63128
$n_{1529.6}$	1529.6	1.63720
$n_{1060.0}$	1060.0	1.64371
$n_t$	1014.0	1.64450
$n_s$	852.1	1.64785
$n_r$	706.5	1.65237
$n_C$	656.3	1.65455
$n_{C'}$	643.8	1.65517
$n_{632.8}$	632.8	1.65574
$n_D$	589.3	1.65833
$n_d$	587.6	1.65844
$n_e$	546.1	1.66152
$n_F$	486.1	1.66749
$n_{F'}$	480.0	1.66824
$n_g$	435.8	1.67471
$n_h$	404.7	1.68079
$n_i$	365.0	1.69139
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.592226590
$B_2$	0.103520774
$B_3$	1.051740160
$C_1$	0.009202846
$C_2$	0.0423530072
$C_3$	106.92737400

### Constants of Formula for $dn/dT$

$D_0$	7.29E-07
$D_1$	1.17E-08
$D_2$	-1.50E-11
$E_0$	6.08E-07
$E_1$	7.66E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.189

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.2	3.0	3.9	0.0	0.8	1.6
+20/+40	2.2	3.2	4.2	0.8	1.8	2.7
+60/+80	2.4	3.5	4.5	1.2	2.3	3.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.730	0.450
2325	0.850	0.660
1970	0.963	0.910
1530	0.992	0.980
1060	0.996	0.990
700	0.997	0.993
660	0.997	0.992
620	0.997	0.992
580	0.997	0.993
546	0.996	0.990
500	0.993	0.982
460	0.987	0.968
436	0.982	0.956
420	0.976	0.940
405	0.963	0.910
400	0.959	0.900
390	0.940	0.860
380	0.900	0.760
370	0.800	0.580
365	0.730	0.450
350	0.340	0.060
334	0.020	
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  38/34

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2592
$P_{C,s}$	0.5181
$P_{d,C}$	0.3003
$P_{e,d}$	0.2380
$P_{g,F}$	0.5575
$P_{i,h}$	0.8192
<b>Relative Partial Dispersion P'</b>	
$P'_{s,t}$	0.2566
$P'_{C,s}$	0.5598
$P'_{d,C'}$	0.2502
$P'_{e,d}$	0.2355
$P'_{g,F'}$	0.4944
$P'_{i,h}$	0.8108

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0090
$\Delta P_{C,s}$	-0.0034
$\Delta P_{F,e}$	0.0001
$\Delta P_{g,F}$	-0.0007
$\Delta P_{i,g}$	-0.0081

### Chemical Properties

CR	2
FR	3
SR	52.2
AR	2.2
PR	3.2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.0
$T_g$ [°C]	645
$T_{10}^{13}$ [°C]	637
$T_{10}^{7.6}$ [°C]	751
$c_p$ [J/(g·K)]	0.574
$\lambda$ [W/(m·K)]	
$\rho$ [g/cm <sup>3</sup> ]	3.71
$E$ [ $10^3$ N/mm <sup>2</sup> ]	88
$\mu$	0.278
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.90
$HK_{0.1/20}$	590
HG	5

## N-SSK8 618498.327

$n_d = 1.61773$

$v_d = 49.83$

$n_F - n_C = 0.012397$

$n_e = 1.62068$

$v_e = 49.54$

$n_F - n_C = 0.012529$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.58594
$n_{1970.1}$	1970.1	1.59137
$n_{1529.6}$	1529.6	1.59723
$n_{1060.0}$	1060.0	1.60360
$n_t$	1014.0	1.60436
$n_s$	852.1	1.60759
$n_r$	706.5	1.61192
$n_C$	656.3	1.61401
$n_{C'}$	643.8	1.61460
$n_{632.8}$	632.8	1.61515
$n_D$	589.3	1.61762
$n_d$	587.6	1.61773
$n_e$	546.1	1.62068
$n_F$	486.1	1.62641
$n_{F'}$	480.0	1.62713
$n_g$	435.8	1.63335
$n_h$	404.7	1.63923
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.448578670
$B_2$	0.117965926
$B_3$	1.069375280
$C_1$	0.008693101
$C_2$	0.0421566593
$C_3$	111.30066600

### Constants of Formula for $dn/dT$

$D_0$	5.34E-07
$D_1$	1.27E-08
$D_2$	-1.75E-11
$E_0$	5.40E-07
$E_1$	7.05E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.224

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.9	2.7	3.5	-0.2	0.5	1.3
+20/+40	2.0	2.9	3.9	0.6	1.5	2.4
+60/+80	2.2	3.2	4.2	1.1	2.1	3.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.730	0.460
2325	0.850	0.660
1970	0.959	0.900
1530	0.992	0.980
1060	0.997	0.993
700	0.998	0.994
660	0.996	0.991
620	0.996	0.990
580	0.997	0.992
546	0.997	0.992
500	0.994	0.984
460	0.987	0.969
436	0.982	0.955
420	0.975	0.940
405	0.959	0.900
400	0.950	0.880
390	0.920	0.810
380	0.850	0.660
370	0.730	0.450
365	0.630	0.310
350	0.190	0.010
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  39/35

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2606
$P_{C,s}$	0.5179
$P_{d,C}$	0.2999
$P_{e,d}$	0.2378
$P_{g,F}$	0.5602
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2579
$P'_{C,s}$	0.5594
$P'_{d,C'}$	0.2498
$P'_{e,d}$	0.2353
$P'_{g,F'}$	0.4967
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0028
$\Delta P_{C,s}$	-0.0012
$\Delta P_{F,e}$	0.0001
$\Delta P_{g,F}$	0.0002
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1.3
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.2
$T_g$ [°C]	616
$T_{10}^{13}$ [°C]	604
$T_{10}^{7.6}$ [°C]	742
$c_p$ [J/(g·K)]	0.640
$\lambda$ [W/(m·K)]	0.840
$\rho$ [g/cm <sup>3</sup> ]	3.27
$E$ [ $10^3$ N/mm <sup>2</sup> ]	84
$\mu$	0.251
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.36
$HK_{0.1/20}$	570
HG	3



## N-LAK7 652585.384

$n_d = 1.65160$

$v_d = 58.52$

$n_F - n_C = 0.011135$

$n_e = 1.65425$

$v_e = 58.26$

$n_F - n_C = 0.011229$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.61875
$n_{1970.1}$	1970.1	1.62499
$n_{1529.6}$	1529.6	1.63156
$n_{1060.0}$	1060.0	1.63828
$n_t$	1014.0	1.63904
$n_s$	852.1	1.64220
$n_r$	706.5	1.64628
$n_C$	656.3	1.64821
$n_{C'}$	643.8	1.64875
$n_{632.8}$	632.8	1.64925
$n_D$	589.3	1.65150
$n_d$	587.6	1.65160
$n_e$	546.1	1.65425
$n_F$	486.1	1.65934
$n_{F'}$	480.0	1.65998
$n_g$	435.8	1.66539
$n_h$	404.7	1.67042
$n_i$	365.0	1.67897
$n_{334.1}$	334.1	1.68820
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.236798890
$B_2$	0.445051837
$B_3$	1.017458880
$C_1$	0.006101055
$C_2$	0.0201388334
$C_3$	90.63803800

### Constants of Formula for $dn/dT$

$D_0$	-3.40E-06
$D_1$	1.17E-08
$D_2$	2.38E-11
$E_0$	4.96E-07
$E_1$	4.44E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.107

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	0.2	0.8	1.3	-2.0	-1.5	-1.0
+20/+40	0.0	0.7	1.3	-1.4	-0.7	-0.2
+60/+80	0.3	1.0	1.7	-0.8	-0.1	0.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.550	0.220
2325	0.750	0.490
1970	0.940	0.860
1530	0.989	0.972
1060	0.999	0.998
700	0.999	0.997
660	0.998	0.996
620	0.998	0.995
580	0.998	0.995
546	0.998	0.995
500	0.997	0.992
460	0.994	0.984
436	0.992	0.980
420	0.991	0.977
405	0.989	0.973
400	0.988	0.970
390	0.984	0.961
380	0.978	0.950
370	0.966	0.920
365	0.956	0.890
350	0.910	0.790
334	0.800	0.570
320	0.620	0.300
310	0.420	0.110
300	0.190	0.020
290	0.050	0.000
280	0.000	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  35/29

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2835
$P_{C,s}$	0.5400
$P_{d,C}$	0.3044
$P_{e,d}$	0.2385
$P_{g,F}$	0.5433
$P_{i,h}$	0.7687

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2812
$P'_{C,s}$	0.5836
$P'_{d,C'}$	0.2538
$P'_{e,d}$	0.2365
$P'_{g,F'}$	0.4823
$P'_{i,h}$	0.7622

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0010
$\Delta P_{C,s}$	0.0007
$\Delta P_{F,e}$	-0.0005
$\Delta P_{g,F}$	-0.0021
$\Delta P_{i,g}$	-0.0140

### Chemical Properties

CR	3
FR	2
SR	53.3
AR	3.3
PR	4.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.2
$T_g$ [°C]	618
$T_{10}^{13}$ [°C]	626
$T_{10}^{7.6}$ [°C]	716
$c_p$ [J/(g·K)]	0.530
$\lambda$ [W/(m·K)]	0.740
$\rho$ [g/cm <sup>3</sup> ]	3.84
$E$ [ $10^3$ N/mm <sup>2</sup> ]	90
$\mu$	0.277
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.65
$HK_{0.1/20}$	600
HG	5

## N-LAK8 713538.375

$n_d = 1.71300$

$v_d = 53.83$

$n_F - n_C = 0.013245$

$n_e = 1.71616$

$v_e = 53.61$

$n_F - n_C = 0.013359$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.67294
$n_{1970.1}$	1970.1	1.68075
$n_{1529.6}$	1529.6	1.68890
$n_{1060.0}$	1060.0	1.69710
$n_t$	1014.0	1.69802
$n_s$	852.1	1.70181
$n_r$	706.5	1.70668
$n_C$	656.3	1.70897
$n_{C'}$	643.8	1.70962
$n_{632.8}$	632.8	1.71022
$n_D$	589.3	1.71289
$n_d$	587.6	1.71300
$n_e$	546.1	1.71616
$n_F$	486.1	1.72222
$n_{F'}$	480.0	1.72297
$n_g$	435.8	1.72944
$n_h$	404.7	1.73545
$n_i$	365.0	1.74573
$n_{334.1}$	334.1	1.75687
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.331831670
$B_2$	0.546623206
$B_3$	1.190840150
$C_1$	0.006200239
$C_2$	0.0216465439
$C_3$	82.58277360

### Constants of Formula for $dn/dT$

$D_0$	4.10E-06
$D_1$	1.25E-08
$D_2$	-1.60E-11
$E_0$	4.30E-07
$E_1$	6.29E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.213

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.0	4.7	5.4	1.7	2.4	3.0
+20/+40	4.1	5.0	5.8	2.6	3.5	4.3
+60/+80	4.3	5.2	6.2	3.1	4.1	5.0

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.400	0.100
2325	0.710	0.420
1970	0.950	0.880
1530	0.992	0.979
1060	0.998	0.994
700	0.998	0.996
660	0.998	0.995
620	0.998	0.994
580	0.998	0.994
546	0.998	0.995
500	0.998	0.994
460	0.995	0.987
436	0.992	0.979
420	0.988	0.970
405	0.981	0.952
400	0.977	0.940
390	0.965	0.920
380	0.950	0.870
370	0.910	0.780
365	0.880	0.720
350	0.740	0.470
334	0.510	0.190
320	0.280	0.040
310	0.140	0.010
300	0.040	
290	0.010	
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  37/30

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2861
$P_{C,s}$	0.5408
$P_{d,C}$	0.3042
$P_{e,d}$	0.2383
$P_{g,F}$	0.5450
$P_{i,h}$	0.7764

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2836
$P'_{C,s}$	0.5843
$P'_{d,C'}$	0.2536
$P'_{e,d}$	0.2363
$P'_{g,F'}$	0.4838
$P'_{i,h}$	0.7698

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0266
$\Delta P_{C,s}$	0.0124
$\Delta P_{F,e}$	-0.0026
$\Delta P_{g,F}$	-0.0083
$\Delta P_{i,g}$	-0.0428

### Chemical Properties

CR	3
FR	2
SR	52.3
AR	1
PR	3.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.7
$T_g$ [°C]	643
$T_{10}^{13}$ [°C]	635
$T_{10}^{7.6}$ [°C]	717
$c_p$ [J/(g·K)]	0.620
$\lambda$ [W/(m·K)]	0.840
$\rho$ [g/cm <sup>3</sup> ]	3.75
$E$ [ $10^3$ N/mm <sup>2</sup> ]	115
$\mu$	0.289
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.81
$HK_{0.1/20}$	740
HG	2

## N-LAK9 691547.351

$n_d = 1.69100$   
 $n_e = 1.69401$

$v_d = 54.71$   
 $v_e = 54.48$

$n_F - n_C = 0.012631$   
 $n_{F'} - n_{C'} = 0.012738$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.65294
$n_{1970.1}$	1970.1	1.66032
$n_{1529.6}$	1529.6	1.66804
$n_{1060.0}$	1060.0	1.67584
$n_t$	1014.0	1.67672
$n_s$	852.1	1.68033
$n_r$	706.5	1.68497
$n_C$	656.3	1.68716
$n_{C'}$	643.8	1.68777
$n_{632.8}$	632.8	1.68834
$n_D$	589.3	1.69089
$n_d$	587.6	1.69100
$n_e$	546.1	1.69401
$n_F$	486.1	1.69979
$n_{F'}$	480.0	1.70051
$n_g$	435.8	1.70667
$n_h$	404.7	1.71239
$n_i$	365.0	1.72219
$n_{334.1}$	334.1	1.73281
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.462319050
$B_2$	0.344399589
$B_3$	1.155083720
$C_1$	0.007242702
$C_2$	0.0243353131
$C_3$	85.46868680

### Constants of Formula for $dn/dT$

$D_0$	2.11E-06
$D_1$	1.11E-08
$D_2$	1.82E-12
$E_0$	4.74E-07
$E_1$	-3.47E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.146

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.0	3.9	4.6	0.8	1.6	2.3
+20/+40	2.9	3.7	4.4	1.5	2.2	2.9
+60/+80	3.1	3.8	4.4	2.0	2.7	3.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.460	0.140
2325	0.710	0.420
1970	0.940	0.860
1530	0.986	0.966
1060	0.998	0.995
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.994
546	0.998	0.994
500	0.997	0.992
460	0.994	0.984
436	0.991	0.977
420	0.988	0.970
405	0.983	0.957
400	0.980	0.950
390	0.971	0.930
380	0.954	0.890
370	0.930	0.830
365	0.910	0.780
350	0.790	0.550
334	0.530	0.200
320	0.210	0.020
310	0.070	0.000
300	0.010	
290	0.000	
280	0.000	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  37/31

### Remarks

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2859
$P_{C,s}$	0.5409
$P_{d,C}$	0.3043
$P_{e,d}$	0.2384
$P_{g,F}$	0.5447
$P_{i,h}$	0.7756

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2834
$P'_{C,s}$	0.5844
$P'_{d,C'}$	0.2536
$P'_{e,d}$	0.2363
$P'_{g,F'}$	0.4835
$P'_{i,h}$	0.7690

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0223
$\Delta P_{C,s}$	0.0105
$\Delta P_{F,e}$	-0.0023
$\Delta P_{g,F}$	-0.0071
$\Delta P_{i,g}$	-0.0367

### Chemical Properties

CR	3
FR	3
SR	52
AR	1.2
PR	4.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.5
$T_g$ [°C]	656
$T_{10}^{13}$ [°C]	645
$T_{10}^{7.6}$ [°C]	722
$c_p$ [J/(g·K)]	0.649
$\lambda$ [W/(m·K)]	0.908
$\rho$ [g/cm <sup>3</sup> ]	3.51
$E$ [ $10^3$ N/mm <sup>2</sup> ]	110
$\mu$	0.285
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.83
$HK_{0.1/20}$	700
HG	3

## N-LAK10 720506.369

$n_d = 1.72003$

$v_d = 50.62$

$n_F - n_C = 0.014224$

$n_e = 1.72341$

$v_e = 50.39$

$n_F - n_C = 0.014357$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.67890
$n_{1970.1}$	1970.1	1.68670
$n_{1529.6}$	1529.6	1.69488
$n_{1060.0}$	1060.0	1.70324
$n_t$	1014.0	1.70419
$n_s$	852.1	1.70815
$n_r$	706.5	1.71328
$n_C$	656.3	1.71572
$n_{C'}$	643.8	1.71641
$n_{632.8}$	632.8	1.71705
$n_D$	589.3	1.71990
$n_d$	587.6	1.72003
$n_e$	546.1	1.72341
$n_F$	486.1	1.72995
$n_{F'}$	480.0	1.73077
$n_g$	435.8	1.73779
$n_h$	404.7	1.74438
$n_i$	365.0	1.75578
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.728780170
$B_2$	0.169257825
$B_3$	1.193869560
$C_1$	0.008860146
$C_2$	0.0363416509
$C_3$	82.90090690

### Constants of Formula for $dn/dT$

$D_0$	4.10E-06
$D_1$	1.23E-08
$D_2$	-7.85E-12
$E_0$	5.08E-07
$E_1$	5.76E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.205

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.1	5.0	5.8	1.8	2.6	3.4
+20/+40	4.2	5.1	6.1	2.7	3.6	4.6
+60/+80	4.4	5.4	6.5	3.2	4.3	5.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.430	0.120
2325	0.720	0.440
1970	0.950	0.880
1530	0.991	0.977
1060	0.998	0.995
700	0.998	0.995
660	0.998	0.994
620	0.998	0.994
580	0.997	0.993
546	0.998	0.994
500	0.995	0.988
460	0.991	0.977
436	0.988	0.970
420	0.980	0.951
405	0.970	0.930
400	0.964	0.910
390	0.950	0.880
380	0.920	0.810
370	0.860	0.690
365	0.800	0.580
350	0.500	0.180
334	0.060	
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  38/33

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2779
$P_{C,s}$	0.5328
$P_{d,C}$	0.3025
$P_{e,d}$	0.2381
$P_{g,F}$	0.5515
$P_{i,h}$	0.8015

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2753
$P'_{C,s}$	0.5755
$P'_{d,C'}$	0.2521
$P'_{e,d}$	0.2359
$P'_{g,F'}$	0.4894
$P'_{i,h}$	0.7941

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0256
$\Delta P_{C,s}$	0.0119
$\Delta P_{F,e}$	-0.0024
$\Delta P_{g,F}$	-0.0072
$\Delta P_{i,g}$	-0.0354

### Chemical Properties

CR	2
FR	2
SR	52.3
AR	1
PR	3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.7
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.8
$T_g$ [°C]	636
$T_{10}^{13}$ [°C]	631
$T_{10}^{7.6}$ [°C]	714
$c_p$ [J/(g·K)]	0.640
$\lambda$ [W/(m·K)]	0.860
$\rho$ [g/cm <sup>3</sup> ]	3.69
$E$ [ $10^3$ N/mm <sup>2</sup> ]	116
$\mu$	0.286
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.97
$HK_{0.1/20}$	780
HG	2

## N-LAK12 678552.410

$n_d = 1.67790$

$v_d = 55.20$

$n_F - n_C = 0.012281$

$n_e = 1.68083$

$v_e = 54.92$

$n_F - n_C = 0.012396$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.64541
$n_{1970.1}$	1970.1	1.65107
$n_{1529.6}$	1529.6	1.65713
$n_{1060.0}$	1060.0	1.66366
$n_t$	1014.0	1.66443
$n_s$	852.1	1.66772
$n_r$	706.5	1.67209
$n_C$	656.3	1.67419
$n_{C'}$	643.8	1.67478
$n_{632.8}$	632.8	1.67533
$n_D$	589.3	1.67779
$n_d$	587.6	1.67790
$n_e$	546.1	1.68083
$n_F$	486.1	1.68647
$n_{F'}$	480.0	1.68717
$n_g$	435.8	1.69320
$n_h$	404.7	1.69882
$n_i$	365.0	1.70842
$n_{334.1}$	334.1	1.71881
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.173657040
$B_2$	0.588992398
$B_3$	0.978014394
$C_1$	0.005770318
$C_2$	0.0200401678
$C_3$	95.48734820

### Constants of Formula for $dn/dT$

$D_0$	-5.67E-06
$D_1$	8.27E-09
$D_2$	1.27E-12
$E_0$	5.25E-07
$E_1$	6.30E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.162

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-1.0	-0.3	0.3	-3.2	-2.6	-2.0
+20/+40	-1.2	-0.4	0.3	-2.7	-1.9	-1.2
+60/+80	-1.2	-0.3	0.5	-2.3	-1.5	-0.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.590	0.270
2325	0.760	0.510
1970	0.940	0.850
1530	0.990	0.975
1060	0.997	0.992
700	0.997	0.993
660	0.996	0.989
620	0.995	0.988
580	0.996	0.990
546	0.996	0.991
500	0.994	0.986
460	0.987	0.968
436	0.983	0.958
420	0.981	0.952
405	0.977	0.940
400	0.976	0.940
390	0.967	0.920
380	0.950	0.870
370	0.910	0.790
365	0.880	0.730
350	0.730	0.460
334	0.470	0.150
320	0.150	0.010
310	0.030	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  37/31

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2673
$P_{C,s}$	0.5269
$P_{d,C}$	0.3024
$P_{e,d}$	0.2383
$P_{g,F}$	0.5485
$P_{i,h}$	0.7818

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2648
$P'_{C,s}$	0.5695
$P'_{d,C'}$	0.2521
$P'_{e,d}$	0.2361
$P'_{g,F'}$	0.4866
$P'_{i,h}$	0.7746

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0126
$\Delta P_{C,s}$	-0.0047
$\Delta P_{F,e}$	-0.0001
$\Delta P_{g,F}$	-0.0024
$\Delta P_{i,g}$	-0.0226

### Chemical Properties

CR	3
FR	1
SR	53.3
AR	3.3
PR	4.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.3
$T_g$ [°C]	614
$T_{10}^{13}$ [°C]	606
$T_{10}^{7.6}$ [°C]	714
$c_p$ [J/(g·K)]	0.510
$\lambda$ [W/(m·K)]	0.680
$\rho$ [g/cm <sup>3</sup> ]	4.10
$E$ [ $10^3$ N/mm <sup>2</sup> ]	87
$\mu$	0.288
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.44
$HK_{0.1/20}$	560
HG	6

## N-LAK14 697554.363

$n_d = 1.69680$

$v_d = 55.41$

$n_F - n_C = 0.012575$

$n_e = 1.69980$

$v_e = 55.19$

$n_F - n_C = 0.012679$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.65783
$n_{1970.1}$	1970.1	1.66554
$n_{1529.6}$	1529.6	1.67357
$n_{1060.0}$	1060.0	1.68157
$n_t$	1014.0	1.68246
$n_s$	852.1	1.68612
$n_r$	706.5	1.69077
$n_C$	656.3	1.69297
$n_{C'}$	643.8	1.69358
$n_{632.8}$	632.8	1.69415
$n_D$	589.3	1.69669
$n_d$	587.6	1.69680
$n_e$	546.1	1.69980
$n_F$	486.1	1.70554
$n_{F'}$	480.0	1.70626
$n_g$	435.8	1.71237
$n_h$	404.7	1.71804
$n_i$	365.0	1.72772
$n_{334.1}$	334.1	1.73819
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.507812120
$B_2$	0.318866829
$B_3$	1.142872130
$C_1$	0.007460987
$C_2$	0.0242024834
$C_3$	80.95651650

### Constants of Formula for $dn/dT$

$D_0$	2.68E-06
$D_1$	1.15E-08
$D_2$	-1.44E-11
$E_0$	3.72E-07
$E_1$	5.53E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.226

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.2	3.8	4.4	0.9	1.5	2.1
+20/+40	3.2	4.0	4.7	1.8	2.5	3.2
+60/+80	3.4	4.2	5.0	2.2	3.0	3.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.380	0.090
2325	0.670	0.370
1970	0.930	0.840
1530	0.984	0.960
1060	0.998	0.995
700	0.998	0.995
660	0.998	0.994
620	0.997	0.992
580	0.997	0.993
546	0.998	0.995
500	0.997	0.992
460	0.994	0.984
436	0.991	0.977
420	0.988	0.971
405	0.984	0.960
400	0.981	0.953
390	0.971	0.930
380	0.959	0.900
370	0.930	0.840
365	0.910	0.800
350	0.820	0.610
334	0.640	0.330
320	0.430	0.120
310	0.240	0.040
300	0.090	0.000
290	0.020	
280	0.000	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  36/27

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2903
$P_{C,s}$	0.5447
$P_{d,C}$	0.3049
$P_{e,d}$	0.2384
$P_{g,F}$	0.5427
$P_{i,h}$	0.7701

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2880
$P'_{C,s}$	0.5885
$P'_{d,C'}$	0.2542
$P'_{e,d}$	0.2365
$P'_{g,F'}$	0.4819
$P'_{i,h}$	0.7638

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0273
$\Delta P_{C,s}$	0.0127
$\Delta P_{F,e}$	-0.0026
$\Delta P_{g,F}$	-0.0079
$\Delta P_{i,g}$	-0.0386

### Chemical Properties

CR	3
FR	2
SR	52.3
AR	1
PR	3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.9
$T_g$ [°C]	661
$T_{10}^{13}$ [°C]	653
$T_{10}^{7.6}$ [°C]	734
$c_p$ [J/(g·K)]	0.630
$\lambda$ [W/(m·K)]	0.890
$\rho$ [g/cm <sup>3</sup> ]	3.63
$E$ [ $10^3$ N/mm <sup>2</sup> ]	111
$\mu$	0.283
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.73
$HK_{0.1/20}$	730
HG	2

## N-LAK21 640601.374

$n_d = 1.64049$

$v_d = 60.10$

$n_F - n_C = 0.010657$

$n_e = 1.64304$

$v_e = 59.86$

$n_F - n_C = 0.010743$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.60776
$n_{1970.1}$	1970.1	1.61416
$n_{1529.6}$	1529.6	1.62086
$n_{1060.0}$	1060.0	1.62759
$n_t$	1014.0	1.62834
$n_s$	852.1	1.63143
$n_r$	706.5	1.63538
$n_C$	656.3	1.63724
$n_{C'}$	643.8	1.63776
$n_{632.8}$	632.8	1.63825
$n_D$	589.3	1.64040
$n_d$	587.6	1.64049
$n_e$	546.1	1.64304
$n_F$	486.1	1.64790
$n_{F'}$	480.0	1.64850
$n_g$	435.8	1.65366
$n_h$	404.7	1.65844
$n_i$	365.0	1.66657
$n_{334.1}$	334.1	1.67532
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.227181160
$B_2$	0.420783743
$B_3$	1.012848430
$C_1$	0.006020757
$C_2$	0.0196862889
$C_3$	88.43700990

### Constants of Formula for $dn/dT$

$D_0$	-2.36E-06
$D_1$	1.15E-08
$D_2$	1.11E-11
$E_0$	3.10E-07
$E_1$	2.78E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.234

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	0.6	1.1	1.6	-1.6	-1.2	-0.7
+20/+40	0.5	1.0	1.6	-0.9	-0.4	0.1
+60/+80	0.7	1.3	1.9	-0.4	0.1	0.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.540	0.210
2325	0.750	0.490
1970	0.950	0.870
1530	0.988	0.970
1060	0.998	0.994
700	0.998	0.994
660	0.996	0.991
620	0.996	0.990
580	0.997	0.992
546	0.997	0.992
500	0.995	0.988
460	0.990	0.976
436	0.987	0.969
420	0.985	0.963
405	0.982	0.955
400	0.979	0.950
390	0.971	0.930
380	0.959	0.900
370	0.930	0.830
365	0.910	0.780
350	0.800	0.570
334	0.570	0.240
320	0.250	0.040
310	0.060	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  37/31

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2900
$P_{C,s}$	0.5453
$P_{d,C}$	0.3052
$P_{e,d}$	0.2385
$P_{g,F}$	0.5411
$P_{i,h}$	0.7630

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2877
$P'_{C,s}$	0.5892
$P'_{d,C'}$	0.2545
$P'_{e,d}$	0.2366
$P'_{g,F'}$	0.4804
$P'_{i,h}$	0.7569

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0052
$\Delta P_{C,s}$	0.0023
$\Delta P_{F,e}$	-0.0005
$\Delta P_{g,F}$	-0.0017
$\Delta P_{i,g}$	-0.0090

### Chemical Properties

CR	4
FR	2
SR	53.2
AR	4.3
PR	4.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.1
$T_g$ [°C]	639
$T_{10}^{13}$ [°C]	627
$T_{10}^{7.6}$ [°C]	716
$c_p$ [J/(g·K)]	0.590
$\lambda$ [W/(m·K)]	0.880
$\rho$ [g/cm <sup>3</sup> ]	3.74
$E$ [ $10^3$ N/mm <sup>2</sup> ]	91
$\mu$	0.272
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.74
$HK_{0.1/20}$	600
HG	5

## N-LAK22 651559.377

$n_d = 1.65113$

$v_d = 55.89$

$n_F - n_C = 0.011650$

$n_e = 1.65391$

$v_e = 55.63$

$n_F - n_C = 0.011755$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.61915
$n_{1970.1}$	1970.1	1.62488
$n_{1529.6}$	1529.6	1.63100
$n_{1060.0}$	1060.0	1.63747
$n_t$	1014.0	1.63823
$n_s$	852.1	1.64141
$n_r$	706.5	1.64560
$n_C$	656.3	1.64760
$n_{C'}$	643.8	1.64816
$n_{632.8}$	632.8	1.64868
$n_D$	589.3	1.65103
$n_d$	587.6	1.65113
$n_e$	546.1	1.65391
$n_F$	486.1	1.65925
$n_{F'}$	480.0	1.65992
$n_g$	435.8	1.66562
$n_h$	404.7	1.67092
$n_i$	365.0	1.67997
$n_{334.1}$	334.1	1.68975
$n_{312.6}$	312.6	1.69876
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.142297810
$B_2$	0.535138441
$B_3$	1.040883850
$C_1$	0.005857786
$C_2$	0.0198546147
$C_3$	100.83401700

### Constants of Formula for $dn/dT$

$D_0$	1.36E-06
$D_1$	1.49E-08
$D_2$	-1.29E-11
$E_0$	3.41E-07
$E_1$	2.09E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.262

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.2	2.9	3.6	0.0	0.6	1.3
+20/+40	2.4	3.1	3.9	1.0	1.7	2.4
+60/+80	2.7	3.4	4.2	1.6	2.3	3.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.71	0.43
2325	0.85	0.67
1970	0.967	0.92
1530	0.994	0.986
1060	0.999	0.998
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.995
546	0.998	0.995
500	0.996	0.991
460	0.994	0.986
436	0.993	0.983
420	0.993	0.982
405	0.992	0.979
400	0.991	0.977
390	0.989	0.972
380	0.985	0.963
370	0.978	0.95
365	0.973	0.93
350	0.95	0.87
334	0.89	0.74
320	0.77	0.52
310	0.63	0.31
300	0.43	0.12
290	0.21	0.02
280	0.11	0.00
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  34/28

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2729
$P_{C,s}$	0.5314
$P_{d,C}$	0.3031
$P_{e,d}$	0.2384
$P_{g,F}$	0.5467
$P_{i,h}$	0.7771

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2704
$P'_{C,s}$	0.5744
$P'_{d,C'}$	0.2527
$P'_{e,d}$	0.2362
$P'_{g,F'}$	0.4851
$P'_{i,h}$	0.7702

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0058
$\Delta P_{C,s}$	-0.0018
$\Delta P_{F,e}$	-0.0005
$\Delta P_{g,F}$	-0.0031
$\Delta P_{i,g}$	-0.0236

### Chemical Properties

CR	2
FR	2
SR	51.2
AR	1
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$T_g$ [°C]	689
$T_{10}^{13}$ [°C]	673
$T_{10}^{7.6}$ [°C]	
$c_p$ [J/(g·K)]	0.540
$\lambda$ [W/(m·K)]	0.750
$\rho$ [g/cm <sup>3</sup> ]	3.77
$E$ [ $10^3$ N/mm <sup>2</sup> ]	90
$\mu$	0.266
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.82
HK <sub>0.1/20</sub>	600
HG	4



## N-LAK28 744508.409

$n_d = 1.74429$

$v_d = 50.77$

$n_F - n_C = 0.014660$

$n_e = 1.74778$

$v_e = 50.54$

$n_F - n_C = 0.014797$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.70318
$n_{1970.1}$	1970.1	1.71077
$n_{1529.6}$	1529.6	1.71877
$n_{1060.0}$	1060.0	1.72709
$n_t$	1014.0	1.72805
$n_s$	852.1	1.73207
$n_r$	706.5	1.73734
$n_C$	656.3	1.73985
$n_{C'}$	643.8	1.74056
$n_{632.8}$	632.8	1.74121
$n_D$	589.3	1.74416
$n_d$	587.6	1.74429
$n_e$	546.1	1.74778
$n_F$	486.1	1.75451
$n_{F'}$	480.0	1.75535
$n_g$	435.8	1.76257
$n_h$	404.7	1.76931
$n_i$	365.0	1.78090
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.504419860
$B_2$	0.474120561
$B_3$	1.177843540
$C_1$	0.007196656
$C_2$	0.0249143227
$C_3$	83.14432100

### Constants of Formula for $dn/dT$

$D_0$	5.01E-06
$D_1$	1.12E-08
$D_2$	-1.08E-11
$E_0$	4.68E-07
$E_1$	3.34E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.226

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.7	5.6	6.6	2.4	3.3	4.1
+20/+40	4.7	5.7	6.7	3.3	4.2	5.2
+60/+80	4.9	5.9	7.0	3.7	4.7	5.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500		
2325	0.700	0.410
1970	0.950	0.880
1530	0.992	0.980
1060	0.998	0.995
700	0.998	0.994
660	0.997	0.993
620	0.997	0.993
580	0.997	0.993
546	0.998	0.994
500	0.997	0.992
460	0.992	0.980
436	0.988	0.970
420	0.980	0.950
405	0.959	0.900
400	0.950	0.870
390	0.910	0.800
380	0.850	0.670
370	0.760	0.500
365	0.690	0.390
350	0.380	0.090
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  40/34

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2740
$P_{C,s}$	0.5307
$P_{d,C}$	0.3025
$P_{e,d}$	0.2382
$P_{g,F}$	0.5499
$P_{i,h}$	0.7905

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2715
$P'_{C,s}$	0.5734
$P'_{d,C'}$	0.2521
$P'_{e,d}$	0.2360
$P'_{g,F'}$	0.4879
$P'_{i,h}$	0.7832

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0189
$\Delta P_{C,s}$	0.0095
$\Delta P_{F,e}$	-0.0024
$\Delta P_{g,F}$	-0.0085
$\Delta P_{i,g}$	-0.0484

### Chemical Properties

CR	2
FR	1
SR	52.3
AR	1
PR	3.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.7
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.8
$T_g$ [°C]	625
$T_{10}^{13}$ [°C]	
$T_{10}^{7.6}$ [°C]	
$c_p$ [J/(g·K)]	0.595
$\lambda$ [W/(m·K)]	0.837
$\rho$ [g/cm <sup>3</sup> ]	4.09
$E$ [ $10^3$ N/mm <sup>2</sup> ]	117
$\mu$	0.291
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.71
$HK_{0.1/20}$	740

## N-LAK33B 755523.422

$n_d = 1.75500$

$v_d = 52.30$

$n_F - n_C = 0.014436$

$n_e = 1.75844$

$v_e = 52.07$

$n_F - n_C = 0.014566$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.71387
$n_{1970.1}$	1970.1	1.72155
$n_{1529.6}$	1529.6	1.72962
$n_{1060.0}$	1060.0	1.73796
$n_t$	1014.0	1.73892
$n_s$	852.1	1.74292
$n_r$	706.5	1.74814
$n_C$	656.3	1.75062
$n_{C'}$	643.8	1.75132
$n_{632.8}$	632.8	1.75197
$n_D$	589.3	1.75487
$n_d$	587.6	1.75500
$n_e$	546.1	1.75844
$n_F$	486.1	1.76506
$n_{F'}$	480.0	1.76589
$n_g$	435.8	1.77296
$n_h$	404.7	1.77954
$n_i$	365.0	1.79082
$n_{334.1}$	334.1	1.80306
$n_{312.6}$	312.6	1.81436
$n_{296.7}$	296.7	1.82471
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.422886010
$B_2$	0.593661336
$B_3$	1.161352600
$C_1$	0.006702835
$C_2$	0.0219416210
$C_3$	80.74077010

### Constants of Formula for $dn/dT$

$D_0$	2.77E-06
$D_1$	1.24E-08
$D_2$	1.22E-11
$E_0$	5.19E-07
$E_1$	6.02E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.184

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.5	4.4	5.2	1.2	2.0	2.8
+20/+40	3.5	4.5	5.4	2.0	3.0	3.9
+60/+80	3.9	4.9	5.9	2.7	3.7	4.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.400	0.100
2325	0.680	0.380
1970	0.940	0.850
1530	0.985	0.963
1060	0.998	0.995
700	0.998	0.995
660	0.998	0.994
620	0.997	0.993
580	0.998	0.994
546	0.998	0.995
500	0.997	0.993
460	0.994	0.986
436	0.992	0.979
420	0.988	0.971
405	0.982	0.956
400	0.980	0.950
390	0.971	0.930
380	0.954	0.890
370	0.930	0.830
365	0.910	0.790
350	0.820	0.610
334	0.660	0.350
320	0.460	0.140
310	0.280	0.030
300	0.220	0.010
290	0.120	0.000
280	0.020	
270	0.000	
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  37/28

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2768
$P_{C,s}$	0.5337
$P_{d,C}$	0.3032
$P_{e,d}$	0.2383
$P_{g,F}$	0.5473
$P_{i,h}$	0.7813

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2744
$P'_{C,s}$	0.5767
$P'_{d,C'}$	0.2527
$P'_{e,d}$	0.2362
$P'_{g,F'}$	0.4857
$P'_{i,h}$	0.7743

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0175
$\Delta P_{C,s}$	0.0089
$\Delta P_{F,e}$	-0.0024
$\Delta P_{g,F}$	-0.0085
$\Delta P_{i,g}$	-0.0484

### Chemical Properties

CR	1
FR	1
SR	51.3
AR	1
PR	2
SR-J	4
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$T_g$ [°C]	668
$T_{10}^{13}$ [°C]	670
$T_{10}^{7.6}$ [°C]	750
$c_p$ [J/(g*K)]	0.560
$\lambda$ [W/(m*K)]	0.890
AT [°C]	702
$\rho$ [g/cm <sup>3</sup> ]	4.22
E [ $10^3$ N/mm <sup>2</sup> ]	122
$\mu$	0.295
K [ $10^{-6}$ mm <sup>2</sup> /N]	1.43
HK <sub>0.1/20</sub>	797

## N-LAK34 729545.402

$n_d = 1.72916$   
 $n_e = 1.73235$

$v_d = 54.50$   
 $v_e = 54.27$

$n_F - n_C = 0.013379$   
 $n_{F'} - n_{C'} = 0.013493$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.68925
$n_{1970.1}$	1970.1	1.69695
$n_{1529.6}$	1529.6	1.70500
$n_{1060.0}$	1060.0	1.71315
$n_t$	1014.0	1.71407
$n_s$	852.1	1.71787
$n_r$	706.5	1.72277
$n_C$	656.3	1.72509
$n_{C'}$	643.8	1.72574
$n_{632.8}$	632.8	1.72634
$n_D$	589.3	1.72904
$n_d$	587.6	1.72916
$n_e$	546.1	1.73235
$n_F$	486.1	1.73847
$n_{F'}$	480.0	1.73923
$n_g$	435.8	1.74575
$n_h$	404.7	1.75180
$n_i$	365.0	1.76214
$n_{334.1}$	334.1	1.77331
$n_{312.6}$	312.6	1.78359
$n_{296.7}$	296.7	1.79296
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.266614420
$B_2$	0.665919318
$B_3$	1.124961200
$C_1$	0.005892781
$C_2$	0.0197509041
$C_3$	78.88941740

### Constants of Formula for $dn/dT$

$D_0$	1.96E-06
$D_1$	9.65E-09
$D_2$	4.40E-12
$E_0$	4.91E-07
$E_1$	5.28E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.161

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.1	3.9	4.6	0.8	1.5	2.2
+20/+40	3.0	3.8	4.6	1.5	2.3	3.1
+60/+80	3.1	4.0	4.9	2.0	2.9	3.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.400	0.100
2325	0.670	0.370
1970	0.940	0.850
1530	0.984	0.960
1060	0.998	0.995
700	0.999	0.997
660	0.999	0.997
620	0.998	0.996
580	0.998	0.995
546	0.999	0.997
500	0.998	0.994
460	0.995	0.987
436	0.992	0.979
420	0.989	0.972
405	0.983	0.959
400	0.981	0.952
390	0.976	0.940
380	0.963	0.910
370	0.940	0.860
365	0.920	0.820
350	0.850	0.670
334	0.710	0.430
320	0.530	0.200
310	0.380	0.070
300	0.280	0.030
290	0.170	0.010
280	0.070	
270	0.010	
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  37/28

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2841
$P_{C,s}$	0.5398
$P_{d,C}$	0.3042
$P_{e,d}$	0.2384
$P_{g,F}$	0.5443
$P_{i,h}$	0.7726

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2817
$P'_{C,s}$	0.5833
$P'_{d,C'}$	0.2536
$P'_{e,d}$	0.2364
$P'_{g,F'}$	0.4832
$P'_{i,h}$	0.7661

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0204
$\Delta P_{C,s}$	0.0099
$\Delta P_{F,e}$	-0.0024
$\Delta P_{g,F}$	-0.0079
$\Delta P_{i,g}$	-0.0423

### Chemical Properties

CR	1
FR	0
SR	52.3
AR	1
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.9
$T_g$ [°C]	668
$T_{10}^{13}$ [°C]	668
$T_{10}^{7.6}$ [°C]	740
$c_p$ [J/(g·K)]	0.520
$\lambda$ [W/(m·K)]	0.820
$\rho$ [g/cm <sup>3</sup> ]	4.02
$E$ [ $10^3$ N/mm <sup>2</sup> ]	117
$\mu$	0.290
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.52
$HK_{0.1/20}$	740
HG	2

## P-LAK35 693532.385

$n_d = 1.69350$

$v_d = 53.20$

$n_F - n_C = 0.013036$

$n_e = 1.69661$

$v_e = 52.95$

$n_F - n_C = 0.013156$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.65762
$n_{1970.1}$	1970.1	1.66411
$n_{1529.6}$	1529.6	1.67100
$n_{1060.0}$	1060.0	1.67824
$n_t$	1014.0	1.67909
$n_s$	852.1	1.68264
$n_r$	706.5	1.68732
$n_C$	656.3	1.68955
$n_{C'}$	643.8	1.69018
$n_{632.8}$	632.8	1.69077
$n_D$	589.3	1.69338
$n_d$	587.6	1.69350
$n_e$	546.1	1.69661
$n_F$	486.1	1.70259
$n_{F'}$	480.0	1.70334
$n_g$	435.8	1.70974
$n_h$	404.7	1.71569
$n_i$	365.0	1.72590
$n_{334.1}$	334.1	1.73698
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.393242600
$B_2$	0.418882766
$B_3$	1.043807000
$C_1$	0.007159597
$C_2$	0.0233637446
$C_3$	88.32844260

### Constants of Formula for $dn/dT$

$D_0$	-1.90E-06
$D_1$	7.99E-09
$D_2$	7.76E-12
$E_0$	5.64E-07
$E_1$	6.57E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.185

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.1	1.9	2.7	-1.2	-0.4	0.3
+20/+40	0.8	1.7	2.6	-0.7	0.2	1.1
+60/+80	0.9	1.9	2.9	-0.3	0.7	1.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.550	0.220
2325	0.760	0.500
1970	0.950	0.870
1530	0.992	0.981
1060	0.999	0.999
700	0.997	0.993
660	0.997	0.992
620	0.997	0.992
580	0.997	0.993
546	0.998	0.994
500	0.997	0.992
460	0.994	0.985
436	0.992	0.980
420	0.991	0.977
405	0.989	0.973
400	0.988	0.970
390	0.984	0.960
380	0.976	0.940
370	0.962	0.910
365	0.950	0.880
350	0.890	0.740
334	0.750	0.480
320	0.540	0.210
310	0.350	0.060
300	0.160	0.010
290	0.030	0.000
280	0.000	
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  36/29

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2723
$P_{C,s}$	0.5304
$P_{d,C}$	0.3028
$P_{e,d}$	0.2383
$P_{g,F}$	0.5482
$P_{i,h}$	0.7832

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2698
$P'_{C,s}$	0.5732
$P'_{d,C'}$	0.2524
$P'_{e,d}$	0.2361
$P'_{g,F'}$	0.4864
$P'_{i,h}$	0.7761

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0053
$\Delta P_{C,s}$	0.0034
$\Delta P_{F,e}$	-0.0015
$\Delta P_{g,F}$	-0.0061
$\Delta P_{i,g}$	-0.0379

### Chemical Properties

CR	2
FR	5
SR	53.3
AR	1.3
PR	4.3
SR-J	4
WR-J	3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.7
$T_g$ [°C]	508
$T_{10}^{13}$ [°C]	511
$T_{10}^{7.6}$ [°C]	598
$c_p$ [J/(g·K)]	0.630
$\lambda$ [W/(m·K)]	0.720
AT [°C]	544
$\rho$ [g/cm <sup>3</sup> ]	3.85
E [ $10^3$ N/mm <sup>2</sup> ]	101
$\mu$	0.289
K [ $10^{-6}$ mm <sup>2</sup> /N]	1.76
HK <sub>0.1/20</sub>	616
Abrasion Aa	119

## LLF1 548458.294

$n_d = 1.54814$   
 $n_e = 1.55099$

$v_d = 45.75$   
 $v_e = 45.47$

$n_F - n_C = 0.011981$   
 $n_P - n_C = 0.012118$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.51865
$n_{1970.1}$	1970.1	1.52354
$n_{1529.6}$	1529.6	1.52884
$n_{1060.0}$	1060.0	1.53470
$n_t$	1014.0	1.53541
$n_s$	852.1	1.53845
$n_r$	706.5	1.54256
$n_C$	656.3	1.54457
$n_{C'}$	643.8	1.54513
$n_{632.8}$	632.8	1.54566
$n_D$	589.3	1.54803
$n_d$	587.6	1.54814
$n_e$	546.1	1.55099
$n_F$	486.1	1.55655
$n_{F'}$	480.0	1.55725
$n_g$	435.8	1.56333
$n_h$	404.7	1.56911
$n_i$	365.0	1.57932
$n_{334.1}$	334.1	1.59092
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.216401250
$B_2$	0.133664540
$B_3$	0.883399468
$C_1$	0.008578072
$C_2$	0.0420143003
$C_3$	107.59306000

### Constants of Formula for $dn/dT$

$D_0$	3.25E-07
$D_1$	1.74E-08
$D_2$	-6.12E-11
$E_0$	6.53E-07
$E_1$	2.58E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.233

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.5	2.4	3.4	-0.6	0.3	1.3
+20/+40	1.9	2.9	3.9	0.6	1.5	2.5
+60/+80	2.0	3.0	4.1	1.0	2.0	3.0

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.76	0.50
2325	0.82	0.61
1970	0.93	0.84
1530	0.996	0.990
1060	0.998	0.996
700	0.999	0.997
660	0.998	0.996
620	0.998	0.996
580	0.999	0.997
546	0.999	0.997
500	0.998	0.996
460	0.998	0.996
436	0.998	0.996
420	0.998	0.995
405	0.998	0.994
400	0.997	0.993
390	0.997	0.992
380	0.995	0.988
370	0.994	0.984
365	0.992	0.981
350	0.982	0.955
334	0.92	0.81
320	0.62	0.30
310	0.24	0.01
300	0.02	
290	0.00	
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  33/31

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2537
$P_{C,s}$	0.5108
$P_{d,C}$	0.2983
$P_{e,d}$	0.2376
$P_{g,F}$	0.5660
$P_{i,h}$	0.8520

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2508
$P'_{C,s}$	0.5516
$P'_{d,C'}$	0.2484
$P'_{e,d}$	0.2349
$P'_{g,F'}$	0.5017
$P'_{i,h}$	0.8424

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0025
$\Delta P_{C,s}$	0.0012
$\Delta P_{F,e}$	-0.0003
$\Delta P_{g,F}$	-0.0009
$\Delta P_{i,g}$	-0.0062

### Chemical Properties

CR	1
FR	0
SR	1
AR	2
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.2
$T_g$ [°C]	431
$T_{10}^{13}$ [°C]	426
$T_{10}^{7.6}$ [°C]	628
$c_p$ [J/(g·K)]	0.650
$\lambda$ [W/(m·K)]	0.990
$\rho$ [g/cm <sup>3</sup> ]	2.94
$E$ [ $10^3$ N/mm <sup>2</sup> ]	60
$\mu$	0.208
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.03
$HK_{0.1/20}$	450
HG	3

## LLF1HTi 548459.294

$n_d = 1.54815$

$v_d = 45.90$

$n_F - n_C = 0.011942$

$n_e = 1.55099$

$v_e = 45.62$

$n_F - n_C = 0.012078$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.51863
$n_{1970.1}$	1970.1	1.52354
$n_{1529.6}$	1529.6	1.52886
$n_{1060.0}$	1060.0	1.53473
$n_t$	1014.0	1.53544
$n_s$	852.1	1.53848
$n_r$	706.5	1.54259
$n_C$	656.3	1.54459
$n_{C'}$	643.8	1.54515
$n_{632.8}$	632.8	1.54568
$n_D$	589.3	1.54804
$n_d$	587.6	1.54815
$n_e$	546.1	1.55099
$n_F$	486.1	1.55653
$n_{F'}$	480.0	1.55723
$n_g$	435.8	1.56328
$n_h$	404.7	1.56904
$n_i$	365.0	1.57920
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.225104450
$B_2$	0.125155671
$B_3$	0.892236751
$C_1$	0.008704321
$C_2$	0.0427325235
$C_3$	108.04996800

### Constants of Formula for $dn/dT$

$D_0$	2.55E-07
$D_1$	1.41E-08
$D_2$	-3.32E-11
$E_0$	6.74E-07
$E_1$	6.27E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.227

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/\text{K}$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/\text{K}$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.7	2.6	3.5	-0.4	0.5	1.4
+20/+40	1.8	2.9	3.9	0.5	1.5	2.5
+60/+80	2.0	3.1	4.2	0.9	2.0	3.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.74	0.48
2325	0.80	0.58
1970	0.93	0.83
1530	0.996	0.990
1060	0.999	0.999
700	0.999	0.999
660	0.999	0.998
620	0.999	0.998
580	0.999	0.998
546	0.999	0.998
500	0.999	0.998
460	0.999	0.998
436	0.999	0.997
420	0.999	0.997
405	0.999	0.997
400	0.999	0.997
390	0.998	0.996
380	0.998	0.995
370	0.998	0.994
365	0.997	0.993
350	0.993	0.982
334	0.955	0.89
320	0.72	0.44
310	0.23	0.03
300	0.00	0.00
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  33/31

### Remarks

i-line glass

### Relative Partial Dispersion P

$P_{s,t}$	0.2544
$P_{C,s}$	0.5114
$P_{d,C}$	0.2985
$P_{e,d}$	0.2376
$P_{g,F}$	0.5656
$P_{i,h}$	0.8512
<b>Relative Partial Dispersion P'</b>	
$P'_{s,t}$	0.2515
$P'_{C,s}$	0.5523
$P'_{d,C'}$	0.2485
$P'_{e,d}$	0.2349
$P'_{g,F'}$	0.5014
$P'_{i,h}$	0.8416

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0031
$\Delta P_{C,s}$	0.0015
$\Delta P_{F,e}$	-0.0003
$\Delta P_{g,F}$	-0.0010
$\Delta P_{i,g}$	-0.0062

### Chemical Properties

CR	1
FR	0
SR	1
AR	2
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/\text{K}$ ]	8.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/\text{K}$ ]	9.2
$T_g$ [°C]	431
$T_{10}^{13}$ [°C]	426
$T_{10}^{7.6}$ [°C]	628
$c_p$ [J/(g·K)]	0.650
$\lambda$ [W/(m·K)]	0.990
$\rho$ [g/cm <sup>3</sup> ]	2.94
$E$ [ $10^3$ N/mm <sup>2</sup> ]	60
$\mu$	0.208
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.03
$HK_{0.1/20}$	450

## LF5 581409.322

$n_d = 1.58144$

$v_d = 40.85$

$n_F - n_C = 0.014233$

$n_e = 1.58482$

$v_e = 40.57$

$n_F - n_C = 0.014413$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.54966
$n_{1970.1}$	1970.1	1.55445
$n_{1529.6}$	1529.6	1.55975
$n_{1060.0}$	1060.0	1.56594
$n_t$	1014.0	1.56672
$n_s$	852.1	1.57014
$n_r$	706.5	1.57489
$n_C$	656.3	1.57723
$n_{C'}$	643.8	1.57789
$n_{632.8}$	632.8	1.57851
$n_D$	589.3	1.58132
$n_d$	587.6	1.58144
$n_e$	546.1	1.58482
$n_F$	486.1	1.59146
$n_{F'}$	480.0	1.59231
$n_g$	435.8	1.59964
$n_h$	404.7	1.60668
$n_i$	365.0	1.61926
$n_{334.1}$	334.1	1.63380
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.280356280
$B_2$	0.163505973
$B_3$	0.893930112
$C_1$	0.009298544
$C_2$	0.0449135769
$C_3$	110.49368500

### Constants of Formula for $dn/dT$

$D_0$	-2.27E-06
$D_1$	9.71E-09
$D_2$	-2.83E-11
$E_0$	8.36E-07
$E_1$	9.95E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.228

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	0.8	1.9	3.1	-1.3	-0.2	0.9
+20/+40	0.8	2.0	3.4	-0.6	0.7	2.0
+60/+80	0.8	2.2	3.7	-0.3	1.1	2.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500		
2325	0.85	0.66
1970	0.95	0.87
1530	0.997	0.992
1060	0.999	0.998
700	0.999	0.998
660	0.999	0.998
620	0.999	0.998
580	0.999	0.997
546	0.999	0.997
500	0.998	0.996
460	0.998	0.995
436	0.998	0.994
420	0.997	0.993
405	0.997	0.992
400	0.997	0.992
390	0.994	0.984
380	0.989	0.973
370	0.984	0.961
365	0.981	0.954
350	0.950	0.88
334	0.80	0.57
320	0.32	0.04
310	0.04	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  34/31

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2401
$P_{C,s}$	0.4981
$P_{d,C}$	0.2959
$P_{e,d}$	0.2373
$P_{g,F}$	0.5748
$P_{i,h}$	0.8836

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2371
$P'_{C,s}$	0.5378
$P'_{d,C'}$	0.2462
$P'_{e,d}$	0.2343
$P'_{g,F'}$	0.5091
$P'_{i,h}$	0.8726

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0006
$\Delta P_{C,s}$	0.0000
$\Delta P_{F,e}$	-0.0001
$\Delta P_{g,F}$	-0.0003
$\Delta P_{i,g}$	-0.0037

### Chemical Properties

CR	2
FR	0
SR	1
AR	2.3
PR	2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.6
$T_g$ [°C]	419
$T_{10}^{13}$ [°C]	411
$T_{10}^{7.6}$ [°C]	585
$c_p$ [J/(g·K)]	0.657
$\lambda$ [W/(m·K)]	0.866
$\rho$ [g/cm <sup>3</sup> ]	3.22
$E$ [ $10^3$ N/mm <sup>2</sup> ]	59
$\mu$	0.223
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.80
$HK_{0.1/20}$	450
HG	2

## LF5HTi 581409.322

$n_d = 1.58144$

$v_d = 40.89$

$n_F - n_C = 0.014220$

$n_e = 1.58482$

$v_e = 40.61$

$n_F - n_C = 0.014400$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.54970
$n_{1970.1}$	1970.1	1.55448
$n_{1529.6}$	1529.6	1.55978
$n_{1060.0}$	1060.0	1.56596
$n_t$	1014.0	1.56674
$n_s$	852.1	1.57015
$n_r$	706.5	1.57490
$n_C$	656.3	1.57724
$n_{C'}$	643.8	1.57790
$n_{632.8}$	632.8	1.57852
$n_D$	589.3	1.58132
$n_d$	587.6	1.58144
$n_e$	546.1	1.58482
$n_F$	486.1	1.59145
$n_{F'}$	480.0	1.59230
$n_g$	435.8	1.59963
$n_h$	404.7	1.60665
$n_i$	365.0	1.61921
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.285529240
$B_2$	0.158357622
$B_3$	0.892175122
$C_1$	0.009398863
$C_2$	0.0452566659
$C_3$	110.54482900

### Constants of Formula for $dn/dT$

$D_0$	-2.26E-06
$D_1$	1.17E-08
$D_2$	-4.14E-11
$E_0$	8.24E-07
$E_1$	7.78E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.232

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	0.7	1.8	3.0	-1.4	-0.3	0.8
+20/+40	0.8	2.0	3.4	-0.6	0.7	2.0
+60/+80	0.8	2.2	3.6	-0.3	1.1	2.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.78	0.53
2325	0.83	0.63
1970	0.94	0.85
1530	0.996	0.991
1060	0.999	0.999
700	0.999	0.999
660	0.999	0.999
620	0.999	0.999
580	0.999	0.999
546	0.999	0.999
500	0.999	0.998
460	0.999	0.998
436	0.999	0.998
420	0.999	0.997
405	0.999	0.997
400	0.999	0.997
390	0.999	0.996
380	0.998	0.995
370	0.997	0.993
365	0.996	0.991
350	0.985	0.962
334	0.89	0.75
320	0.38	0.09
310	0.02	0.00
300	0.00	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  33/31

### Remarks

i-line glass  
lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2401
$P_{C,s}$	0.4982
$P_{d,C}$	0.2959
$P_{e,d}$	0.2373
$P_{g,F}$	0.5746
$P_{i,h}$	0.8831

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2371
$P'_{C,s}$	0.5380
$P'_{d,C'}$	0.2462
$P'_{e,d}$	0.2343
$P'_{g,F'}$	0.5090
$P'_{i,h}$	0.8721

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0006
$\Delta P_{C,s}$	0.0000
$\Delta P_{F,e}$	-0.0001
$\Delta P_{g,F}$	-0.0004
$\Delta P_{i,g}$	-0.0041

### Chemical Properties

CR	2
FR	0
SR	1
AR	2.3
PR	2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.6
$T_g$ [°C]	419
$T_{10}^{13}$ [°C]	411
$T_{10}^{7.6}$ [°C]	585
$c_p$ [J/(g·K)]	0.657
$\lambda$ [W/(m·K)]	0.866
$\rho$ [g/cm <sup>3</sup> ]	3.22
$E$ [ $10^3$ N/mm <sup>2</sup> ]	59
$\mu$	0.223
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.80
$HK_{0.1/20}$	450



## N-F2 620364.265

$n_d = 1.62005$

$v_d = 36.43$

$n_F - n_C = 0.017020$

$n_e = 1.62408$

$v_e = 36.16$

$n_F - n_C = 0.017258$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.58136
$n_{1970.1}$	1970.1	1.58744
$n_{1529.6}$	1529.6	1.59410
$n_{1060.0}$	1060.0	1.60167
$n_t$	1014.0	1.60261
$n_s$	852.1	1.60667
$n_r$	706.5	1.61229
$n_C$	656.3	1.61506
$n_{C'}$	643.8	1.61584
$n_{632.8}$	632.8	1.61658
$n_D$	589.3	1.61990
$n_d$	587.6	1.62005
$n_e$	546.1	1.62408
$n_F$	486.1	1.63208
$n_{F'}$	480.0	1.63310
$n_g$	435.8	1.64209
$n_h$	404.7	1.65087
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.397570370
$B_2$	0.159201403
$B_3$	1.268654300
$C_1$	0.009959061
$C_2$	0.0546931752
$C_3$	119.24834600

### Constants of Formula for $dn/dT$

$D_0$	4.62E-07
$D_1$	1.17E-08
$D_2$	-2.35E-11
$E_0$	7.47E-07
$E_1$	9.81E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.263

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.0	3.2	4.6	-0.1	1.0	2.3
+20/+40	2.1	3.5	5.1	0.7	2.0	3.6
+60/+80	2.2	3.7	5.5	1.1	2.6	4.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.75	0.48
2325	0.84	0.64
1970	0.950	0.88
1530	0.991	0.977
1060	0.998	0.996
700	0.997	0.992
660	0.996	0.990
620	0.996	0.991
580	0.997	0.993
546	0.997	0.992
500	0.994	0.984
460	0.989	0.973
436	0.985	0.963
420	0.980	0.950
405	0.959	0.90
400	0.95	0.87
390	0.89	0.75
380	0.76	0.51
370	0.48	0.16
365	0.28	0.04
350	0.10	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  39/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2389
$P_{C,s}$	0.4925
$P_{d,C}$	0.2935
$P_{e,d}$	0.2366
$P_{g,F}$	0.5881
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2356
$P'_{C,s}$	0.5312
$P'_{d,C'}$	0.2440
$P'_{e,d}$	0.2334
$P'_{g,F'}$	0.5208
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0137
$\Delta P_{C,s}$	0.0047
$\Delta P_{F,e}$	0.0006
$\Delta P_{g,F}$	0.0056
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.1
$T_g$ [°C]	569
$T_{10}^{13}$ [°C]	567
$T_{10}^{7.6}$ [°C]	686
$c_p$ [J/(g·K)]	0.810
$\lambda$ [W/(m·K)]	1.050
$\rho$ [g/cm <sup>3</sup> ]	2.65
$E$ [ $10^3$ N/mm <sup>2</sup> ]	82
$\mu$	0.228
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.03
$HK_{0.1/20}$	600
HG	2

## F2HT 620364.360

$n_d = 1.62004$

$v_d = 36.37$

$n_F - n_C = 0.017050$

$n_e = 1.62408$

$v_e = 36.11$

$n_F - n_C = 0.017284$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.58465
$n_{1970.1}$	1970.1	1.58958
$n_{1529.6}$	1529.6	1.59513
$n_{1060.0}$	1060.0	1.60190
$n_t$	1014.0	1.60279
$n_s$	852.1	1.60671
$n_r$	706.5	1.61227
$n_C$	656.3	1.61503
$n_{C'}$	643.8	1.61582
$n_{632.8}$	632.8	1.61656
$n_D$	589.3	1.61989
$n_d$	587.6	1.62004
$n_e$	546.1	1.62408
$n_F$	486.1	1.63208
$n_{F'}$	480.0	1.63310
$n_g$	435.8	1.64202
$n_h$	404.7	1.65064
$n_i$	365.0	1.66623
$n_{334.1}$	334.1	1.68455
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.345333590
$B_2$	0.209073176
$B_3$	0.937357162
$C_1$	0.009977439
$C_2$	0.0470450767
$C_3$	111.88676400

### Constants of Formula for $dn/dT$

$D_0$	1.51E-06
$D_1$	1.56E-08
$D_2$	-2.78E-11
$E_0$	9.34E-07
$E_1$	1.04E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.250

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.4	3.9	5.5	0.3	1.6	3.2
+20/+40	2.7	4.4	6.3	1.3	3.0	4.8
+60/+80	3.0	4.8	6.8	1.9	3.7	5.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.870	0.710
2325	0.910	0.800
1970	0.968	0.920
1530	0.998	0.994
1060	0.999	0.998
700	0.999	0.998
660	0.999	0.997
620	0.999	0.998
580	0.999	0.998
546	0.999	0.998
500	0.999	0.997
460	0.998	0.995
436	0.998	0.994
420	0.997	0.994
405	0.997	0.992
400	0.996	0.991
390	0.995	0.988
380	0.993	0.982
370	0.988	0.971
365	0.983	0.957
350	0.930	0.830
334	0.570	0.240
320	0.080	0.000
310	0.000	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  35/32

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2301
$P_{C,s}$	0.4882
$P_{d,C}$	0.2938
$P_{e,d}$	0.2370
$P_{g,F}$	0.5828
$P_{i,h}$	0.9142

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2270
$P'_{C,s}$	0.5270
$P'_{d,C'}$	0.2443
$P'_{e,d}$	0.2338
$P'_{g,F'}$	0.5159
$P'_{i,h}$	0.9018

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0008
$\Delta P_{C,s}$	0.0005
$\Delta P_{F,e}$	0.0000
$\Delta P_{g,F}$	0.0002
$\Delta P_{i,g}$	0.0006

### Chemical Properties

CR	1
FR	0
SR	1
AR	2.3
PR	1.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.2
$T_g$ [°C]	434
$T_{10}^{13}$ [°C]	430
$T_{10}^{7.6}$ [°C]	594
$c_p$ [J/(g·K)]	0.557
$\lambda$ [W/(m·K)]	0.780
$\rho$ [g/cm <sup>3</sup> ]	3.60
$E$ [ $10^3$ N/mm <sup>2</sup> ]	57
$\mu$	0.220
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.81
$HK_{0.1/20}$	420
HG	2

## F2HTi 620364.360

$n_d = 1.62004$

$v_d = 36.37$

$n_F - n_C = 0.017050$

$n_e = 1.62408$

$v_e = 36.11$

$n_F - n_C = 0.017284$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.58465
$n_{1970.1}$	1970.1	1.58958
$n_{1529.6}$	1529.6	1.59513
$n_{1060.0}$	1060.0	1.60190
$n_t$	1014.0	1.60279
$n_s$	852.1	1.60671
$n_r$	706.5	1.61227
$n_C$	656.3	1.61503
$n_{C'}$	643.8	1.61582
$n_{632.8}$	632.8	1.61656
$n_D$	589.3	1.61989
$n_d$	587.6	1.62004
$n_e$	546.1	1.62408
$n_F$	486.1	1.63208
$n_{F'}$	480.0	1.63310
$n_g$	435.8	1.64202
$n_h$	404.7	1.65064
$n_i$	365.0	1.66623
$n_{334.1}$	334.1	1.68455
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.345333590
$B_2$	0.209073176
$B_3$	0.937357162
$C_1$	0.009977439
$C_2$	0.0470450767
$C_3$	111.88676400

### Constants of Formula for $dn/dT$

$D_0$	1.51E-06
$D_1$	1.56E-08
$D_2$	-2.78E-11
$E_0$	9.34E-07
$E_1$	1.04E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.250

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.4	3.9	5.5	0.3	1.6	3.2
+20/+40	2.7	4.4	6.3	1.3	3.0	4.8
+60/+80	3.0	4.8	6.8	1.9	3.7	5.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.870	0.710
2325	0.910	0.800
1970	0.968	0.920
1530	0.998	0.994
1060	0.999	0.998
700	0.999	0.998
660	0.999	0.997
620	0.999	0.998
580	0.999	0.998
546	0.999	0.998
500	0.999	0.997
460	0.998	0.994
436	0.997	0.993
420	0.996	0.991
405	0.995	0.987
400	0.994	0.986
390	0.994	0.986
380	0.994	0.985
370	0.989	0.973
365	0.985	0.962
350	0.930	0.830
334	0.600	0.270
320	0.080	0.000
310	0.000	0.000
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  0,000000

### Remarks

i-line glass  
lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2301
$P_{C,s}$	0.4882
$P_{d,C}$	0.2938
$P_{e,d}$	0.2370
$P_{g,F}$	0.5828
$P_{i,h}$	0.9142

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2270
$P'_{C,s}$	0.5270
$P'_{d,C'}$	0.2443
$P'_{e,d}$	0.2338
$P'_{g,F'}$	0.5159
$P'_{i,h}$	0.9018

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0008
$\Delta P_{C,s}$	0.0005
$\Delta P_{F,e}$	0.0000
$\Delta P_{g,F}$	0.0002
$\Delta P_{i,g}$	0.0006

### Chemical Properties

CR	1
FR	0
SR	1
AR	2.3
PR	1.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.2
$T_g$ [°C]	434
$T_{10}^{13}$ [°C]	430
$T_{10}^{7.6}$ [°C]	594
$c_p$ [J/(g·K)]	0.557
$\lambda$ [W/(m·K)]	0.780
$\rho$ [g/cm <sup>3</sup> ]	3.60
$E$ [ $10^3$ N/mm <sup>2</sup> ]	57
$\mu$	0.220
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.81
$HK_{0.1/20}$	420
HG	2

## F5 603380.347

$n_d = 1.60342$   
 $n_e = 1.60718$

$v_d = 38.03$   
 $v_e = 37.77$

$n_F - n_C = 0.015867$   
 $n_{F'} - n_{C'} = 0.016078$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.56934
$n_{1970.1}$	1970.1	1.57427
$n_{1529.6}$	1529.6	1.57979
$n_{1060.0}$	1060.0	1.58636
$n_t$	1014.0	1.58721
$n_s$	852.1	1.59093
$n_r$	706.5	1.59616
$n_C$	656.3	1.59875
$n_{C'}$	643.8	1.59948
$n_{632.8}$	632.8	1.60017
$n_D$	589.3	1.60328
$n_d$	587.6	1.60342
$n_e$	546.1	1.60718
$n_F$	486.1	1.61461
$n_{F'}$	480.0	1.61556
$n_g$	435.8	1.62381
$n_h$	404.7	1.63176
$n_i$	365.0	1.64606
$n_{334.1}$	334.1	1.66276
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.310446300
$B_2$	0.196034260
$B_3$	0.966129770
$C_1$	0.009586330
$C_2$	0.0457627627
$C_3$	115.01188300

### Constants of Formula for $dn/dT$

$D_0$	2.13E-06
$D_1$	1.65E-08
$D_2$	-6.98E-11
$E_0$	1.02E-06
$E_1$	6.56E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.208

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.5	4.0	5.5	0.4	1.8	3.3
+20/+40	3.0	4.6	6.2	1.6	3.2	4.8
+60/+80	3.1	4.8	6.5	2.0	3.7	5.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.790	0.550
2325	0.840	0.650
1970	0.940	0.860
1530	0.995	0.987
1060	0.999	0.998
700	0.999	0.997
660	0.998	0.996
620	0.998	0.995
580	0.998	0.995
546	0.998	0.995
500	0.998	0.994
460	0.996	0.991
436	0.996	0.990
420	0.995	0.988
405	0.994	0.985
400	0.993	0.982
390	0.989	0.973
380	0.984	0.960
370	0.971	0.930
365	0.963	0.910
350	0.900	0.760
334	0.620	0.300
320	0.080	0.000
310	0.000	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  35/32

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2346
$P_{C,s}$	0.4925
$P_{d,C}$	0.2946
$P_{e,d}$	0.2371
$P_{g,F}$	0.5795
$P_{i,h}$	0.9015

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2315
$P'_{C,s}$	0.5317
$P'_{d,C'}$	0.2451
$P'_{e,d}$	0.2340
$P'_{g,F'}$	0.5131
$P'_{i,h}$	0.8897

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0017
$\Delta P_{C,s}$	0.0009
$\Delta P_{F,e}$	-0.0001
$\Delta P_{g,F}$	-0.0003
$\Delta P_{i,g}$	-0.0028

### Chemical Properties

CR	1
FR	0
SR	1
AR	2.3
PR	2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.9
$T_g$ [°C]	438
$T_{10}^{13}$ [°C]	425
$T_{10}^{7.6}$ [°C]	608
$c_p$ [J/(g·K)]	0.560
$\lambda$ [W/(m·K)]	0.880
$\rho$ [g/cm <sup>3</sup> ]	3.47
$E$ [ $10^3$ N/mm <sup>2</sup> ]	58
$\mu$	0.220
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.92
$HK_{0.1/20}$	450
HG	3

## N-F2 620364.265

$n_d = 1.62005$   
 $n_e = 1.62408$

$v_d = 36.43$   
 $v_e = 36.16$

$n_F - n_C = 0.017020$   
 $n_{F'} - n_{C'} = 0.017258$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.58136
$n_{1970.1}$	1970.1	1.58744
$n_{1529.6}$	1529.6	1.59410
$n_{1060.0}$	1060.0	1.60167
$n_t$	1014.0	1.60261
$n_s$	852.1	1.60667
$n_r$	706.5	1.61229
$n_C$	656.3	1.61506
$n_{C'}$	643.8	1.61584
$n_{632.8}$	632.8	1.61658
$n_D$	589.3	1.61990
$n_d$	587.6	1.62005
$n_e$	546.1	1.62408
$n_F$	486.1	1.63208
$n_{F'}$	480.0	1.63310
$n_g$	435.8	1.64209
$n_h$	404.7	1.65087
$n_i$	365.0	365.0
$n_{334.1}$	334.1	334.1
$n_{312.6}$	312.6	312.6
$n_{296.7}$	296.7	296.7
$n_{280.4}$	280.4	280.4
$n_{248.3}$	248.3	248.3

### Constants of Dispersion Formula

$B_1$	1.397570370
$B_2$	0.159201403
$B_3$	1.268654300
$C_1$	0.009959061
$C_2$	0.0546931752
$C_3$	119.24834600

### Constants of Formula for $dn/dT$

$D_0$	4.62E-07
$D_1$	1.17E-08
$D_2$	-2.35E-11
$E_0$	7.47E-07
$E_1$	9.81E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.263

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.0	3.2	4.6	-0.1	1.0	2.3
+20/+40	2.1	3.5	5.1	0.7	2.0	3.6
+60/+80	2.2	3.7	5.5	1.1	2.6	4.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.75	0.48
2325	0.84	0.64
1970	0.950	0.88
1530	0.991	0.977
1060	0.998	0.996
700	0.997	0.992
660	0.996	0.990
620	0.996	0.991
580	0.997	0.993
546	0.997	0.992
500	0.994	0.984
460	0.989	0.973
436	0.985	0.963
420	0.980	0.950
405	0.959	0.90
400	0.95	0.87
390	0.89	0.75
380	0.76	0.51
370	0.48	0.16
365	0.28	0.04
350	0.10	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  39/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2389
$P_{C,s}$	0.4925
$P_{d,C}$	0.2935
$P_{e,d}$	0.2366
$P_{g,F}$	0.5881
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2356
$P'_{C,s}$	0.5312
$P'_{d,C'}$	0.2440
$P'_{e,d}$	0.2334
$P'_{g,F'}$	0.5208
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0137
$\Delta P_{C,s}$	0.0047
$\Delta P_{F,e}$	0.0006
$\Delta P_{g,F}$	0.0056
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.1
$T_g$ [°C]	569
$T_{10}^{13}$ [°C]	567
$T_{10}^{7.6}$ [°C]	686
$c_p$ [J/(g*K)]	0.810
$\lambda$ [W/(m*K)]	1.050
$\rho$ [g/cm <sup>3</sup> ]	2.65
$E$ [ $10^3$ N/mm <sup>2</sup> ]	82
$\mu$	0.228
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.03
$HK_{0.1/20}$	600
HG	2

## N-BASF2 664360.315

$n_d = 1.66446$   
 $n_e = 1.66883$

$v_d = 36.00$   
 $v_e = 35.73$

$n_F - n_C = 0.018457$   
 $n_F - n_C = 0.018720$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.62552
$n_{1970.1}$	1970.1	1.63109
$n_{1529.6}$	1529.6	1.63734
$n_{1060.0}$	1060.0	1.64484
$n_t$	1014.0	1.64581
$n_s$	852.1	1.65007
$n_r$	706.5	1.65607
$n_C$	656.3	1.65905
$n_{C'}$	643.8	1.65990
$n_{632.8}$	632.8	1.66070
$n_D$	589.3	1.66430
$n_d$	587.6	1.66446
$n_e$	546.1	1.66883
$n_F$	486.1	1.67751
$n_{F'}$	480.0	1.67862
$n_g$	435.8	1.68838
$n_h$	404.7	1.69792
$n_i$	365.0	365.0
$n_{334.1}$	334.1	334.1
$n_{312.6}$	312.6	312.6
$n_{296.7}$	296.7	296.7
$n_{280.4}$	280.4	280.4
$n_{248.3}$	248.3	248.3

### Constants of Dispersion Formula

$B_1$	1.536520810
$B_2$	0.156971102
$B_3$	1.301968150
$C_1$	0.010843573
$C_2$	0.0562278762
$C_3$	131.33970000

### Constants of Formula for $dn/dT$

$D_0$	1.89E-06
$D_1$	1.22E-08
$D_2$	-1.61E-11
$E_0$	7.77E-07
$E_1$	9.96E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.256

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.8	4.1	5.6	0.6	1.9	3.3
+20/+40	2.9	4.4	6.2	1.5	3.0	4.7
+60/+80	3.1	4.8	6.7	2.0	3.6	5.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.860	0.680
2325	0.900	0.760
1970	0.971	0.930
1530	0.994	0.985
1060	0.999	0.997
700	0.996	0.990
660	0.994	0.985
620	0.994	0.985
580	0.995	0.987
546	0.994	0.985
500	0.988	0.971
460	0.980	0.951
436	0.971	0.930
420	0.954	0.890
405	0.910	0.800
400	0.890	0.750
390	0.800	0.580
380	0.630	0.320
370	0.320	0.060
365	0.160	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  41/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2309
$P_{C,s}$	0.4869
$P_{d,C}$	0.2929
$P_{e,d}$	0.2367
$P_{g,F}$	0.5890
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2277
$P'_{C,s}$	0.5253
$P'_{d,C'}$	0.2435
$P'_{e,d}$	0.2333
$P'_{g,F'}$	0.5214
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0021
$\Delta P_{C,s}$	0.0001
$\Delta P_{F,e}$	0.0010
$\Delta P_{g,F}$	0.0057
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.1
$T_g$ [°C]	619
$T_{10}^{13}$ [°C]	622
$T_{10}^{7.6}$ [°C]	766
$c_p$ [J/(g·K)]	0.660
$\lambda$ [W/(m·K)]	0.940
$\rho$ [g/cm <sup>3</sup> ]	3.15
$E$ [ $10^3$ N/mm <sup>2</sup> ]	84
$\mu$	0.247
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.04
$HK_{0.1/20}$	580
HG	3

## N-BASF64 704394.320

$n_d = 1.70400$

$v_d = 39.38$

$n_F - n_C = 0.017875$

$n_e = 1.70824$

$v_e = 39.12$

$n_F - n_C = 0.018105$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.66373
$n_{1970.1}$	1970.1	1.66988
$n_{1529.6}$	1529.6	1.67667
$n_{1060.0}$	1060.0	1.68453
$n_t$	1014.0	1.68551
$n_s$	852.1	1.68982
$n_r$	706.5	1.69578
$n_C$	656.3	1.69872
$n_{C'}$	643.8	1.69955
$n_{632.8}$	632.8	1.70033
$n_D$	589.3	1.70384
$n_d$	587.6	1.70400
$n_e$	546.1	1.70824
$n_F$	486.1	1.71659
$n_{F'}$	480.0	1.71765
$n_g$	435.8	1.72690
$n_h$	404.7	1.73581
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.655542680
$B_2$	0.171319770
$B_3$	1.336644480
$C_1$	0.010448564
$C_2$	0.0499394756
$C_3$	118.96147200

### Constants of Formula for $dn/dT$

$D_0$	1.60E-06
$D_1$	1.02E-08
$D_2$	-2.68E-11
$E_0$	7.87E-07
$E_1$	9.65E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.229

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.8	4.1	5.5	0.6	1.8	3.1
+20/+40	2.8	4.3	5.9	1.4	2.8	4.4
+60/+80	2.9	4.5	6.3	1.8	3.4	5.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.730	0.450
2325	0.850	0.670
1970	0.959	0.900
1530	0.988	0.970
1060	0.994	0.985
700	0.988	0.970
660	0.982	0.955
620	0.979	0.950
580	0.979	0.950
546	0.980	0.950
500	0.976	0.940
460	0.967	0.920
436	0.959	0.900
420	0.950	0.880
405	0.930	0.840
400	0.920	0.820
390	0.890	0.750
380	0.820	0.610
370	0.670	0.370
365	0.550	0.220
350	0.090	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  40/35

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2408
$P_{C,s}$	0.4979
$P_{d,C}$	0.2956
$P_{e,d}$	0.2372
$P_{g,F}$	0.5769
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2377
$P'_{C,s}$	0.5375
$P'_{d,C'}$	0.2459
$P'_{e,d}$	0.2342
$P'_{g,F'}$	0.5110
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0069
$\Delta P_{C,s}$	0.0032
$\Delta P_{F,e}$	-0.0004
$\Delta P_{g,F}$	-0.0006
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	3.2
AR	1.2
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.7
$T_g$ [°C]	582
$T_{10}^{13}$ [°C]	585
$T_{10}^{7.6}$ [°C]	712
$c_p$ [J/(g·K)]	
$\lambda$ [W/(m·K)]	
$\rho$ [g/cm <sup>3</sup> ]	3.20
$E$ [ $10^3$ N/mm <sup>2</sup> ]	105
$\mu$	0.264
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.38
$HK_{0.1/20}$	650
HG	4

## N-LAF2 744449.430

$n_d = 1.74397$   
 $n_e = 1.74791$

$v_d = 44.85$   
 $v_e = 44.57$

$n_F - n_C = 0.016588$   
 $n_{F'} - n_{C'} = 0.016780$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.70582
$n_{1970.1}$	1970.1	1.71169
$n_{1529.6}$	1529.6	1.71816
$n_{1060.0}$	1060.0	1.72563
$n_t$	1014.0	1.72656
$n_s$	852.1	1.73064
$n_r$	706.5	1.73627
$n_C$	656.3	1.73903
$n_{C'}$	643.8	1.73981
$n_{632.8}$	632.8	1.74054
$n_D$	589.3	1.74383
$n_d$	587.6	1.74397
$n_e$	546.1	1.74791
$n_F$	486.1	1.75562
$n_{F'}$	480.0	1.75659
$n_g$	435.8	1.76500
$n_h$	404.7	1.77298
$n_i$	365.0	1.78703
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.809842270
$B_2$	0.157295550
$B_3$	1.093003700
$C_1$	0.010171162
$C_2$	0.0442431765
$C_3$	100.68774800

### Constants of Formula for $dn/dT$

$D_0$	-3.64E-06
$D_1$	9.20E-09
$D_2$	-6.00E-12
$E_0$	6.43E-07
$E_1$	6.11E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.220

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	0.0	1.0	2.1	-2.3	-1.3	-0.3
+20/+40	-0.1	1.0	2.3	-1.6	-0.5	0.7
+60/+80	-0.1	1.2	2.5	-1.2	0.0	1.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.690	0.400
2325	0.860	0.690
1970	0.951	0.880
1530	0.994	0.985
1060	0.999	0.997
700	0.998	0.996
660	0.997	0.993
620	0.997	0.992
580	0.997	0.993
546	0.998	0.994
500	0.993	0.983
460	0.985	0.962
436	0.976	0.940
420	0.965	0.920
405	0.940	0.870
400	0.930	0.840
390	0.900	0.760
380	0.830	0.630
370	0.710	0.430
365	0.630	0.310
350	0.230	0.030
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  40/34

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2459
$P_{C,s}$	0.5057
$P_{d,C}$	0.2979
$P_{e,d}$	0.2377
$P_{g,F}$	0.5656
$P_{i,h}$	0.8470

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2431
$P'_{C,s}$	0.5464
$P'_{d,C'}$	0.2481
$P'_{e,d}$	0.2350
$P'_{g,F'}$	0.5012
$P'_{i,h}$	0.8373

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0061
$\Delta P_{C,s}$	-0.0017
$\Delta P_{F,e}$	-0.0004
$\Delta P_{g,F}$	-0.0027
$\Delta P_{i,g}$	-0.0202

### Chemical Properties

CR	2
FR	3
SR	52.2
AR	1
PR	2.2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.1
$T_g$ [°C]	653
$T_{10}^{13}$ [°C]	645
$T_{10}^{7.6}$ [°C]	734
$c_p$ [J/(g·K)]	0.510
$\lambda$ [W/(m·K)]	0.670
$\rho$ [g/cm <sup>3</sup> ]	4.30
$E$ [ $10^3$ N/mm <sup>2</sup> ]	94
$\mu$	0.288
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.42
$HK_{0.1/20}$	530
HG	6



## N-LAF7 749348.373

$n_d = 1.74950$

$v_d = 34.82$

$n_F - n_C = 0.021525$

$n_e = 1.75459$

$v_e = 34.56$

$n_F - n_C = 0.021833$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.70344
$n_{1970.1}$	1970.1	1.71021
$n_{1529.6}$	1529.6	1.71772
$n_{1060.0}$	1060.0	1.72659
$n_t$	1014.0	1.72773
$n_s$	852.1	1.73272
$n_r$	706.5	1.73972
$n_C$	656.3	1.74320
$n_{C'}$	643.8	1.74419
$n_{632.8}$	632.8	1.74511
$n_D$	589.3	1.74931
$n_d$	587.6	1.74950
$n_e$	546.1	1.75459
$n_F$	486.1	1.76472
$n_{F'}$	480.0	1.76602
$n_g$	435.8	1.77741
$n_h$	404.7	1.78854
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.740287640
$B_2$	0.226710554
$B_3$	1.325255480
$C_1$	0.010792558
$C_2$	0.0538626639
$C_3$	106.26866500

### Constants of Formula for $dn/dT$

$D_0$	9.21E-07
$D_1$	1.10E-08
$D_2$	-1.75E-11
$E_0$	7.67E-07
$E_1$	1.10E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.264

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.5	3.9	5.6	0.2	1.5	3.1
+20/+40	2.6	4.3	6.3	1.1	2.7	4.7
+60/+80	2.7	4.6	6.8	1.6	3.4	5.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.670	0.370
2325	0.860	0.680
1970	0.969	0.920
1530	0.995	0.987
1060	0.998	0.996
700	0.997	0.993
660	0.997	0.992
620	0.997	0.992
580	0.996	0.990
546	0.994	0.985
500	0.988	0.971
460	0.977	0.940
436	0.965	0.910
420	0.950	0.870
405	0.920	0.810
400	0.910	0.780
390	0.860	0.680
380	0.770	0.520
370	0.570	0.250
365	0.380	0.090
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  41/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2317
$P_{C,s}$	0.4870
$P_{d,C}$	0.2928
$P_{e,d}$	0.2366
$P_{g,F}$	0.5894
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2284
$P'_{C,s}$	0.5254
$P'_{d,C'}$	0.2434
$P'_{e,d}$	0.2333
$P'_{g,F'}$	0.5218
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0085
$\Delta P_{C,s}$	0.0029
$\Delta P_{F,e}$	0.0005
$\Delta P_{g,F}$	0.0042
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	2
SR	51.3
AR	1.2
PR	1.2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$T_g$ [°C]	568
$T_{10}^{13}$ [°C]	563
$T_{10}^{7.6}$ [°C]	669
$c_p$ [J/(g·K)]	0.620
$\lambda$ [W/(m·K)]	0.830
$\rho$ [g/cm <sup>3</sup> ]	3.73
$E$ [ $10^3$ N/mm <sup>2</sup> ]	96
$\mu$	0.271
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.57
$HK_{0.1/20}$	530
HG	5

## N-LAF21 788475.428

$n_d = 1.78800$

$v_d = 47.49$

$n_F - n_C = 0.016593$

$n_e = 1.79195$

$v_e = 47.25$

$n_F - n_C = 0.016761$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.74419
$n_{1970.1}$	1970.1	1.75191
$n_{1529.6}$	1529.6	1.76014
$n_{1060.0}$	1060.0	1.76892
$n_t$	1014.0	1.76995
$n_s$	852.1	1.77434
$n_r$	706.5	1.78019
$n_C$	656.3	1.78301
$n_{C'}$	643.8	1.78380
$n_{632.8}$	632.8	1.78454
$n_D$	589.3	1.78785
$n_d$	587.6	1.78800
$n_e$	546.1	1.79195
$n_F$	486.1	1.79960
$n_{F'}$	480.0	1.80056
$n_g$	435.8	1.80882
$n_h$	404.7	1.81657
$n_i$	365.0	1.83002
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.871345290
$B_2$	0.250783010
$B_3$	1.220486390
$C_1$	0.009333223
$C_2$	0.0345637762
$C_3$	83.24048660

### Constants of Formula for $dn/dT$

$D_0$	3.11E-06
$D_1$	1.13E-08
$D_2$	-2.07E-11
$E_0$	5.88E-07
$E_1$	6.32E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.199

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.8	4.8	5.8	1.4	2.4	3.3
+20/+40	3.9	5.1	6.2	2.3	3.5	4.6
+60/+80	4.0	5.3	6.5	2.8	4.1	5.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.430	0.120
2325	0.710	0.430
1970	0.940	0.860
1530	0.988	0.971
1060	0.998	0.996
700	0.998	0.994
660	0.997	0.993
620	0.997	0.992
580	0.997	0.992
546	0.997	0.993
500	0.996	0.989
460	0.990	0.976
436	0.985	0.964
420	0.981	0.952
405	0.971	0.930
400	0.966	0.920
390	0.950	0.880
380	0.920	0.810
370	0.870	0.710
365	0.830	0.630
350	0.640	0.330
334	0.280	0.040
320	0.030	0.000
310	0.000	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  39/32

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2646
$P_{C,s}$	0.5222
$P_{d,C}$	0.3009
$P_{e,d}$	0.2380
$P_{g,F}$	0.5555
$P_{i,h}$	0.8106

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2619
$P'_{C,s}$	0.5641
$P'_{d,C'}$	0.2507
$P'_{e,d}$	0.2356
$P'_{g,F'}$	0.4927
$P'_{i,h}$	0.8025

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0165
$\Delta P_{C,s}$	0.0086
$\Delta P_{F,e}$	-0.0024
$\Delta P_{g,F}$	-0.0084
$\Delta P_{i,g}$	-0.0481

### Chemical Properties

CR	1
FR	1
SR	51.3
AR	1
PR	1.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$T_g$ [°C]	653
$T_{10}^{13}$ [°C]	659
$T_{10}^{7.6}$ [°C]	729
$c_p$ [J/(g·K)]	0.550
$\lambda$ [W/(m·K)]	0.830
$\rho$ [g/cm <sup>3</sup> ]	4.28
$E$ [ $10^3$ N/mm <sup>2</sup> ]	124
$\mu$	0.295
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.46
$HK_{0.1/20}$	730
HG	2

## N-LAF33 786441.436

$n_d = 1.78582$   
 $n_e = 1.79007$

$v_d = 44.05$   
 $v_e = 43.80$

$n_F - n_C = 0.017839$   
 $n_{F'} - n_{C'} = 0.018038$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.74262
$n_{1970.1}$	1970.1	1.74968
$n_{1529.6}$	1529.6	1.75732
$n_{1060.0}$	1060.0	1.76584
$n_t$	1014.0	1.76689
$n_s$	852.1	1.77138
$n_r$	706.5	1.77751
$n_C$	656.3	1.78049
$n_{C'}$	643.8	1.78134
$n_{632.8}$	632.8	1.78213
$n_D$	589.3	1.78567
$n_d$	587.6	1.78582
$n_e$	546.1	1.79007
$n_F$	486.1	1.79833
$n_{F'}$	480.0	1.79937
$n_g$	435.8	1.80837
$n_h$	404.7	1.81687
$n_i$	365.0	1.83175
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.796534170
$B_2$	0.311577903
$B_3$	1.159818630
$C_1$	0.009273135
$C_2$	0.0358201181
$C_3$	87.34487120

### Constants of Formula for $dn/dT$

$D_0$	8.17E-06
$D_1$	1.24E-08
$D_2$	-1.65E-11
$E_0$	7.11E-07
$E_1$	8.59E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.210

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.8	8.1	9.4	4.4	5.7	7.0
+20/+40	7.0	8.5	10.0	5.5	6.9	8.4
+60/+80	7.2	8.9	10.5	6.0	7.6	9.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.470	0.150
2325	0.740	0.480
1970	0.950	0.870
1530	0.990	0.974
1060	0.999	0.998
700	0.998	0.996
660	0.998	0.995
620	0.998	0.994
580	0.998	0.994
546	0.998	0.994
500	0.995	0.988
460	0.989	0.973
436	0.983	0.959
420	0.978	0.950
405	0.968	0.920
400	0.963	0.910
390	0.950	0.870
380	0.920	0.810
370	0.870	0.710
365	0.840	0.650
350	0.690	0.400
334	0.380	0.090
320	0.080	0.000
310	0.000	0.000
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  39/32

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2520
$P_{C,s}$	0.5107
$P_{d,C}$	0.2988
$P_{e,d}$	0.2378
$P_{g,F}$	0.5626
$P_{i,h}$	0.8339

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2492
$P'_{C,s}$	0.5518
$P'_{d,C'}$	0.2488
$P'_{e,d}$	0.2351
$P'_{g,F'}$	0.4987
$P'_{i,h}$	0.8247

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0088
$\Delta P_{C,s}$	0.0052
$\Delta P_{F,e}$	-0.0018
$\Delta P_{g,F}$	-0.0071
$\Delta P_{i,g}$	-0.0443

### Chemical Properties

CR	1
FR	2
SR	52.2
AR	1
PR	3
SR-J	6
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.7
$T_g$ [°C]	600
$T_{10}^{13}$ [°C]	585
$T_{10}^{7.6}$ [°C]	673
$c_p$ [J/(g·K)]	0.570
$\lambda$ [W/(m·K)]	0.800
AT [°C]	628
$\rho$ [g/cm <sup>3</sup> ]	4.36
E [ $10^3$ N/mm <sup>2</sup> ]	111
$\mu$	0.301
K [ $10^{-6}$ mm <sup>2</sup> /N]	2.21
HK <sub>0.1/20</sub>	730
HG	1
Abrasion Aa	67

## N-LAF34 773496.424

$n_d = 1.77250$

$v_d = 49.62$

$n_F - n_C = 0.015568$

$n_e = 1.77621$

$v_e = 49.38$

$n_F - n_C = 0.015719$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.73085
$n_{1970.1}$	1970.1	1.73824
$n_{1529.6}$	1529.6	1.74610
$n_{1060.0}$	1060.0	1.75447
$n_t$	1014.0	1.75546
$n_s$	852.1	1.75962
$n_r$	706.5	1.76515
$n_C$	656.3	1.76780
$n_{C'}$	643.8	1.76855
$n_{632.8}$	632.8	1.76924
$n_D$	589.3	1.77236
$n_d$	587.6	1.77250
$n_e$	546.1	1.77621
$n_F$	486.1	1.78337
$n_{F'}$	480.0	1.78427
$n_g$	435.8	1.79196
$n_h$	404.7	1.79915
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.758369580
$B_2$	0.313537785
$B_3$	1.189252310
$C_1$	0.008728100
$C_2$	0.0293020832
$C_3$	85.17806440

### Constants of Formula for $dn/dT$

$D_0$	3.89E-06
$D_1$	1.02E-08
$D_2$	-1.91E-11
$E_0$	5.88E-07
$E_1$	7.57E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.181

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.2	5.2	6.2	1.9	2.8	3.7
+20/+40	4.3	5.4	6.5	2.7	3.9	4.9
+60/+80	4.4	5.6	6.8	3.2	4.4	5.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.450	0.140
2325	0.730	0.450
1970	0.950	0.870
1530	0.989	0.973
1060	0.999	0.998
700	0.998	0.996
660	0.998	0.996
620	0.998	0.995
580	0.998	0.995
546	0.998	0.996
500	0.997	0.993
460	0.994	0.986
436	0.991	0.978
420	0.988	0.971
405	0.983	0.958
400	0.980	0.950
390	0.971	0.930
380	0.955	0.890
370	0.930	0.830
365	0.910	0.790
350	0.820	0.600
334	0.640	0.330
320	0.420	0.120
310	0.240	0.030
300	0.070	0.000
290	0.000	
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  38/30

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2674
$P_{C,s}$	0.5256
$P_{d,C}$	0.3018
$P_{e,d}$	0.2382
$P_{g,F}$	0.5518
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2648
$P'_{C,s}$	0.5679
$P'_{d,C'}$	0.2515
$P'_{e,d}$	0.2359
$P'_{g,F'}$	0.4895
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0126
$\Delta P_{C,s}$	0.0070
$\Delta P_{F,e}$	-0.0023
$\Delta P_{g,F}$	-0.0085
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	1
SR	51.3
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.0
$T_g$ [°C]	668
$T_{10}^{13}$ [°C]	659
$T_{10}^{7.6}$ [°C]	745
$c_p$ [J/(g·K)]	0.560
$\lambda$ [W/(m·K)]	0.800
$\rho$ [g/cm <sup>3</sup> ]	4.24
$E$ [ $10^3$ N/mm <sup>2</sup> ]	123
$\mu$	0.292
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.44
$HK_{0.1/20}$	770
HG	2

## N-LAF35 743494.412

$n_d = 1.74330$

$v_d = 49.40$

$n_F - n_C = 0.015047$

$n_e = 1.74688$

$v_e = 49.16$

$n_F - n_C = 0.015194$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	
$n_{1970.1}$	1970.1	
$n_{1529.6}$	1529.6	
$n_{1060.0}$	1060.0	1.72588
$n_t$	1014.0	1.72683
$n_s$	852.1	1.73086
$n_r$	706.5	1.73620
$n_C$	656.3	1.73876
$n_{C'}$	643.8	1.73948
$n_{632.8}$	632.8	1.74015
$n_D$	589.3	1.74317
$n_d$	587.6	1.74330
$n_e$	546.1	1.74688
$n_F$	486.1	1.75381
$n_{F'}$	480.0	1.75467
$n_g$	435.8	1.76212
$n_h$	404.7	1.76908
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.516974360
$B_2$	0.455875464
$B_3$	1.074692420
$C_1$	0.007509432
$C_2$	0.0260046715
$C_3$	80.59451590

### Constants of Formula for $dn/dT$

$D_0$	8.98E-06
$D_1$	1.26E-08
$D_2$	-1.23E-11
$E_0$	6.24E-07
$E_1$	6.86E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.194

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	7.0	8.1	9.2	4.7	5.7	6.7
+20/+40	7.1	8.4	9.6	5.6	6.9	8.0
+60/+80	7.3	8.7	10.0	6.2	7.5	8.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.400	0.100
2325	0.710	0.430
1970	0.940	0.850
1530	0.988	0.970
1060	0.998	0.995
700	0.998	0.996
660	0.998	0.996
620	0.998	0.994
580	0.998	0.994
546	0.998	0.995
500	0.997	0.992
460	0.994	0.985
436	0.990	0.976
420	0.987	0.967
405	0.980	0.950
400	0.976	0.940
390	0.966	0.920
380	0.950	0.880
370	0.920	0.810
365	0.900	0.760
350	0.790	0.550
334	0.590	0.270
320	0.350	0.200
310	0.150	0.080
300	0.030	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  38/30

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2674
$P_{C,s}$	0.5253
$P_{d,C}$	0.3017
$P_{e,d}$	0.2381
$P_{g,F}$	0.5523
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2648
$P'_{C,s}$	0.5676
$P'_{d,C'}$	0.2514
$P'_{e,d}$	0.2358
$P'_{g,F'}$	0.4899
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0134
$\Delta P_{C,s}$	0.0072
$\Delta P_{F,e}$	-0.0022
$\Delta P_{g,F}$	-0.0084
$\Delta P_{i,g}$	

### Chemical Properties

CR	2
FR	1
SR	52.3
AR	1
PR	3.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.4
$T_g$ [°C]	589
$T_{10}^{13}$ [°C]	585
$T_{10}^{7.6}$ [°C]	669
$c_p$ [J/(g·K)]	0.570
$\lambda$ [W/(m·K)]	0.800
$\rho$ [g/cm <sup>3</sup> ]	4.12
$E$ [ $10^3$ N/mm <sup>2</sup> ]	109
$\mu$	0.301
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.29
$HK_{0.1/20}$	660
HG	2

## P-LAF37 755457.399

$n_d = 1.75550$

$v_d = 45.66$

$n_F - n_C = 0.016546$

$n_e = 1.75944$

$v_e = 45.42$

$n_F - n_C = 0.016722$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.71338
$n_{1970.1}$	1970.1	1.72058
$n_{1529.6}$	1529.6	1.72830
$n_{1060.0}$	1060.0	1.73669
$n_t$	1014.0	1.73770
$n_s$	852.1	1.74198
$n_r$	706.5	1.74775
$n_C$	656.3	1.75054
$n_{C'}$	643.8	1.75132
$n_{632.8}$	632.8	1.75206
$n_D$	589.3	1.75535
$n_d$	587.6	1.75550
$n_e$	546.1	1.75944
$n_F$	486.1	1.76708
$n_{F'}$	480.0	1.76804
$n_g$	435.8	1.77633
$n_h$	404.7	1.78414
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.760032440
$B_2$	0.248286745
$B_3$	1.159351220
$C_1$	0.009380064
$C_2$	0.0360537464
$C_3$	86.43246930

### Constants of Formula for $dn/dT$

$D_0$	7.03E-06
$D_1$	1.15E-08
$D_2$	7.48E-13
$E_0$	7.25E-07
$E_1$	8.36E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.206

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.1	7.4	8.7	3.8	5.0	6.2
+20/+40	6.1	7.6	9.0	4.6	6.1	7.5
+60/+80	6.4	8.0	9.5	5.2	6.8	8.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.56	0.23
2325	0.81	0.60
1970	0.968	0.92
1530	0.997	0.991
1060	0.999	0.998
700	0.999	0.997
660	0.998	0.995
620	0.998	0.995
580	0.998	0.995
546	0.998	0.995
500	0.997	0.992
460	0.993	0.982
436	0.989	0.973
420	0.986	0.965
405	0.979	0.95
400	0.976	0.94
390	0.965	0.91
380	0.94	0.86
370	0.90	0.78
365	0.87	0.71
350	0.73	0.45
334	0.46	0.15
320	0.18	0.01
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  37/31

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2591
$P_{C,s}$	0.5170
$P_{d,C}$	0.2999
$P_{e,d}$	0.2379
$P_{g,F}$	0.5590
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2563
$P'_{C,s}$	0.5585
$P'_{d,C'}$	0.2498
$P'_{e,d}$	0.2354
$P'_{g,F'}$	0.4957
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0145
$\Delta P_{C,s}$	0.0077
$\Delta P_{F,e}$	-0.0022
$\Delta P_{g,F}$	-0.0080
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	3
SR	52.3
AR	1
PR	3
SR-J	4
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.8
$T_g$ [°C]	506
$T_{10}^{13}$ [°C]	510
$T_{10}^{7.6}$ [°C]	593
$c_p$ [J/(g·K)]	0.640
$\lambda$ [W/(m·K)]	0.900
AT [°C]	546
$\rho$ [g/cm <sup>3</sup> ]	3.99
E [10 <sup>3</sup> N/mm <sup>2</sup> ]	115
$\mu$	0.296
K [10 <sup>-6</sup> mm <sup>2</sup> /N]	2.26
HK <sub>0.1/20</sub>	697
Abrasion Aa	67

## LASF35 022291.541

$n_d = 2.02204$

$v_d = 29.06$

$n_F - n_C = 0.035170$

$n_e = 2.03035$

$v_e = 28.84$

$n_F - n_C = 0.035721$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.95946
$n_{1970.1}$	1970.1	1.96639
$n_{1529.6}$	1529.6	1.97472
$n_{1060.0}$	1060.0	1.98624
$n_t$	1014.0	1.98786
$n_s$	852.1	1.99531
$n_r$	706.5	2.00628
$n_C$	656.3	2.01185
$n_{C'}$	643.8	2.01343
$n_{632.8}$	632.8	2.01493
$n_D$	589.3	2.02173
$n_d$	587.6	2.02204
$n_e$	546.1	2.03035
$n_F$	486.1	2.04702
$n_{F'}$	480.0	2.04916
$n_g$	435.8	2.06805
$n_h$	404.7	2.08663
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	2.455058610
$B_2$	0.453006077
$B_3$	2.385130800
$C_1$	0.013567040
$C_2$	0.0545803020
$C_3$	167.90471500

### Constants of Formula for $dn/dT$

$D_0$	1.43E-07
$D_1$	8.71E-09
$D_2$	-2.71E-11
$E_0$	1.02E-06
$E_1$	1.50E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.263

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.6	5.0	7.8	-0.1	2.2	5.0
+20/+40	2.7	5.5	9.0	1.0	3.8	7.1
+60/+80	2.8	5.9	9.7	1.4	4.5	8.3

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.790	0.550
2325	0.880	0.720
1970	0.973	0.930
1530	0.995	0.987
1060	0.998	0.994
700	0.992	0.981
660	0.990	0.974
620	0.987	0.969
580	0.985	0.962
546	0.977	0.940
500	0.950	0.870
460	0.900	0.770
436	0.850	0.670
420	0.790	0.550
405	0.690	0.390
400	0.630	0.320
390	0.500	0.180
380	0.300	0.050
370	0.100	0.000
365	0.030	
350	0.000	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  45/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2118
$P_{C,s}$	0.4701
$P_{d,C}$	0.2899
$P_{e,d}$	0.2364
$P_{g,F}$	0.5982
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2086
$P'_{C,s}$	0.5073
$P'_{d,C'}$	0.2409
$P'_{e,d}$	0.2327
$P'_{g,F'}$	0.5291
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0009
$\Delta P_{C,s}$	-0.0006
$\Delta P_{F,e}$	0.0006
$\Delta P_{g,F}$	0.0033
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1.3
AR	1
PR	1.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.5
$T_g$ [°C]	774
$T_{10}^{13}$ [°C]	
$T_{10}^{7.6}$ [°C]	
$c_p$ [J/(g·K)]	0.445
$\lambda$ [W/(m·K)]	0.920
$\rho$ [g/cm <sup>3</sup> ]	5.41
$E$ [ $10^3$ N/mm <sup>2</sup> ]	132
$\mu$	0.303
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	0.73
$HK_{0.1/20}$	810
HG	1

## N-LASF9 850322.441

$n_d = 1.85025$   
 $n_e = 1.85650$

$v_d = 32.17$   
 $v_e = 31.93$

$n_F - n_C = 0.026430$   
 $n_{F'} - n_{C'} = 0.026827$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.80058
$n_{1970.1}$	1970.1	1.80659
$n_{1529.6}$	1529.6	1.81364
$n_{1060.0}$	1060.0	1.82293
$n_t$	1014.0	1.82420
$n_s$	852.1	1.82997
$n_r$	706.5	1.83834
$n_C$	656.3	1.84255
$n_{C'}$	643.8	1.84376
$n_{632.8}$	632.8	1.84489
$n_D$	589.3	1.85002
$n_d$	587.6	1.85025
$n_e$	546.1	1.85650
$n_F$	486.1	1.86898
$n_{F'}$	480.0	1.87058
$n_g$	435.8	1.88467
$n_h$	404.7	1.89845
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	2.000295470
$B_2$	0.298926886
$B_3$	1.806918430
$C_1$	0.012142602
$C_2$	0.0538736236
$C_3$	156.53082900

### Constants of Formula for $dn/dT$

$D_0$	1.05E-06
$D_1$	1.02E-08
$D_2$	-2.38E-11
$E_0$	9.19E-07
$E_1$	1.18E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.257

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.8	4.7	6.9	0.4	2.2	4.3
+20/+40	2.9	5.1	7.7	1.4	3.5	6.0
+60/+80	3.1	5.5	8.2	1.8	4.2	6.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.810	0.600
2325	0.870	0.710
1970	0.967	0.920
1530	0.994	0.986
1060	0.998	0.994
700	0.994	0.986
660	0.992	0.981
620	0.992	0.979
580	0.991	0.978
546	0.989	0.972
500	0.978	0.950
460	0.958	0.900
436	0.930	0.840
420	0.900	0.770
405	0.830	0.630
400	0.800	0.570
390	0.690	0.400
380	0.530	0.200
370	0.270	0.040
365	0.140	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  41/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2181
$P_{C,s}$	0.4762
$P_{d,C}$	0.2912
$P_{e,d}$	0.2366
$P_{g,F}$	0.5934
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2149
$P'_{C,s}$	0.5140
$P'_{d,C'}$	0.2420
$P'_{e,d}$	0.2330
$P'_{g,F'}$	0.5250
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0032
$\Delta P_{C,s}$	-0.0016
$\Delta P_{F,e}$	0.0008
$\Delta P_{g,F}$	0.0037
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	2
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$T_g$ [°C]	683
$T_{10}^{13}$ [°C]	700
$T_{10}^{7.6}$ [°C]	817
$c_p$ [J/(g·K)]	0.530
$\lambda$ [W/(m·K)]	0.790
$\rho$ [g/cm <sup>3</sup> ]	4.41
$E$ [ $10^3$ N/mm <sup>2</sup> ]	109
$\mu$	0.288
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.72
$HK_{0.1/20}$	515
HG	4
Abrasion Aa	120



## N-LASF9HT 850322.441

$n_d = 1.85025$   
 $n_e = 1.85650$

$v_d = 32.17$   
 $v_e = 31.93$

$n_F - n_C = 0.026430$   
 $n_{F'} - n_{C'} = 0.026827$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.80058
$n_{1970.1}$	1970.1	1.80659
$n_{1529.6}$	1529.6	1.81364
$n_{1060.0}$	1060.0	1.82293
$n_t$	1014.0	1.82420
$n_s$	852.1	1.82997
$n_r$	706.5	1.83834
$n_C$	656.3	1.84255
$n_{C'}$	643.8	1.84376
$n_{632.8}$	632.8	1.84489
$n_D$	589.3	1.85002
$n_d$	587.6	1.85025
$n_e$	546.1	1.85650
$n_F$	486.1	1.86898
$n_{F'}$	480.0	1.87058
$n_g$	435.8	1.88467
$n_h$	404.7	1.89845
$n_i$	365.0	365.0
$n_{334.1}$	334.1	334.1
$n_{312.6}$	312.6	312.6
$n_{296.7}$	296.7	296.7
$n_{280.4}$	280.4	280.4
$n_{248.3}$	248.3	248.3

### Constants of Dispersion Formula

$B_1$	2.000295470
$B_2$	0.298926886
$B_3$	1.806918430
$C_1$	0.012142602
$C_2$	0.0538736236
$C_3$	156.53082900

### Constants of Formula for $dn/dT$

$D_0$	1.05E-06
$D_1$	1.02E-08
$D_2$	-2.38E-11
$E_0$	9.19E-07
$E_1$	1.18E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.257

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.8	4.7	6.9	0.4	2.2	4.3
+20/+40	2.9	5.1	7.7	1.4	3.5	6.0
+60/+80	3.1	5.5	8.2	1.8	4.2	6.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.810	0.600
2325	0.870	0.710
1970	0.967	0.920
1530	0.994	0.986
1060	0.998	0.994
700	0.994	0.986
660	0.992	0.981
620	0.992	0.979
580	0.991	0.978
546	0.989	0.972
500	0.978	0.950
460	0.958	0.900
436	0.940	0.860
420	0.920	0.800
405	0.870	0.700
400	0.840	0.650
390	0.770	0.510
380	0.630	0.310
370	0.390	0.100
365	0.250	0.030
350	0.010	0.000
334	0.000	0.000
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  40/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2181
$P_{C,s}$	0.4762
$P_{d,C}$	0.2912
$P_{e,d}$	0.2366
$P_{g,F}$	0.5934
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2149
$P'_{C,s}$	0.5140
$P'_{d,C'}$	0.2420
$P'_{e,d}$	0.2330
$P'_{g,F'}$	0.5250
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0032
$\Delta P_{C,s}$	-0.0016
$\Delta P_{F,e}$	0.0008
$\Delta P_{g,F}$	0.0037
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	2
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$T_g$ [°C]	683
$T_{10}^{13}$ [°C]	700
$T_{10}^{7.6}$ [°C]	817
$c_p$ [J/(g·K)]	0.530
$\lambda$ [W/(m·K)]	0.790
$\rho$ [g/cm <sup>3</sup> ]	4.41
$E$ [ $10^3$ N/mm <sup>2</sup> ]	109
$\mu$	0.288
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.72
$HK_{0.1/20}$	515
HG	4

## N-LASF31A 883408.551

$n_d = 1.88300$

$v_d = 40.76$

$n_F - n_C = 0.021663$

$n_e = 1.88815$

$v_e = 40.52$

$n_F - n_C = 0.021921$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.83590
$n_{1970.1}$	1970.1	1.84267
$n_{1529.6}$	1529.6	1.85026
$n_{1060.0}$	1060.0	1.85937
$n_t$	1014.0	1.86054
$n_s$	852.1	1.86572
$n_r$	706.5	1.87298
$n_C$	656.3	1.87656
$n_{C'}$	643.8	1.87757
$n_{632.8}$	632.8	1.87853
$n_D$	589.3	1.88281
$n_d$	587.6	1.88300
$n_e$	546.1	1.88815
$n_F$	486.1	1.89822
$n_{F'}$	480.0	1.89950
$n_g$	435.8	1.91050
$n_h$	404.7	1.92093
$n_i$	365.0	1.93920
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.964850750
$B_2$	0.475231259
$B_3$	1.483601090
$C_1$	0.009820602
$C_2$	0.0344713438
$C_3$	110.73986300

### Constants of Formula for $dn/dT$

$D_0$	1.67E-06
$D_1$	8.90E-09
$D_2$	-8.73E-12
$E_0$	7.47E-07
$E_1$	7.46E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.207

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.4	4.8	6.3	0.9	2.3	3.7
+20/+40	3.3	4.9	6.6	1.7	3.3	4.9
+60/+80	3.4	5.2	6.9	2.2	3.9	5.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.640	0.320
2325	0.820	0.620
1970	0.963	0.910
1530	0.993	0.983
1060	0.998	0.995
700	0.997	0.992
660	0.996	0.991
620	0.996	0.990
580	0.996	0.990
546	0.996	0.990
500	0.991	0.978
460	0.980	0.950
436	0.970	0.930
420	0.960	0.900
405	0.940	0.860
400	0.930	0.840
390	0.910	0.780
380	0.860	0.690
370	0.780	0.540
365	0.730	0.450
350	0.490	0.170
334	0.130	0.010
320	0.060	0.000
310	0.000	
300	0.000	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  38/33

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2391
$P_{C,s}$	0.5004
$P_{d,C}$	0.2972
$P_{e,d}$	0.2377
$P_{g,F}$	0.5667
$P_{i,h}$	0.8436

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2363
$P'_{C,s}$	0.5407
$P'_{d,C'}$	0.2475
$P'_{e,d}$	0.2349
$P'_{g,F'}$	0.5021
$P'_{i,h}$	0.8337

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0012
$\Delta P_{C,s}$	0.0025
$\Delta P_{F,e}$	-0.0019
$\Delta P_{g,F}$	-0.0085
$\Delta P_{i,g}$	-0.0575

### Chemical Properties

CR	1
FR	0
SR	2.3
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.7
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.7
$T_g$ [°C]	719
$T_{10}^{13}$ [°C]	720
$T_{10}^{7.6}$ [°C]	830
$c_p$ [J/(g·K)]	0.440
$\lambda$ [W/(m·K)]	0.790
$\rho$ [g/cm <sup>3</sup> ]	5.51
$E$ [ $10^3$ N/mm <sup>2</sup> ]	126
$\mu$	0.301
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.18
$HK_{0.1/20}$	650
HG	2

## N-LASF40 834373.443

$n_d = 1.83404$

$v_d = 37.30$

$n_F - n_C = 0.022363$

$n_e = 1.83935$

$v_e = 37.04$

$n_F - n_C = 0.022658$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.78600
$n_{1970.1}$	1970.1	1.79298
$n_{1529.6}$	1529.6	1.80074
$n_{1060.0}$	1060.0	1.80999
$n_t$	1014.0	1.81118
$n_s$	852.1	1.81643
$n_r$	706.5	1.82380
$n_C$	656.3	1.82745
$n_{C'}$	643.8	1.82849
$n_{632.8}$	632.8	1.82946
$n_D$	589.3	1.83385
$n_d$	587.6	1.83404
$n_e$	546.1	1.83935
$n_F$	486.1	1.84981
$n_{F'}$	480.0	1.85114
$n_g$	435.8	1.86275
$n_h$	404.7	1.87393
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.985503310
$B_2$	0.274057042
$B_3$	1.289456610
$C_1$	0.010958331
$C_2$	0.0474551603
$C_3$	96.90852860

### Constants of Formula for $dn/dT$

$D_0$	8.10E-06
$D_1$	1.25E-08
$D_2$	-1.73E-11
$E_0$	8.27E-07
$E_1$	1.08E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.238

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	7.1	8.8	10.6	4.6	6.3	8.0
+20/+40	7.3	9.3	11.4	5.7	7.7	9.8
+60/+80	7.6	9.7	12.0	6.3	8.5	10.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.570	0.240
2325	0.810	0.590
1970	0.963	0.910
1530	0.993	0.982
1060	0.998	0.995
700	0.998	0.996
660	0.998	0.994
620	0.997	0.993
580	0.997	0.992
546	0.995	0.988
500	0.987	0.969
460	0.973	0.930
436	0.954	0.890
420	0.940	0.850
405	0.910	0.780
400	0.890	0.750
390	0.840	0.650
380	0.760	0.510
370	0.600	0.280
365	0.470	0.150
350	0.040	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  39/35

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2346
$P_{C,s}$	0.4929
$P_{d,C}$	0.2948
$P_{e,d}$	0.2371
$P_{g,F}$	0.5786
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2315
$P'_{C,s}$	0.5321
$P'_{d,C'}$	0.2453
$P'_{e,d}$	0.2340
$P'_{g,F'}$	0.5124
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0055
$\Delta P_{C,s}$	0.0030
$\Delta P_{F,e}$	-0.0007
$\Delta P_{g,F}$	-0.0024
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	1
SR	51.2
AR	1
PR	1.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.9
$T_g$ [°C]	590
$T_{10}^{13}$ [°C]	591
$T_{10}^{7.6}$ [°C]	677
$c_p$ [J/(g·K)]	0.550
$\lambda$ [W/(m·K)]	0.810
$\rho$ [g/cm <sup>3</sup> ]	4.43
$E$ [ $10^3$ N/mm <sup>2</sup> ]	111
$\mu$	0.304
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.19
$HK_{0.1/20}$	580
HG	1

## N-LASF41 835431.485

$n_d = 1.83501$

$v_d = 43.13$

$n_F - n_C = 0.019361$

$n_e = 1.83961$

$v_e = 42.88$

$n_F - n_C = 0.019578$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.78859
$n_{1970.1}$	1970.1	1.79608
$n_{1529.6}$	1529.6	1.80423
$n_{1060.0}$	1060.0	1.81338
$n_t$	1014.0	1.81450
$n_s$	852.1	1.81936
$n_r$	706.5	1.82599
$n_C$	656.3	1.82923
$n_{C'}$	643.8	1.83014
$n_{632.8}$	632.8	1.83100
$n_D$	589.3	1.83484
$n_d$	587.6	1.83501
$n_e$	546.1	1.83961
$n_F$	486.1	1.84859
$n_{F'}$	480.0	1.84972
$n_g$	435.8	1.85949
$n_h$	404.7	1.86872
$n_i$	365.0	1.88486
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.863483310
$B_2$	0.413307255
$B_3$	1.357848150
$C_1$	0.009103682
$C_2$	0.0339247268
$C_3$	93.35805950

### Constants of Formula for $dn/dT$

$D_0$	3.03E-06
$D_1$	1.04E-08
$D_2$	-1.30E-11
$E_0$	6.62E-07
$E_1$	7.82E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.209

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.0	5.2	6.4	1.5	2.7	3.9
+20/+40	4.0	5.4	6.8	2.4	3.8	5.2
+60/+80	4.2	5.7	7.2	2.9	4.5	6.0

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.480	0.160
2325	0.760	0.510
1970	0.950	0.880
1530	0.993	0.983
1060	0.998	0.995
700	0.998	0.995
660	0.998	0.994
620	0.997	0.993
580	0.998	0.994
546	0.997	0.993
500	0.994	0.984
460	0.985	0.962
436	0.976	0.940
420	0.967	0.920
405	0.954	0.890
400	0.950	0.880
390	0.930	0.830
380	0.890	0.750
370	0.830	0.630
365	0.790	0.550
350	0.590	0.270
334	0.290	0.040
320	0.040	
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  37/32

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2508
$P_{C,s}$	0.5098
$P_{d,C}$	0.2986
$P_{e,d}$	0.2378
$P_{g,F}$	0.5629
$P_{i,h}$	0.8338

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2480
$P'_{C,s}$	0.5507
$P'_{d,C'}$	0.2487
$P'_{e,d}$	0.2351
$P'_{g,F'}$	0.4989
$P'_{i,h}$	0.8245

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0110
$\Delta P_{C,s}$	0.0063
$\Delta P_{F,e}$	-0.0021
$\Delta P_{g,F}$	-0.0083
$\Delta P_{i,g}$	-0.0520

### Chemical Properties

CR	1
FR	1
SR	4
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$T_g$ [°C]	651
$T_{10}^{13}$ [°C]	658
$T_{10}^{7.6}$ [°C]	739
$c_p$ [J/(g·K)]	0.490
$\lambda$ [W/(m·K)]	0.790
$\rho$ [g/cm <sup>3</sup> ]	4.85
$E$ [ $10^3$ N/mm <sup>2</sup> ]	124
$\mu$	0.294
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.57
$HK_{0.1/20}$	760
HG	2

## N-LASF43 806406.426

$n_d = 1.80610$

$v_d = 40.61$

$n_F - n_C = 0.019850$

$n_e = 1.81081$

$v_e = 40.36$

$n_F - n_C = 0.020089$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.75901
$n_{1970.1}$	1970.1	1.76662
$n_{1529.6}$	1529.6	1.77488
$n_{1060.0}$	1060.0	1.78413
$n_t$	1014.0	1.78527
$n_s$	852.1	1.79018
$n_r$	706.5	1.79691
$n_C$	656.3	1.80020
$n_{C'}$	643.8	1.80113
$n_{632.8}$	632.8	1.80200
$n_D$	589.3	1.80593
$n_d$	587.6	1.80610
$n_e$	546.1	1.81081
$n_F$	486.1	1.82005
$n_{F'}$	480.0	1.82122
$n_g$	435.8	1.83137
$n_h$	404.7	1.84106
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.935028270
$B_2$	0.236629350
$B_3$	1.262913440
$C_1$	0.010400141
$C_2$	0.0447505292
$C_3$	87.43756900

### Constants of Formula for $dn/dT$

$D_0$	4.77E-06
$D_1$	1.14E-08
$D_2$	-2.68E-12
$E_0$	6.62E-07
$E_1$	8.84E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.234

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.9	6.2	7.6	2.5	3.8	5.0
+20/+40	5.0	6.5	8.1	3.4	4.9	6.4
+60/+80	5.2	6.9	8.6	4.0	5.6	7.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.400	0.100
2325	0.710	0.430
1970	0.940	0.850
1530	0.984	0.960
1060	0.998	0.994
700	0.998	0.995
660	0.998	0.995
620	0.997	0.993
580	0.996	0.991
546	0.995	0.988
500	0.990	0.975
460	0.980	0.950
436	0.967	0.920
420	0.954	0.890
405	0.930	0.840
400	0.920	0.810
390	0.880	0.730
380	0.820	0.610
370	0.710	0.420
365	0.620	0.300
350	0.220	0.020
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  42/34

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2476
$P_{C,s}$	0.5049
$P_{d,C}$	0.2972
$P_{e,d}$	0.2374
$P_{g,F}$	0.5703
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2446
$P'_{C,s}$	0.5452
$P'_{d,C'}$	0.2473
$P'_{e,d}$	0.2346
$P'_{g,F'}$	0.5053
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0149
$\Delta P_{C,s}$	0.0073
$\Delta P_{F,e}$	-0.0016
$\Delta P_{g,F}$	-0.0052
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	1
SR	51.3
AR	1
PR	2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.7
$T_g$ [°C]	614
$T_{10}^{13}$ [°C]	615
$T_{10}^{7.6}$ [°C]	699
$c_p$ [J/(g·K)]	0.550
$\lambda$ [W/(m·K)]	0.810
$\rho$ [g/cm <sup>3</sup> ]	4.26
$E$ [ $10^3$ N/mm <sup>2</sup> ]	114
$\mu$	0.290
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.92
$HK_{0.1/20}$	720
HG	2

## N-LASF44 804465.444

$n_d = 1.80420$

$v_d = 46.50$

$n_F - n_C = 0.017294$

$n_e = 1.80832$

$v_e = 46.25$

$n_F - n_C = 0.017476$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.76070
$n_{1970.1}$	1970.1	1.76801
$n_{1529.6}$	1529.6	1.77590
$n_{1060.0}$	1060.0	1.78455
$n_t$	1014.0	1.78560
$n_s$	852.1	1.79006
$n_r$	706.5	1.79609
$n_C$	656.3	1.79901
$n_{C'}$	643.8	1.79983
$n_{632.8}$	632.8	1.80060
$n_D$	589.3	1.80405
$n_d$	587.6	1.80420
$n_e$	546.1	1.80832
$n_F$	486.1	1.81630
$n_{F'}$	480.0	1.81731
$n_g$	435.8	1.82594
$n_h$	404.7	1.83405
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.788971050
$B_2$	0.386758670
$B_3$	1.305062430
$C_1$	0.008725063
$C_2$	0.0308085023
$C_3$	92.77438240

### Constants of Formula for $dn/dT$

$D_0$	3.32E-06
$D_1$	1.12E-08
$D_2$	-8.52E-12
$E_0$	5.88E-07
$E_1$	7.13E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.209

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.0	5.1	6.1	1.6	2.6	3.6
+20/+40	4.0	5.3	6.5	2.5	3.7	4.9
+60/+80	4.2	5.6	6.9	3.0	4.4	5.7

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.470	0.150
2325	0.740	0.470
1970	0.950	0.870
1530	0.990	0.975
1060	0.998	0.995
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.995
546	0.998	0.995
500	0.996	0.989
460	0.991	0.977
436	0.986	0.965
420	0.980	0.950
405	0.967	0.920
400	0.963	0.910
390	0.950	0.870
380	0.910	0.790
370	0.860	0.690
365	0.820	0.620
350	0.660	0.350
334	0.380	0.090
320	0.150	
310	0.070	
300	0.030	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  40/31

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2582
$P_{C,s}$	0.5171
$P_{d,C}$	0.3002
$P_{e,d}$	0.2380
$P_{g,F}$	0.5572
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2555
$P'_{C,s}$	0.5588
$P'_{d,C'}$	0.2501
$P'_{e,d}$	0.2355
$P'_{g,F'}$	0.4941
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0098
$\Delta P_{C,s}$	0.0058
$\Delta P_{F,e}$	-0.0021
$\Delta P_{g,F}$	-0.0084
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	1
SR	4
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$T_g$ [°C]	655
$T_{10}^{13}$ [°C]	659
$T_{10}^{7.6}$ [°C]	742
$c_p$ [J/(g·K)]	0.530
$\lambda$ [W/(m·K)]	0.820
$\rho$ [g/cm <sup>3</sup> ]	4.44
$E$ [ $10^3$ N/mm <sup>2</sup> ]	124
$\mu$	0.293
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.41
$HK_{0.1/20}$	770
HG	2

## N-LASF45 801350.363

$n_d = 1.80107$   
 $n_e = 1.80650$

$v_d = 34.97$   
 $v_e = 34.72$

$n_F - n_C = 0.022905$   
 $n_{F'} - n_{C'} = 0.023227$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.75487
$n_{1970.1}$	1970.1	1.76104
$n_{1529.6}$	1529.6	1.76809
$n_{1060.0}$	1060.0	1.77689
$n_t$	1014.0	1.77805
$n_s$	852.1	1.78325
$n_r$	706.5	1.79066
$n_C$	656.3	1.79436
$n_{C'}$	643.8	1.79541
$n_{632.8}$	632.8	1.79640
$n_D$	589.3	1.80087
$n_d$	587.6	1.80107
$n_e$	546.1	1.80650
$n_F$	486.1	1.81726
$n_{F'}$	480.0	1.81864
$n_g$	435.8	1.83068
$n_h$	404.7	1.84237
$n_i$	365.0	365.0
$n_{334.1}$	334.1	334.1
$n_{312.6}$	312.6	312.6
$n_{296.7}$	296.7	296.7
$n_{280.4}$	280.4	280.4
$n_{248.3}$	248.3	248.3

### Constants of Dispersion Formula

$B_1$	1.871401980
$B_2$	0.267777879
$B_3$	1.730300080
$C_1$	0.011217192
$C_2$	0.0505134972
$C_3$	147.10650500

### Constants of Formula for $dn/dT$

$D_0$	2.78E-06
$D_1$	8.73E-09
$D_2$	-2.65E-11
$E_0$	8.24E-07
$E_1$	1.15E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.255

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.8	5.4	7.3	1.4	3.0	4.7
+20/+40	3.8	5.7	7.9	2.3	4.1	6.2
+60/+80	3.8	5.9	8.3	2.6	4.7	7.0

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.810	0.580
2325	0.880	0.720
1970	0.972	0.930
1530	0.995	0.988
1060	0.999	0.997
700	0.996	0.990
660	0.995	0.987
620	0.994	0.984
580	0.994	0.986
546	0.993	0.982
500	0.983	0.958
460	0.965	0.920
436	0.950	0.870
420	0.920	0.820
405	0.880	0.720
400	0.860	0.680
390	0.790	0.550
380	0.670	0.370
370	0.480	0.150
365	0.340	0.060
350	0.010	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  44/35

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2268
$P_{C,s}$	0.4849
$P_{d,C}$	0.2930
$P_{e,d}$	0.2368
$P_{g,F}$	0.5859
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2237
$P'_{C,s}$	0.5235
$P'_{d,C'}$	0.2437
$P'_{e,d}$	0.2336
$P'_{g,F'}$	0.5186
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0009
$\Delta P_{C,s}$	0.0005
$\Delta P_{F,e}$	0.0001
$\Delta P_{g,F}$	0.0009
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	3.2
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.6
$T_g$ [°C]	647
$T_{10}^{13}$ [°C]	652
$T_{10}^{7.6}$ [°C]	773
$c_p$ [J/(g·K)]	0.660
$\lambda$ [W/(m·K)]	1.020
$\rho$ [g/cm <sup>3</sup> ]	3.63
$E$ [ $10^3$ N/mm <sup>2</sup> ]	116
$\mu$	0.281
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.01
$HK_{0.1/20}$	630
HG	3

## N-LASF45HT 801350.363

$n_d = 1.80107$   
 $n_e = 1.80650$

$v_d = 34.97$   
 $v_e = 34.72$

$n_F - n_C = 0.022905$   
 $n_{F'} - n_{C'} = 0.023227$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.75487
$n_{1970.1}$	1970.1	1.76104
$n_{1529.6}$	1529.6	1.76809
$n_{1060.0}$	1060.0	1.77689
$n_t$	1014.0	1.77805
$n_s$	852.1	1.78325
$n_r$	706.5	1.79066
$n_C$	656.3	1.79436
$n_{C'}$	643.8	1.79541
$n_{632.8}$	632.8	1.79640
$n_D$	589.3	1.80087
$n_d$	587.6	1.80107
$n_e$	546.1	1.80650
$n_F$	486.1	1.81726
$n_{F'}$	480.0	1.81864
$n_g$	435.8	1.83068
$n_h$	404.7	1.84237
$n_i$	365.0	365.0
$n_{334.1}$	334.1	334.1
$n_{312.6}$	312.6	312.6
$n_{296.7}$	296.7	296.7
$n_{280.4}$	280.4	280.4
$n_{248.3}$	248.3	248.3

### Constants of Dispersion Formula

$B_1$	1.871401980
$B_2$	0.267777879
$B_3$	1.730300080
$C_1$	0.011217192
$C_2$	0.0505134972
$C_3$	147.10650500

### Constants of Formula for $dn/dT$

$D_0$	2.78E-06
$D_1$	8.73E-09
$D_2$	-2.65E-11
$E_0$	8.24E-07
$E_1$	1.15E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.255

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.8	5.4	7.3	1.4	3.0	4.7
+20/+40	3.8	5.7	7.9	2.3	4.1	6.2
+60/+80	3.8	5.9	8.3	2.6	4.7	7.0

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.810	0.580
2325	0.880	0.720
1970	0.972	0.930
1530	0.995	0.988
1060	0.999	0.997
700	0.996	0.990
660	0.995	0.987
620	0.994	0.986
580	0.994	0.986
546	0.993	0.983
500	0.985	0.964
460	0.972	0.930
436	0.958	0.900
420	0.940	0.860
405	0.910	0.780
400	0.890	0.740
390	0.830	0.620
380	0.720	0.440
370	0.530	0.200
365	0.400	0.100
350	0.030	0.000
334	0.000	0.000
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  43/35

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2268
$P_{C,s}$	0.4849
$P_{d,C}$	0.2930
$P_{e,d}$	0.2368
$P_{g,F}$	0.5859
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2237
$P'_{C,s}$	0.5235
$P'_{d,C'}$	0.2437
$P'_{e,d}$	0.2336
$P'_{g,F'}$	0.5186
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0009
$\Delta P_{C,s}$	0.0005
$\Delta P_{F,e}$	0.0001
$\Delta P_{g,F}$	0.0009
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	3.2
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.6
$T_g$ [°C]	647
$T_{10}^{13}$ [°C]	652
$T_{10}^{7.6}$ [°C]	773
$c_p$ [J/(g·K)]	0.660
$\lambda$ [W/(m·K)]	1.020
$\rho$ [g/cm <sup>3</sup> ]	3.63
$E$ [ $10^3$ N/mm <sup>2</sup> ]	116
$\mu$	0.281
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.01
$HK_{0.1/20}$	630
HG	3



## N-LASF46A 904313.445

$n_d = 1.90366$   
 $n_e = 1.91048$

$v_d = 31.32$   
 $v_e = 31.09$

$n_F - n_C = 0.028853$   
 $n_{F'} - n_{C'} = 0.029287$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.84576
$n_{1970.1}$	1970.1	1.85364
$n_{1529.6}$	1529.6	1.86255
$n_{1060.0}$	1060.0	1.87353
$n_t$	1014.0	1.87498
$n_s$	852.1	1.88143
$n_r$	706.5	1.89064
$n_C$	656.3	1.89526
$n_{C'}$	643.8	1.89657
$n_{632.8}$	632.8	1.89781
$n_D$	589.3	1.90341
$n_d$	587.6	1.90366
$n_e$	546.1	1.91048
$n_F$	486.1	1.92411
$n_{F'}$	480.0	1.92586
$n_g$	435.8	1.94129
$n_h$	404.7	1.95645
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	2.167015660
$B_2$	0.319812761
$B_3$	1.660044860
$C_1$	0.012359552
$C_2$	0.0560610282
$C_3$	107.04771800

### Constants of Formula for $dn/dT$

$D_0$	3.53E-06
$D_1$	1.24E-08
$D_2$	-1.87E-11
$E_0$	8.39E-07
$E_1$	1.04E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.275

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.4	6.4	8.8	1.9	3.8	6.1
+20/+40	4.7	7.0	9.8	3.1	5.3	8.1
+60/+80	5.0	7.4	10.5	3.7	6.1	9.2

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.560	0.230
2325	0.790	0.560
1970	0.954	0.890
1530	0.991	0.977
1060	0.999	0.997
700	0.996	0.989
660	0.994	0.985
620	0.993	0.983
580	0.993	0.982
546	0.991	0.978
500	0.980	0.950
460	0.959	0.900
436	0.940	0.850
420	0.910	0.780
405	0.850	0.660
400	0.820	0.600
390	0.710	0.420
380	0.500	0.180
370	0.180	0.010
365	0.050	0.000
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  41/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2236
$P_{C,s}$	0.4793
$P_{d,C}$	0.2912
$P_{e,d}$	0.2364
$P_{g,F}$	0.5953
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2203
$P'_{C,s}$	0.5170
$P'_{d,C'}$	0.2420
$P'_{e,d}$	0.2329
$P'_{g,F'}$	0.5268
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0094
$\Delta P_{C,s}$	0.0034
$\Delta P_{F,e}$	0.0005
$\Delta P_{g,F}$	0.0042
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	3
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.2
$T_g$ [°C]	638
$T_{10}^{13}$ [°C]	639
$T_{10}^{7.6}$ [°C]	733
$c_p$ [J/(g·K)]	0.540
$\lambda$ [W/(m·K)]	0.910
$\rho$ [g/cm <sup>3</sup> ]	4.45
$E$ [ $10^3$ N/mm <sup>2</sup> ]	124
$\mu$	0.298
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.64
$HK_{0.1/20}$	666
HG	1
Abrasion Aa	88

## N-LASF46B 904313.451

$n_d = 1.90366$   
 $n_e = 1.91048$

$v_d = 31.32$   
 $v_e = 31.09$

$n_F - n_C = 0.028852$   
 $n_{F'} - n_{C'} = 0.029289$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.84657
$n_{1970.1}$	1970.1	1.85418
$n_{1529.6}$	1529.6	1.86283
$n_{1060.0}$	1060.0	1.87362
$n_t$	1014.0	1.87505
$n_s$	852.1	1.88146
$n_r$	706.5	1.89065
$n_C$	656.3	1.89526
$n_{C'}$	643.8	1.89657
$n_{632.8}$	632.8	1.89781
$n_D$	589.3	1.90341
$n_d$	587.6	1.90366
$n_e$	546.1	1.91048
$n_F$	486.1	1.92411
$n_{F'}$	480.0	1.92586
$n_g$	435.8	1.94130
$n_h$	404.7	1.95647
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	2.179889220
$B_2$	0.306495184
$B_3$	1.568824370
$C_1$	0.012580538
$C_2$	0.0567191367
$C_3$	105.31653800

### Constants of Formula for $dn/dT$

$D_0$	5.98E-06
$D_1$	1.30E-08
$D_2$	-3.50E-12
$E_0$	9.13E-07
$E_1$	1.24E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.267

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.1	8.2	10.7	3.6	5.6	8.1
+20/+40	6.4	8.9	11.8	4.8	7.2	10.1
+60/+80	6.8	9.5	12.7	5.5	8.2	11.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.560	0.230
2325	0.790	0.550
1970	0.954	0.890
1530	0.991	0.977
1060	0.998	0.996
700	0.996	0.989
660	0.993	0.983
620	0.992	0.980
580	0.991	0.978
546	0.989	0.972
500	0.977	0.940
460	0.954	0.890
436	0.930	0.840
420	0.900	0.770
405	0.850	0.660
400	0.820	0.600
390	0.710	0.420
380	0.500	0.180
370	0.180	0.010
365	0.050	0.000
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  41/37

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2222
$P_{C,s}$	0.4783
$P_{d,C}$	0.2911
$P_{e,d}$	0.2364
$P_{g,F}$	0.5956
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2189
$P'_{C,s}$	0.5160
$P'_{d,C'}$	0.2419
$P'_{e,d}$	0.2329
$P'_{g,F'}$	0.5270
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0069
$\Delta P_{C,s}$	0.0024
$\Delta P_{F,e}$	0.0006
$\Delta P_{g,F}$	0.0045
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	3.3
AR	1
PR	1
SR-J	2
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.1
$T_g$ [°C]	611
$T_{10}^{13}$ [°C]	613
$T_{10}^{7.6}$ [°C]	703
$c_p$ [J/(g·K)]	0.550
$\lambda$ [W/(m·K)]	0.880
AT [°C]	649
$\rho$ [g/cm <sup>3</sup> ]	4.51
E [10 <sup>3</sup> N/mm <sup>2</sup> ]	121
$\mu$	0.303
K [10 <sup>-6</sup> mm <sup>2</sup> /N]	1.87
HK <sub>0.1/20</sub>	712
Abrasion Aa	55

## N-LASF55 954306.486

$n_d = 1.95380$

$v_d = 30.56$

$n_F - n_C = 0.031211$

$n_e = 1.96118$

$v_e = 30.33$

$n_F - n_C = 0.031688$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.89507
$n_{1970.1}$	1970.1	1.90226
$n_{1529.6}$	1529.6	1.91065
$n_{1060.0}$	1060.0	1.92162
$n_t$	1014.0	1.92312
$n_s$	852.1	1.92991
$n_r$	706.5	1.93976
$n_C$	656.3	1.94473
$n_{C'}$	643.8	1.94614
$n_{632.8}$	632.8	1.94748
$n_D$	589.3	1.95353
$n_d$	587.6	1.95380
$n_e$	546.1	1.96118
$n_F$	486.1	1.97594
$n_{F'}$	480.0	1.97783
$n_g$	435.8	1.99454
$n_h$	404.7	2.01096
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	2.308612280
$B_2$	0.354736638
$B_3$	1.922271250
$C_1$	0.013044700
$C_2$	0.0557524221
$C_3$	133.19686900

### Constants of Formula for $dn/dT$

$D_0$	2.25E-06
$D_1$	1.09E-08
$D_2$	-1.64E-11
$E_0$	9.64E-07
$E_1$	1.25E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.262

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.9	6.1	8.7	1.3	3.4	5.9
+20/+40	4.0	6.6	9.7	2.4	4.9	7.9
+60/+80	4.3	7.1	10.5	3.0	5.8	9.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.710	0.420
2325	0.850	0.660
1970	0.967	0.920
1530	0.995	0.987
1060	0.999	0.997
700	0.995	0.988
660	0.993	0.983
620	0.991	0.977
580	0.987	0.969
546	0.981	0.954
500	0.959	0.900
460	0.920	0.810
436	0.870	0.710
420	0.810	0.590
405	0.700	0.410
400	0.650	0.340
390	0.500	0.180
380	0.310	0.050
370	0.100	0.000
365	0.030	0.000
350	0.000	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  44/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2175
$P_{C,s}$	0.4748
$P_{d,C}$	0.2907
$P_{e,d}$	0.2364
$P_{g,F}$	0.5961
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2142
$P'_{C,s}$	0.5123
$P'_{d,C'}$	0.2416
$P'_{e,d}$	0.2329
$P'_{g,F'}$	0.5274
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0023
$\Delta P_{C,s}$	0.0007
$\Delta P_{F,e}$	0.0006
$\Delta P_{g,F}$	0.0037
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	2.3
AR	1
PR	1
SR-J	1
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.7
$T_g$ [°C]	718
$T_{10}^{13}$ [°C]	722
$T_{10}^{7.6}$ [°C]	796
$c_p$ [J/(g·K)]	0.500
$\lambda$ [W/(m·K)]	0.900
$\rho$ [g/cm <sup>3</sup> ]	4.86
$E$ [ $10^3$ N/mm <sup>2</sup> ]	126
$\mu$	0.300
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.16
$HK_{0.1/20}$	710
HG	2

## P-LASF47 806409.454

$n_d = 1.80610$

$v_d = 40.90$

$n_F - n_C = 0.019709$

$n_e = 1.81078$

$v_e = 40.66$

$n_{F'} - n_{C'} = 0.019941$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.76040
$n_{1970.1}$	1970.1	1.76755
$n_{1529.6}$	1529.6	1.77538
$n_{1060.0}$	1060.0	1.78432
$n_t$	1014.0	1.78544
$n_s$	852.1	1.79028
$n_r$	706.5	1.79696
$n_C$	656.3	1.80023
$n_{C'}$	643.8	1.80116
$n_{632.8}$	632.8	1.80203
$n_D$	589.3	1.80593
$n_d$	587.6	1.80610
$n_e$	546.1	1.81078
$n_F$	486.1	1.81994
$n_{F'}$	480.0	1.82110
$n_g$	435.8	1.83112
$n_h$	404.7	1.84064
$n_i$	365.0	1.85739
$n_{334.1}$	334.1	1.87632
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.855431010
$B_2$	0.315854649
$B_3$	1.285618390
$C_1$	0.010032820
$C_2$	0.0387095168
$C_3$	94.54215070

### Constants of Formula for $dn/dT$

$D_0$	7.87E-06
$D_1$	1.09E-08
$D_2$	-1.56E-11
$E_0$	7.58E-07
$E_1$	8.92E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.218

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.8	8.3	9.8	4.5	5.9	7.3
+20/+40	6.9	8.6	10.3	5.4	7.0	8.7
+60/+80	7.1	8.9	10.8	5.9	7.7	9.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.530	0.200
2325	0.780	0.530
1970	0.950	0.880
1530	0.992	0.981
1060	0.999	0.998
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.994
546	0.998	0.994
500	0.995	0.988
460	0.990	0.975
436	0.985	0.963
420	0.980	0.950
405	0.971	0.930
400	0.967	0.920
390	0.954	0.890
380	0.930	0.830
370	0.880	0.720
365	0.840	0.650
350	0.660	0.350
334	0.250	0.030
320	0.010	
310	0.000	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  39/33

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2459
$P_{C,s}$	0.5049
$P_{d,C}$	0.2976
$P_{e,d}$	0.2376
$P_{g,F}$	0.5671
$P_{i,h}$	0.8502

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2430
$P'_{C,s}$	0.5453
$P'_{d,C'}$	0.2478
$P'_{e,d}$	0.2348
$P'_{g,F'}$	0.5025
$P'_{i,h}$	0.8403

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0117
$\Delta P_{C,s}$	0.0066
$\Delta P_{F,e}$	-0.0021
$\Delta P_{g,F}$	-0.0079
$\Delta P_{i,g}$	-0.0482

### Chemical Properties

CR	1
FR	1
SR	51.4
AR	1
PR	2.2
SR-J	3
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$T_g$ [°C]	530
$T_{10}^{13}$ [°C]	532
$T_{10}^{7.6}$ [°C]	627
$c_p$ [J/(g·K)]	0.550
$\lambda$ [W/(m·K)]	0.850
AT [°C]	580
$\rho$ [g/cm <sup>3</sup> ]	4.54
$E$ [ $10^3$ N/mm <sup>2</sup> ]	120
$\mu$	0.298
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.39
HK <sub>0.1/20</sub>	620
HG	2
Abrasion Aa	70

## P-LASF50 809405.454

$n_d = 1.80860$

$v_d = 40.46$

$n_F - n_C = 0.019985$

$n_e = 1.81335$

$v_e = 40.22$

$n_F - n_C = 0.020223$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.76261
$n_{1970.1}$	1970.1	1.76975
$n_{1529.6}$	1529.6	1.77759
$n_{1060.0}$	1060.0	1.78657
$n_t$	1014.0	1.78770
$n_s$	852.1	1.79259
$n_r$	706.5	1.79934
$n_C$	656.3	1.80266
$n_{C'}$	643.8	1.80359
$n_{632.8}$	632.8	1.80447
$n_D$	589.3	1.80842
$n_d$	587.6	1.80860
$n_e$	546.1	1.81335
$n_F$	486.1	1.82264
$n_{F'}$	480.0	1.82382
$n_g$	435.8	1.83399
$n_h$	404.7	1.84367
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.849105530
$B_2$	0.329828674
$B_3$	1.304009010
$C_1$	0.009992348
$C_2$	0.0387437988
$C_3$	95.89676810

### Constants of Formula for $dn/dT$

$D_0$	8.04E-06
$D_1$	1.20E-08
$D_2$	-2.19E-11
$E_0$	8.20E-07
$E_1$	9.08E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.209

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.9	8.5	10.0	4.5	6.0	7.5
+20/+40	7.1	8.9	10.6	5.5	7.3	9.0
+60/+80	7.3	9.2	11.1	6.1	8.0	9.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.530	0.200
2325	0.780	0.530
1970	0.950	0.880
1530	0.992	0.981
1060	0.999	0.998
700	0.998	0.995
660	0.997	0.993
620	0.997	0.992
580	0.997	0.992
546	0.997	0.992
500	0.995	0.987
460	0.990	0.975
436	0.985	0.963
420	0.980	0.950
405	0.971	0.930
400	0.967	0.920
390	0.954	0.890
380	0.930	0.830
370	0.880	0.720
365	0.840	0.650
350	0.660	0.350
334	0.290	0.030
320	0.030	
310	0.000	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  39/32

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2448
$P_{C,s}$	0.5037
$P_{d,C}$	0.2973
$P_{e,d}$	0.2376
$P_{g,F}$	0.5680
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2419
$P'_{C,s}$	0.5441
$P'_{d,C'}$	0.2475
$P'_{e,d}$	0.2348
$P'_{g,F'}$	0.5032
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0116
$\Delta P_{C,s}$	0.0065
$\Delta P_{F,e}$	-0.0020
$\Delta P_{g,F}$	-0.0078
$\Delta P_{i,g}$	

### Chemical Properties

CR	
FR	
SR	
AR	
PR	
SR-J	3
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.9
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$T_g$ [°C]	527
$T_{10}^{13}$ [°C]	526
$T_{10}^{7.6}$ [°C]	660
$c_p$ [J/(g·K)]	0.560
$\lambda$ [W/(m·K)]	0.950
AT [°C]	571
$\rho$ [g/cm <sup>3</sup> ]	4.54
$E$ [ $10^3$ N/mm <sup>2</sup> ]	119
$\mu$	0.298
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.41
HK <sub>0.1/20</sub>	655
Abrasion Aa	62

## P-LASF51 810409.458

$n_d = 1.81000$

$v_d = 40.93$

$n_F - n_C = 0.019792$

$n_e = 1.81470$

$v_e = 40.68$

$n_F - n_C = 0.020025$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.76437
$n_{1970.1}$	1970.1	1.77145
$n_{1529.6}$	1529.6	1.77923
$n_{1060.0}$	1060.0	1.78815
$n_t$	1014.0	1.78927
$n_s$	852.1	1.79413
$n_r$	706.5	1.80082
$n_C$	656.3	1.80411
$n_{C'}$	643.8	1.80504
$n_{632.8}$	632.8	1.80591
$n_D$	589.3	1.80983
$n_d$	587.6	1.81000
$n_e$	546.1	1.81470
$n_F$	486.1	1.82390
$n_{F'}$	480.0	1.82506
$n_g$	435.8	1.83512
$n_h$	404.7	1.84467
$n_i$	365.0	1.86148
$n_{334.1}$	334.1	1.88043
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.845688060
$B_2$	0.339001600
$B_3$	1.324189210
$C_1$	0.009884956
$C_2$	0.0378097402
$C_3$	97.84154300

### Constants of Formula for $dn/dT$

$D_0$	7.79E-06
$D_1$	1.10E-08
$D_2$	-2.03E-11
$E_0$	7.86E-07
$E_1$	8.78E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.215

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.8	8.3	9.9	4.4	5.9	7.3
+20/+40	6.9	8.7	10.4	5.4	7.1	8.8
+60/+80	7.1	8.9	10.8	5.9	7.7	9.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.530	0.200
2325	0.780	0.530
1970	0.950	0.880
1530	0.992	0.981
1060	0.999	0.998
700	0.998	0.995
660	0.997	0.993
620	0.997	0.992
580	0.997	0.992
546	0.997	0.992
500	0.995	0.987
460	0.990	0.975
436	0.985	0.963
420	0.980	0.950
405	0.971	0.930
400	0.967	0.920
390	0.954	0.890
380	0.930	0.830
370	0.880	0.720
365	0.840	0.650
350	0.660	0.350
334	0.250	0.030
320	0.010	
310	0.000	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  39/33

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2453
$P_{C,s}$	0.5045
$P_{d,C}$	0.2976
$P_{e,d}$	0.2376
$P_{g,F}$	0.5670
$P_{i,h}$	0.8491

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2425
$P'_{C,s}$	0.5450
$P'_{d,C'}$	0.2477
$P'_{e,d}$	0.2348
$P'_{g,F'}$	0.5024
$P'_{i,h}$	0.8392

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0107
$\Delta P_{C,s}$	0.0062
$\Delta P_{F,e}$	-0.0021
$\Delta P_{g,F}$	-0.0080
$\Delta P_{i,g}$	-0.0494

### Chemical Properties

CR	1
FR	1
SR	51.3
AR	1
PR	2.2
SR-J	3
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$T_g$ [°C]	526
$T_{10}^{13}$ [°C]	534
$T_{10}^{7.6}$ [°C]	629
$c_p$ [J/(g·K)]	0.560
$\lambda$ [W/(m·K)]	0.870
AT [°C]	570
$\rho$ [g/cm <sup>3</sup> ]	4.58
E [ $10^3$ N/mm <sup>2</sup> ]	119
$\mu$	0.299
K [ $10^{-6}$ mm <sup>2</sup> /N]	2.32
HK <sub>0.1/20</sub>	722
Abrasion Aa	66

## N-SF1 717296.303

$n_d = 1.71736$   
 $n_e = 1.72308$

$v_d = 29.62$   
 $v_e = 29.39$

$n_F - n_C = 0.024219$   
 $n_F - n_C = 0.024606$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.67021
$n_{1970.1}$	1970.1	1.67641
$n_{1529.6}$	1529.6	1.68350
$n_{1060.0}$	1060.0	1.69240
$n_t$	1014.0	1.69358
$n_s$	852.1	1.69889
$n_r$	706.5	1.70651
$n_C$	656.3	1.71035
$n_{C'}$	643.8	1.71144
$n_{632.8}$	632.8	1.71247
$n_D$	589.3	1.71715
$n_d$	587.6	1.71736
$n_e$	546.1	1.72308
$n_F$	486.1	1.73457
$n_{F'}$	480.0	1.73605
$n_g$	435.8	1.74919
$n_h$	404.7	1.76224
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.608651580
$B_2$	0.237725916
$B_3$	1.515306530
$C_1$	0.011965488
$C_2$	0.0590589722
$C_3$	135.52167600

### Constants of Formula for $dn/dT$

$D_0$	-3.72E-06
$D_1$	8.05E-09
$D_2$	-1.71E-11
$E_0$	8.98E-07
$E_1$	1.34E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.276

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	0.1	1.7	3.6	-2.2	-0.7	1.2
+20/+40	0.0	1.8	4.2	-1.5	0.3	2.7
+60/+80	0.0	2.1	4.8	-1.1	0.9	3.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.730	0.460
2325	0.800	0.580
1970	0.940	0.850
1530	0.989	0.973
1060	0.998	0.995
700	0.996	0.990
660	0.994	0.986
620	0.995	0.987
580	0.996	0.990
546	0.994	0.986
500	0.987	0.968
460	0.976	0.940
436	0.963	0.910
420	0.950	0.870
405	0.900	0.760
400	0.870	0.700
390	0.770	0.520
380	0.570	0.250
370	0.250	0.030
365	0.100	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  41/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2190
$P_{C,s}$	0.4733
$P_{d,C}$	0.2895
$P_{e,d}$	0.2360
$P_{g,F}$	0.6037
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2156
$P'_{C,s}$	0.5103
$P'_{d,C'}$	0.2405
$P'_{e,d}$	0.2323
$P'_{g,F'}$	0.5340
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0068
$\Delta P_{C,s}$	0.0013
$\Delta P_{F,e}$	0.0016
$\Delta P_{g,F}$	0.0097
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.5
$T_g$ [°C]	553
$T_{10}^{13}$ [°C]	554
$T_{10}^{7.6}$ [°C]	660
$c_p$ [J/(g·K)]	0.750
$\lambda$ [W/(m·K)]	1.000
$\rho$ [g/cm <sup>3</sup> ]	3.03
$E$ [ $10^3$ N/mm <sup>2</sup> ]	90
$\mu$	0.250
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.72
$HK_{0.1/20}$	540
HG	5

## N-SF2 648338.272

$n_d = 1.64769$

$v_d = 33.82$

$n_F - n_C = 0.019151$

$n_e = 1.65222$

$v_e = 33.56$

$n_F - n_C = 0.019435$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.60661
$n_{1970.1}$	1970.1	1.61268
$n_{1529.6}$	1529.6	1.61944
$n_{1060.0}$	1060.0	1.62738
$n_t$	1014.0	1.62839
$n_s$	852.1	1.63282
$n_r$	706.5	1.63902
$n_C$	656.3	1.64210
$n_{C'}$	643.8	1.64298
$n_{632.8}$	632.8	1.64380
$n_D$	589.3	1.64752
$n_d$	587.6	1.64769
$n_e$	546.1	1.65222
$n_F$	486.1	1.66125
$n_{F'}$	480.0	1.66241
$n_g$	435.8	1.67265
$n_h$	404.7	1.68273
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.473431270
$B_2$	0.163681849
$B_3$	1.369208990
$C_1$	0.010901910
$C_2$	0.0585683687
$C_3$	127.40493300

### Constants of Formula for $dn/dT$

$D_0$	3.10E-06
$D_1$	1.75E-08
$D_2$	6.62E-11
$E_0$	7.51E-07
$E_1$	8.99E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.277

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.4	4.8	6.4	1.3	2.5	4.1
+20/+40	3.5	5.1	7.0	2.1	3.6	5.5
+60/+80	4.2	5.9	8.0	3.1	4.8	6.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.850	0.670
2325	0.900	0.760
1970	0.971	0.930
1530	0.994	0.984
1060	0.999	0.997
700	0.995	0.987
660	0.994	0.984
620	0.994	0.984
580	0.995	0.987
546	0.994	0.986
500	0.990	0.975
460	0.984	0.961
436	0.979	0.950
420	0.970	0.930
405	0.940	0.870
400	0.930	0.830
390	0.860	0.680
380	0.690	0.400
370	0.330	0.060
365	0.130	0.010
350	0.000	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  40/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2311
$P_{C,s}$	0.4848
$P_{d,C}$	0.2918
$P_{e,d}$	0.2364
$P_{g,F}$	0.5950
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2277
$P'_{C,s}$	0.5228
$P'_{d,C'}$	0.2425
$P'_{e,d}$	0.2329
$P'_{g,F'}$	0.5267
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0106
$\Delta P_{C,s}$	0.0031
$\Delta P_{F,e}$	0.0012
$\Delta P_{g,F}$	0.0081
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1.2
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.7
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.8
$T_g$ [°C]	608
$T_{10}^{13}$ [°C]	607
$T_{10}^{7.6}$ [°C]	731
$c_p$ [J/(g·K)]	0.790
$\lambda$ [W/(m·K)]	1.140
$\rho$ [g/cm <sup>3</sup> ]	2.72
$E$ [ $10^3$ N/mm <sup>2</sup> ]	86
$\mu$	0.231
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.06
$HK_{0.1/20}$	539



## N-SF4 755274.315

$n_d = 1.75513$

$v_d = 27.38$

$n_F - n_C = 0.027583$

$n_e = 1.76164$

$v_e = 27.16$

$n_F - n_C = 0.028044$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.70434
$n_{1970.1}$	1970.1	1.71052
$n_{1529.6}$	1529.6	1.71773
$n_{1060.0}$	1060.0	1.72717
$n_t$	1014.0	1.72846
$n_s$	852.1	1.73432
$n_r$	706.5	1.74286
$n_C$	656.3	1.74719
$n_{C'}$	643.8	1.74842
$n_{632.8}$	632.8	1.74959
$n_D$	589.3	1.75489
$n_d$	587.6	1.75513
$n_e$	546.1	1.76164
$n_F$	486.1	1.77477
$n_{F'}$	480.0	1.77647
$n_g$	435.8	1.79158
$n_h$	404.7	1.80668
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.677802820
$B_2$	0.282849893
$B_3$	1.635392760
$C_1$	0.012679345
$C_2$	0.0602038419
$C_3$	145.76049600

### Constants of Formula for $dn/dT$

$D_0$	-4.88E-06
$D_1$	6.57E-09
$D_2$	-2.72E-11
$E_0$	9.67E-07
$E_1$	1.48E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.282

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.5	1.2	3.5	-2.9	-1.2	1.0
+20/+40	-0.7	1.4	4.2	-2.2	-0.1	2.6
+60/+80	-0.8	1.6	4.7	-1.9	0.4	3.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.780	0.530
2325	0.820	0.600
1970	0.940	0.860
1530	0.992	0.980
1060	0.999	0.999
700	0.994	0.984
660	0.991	0.978
620	0.992	0.979
580	0.993	0.982
546	0.991	0.977
500	0.979	0.950
460	0.961	0.910
436	0.940	0.860
420	0.920	0.800
405	0.860	0.690
400	0.830	0.630
390	0.740	0.470
380	0.560	0.240
370	0.250	0.030
365	0.100	0.000
350	0.000	0.000
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  43/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2123
$P_{C,s}$	0.4666
$P_{d,C}$	0.2880
$P_{e,d}$	0.2358
$P_{g,F}$	0.6096
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2088
$P'_{C,s}$	0.5030
$P'_{d,C'}$	0.2392
$P'_{e,d}$	0.2319
$P'_{g,F'}$	0.5390
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0040
$\Delta P_{C,s}$	-0.0002
$\Delta P_{F,e}$	0.0022
$\Delta P_{g,F}$	0.0118
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1.3
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.9
$T_g$ [°C]	570
$T_{10}^{13}$ [°C]	559
$T_{10}^{7.6}$ [°C]	661
$c_p$ [J/(g·K)]	0.760
$\lambda$ [W/(m·K)]	0.950
$\rho$ [g/cm <sup>3</sup> ]	3.15
$E$ [ $10^3$ N/mm <sup>2</sup> ]	90
$\mu$	0.256
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.76
$HK_{0.1/20}$	520
HG	6

## N-SF5 673323.286

$n_d = 1.67271$   
 $n_e = 1.67763$

$v_d = 32.25$   
 $v_e = 32.00$

$n_F - n_C = 0.020858$   
 $n_{F'} - n_{C'} = 0.021177$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.62935
$n_{1970.1}$	1970.1	1.63554
$n_{1529.6}$	1529.6	1.64249
$n_{1060.0}$	1060.0	1.65080
$n_t$	1014.0	1.65188
$n_s$	852.1	1.65661
$n_r$	706.5	1.66330
$n_C$	656.3	1.66664
$n_{C'}$	643.8	1.66759
$n_{632.8}$	632.8	1.66848
$n_D$	589.3	1.67253
$n_d$	587.6	1.67271
$n_e$	546.1	1.67763
$n_F$	486.1	1.68750
$n_{F'}$	480.0	1.68876
$n_g$	435.8	1.69998
$n_h$	404.7	1.71106
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.524818890
$B_2$	0.187085527
$B_3$	1.427290150
$C_1$	0.011254756
$C_2$	0.0588995392
$C_3$	129.14167500

### Constants of Formula for $dn/dT$

$D_0$	-2.51E-07
$D_1$	1.07E-08
$D_2$	-2.40E-11
$E_0$	7.85E-07
$E_1$	1.15E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.278

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.8	3.1	4.8	-0.5	0.8	2.5
+20/+40	1.8	3.4	5.5	0.4	2.0	4.0
+60/+80	1.9	3.7	6.0	0.8	2.5	4.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.760	0.500
2325	0.830	0.630
1970	0.950	0.880
1530	0.990	0.975
1060	0.998	0.994
700	0.996	0.989
660	0.995	0.987
620	0.995	0.988
580	0.996	0.991
546	0.995	0.988
500	0.990	0.976
460	0.982	0.956
436	0.973	0.940
420	0.963	0.910
405	0.930	0.830
400	0.910	0.780
390	0.830	0.620
380	0.640	0.330
370	0.280	0.040
365	0.120	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  40/36

### Remarks

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2270
$P_{C,s}$	0.4807
$P_{d,C}$	0.2910
$P_{e,d}$	0.2362
$P_{g,F}$	0.5984
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2236
$P'_{C,s}$	0.5184
$P'_{d,C'}$	0.2418
$P'_{e,d}$	0.2327
$P'_{g,F'}$	0.5295
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0097
$\Delta P_{C,s}$	0.0027
$\Delta P_{F,e}$	0.0014
$\Delta P_{g,F}$	0.0088
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.9
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.2
$T_g$ [°C]	578
$T_{10}^{13}$ [°C]	576
$T_{10}^{7.6}$ [°C]	693
$c_p$ [J/(g·K)]	0.770
$\lambda$ [W/(m·K)]	1.000
$\rho$ [g/cm <sup>3</sup> ]	2.86
$E$ [ $10^3$ N/mm <sup>2</sup> ]	87
$\mu$	0.237
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.99
$HK_{0.1/20}$	620
HG	3

## N-SF6 805254.337

$n_d = 1.80518$

$v_d = 25.36$

$n_F - n_C = 0.031750$

$n_e = 1.81266$

$v_e = 25.16$

$n_F - n_C = 0.032304$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.74895
$n_{1970.1}$	1970.1	1.75541
$n_{1529.6}$	1529.6	1.76307
$n_{1060.0}$	1060.0	1.77341
$n_t$	1014.0	1.77486
$n_s$	852.1	1.78144
$n_r$	706.5	1.79114
$n_C$	656.3	1.79608
$n_{C'}$	643.8	1.79749
$n_{632.8}$	632.8	1.79883
$n_D$	589.3	1.80491
$n_d$	587.6	1.80518
$n_e$	546.1	1.81266
$n_F$	486.1	1.82783
$n_{F'}$	480.0	1.82980
$n_g$	435.8	1.84738
$n_h$	404.7	1.86506
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.779317630
$B_2$	0.338149866
$B_3$	2.087344740
$C_1$	0.013371418
$C_2$	0.0617533621
$C_3$	174.01759000

### Constants of Formula for $dn/dT$

$D_0$	-4.93E-06
$D_1$	7.02E-09
$D_2$	-2.40E-11
$E_0$	9.84E-07
$E_1$	1.54E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.290

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.7	1.2	3.9	-3.0	-1.2	1.3
+20/+40	-0.8	1.5	4.8	-2.3	0.0	3.1
+60/+80	-0.8	1.8	5.4	-2.0	0.6	4.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.780	0.530
2325	0.810	0.590
1970	0.940	0.860
1530	0.991	0.978
1060	0.998	0.996
700	0.993	0.983
660	0.990	0.976
620	0.991	0.978
580	0.992	0.980
546	0.989	0.972
500	0.977	0.940
460	0.961	0.910
436	0.950	0.870
420	0.920	0.810
405	0.860	0.680
400	0.820	0.610
390	0.700	0.410
380	0.480	0.160
370	0.160	0.010
365	0.000	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  45/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2074
$P_{C,s}$	0.4610
$P_{d,C}$	0.2867
$P_{e,d}$	0.2356
$P_{g,F}$	0.6158
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2039
$P'_{C,s}$	0.4969
$P'_{d,C'}$	0.2380
$P'_{e,d}$	0.2315
$P'_{g,F'}$	0.5443
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0031
$\Delta P_{C,s}$	-0.0010
$\Delta P_{F,e}$	0.0027
$\Delta P_{g,F}$	0.0146
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	2
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.3
$T_g$ [°C]	589
$T_{10}^{13}$ [°C]	593
$T_{10}^{7.6}$ [°C]	669
$c_p$ [J/(g·K)]	0.690
$\lambda$ [W/(m·K)]	0.960
$\rho$ [g/cm <sup>3</sup> ]	3.37
$E$ [ $10^3$ N/mm <sup>2</sup> ]	93
$\mu$	0.262
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.82
$HK_{0.1/20}$	550
HG	4

## N-SF6HT 805254.337

$n_d = 1.80518$

$v_d = 25.36$

$n_F - n_C = 0.031750$

$n_e = 1.81266$

$v_e = 25.16$

$n_F - n_C = 0.032304$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.74895
$n_{1970.1}$	1970.1	1.75541
$n_{1529.6}$	1529.6	1.76307
$n_{1060.0}$	1060.0	1.77341
$n_t$	1014.0	1.77486
$n_s$	852.1	1.78144
$n_r$	706.5	1.79114
$n_C$	656.3	1.79608
$n_{C'}$	643.8	1.79749
$n_{632.8}$	632.8	1.79883
$n_D$	589.3	1.80491
$n_d$	587.6	1.80518
$n_e$	546.1	1.81266
$n_F$	486.1	1.82783
$n_{F'}$	480.0	1.82980
$n_g$	435.8	1.84738
$n_h$	404.7	1.86506
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.779317630
$B_2$	0.338149866
$B_3$	2.087344740
$C_1$	0.013371418
$C_2$	0.0617533621
$C_3$	174.01759000

### Constants of Formula for $dn/dT$

$D_0$	-4.93E-06
$D_1$	7.02E-09
$D_2$	-2.40E-11
$E_0$	9.84E-07
$E_1$	1.54E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.290

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.7	1.2	3.9	-3.0	-1.2	1.3
+20/+40	-0.8	1.5	4.8	-2.3	0.0	3.1
+60/+80	-0.8	1.8	5.4	-2.0	0.6	4.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.790	0.560
2325	0.830	0.620
1970	0.950	0.870
1530	0.992	0.980
1060	0.999	0.997
700	0.994	0.984
660	0.991	0.977
620	0.992	0.979
580	0.992	0.981
546	0.990	0.975
500	0.980	0.950
460	0.966	0.920
436	0.954	0.890
420	0.940	0.850
405	0.900	0.770
400	0.880	0.720
390	0.790	0.560
380	0.590	0.270
370	0.210	0.020
365	0.000	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  44/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2074
$P_{C,s}$	0.4610
$P_{d,C}$	0.2867
$P_{e,d}$	0.2356
$P_{g,F}$	0.6158
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2039
$P'_{C,s}$	0.4969
$P'_{d,C'}$	0.2380
$P'_{e,d}$	0.2315
$P'_{g,F'}$	0.5443
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0031
$\Delta P_{C,s}$	-0.0010
$\Delta P_{F,e}$	0.0027
$\Delta P_{g,F}$	0.0146
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	2
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.3
$T_g$ [°C]	589
$T_{10}^{13}$ [°C]	593
$T_{10}^{7.6}$ [°C]	669
$c_p$ [J/(g·K)]	0.690
$\lambda$ [W/(m·K)]	0.960
$\rho$ [g/cm <sup>3</sup> ]	3.37
$E$ [ $10^3$ N/mm <sup>2</sup> ]	93
$\mu$	0.262
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.82
$HK_{0.1/20}$	550
HG	4

## N-SF6HTultra 805254.337

$n_d = 1.80518$

$v_d = 25.36$

$n_F - n_C = 0.031750$

$n_e = 1.81266$

$v_e = 25.16$

$n_F - n_C = 0.032304$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.74895
$n_{1970.1}$	1970.1	1.75541
$n_{1529.6}$	1529.6	1.76307
$n_{1060.0}$	1060.0	1.77341
$n_t$	1014.0	1.77486
$n_s$	852.1	1.78144
$n_r$	706.5	1.79114
$n_C$	656.3	1.79608
$n_{C'}$	643.8	1.79749
$n_{632.8}$	632.8	1.79883
$n_D$	589.3	1.80491
$n_d$	587.6	1.80518
$n_e$	546.1	1.81266
$n_F$	486.1	1.82783
$n_{F'}$	480.0	1.82980
$n_g$	435.8	1.84738
$n_h$	404.7	1.86506
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.779317630
$B_2$	0.338149866
$B_3$	2.087344740
$C_1$	0.013371418
$C_2$	0.0617533621
$C_3$	174.01759000

### Constants of Formula for $dn/dT$

$D_0$	-4.93E-06
$D_1$	7.02E-09
$D_2$	-2.40E-11
$E_0$	9.84E-07
$E_1$	1.54E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.290

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.7	1.2	3.9	-3.0	-1.2	1.3
+20/+40	-0.8	1.5	4.8	-2.3	0.0	3.1
+60/+80	-0.8	1.8	5.4	-2.0	0.6	4.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.800	0.570
2325	0.830	0.620
1970	0.950	0.880
1530	0.992	0.981
1060	0.999	0.999
700	0.994	0.984
660	0.991	0.978
620	0.992	0.980
580	0.994	0.984
546	0.992	0.981
500	0.984	0.960
460	0.972	0.930
436	0.961	0.910
420	0.950	0.870
405	0.910	0.790
400	0.890	0.740
390	0.800	0.580
380	0.600	0.280
370	0.220	0.020
365	0.000	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  43/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2074
$P_{C,s}$	0.4610
$P_{d,C}$	0.2867
$P_{e,d}$	0.2356
$P_{g,F}$	0.6158
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2039
$P'_{C,s}$	0.4969
$P'_{d,C'}$	0.2380
$P'_{e,d}$	0.2315
$P'_{g,F'}$	0.5443
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0031
$\Delta P_{C,s}$	-0.0010
$\Delta P_{F,e}$	0.0027
$\Delta P_{g,F}$	0.0146
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	2
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.3
$T_g$ [°C]	589
$T_{10}^{13}$ [°C]	593
$T_{10}^{7.6}$ [°C]	669
$c_p$ [J/(g·K)]	0.690
$\lambda$ [W/(m·K)]	0.960
$\rho$ [g/cm <sup>3</sup> ]	3.37
$E$ [ $10^3$ N/mm <sup>2</sup> ]	93
$\mu$	0.262
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.82
$HK_{0.1/20}$	550
HG	4

## N-SF8 689313.290

$n_d = 1.68894$   
 $n_e = 1.69413$

$v_d = 31.31$   
 $v_e = 31.06$

$n_F - n_C = 0.022005$   
 $n_{F'} - n_{C'} = 0.022346$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.64448
$n_{1970.1}$	1970.1	1.65060
$n_{1529.6}$	1529.6	1.65753
$n_{1060.0}$	1060.0	1.66600
$n_t$	1014.0	1.66711
$n_s$	852.1	1.67203
$n_r$	706.5	1.67904
$n_C$	656.3	1.68254
$n_{C'}$	643.8	1.68354
$n_{632.8}$	632.8	1.68448
$n_D$	589.3	1.68874
$n_d$	587.6	1.68894
$n_e$	546.1	1.69413
$n_F$	486.1	1.70455
$n_{F'}$	480.0	1.70589
$n_g$	435.8	1.71775
$n_h$	404.7	1.72948
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.550758120
$B_2$	0.209816918
$B_3$	1.462054910
$C_1$	0.011433834
$C_2$	0.0582725652
$C_3$	133.24165000

### Constants of Formula for $dn/dT$

$D_0$	-1.94E-06
$D_1$	9.70E-09
$D_2$	-2.34E-11
$E_0$	8.32E-07
$E_1$	1.15E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.276

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.0	2.4	4.2	-1.3	0.1	1.8
+20/+40	0.9	2.6	4.8	-0.5	1.2	3.3
+60/+80	1.0	2.9	5.3	-0.1	1.7	4.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.750	0.480
2325	0.820	0.600
1970	0.950	0.870
1530	0.988	0.970
1060	0.997	0.993
700	0.995	0.987
660	0.993	0.983
620	0.993	0.983
580	0.994	0.986
546	0.993	0.983
500	0.985	0.963
460	0.976	0.940
436	0.965	0.910
420	0.950	0.880
405	0.920	0.810
400	0.900	0.770
390	0.830	0.630
380	0.670	0.370
370	0.350	0.070
365	0.160	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  41/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2236
$P_{C,s}$	0.4778
$P_{d,C}$	0.2905
$P_{e,d}$	0.2362
$P_{g,F}$	0.5999
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2202
$P'_{C,s}$	0.5152
$P'_{d,C'}$	0.2413
$P'_{e,d}$	0.2326
$P'_{g,F'}$	0.5308
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0080
$\Delta P_{C,s}$	0.0019
$\Delta P_{F,e}$	0.0014
$\Delta P_{g,F}$	0.0087
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1
SR-J	1
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.9
$T_g$ [°C]	567
$T_{10}^{13}$ [°C]	564
$T_{10}^{7.6}$ [°C]	678
$c_p$ [J/(g·K)]	0.770
$\lambda$ [W/(m·K)]	1.030
$\rho$ [g/cm <sup>3</sup> ]	2.90
$E$ [ $10^3$ N/mm <sup>2</sup> ]	88
$\mu$	0.245
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.95
$HK_{0.1/20}$	600
HG	4

## N-SF10 728285.305

$n_d = 1.72828$   
 $n_e = 1.73430$

$v_d = 28.53$   
 $v_e = 28.31$

$n_F - n_C = 0.025524$   
 $n_{F'} - n_{C'} = 0.025941$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.67981
$n_{1970.1}$	1970.1	1.68597
$n_{1529.6}$	1529.6	1.69308
$n_{1060.0}$	1060.0	1.70217
$n_t$	1014.0	1.70340
$n_s$	852.1	1.70891
$n_r$	706.5	1.71688
$n_C$	656.3	1.72091
$n_{C'}$	643.8	1.72206
$n_{632.8}$	632.8	1.72314
$n_D$	589.3	1.72806
$n_d$	587.6	1.72828
$n_e$	546.1	1.73430
$n_F$	486.1	1.74643
$n_{F'}$	480.0	1.74800
$n_g$	435.8	1.76191
$n_h$	404.7	1.77578
$n_i$	365.0	365.0
$n_{334.1}$	334.1	334.1
$n_{312.6}$	312.6	312.6
$n_{296.7}$	296.7	296.7
$n_{280.4}$	280.4	280.4
$n_{248.3}$	248.3	248.3

### Constants of Dispersion Formula

$B_1$	1.621539020
$B_2$	0.256287842
$B_3$	1.644475520
$C_1$	0.012224146
$C_2$	0.0595736775
$C_3$	147.46879300

### Constants of Formula for $dn/dT$

$D_0$	-4.68E-06
$D_1$	7.41E-09
$D_2$	-1.89E-11
$E_0$	9.49E-07
$E_1$	1.42E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.279

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.4	1.3	3.4	-2.7	-1.1	1.0
+20/+40	-0.5	1.5	4.1	-2.0	-0.1	2.5
+60/+80	-0.5	1.7	4.6	-1.7	0.5	3.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.850	0.660
2325	0.900	0.760
1970	0.971	0.930
1530	0.994	0.985
1060	0.996	0.990
700	0.993	0.983
660	0.990	0.976
620	0.991	0.977
580	0.991	0.978
546	0.989	0.973
500	0.978	0.950
460	0.963	0.910
436	0.950	0.870
420	0.920	0.820
405	0.870	0.700
400	0.840	0.640
390	0.730	0.450
380	0.530	0.200
370	0.180	
365	0.060	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  42/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2160
$P_{C,s}$	0.4701
$P_{d,C}$	0.2888
$P_{e,d}$	0.2359
$P_{g,F}$	0.6066
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2125
$P'_{C,s}$	0.5068
$P'_{d,C'}$	0.2398
$P'_{e,d}$	0.2321
$P'_{g,F'}$	0.5365
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0057
$\Delta P_{C,s}$	0.0007
$\Delta P_{F,e}$	0.0019
$\Delta P_{g,F}$	0.0108
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.8
$T_g$ [°C]	559
$T_{10}^{13}$ [°C]	549
$T_{10}^{7.6}$ [°C]	652
$c_p$ [J/(g·K)]	0.740
$\lambda$ [W/(m·K)]	0.960
$\rho$ [g/cm <sup>3</sup> ]	3.05
$E$ [ $10^3$ N/mm <sup>2</sup> ]	87
$\mu$	0.252
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.92
$HK_{0.1/20}$	540
HG	5

## N-SF11 785257.322

$n_d = 1.78472$

$v_d = 25.68$

$n_F - n_C = 0.030558$

$n_e = 1.79192$

$v_e = 25.47$

$n_F - n_C = 0.031088$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.72937
$n_{1970.1}$	1970.1	1.73600
$n_{1529.6}$	1529.6	1.74377
$n_{1060.0}$	1060.0	1.75401
$n_t$	1014.0	1.75542
$n_s$	852.1	1.76182
$n_r$	706.5	1.77119
$n_C$	656.3	1.77596
$n_{C'}$	643.8	1.77732
$n_{632.8}$	632.8	1.77860
$n_D$	589.3	1.78446
$n_d$	587.6	1.78472
$n_e$	546.1	1.79192
$n_F$	486.1	1.80651
$n_{F'}$	480.0	1.80841
$n_g$	435.8	1.82533
$n_h$	404.7	1.84235
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.737596950
$B_2$	0.313747346
$B_3$	1.898781010
$C_1$	0.013188707
$C_2$	0.0623068142
$C_3$	155.23629000

### Constants of Formula for $dn/dT$

$D_0$	-3.56E-06
$D_1$	9.20E-09
$D_2$	-2.10E-11
$E_0$	9.65E-07
$E_1$	1.44E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.294

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	0.1	2.0	4.6	-2.3	-0.5	2.1
+20/+40	0.1	2.4	5.6	-1.4	0.8	4.0
+60/+80	0.2	2.7	6.3	-1.0	1.5	5.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.830	0.620
2325	0.870	0.700
1970	0.965	0.920
1530	0.994	0.985
1060	0.999	0.998
700	0.994	0.985
660	0.992	0.981
620	0.992	0.981
580	0.994	0.984
546	0.991	0.978
500	0.981	0.953
460	0.967	0.920
436	0.950	0.870
420	0.920	0.810
405	0.850	0.670
400	0.820	0.600
390	0.690	0.390
380	0.430	0.120
370	0.080	0.000
365	0.000	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  44/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2095
$P_{C,s}$	0.4625
$P_{d,C}$	0.2868
$P_{e,d}$	0.2355
$P_{g,F}$	0.6156
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2059
$P'_{C,s}$	0.4984
$P'_{d,C'}$	0.2381
$P'_{e,d}$	0.2315
$P'_{g,F'}$	0.5442
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0052
$\Delta P_{C,s}$	-0.0003
$\Delta P_{F,e}$	0.0027
$\Delta P_{g,F}$	0.0150
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.9
$T_g$ [°C]	592
$T_{10}^{13}$ [°C]	590
$T_{10}^{7.6}$ [°C]	688
$c_p$ [J/(g·K)]	0.710
$\lambda$ [W/(m·K)]	0.950
$\rho$ [g/cm <sup>3</sup> ]	3.22
$E$ [ $10^3$ N/mm <sup>2</sup> ]	92
$\mu$	0.257
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.94
$HK_{0.1/20}$	615
HG	4



## N-SF14 762265.312

$n_d = 1.76182$

$v_d = 26.53$

$n_F - n_C = 0.028715$

$n_e = 1.76859$

$v_e = 26.32$

$n_F - n_C = 0.029204$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.70954
$n_{1970.1}$	1970.1	1.71581
$n_{1529.6}$	1529.6	1.72315
$n_{1060.0}$	1060.0	1.73284
$n_t$	1014.0	1.73417
$n_s$	852.1	1.74022
$n_r$	706.5	1.74907
$n_C$	656.3	1.75356
$n_{C'}$	643.8	1.75485
$n_{632.8}$	632.8	1.75606
$n_D$	589.3	1.76157
$n_d$	587.6	1.76182
$n_e$	546.1	1.76859
$n_F$	486.1	1.78228
$n_{F'}$	480.0	1.78405
$n_g$	435.8	1.79986
$n_h$	404.7	1.81570
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.690223610
$B_2$	0.288870052
$B_3$	1.704518700
$C_1$	0.013051211
$C_2$	0.0613691880
$C_3$	149.51768900

### Constants of Formula for $dn/dT$

$D_0$	-5.56E-06
$D_1$	7.09E-09
$D_2$	-1.09E-11
$E_0$	9.85E-07
$E_1$	1.39E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.287

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.9	0.9	3.4	-3.2	-1.5	0.9
+20/+40	-1.1	1.1	4.1	-2.6	-0.4	2.5
+60/+80	-1.1	1.4	4.7	-2.2	0.2	3.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.800	0.570
2325	0.840	0.640
1970	0.950	0.880
1530	0.992	0.980
1060	0.999	0.998
700	0.994	0.985
660	0.995	0.987
620	0.995	0.987
580	0.995	0.987
546	0.993	0.983
500	0.985	0.964
460	0.975	0.940
436	0.963	0.910
420	0.950	0.870
405	0.910	0.790
400	0.890	0.750
390	0.820	0.610
380	0.640	0.330
370	0.280	0.040
365	0.100	0.000
350	0.000	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  42/36

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2107
$P_{C,s}$	0.4646
$P_{d,C}$	0.2875
$P_{e,d}$	0.2357
$P_{g,F}$	0.6122
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2072
$P'_{C,s}$	0.5008
$P'_{d,C'}$	0.2387
$P'_{e,d}$	0.2318
$P'_{g,F'}$	0.5413
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0044
$\Delta P_{C,s}$	-0.0002
$\Delta P_{F,e}$	0.0024
$\Delta P_{g,F}$	0.0130
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.9
$T_g$ [°C]	566
$T_{10}^{13}$ [°C]	562
$T_{10}^{7.6}$ [°C]	657
$c_p$ [J/(g·K)]	0.750
$\lambda$ [W/(m·K)]	1.000
$\rho$ [g/cm <sup>3</sup> ]	3.12
$E$ [ $10^3$ N/mm <sup>2</sup> ]	88
$\mu$	0.259
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.89
$HK_{0.1/20}$	515
HG	5

## N-SF15 699302.292

$n_d = 1.69892$   
 $n_e = 1.70438$

$v_d = 30.20$   
 $v_e = 29.96$

$n_F - n_C = 0.023142$   
 $n_{F'} - n_{C'} = 0.023511$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.65267
$n_{1970.1}$	1970.1	1.65899
$n_{1529.6}$	1529.6	1.66616
$n_{1060.0}$	1060.0	1.67494
$n_t$	1014.0	1.67609
$n_s$	852.1	1.68122
$n_r$	706.5	1.68854
$n_C$	656.3	1.69222
$n_{C'}$	643.8	1.69326
$n_{632.8}$	632.8	1.69425
$n_D$	589.3	1.69872
$n_d$	587.6	1.69892
$n_e$	546.1	1.70438
$n_F$	486.1	1.71536
$n_{F'}$	480.0	1.71677
$n_g$	435.8	1.72933
$n_h$	404.7	1.74182
$n_i$	365.0	365.0
$n_{334.1}$	334.1	334.1
$n_{312.6}$	312.6	312.6
$n_{296.7}$	296.7	296.7
$n_{280.4}$	280.4	280.4
$n_{248.3}$	248.3	248.3

### Constants of Dispersion Formula

$B_1$	1.570556340
$B_2$	0.218987094
$B_3$	1.508240170
$C_1$	0.011650701
$C_2$	0.0597856897
$C_3$	132.70933900

### Constants of Formula for $dn/dT$

$D_0$	-7.15E-07
$D_1$	1.04E-08
$D_2$	-2.62E-11
$E_0$	8.56E-07
$E_1$	1.29E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.281

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	1.6	3.1	5.0	-0.7	0.8	2.6
+20/+40	1.6	3.4	5.8	0.2	2.0	4.3
+60/+80	1.7	3.7	6.4	0.6	2.6	5.2

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.760	0.510
2325	0.840	0.640
1970	0.954	0.890
1530	0.990	0.976
1060	0.998	0.996
700	0.995	0.988
660	0.993	0.983
620	0.994	0.984
580	0.994	0.986
546	0.994	0.985
500	0.988	0.970
460	0.977	0.940
436	0.964	0.910
420	0.940	0.860
405	0.890	0.740
400	0.860	0.680
390	0.750	0.480
380	0.530	0.200
370	0.160	0.010
365	0.040	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  42/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2216
$P_{C,s}$	0.4751
$P_{d,C}$	0.2897
$P_{e,d}$	0.2360
$P_{g,F}$	0.6038
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2181
$P'_{C,s}$	0.5122
$P'_{d,C'}$	0.2406
$P'_{e,d}$	0.2323
$P'_{g,F'}$	0.5341
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0085
$\Delta P_{C,s}$	0.0018
$\Delta P_{F,e}$	0.0018
$\Delta P_{g,F}$	0.0108
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.3
$T_g$ [°C]	580
$T_{10}^{13}$ [°C]	578
$T_{10}^{7.6}$ [°C]	692
$c_p$ [J/(g·K)]	0.760
$\lambda$ [W/(m·K)]	1.040
$\rho$ [g/cm <sup>3</sup> ]	2.92
$E$ [ $10^3$ N/mm <sup>2</sup> ]	90
$\mu$	0.243
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.04
$HK_{0.1/20}$	610
HG	3

## N-SF57 847238.353

$n_d = 1.84666$   
 $n_e = 1.85504$

$v_d = 23.78$   
 $v_e = 23.59$

$n_F - n_C = 0.035604$   
 $n_{F'} - n_{C'} = 0.036247$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.78502
$n_{1970.1}$	1970.1	1.79190
$n_{1529.6}$	1529.6	1.80011
$n_{1060.0}$	1060.0	1.81138
$n_t$	1014.0	1.81296
$n_s$	852.1	1.82023
$n_r$	706.5	1.83099
$n_C$	656.3	1.83650
$n_{C'}$	643.8	1.83807
$n_{632.8}$	632.8	1.83956
$n_D$	589.3	1.84635
$n_d$	587.6	1.84666
$n_e$	546.1	1.85504
$n_F$	486.1	1.87210
$n_{F'}$	480.0	1.87432
$n_g$	435.8	1.89423
$n_h$	404.7	1.91440
$n_i$	365.0	365.0
$n_{334.1}$	334.1	334.1
$n_{312.6}$	312.6	312.6
$n_{296.7}$	296.7	296.7
$n_{280.4}$	280.4	280.4
$n_{248.3}$	248.3	248.3

### Constants of Dispersion Formula

$B_1$	1.875438310
$B_2$	0.373757490
$B_3$	2.300017970
$C_1$	0.014174952
$C_2$	0.064050927
$C_3$	177.38979500

### Constants of Formula for $dn/dT$

$D_0$	-4.51E-06
$D_1$	8.73E-09
$D_2$	-1.64E-11
$E_0$	1.07E-06
$E_1$	1.57E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.295

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.5	1.7	4.9	-2.9	-0.8	2.3
+20/+40	-0.5	2.2	6.0	-2.1	0.6	4.3
+60/+80	-0.4	2.6	6.9	-1.6	1.3	5.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.810	0.580
2325	0.840	0.640
1970	0.956	0.890
1530	0.992	0.980
1060	0.999	0.997
700	0.991	0.977
660	0.987	0.969
620	0.988	0.971
580	0.990	0.975
546	0.986	0.965
500	0.971	0.930
460	0.950	0.880
436	0.920	0.810
420	0.870	0.710
405	0.780	0.540
400	0.730	0.460
390	0.570	0.250
380	0.300	0.050
370	0.060	0.000
365	0.000	0.000
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  42/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2042
$P_{C,s}$	0.4568
$P_{d,C}$	0.2855
$P_{e,d}$	0.2353
$P_{g,F}$	0.6216
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2005
$P'_{C,s}$	0.4922
$P'_{d,C'}$	0.2369
$P'_{e,d}$	0.2311
$P'_{g,F'}$	0.5493
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0032
$\Delta P_{C,s}$	-0.0015
$\Delta P_{F,e}$	0.0033
$\Delta P_{g,F}$	0.0178
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.9
$T_g$ [°C]	629
$T_{10}^{13}$ [°C]	616
$T_{10}^{7.6}$ [°C]	716
$c_p$ [J/(g*K)]	0.660
$\lambda$ [W/(m*K)]	0.990
$\rho$ [g/cm <sup>3</sup> ]	3.53
$E$ [ $10^3$ N/mm <sup>2</sup> ]	96
$\mu$	0.260
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.78
$HK_{0.1/20}$	520
HG	4
Abrasion Aa	175

## N-SF57HT 847238.353

$n_d = 1.84666$   
 $n_e = 1.85504$

$v_d = 23.78$   
 $v_e = 23.59$

$n_F - n_C = 0.035604$   
 $n_{F'} - n_{C'} = 0.036247$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.78502
$n_{1970.1}$	1970.1	1.79190
$n_{1529.6}$	1529.6	1.80011
$n_{1060.0}$	1060.0	1.81138
$n_t$	1014.0	1.81296
$n_s$	852.1	1.82023
$n_r$	706.5	1.83099
$n_C$	656.3	1.83650
$n_{C'}$	643.8	1.83807
$n_{632.8}$	632.8	1.83956
$n_D$	589.3	1.84635
$n_d$	587.6	1.84666
$n_e$	546.1	1.85504
$n_F$	486.1	1.87210
$n_{F'}$	480.0	1.87432
$n_g$	435.8	1.89423
$n_h$	404.7	1.91440
$n_i$	365.0	365.0
$n_{334.1}$	334.1	334.1
$n_{312.6}$	312.6	312.6
$n_{296.7}$	296.7	296.7
$n_{280.4}$	280.4	280.4
$n_{248.3}$	248.3	248.3

### Constants of Dispersion Formula

$B_1$	1.875438310
$B_2$	0.373757490
$B_3$	2.300017970
$C_1$	0.014174952
$C_2$	0.064050927
$C_3$	177.38979500

### Constants of Formula for $dn/dT$

$D_0$	-4.51E-06
$D_1$	8.73E-09
$D_2$	-1.64E-11
$E_0$	1.07E-06
$E_1$	1.57E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.295

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.5	1.7	4.9	-2.9	-0.8	2.3
+20/+40	-0.5	2.2	6.0	-2.1	0.6	4.3
+60/+80	-0.4	2.6	6.9	-1.6	1.3	5.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.810	0.580
2325	0.840	0.640
1970	0.956	0.890
1530	0.992	0.980
1060	0.999	0.998
700	0.992	0.979
660	0.988	0.971
620	0.989	0.973
580	0.991	0.977
546	0.987	0.967
500	0.972	0.930
460	0.951	0.880
436	0.930	0.830
420	0.900	0.760
405	0.830	0.630
400	0.790	0.560
390	0.660	0.350
380	0.380	0.090
370	0.060	0.000
365	0.000	0.000
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  41/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2042
$P_{C,s}$	0.4568
$P_{d,C}$	0.2855
$P_{e,d}$	0.2353
$P_{g,F}$	0.6216
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2005
$P'_{C,s}$	0.4922
$P'_{d,C'}$	0.2369
$P'_{e,d}$	0.2311
$P'_{g,F'}$	0.5493
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0032
$\Delta P_{C,s}$	-0.0015
$\Delta P_{F,e}$	0.0033
$\Delta P_{g,F}$	0.0178
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.9
$T_g$ [°C]	629
$T_{10}^{13}$ [°C]	616
$T_{10}^{7.6}$ [°C]	716
$c_p$ [J/(g*K)]	0.660
$\lambda$ [W/(m*K)]	0.990
$\rho$ [g/cm <sup>3</sup> ]	3.53
$E$ [ $10^3$ N/mm <sup>2</sup> ]	96
$\mu$	0.260
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.78
$HK_{0.1/20}$	520
HG	4
Abrasion Aa	175

## N-SF57HTultra 847238.353

$n_d = 1.84666$   
 $n_e = 1.85504$

$v_d = 23.78$   
 $v_e = 23.59$

$n_F - n_C = 0.035604$   
 $n_{F'} - n_{C'} = 0.036247$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.78502
$n_{1970.1}$	1970.1	1.79190
$n_{1529.6}$	1529.6	1.80011
$n_{1060.0}$	1060.0	1.81138
$n_t$	1014.0	1.81296
$n_s$	852.1	1.82023
$n_r$	706.5	1.83099
$n_C$	656.3	1.83650
$n_{C'}$	643.8	1.83807
$n_{632.8}$	632.8	1.83956
$n_D$	589.3	1.84635
$n_d$	587.6	1.84666
$n_e$	546.1	1.85504
$n_F$	486.1	1.87210
$n_{F'}$	480.0	1.87432
$n_g$	435.8	1.89423
$n_h$	404.7	1.91440
$n_i$	365.0	365.0
$n_{334.1}$	334.1	334.1
$n_{312.6}$	312.6	312.6
$n_{296.7}$	296.7	296.7
$n_{280.4}$	280.4	280.4
$n_{248.3}$	248.3	248.3

### Constants of Dispersion Formula

$B_1$	1.875438310
$B_2$	0.373757490
$B_3$	2.300017970
$C_1$	0.014174952
$C_2$	0.064050927
$C_3$	177.38979500

### Constants of Formula for $dn/dT$

$D_0$	-4.51E-06
$D_1$	8.73E-09
$D_2$	-1.64E-11
$E_0$	1.07E-06
$E_1$	1.57E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.295

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.5	1.7	4.9	-2.9	-0.8	2.3
+20/+40	-0.5	2.2	6.0	-2.1	0.6	4.3
+60/+80	-0.4	2.6	6.9	-1.6	1.3	5.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.810	0.580
2325	0.840	0.640
1970	0.956	0.890
1530	0.992	0.980
1060	0.999	0.998
700	0.995	0.988
660	0.994	0.985
620	0.993	0.983
580	0.992	0.981
546	0.989	0.973
500	0.978	0.950
460	0.962	0.910
436	0.940	0.860
420	0.920	0.810
405	0.860	0.690
400	0.830	0.630
390	0.700	0.410
380	0.420	0.110
370	0.060	0.000
365	0.000	0.000
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  40/37

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.2042
$P_{C,s}$	0.4568
$P_{d,C}$	0.2855
$P_{e,d}$	0.2353
$P_{g,F}$	0.6216
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2005
$P'_{C,s}$	0.4922
$P'_{d,C'}$	0.2369
$P'_{e,d}$	0.2311
$P'_{g,F'}$	0.5493
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0032
$\Delta P_{C,s}$	-0.0015
$\Delta P_{F,e}$	0.0033
$\Delta P_{g,F}$	0.0178
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.9
$T_g$ [°C]	629
$T_{10}^{13}$ [°C]	616
$T_{10}^{7.6}$ [°C]	716
$c_p$ [J/(g*K)]	0.660
$\lambda$ [W/(m*K)]	0.990
$\rho$ [g/cm <sup>3</sup> ]	3.53
$E$ [ $10^3$ N/mm <sup>2</sup> ]	96
$\mu$	0.260
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.78
$HK_{0.1/20}$	520
HG	4
Abrasion Aa	175

## N-SF66 923209.400

$n_d = 1.92286$

$v_d = 20.88$

$n_F - n_C = 0.044199$

$n_e = 1.93322$

$v_e = 20.70$

$n_F - n_C = 0.045076$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.84839
$n_{1970.1}$	1970.1	1.85665
$n_{1529.6}$	1529.6	1.86650
$n_{1060.0}$	1060.0	1.87999
$n_t$	1014.0	1.88189
$n_s$	852.1	1.89064
$n_r$	706.5	1.90368
$n_C$	656.3	1.91039
$n_{C'}$	643.8	1.91232
$n_{632.8}$	632.8	1.91414
$n_D$	589.3	1.92248
$n_d$	587.6	1.92286
$n_e$	546.1	1.93322
$n_F$	486.1	1.95459
$n_{F'}$	480.0	1.95739
$n_g$	435.8	1.98285
$n_h$	404.7	
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	2.024597600
$B_2$	0.470187196
$B_3$	2.599704330
$C_1$	0.014705323
$C_2$	0.0692998276
$C_3$	161.81760100

### Constants of Formula for $dn/dT$

$D_0$	-4.30E-06
$D_1$	1.15E-08
$D_2$	4.31E-11
$E_0$	9.62E-07
$E_1$	1.62E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.322

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.4	1.9	5.8	-2.9	-0.7	3.1
+20/+40	-0.5	2.4	7.3	-2.1	0.8	5.5
+60/+80	0.1	3.4	8.9	-1.2	2.1	7.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.79	0.56
2325	0.84	0.64
1970	0.95	0.87
1530	0.989	0.973
1060	0.996	0.991
700	0.991	0.977
660	0.987	0.968
620	0.983	0.958
580	0.976	0.94
546	0.963	0.91
500	0.93	0.83
460	0.89	0.74
436	0.83	0.63
420	0.76	0.50
405	0.59	0.27
400	0.50	0.18
390	0.25	0.02
380	0.04	
370	0.00	
365	0.00	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  45/38

### Remarks

### Relative Partial Dispersion P

$P_{s,t}$	0.1980
$P_{C,s}$	0.4467
$P_{d,C}$	0.2822
$P_{e,d}$	0.2345
$P_{g,F}$	0.6394
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.1941
$P'_{C,s}$	0.4808
$P'_{d,C'}$	0.2339
$P'_{e,d}$	0.2299
$P'_{g,F'}$	0.5647
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0007
$\Delta P_{C,s}$	-0.0048
$\Delta P_{F,e}$	0.0059
$\Delta P_{g,F}$	0.0307
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.9
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.8
$T_g$ [°C]	710
$T_{10}^{13}$ [°C]	719
$T_{10}^{7.6}$ [°C]	800
$c_p$ [J/(g·K)]	0.540
$\lambda$ [W/(m·K)]	0.800
$\rho$ [g/cm <sup>3</sup> ]	4.00
$E$ [ $10^3$ N/mm <sup>2</sup> ]	95
$\mu$	0.259
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.91
$HK_{0.1/20}$	440
HG	3

## P-SF8 689313.290

$n_d = 1.68893$   
 $n_e = 1.69414$

$v_d = 31.25$   
 $v_e = 31.01$

$n_F - n_C = 0.022046$   
 $n_{F'} - n_{C'} = 0.022386$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.64480
$n_{1970.1}$	1970.1	1.65079
$n_{1529.6}$	1529.6	1.65760
$n_{1060.0}$	1060.0	1.66598
$n_t$	1014.0	1.66708
$n_s$	852.1	1.67200
$n_r$	706.5	1.67901
$n_C$	656.3	1.68252
$n_{C'}$	643.8	1.68353
$n_{632.8}$	632.8	1.68447
$n_D$	589.3	1.68874
$n_d$	587.6	1.68893
$n_e$	546.1	1.69414
$n_F$	486.1	1.70457
$n_{F'}$	480.0	1.70591
$n_g$	435.8	1.71778
$n_h$	404.7	1.72950
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.553704110
$B_2$	0.206332561
$B_3$	1.397088310
$C_1$	0.011658267
$C_2$	0.0582087757
$C_3$	130.74802800

### Constants of Formula for $dn/dT$

$D_0$	-4.27E-06
$D_1$	8.16E-09
$D_2$	-2.00E-11
$E_0$	9.02E-07
$E_1$	1.22E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.272

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-0.2	1.3	3.2	-2.4	-1.0	0.8
+20/+40	-0.3	1.5	3.7	-1.7	0.0	2.2
+60/+80	-0.3	1.7	4.1	-1.4	0.5	3.0

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.730	0.450
2325	0.800	0.570
1970	0.940	0.850
1530	0.991	0.977
1060	0.999	0.997
700	0.995	0.988
660	0.994	0.984
620	0.994	0.984
580	0.995	0.987
546	0.994	0.986
500	0.989	0.972
460	0.980	0.950
436	0.971	0.930
420	0.959	0.900
405	0.940	0.850
400	0.920	0.820
390	0.870	0.710
380	0.750	0.480
370	0.470	0.150
365	0.260	0.040
350	0.000	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  40/36

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2229
$P_{C,s}$	0.4776
$P_{d,C}$	0.2905
$P_{e,d}$	0.2362
$P_{g,F}$	0.5991
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2195
$P'_{C,s}$	0.5150
$P'_{d,C'}$	0.2414
$P'_{e,d}$	0.2326
$P'_{g,F'}$	0.5301
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0072
$\Delta P_{C,s}$	0.0018
$\Delta P_{F,e}$	0.0013
$\Delta P_{g,F}$	0.0079
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1.2
PR	1
SR-J	1
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	11.1
$T_g$ [°C]	524
$T_{10}^{13}$ [°C]	531
$T_{10}^{7.6}$ [°C]	629
$c_p$ [J/(g·K)]	0.790
$\lambda$ [W/(m·K)]	1.020
AT [°C]	580
$\rho$ [g/cm <sup>3</sup> ]	2.90
E [10 <sup>3</sup> N/mm <sup>2</sup> ]	86
$\mu$	0.253
K [10 <sup>-6</sup> mm <sup>2</sup> /N]	2.73
HK <sub>0.1/20</sub>	533
Abrasion Aa	200

## P-SF68 005210.619

$n_d = 2.00520$   
 $n_e = 2.01643$

$v_d = 21.00$   
 $v_e = 20.82$

$n_F - n_C = 0.047867$   
 $n_{F'} - n_{C'} = 0.048826$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.93381
$n_{1970.1}$	1970.1	1.93968
$n_{1529.6}$	1529.6	1.94732
$n_{1060.0}$	1060.0	1.95970
$n_t$	1014.0	1.96160
$n_s$	852.1	1.97063
$n_r$	706.5	1.98449
$n_C$	656.3	1.99171
$n_{C'}$	643.8	1.99380
$n_{632.8}$	632.8	1.99576
$n_D$	589.3	2.00479
$n_d$	587.6	2.00520
$n_e$	546.1	2.01643
$n_F$	486.1	2.03958
$n_{F'}$	480.0	2.04262
$n_g$	435.8	2.07018
$n_h$	404.7	
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	2.333006700
$B_2$	0.452961396
$B_3$	1.251723390
$C_1$	0.016883842
$C_2$	0.0716086325
$C_3$	118.70747900

### Constants of Formula for $dn/dT$

$D_0$	1.55E-05
$D_1$	2.30E-08
$D_2$	-3.46E-11
$E_0$	2.76E-06
$E_1$	2.93E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.297

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	13.7	21.5	32.3	11.1	18.8	29.5
+20/+40	15.2	24.1	36.5	13.5	22.3	34.6
+60/+80	16.2	25.8	39.1	15.4	25.3	39.2

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.790	0.560
2325	0.910	0.780
1970	0.976	0.940
1530	0.996	0.990
1060	0.999	0.998
700	0.997	0.993
660	0.996	0.989
620	0.994	0.985
580	0.989	0.973
546	0.976	0.940
500	0.910	0.780
460	0.760	0.500
436	0.570	0.250
420	0.300	0.050
405	0.040	0.000
400	0.010	
390	0.000	
380		
370		
365		
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  49/41

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.1885
$P_{C,s}$	0.4406
$P_{d,C}$	0.2817
$P_{e,d}$	0.2346
$P_{g,F}$	0.6392
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.1848
$P'_{C,s}$	0.4746
$P'_{d,C'}$	0.2336
$P'_{e,d}$	0.2300
$P'_{g,F'}$	0.5644
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	-0.0156
$\Delta P_{C,s}$	-0.0113
$\Delta P_{F,e}$	0.0063
$\Delta P_{g,F}$	0.0308
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	5
SR	53.3
AR	1-2,3
PR	2.3
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.7
$T_g$ [°C]	428
$T_{10}^{13}$ [°C]	430
$T_{10}^{7.6}$ [°C]	504
$c_p$ [J/(g·K)]	0.370
$\lambda$ [W/(m·K)]	0.650
AT [°C]	468
$\rho$ [g/cm <sup>3</sup> ]	6.19
E [ $10^3$ N/mm <sup>2</sup> ]	79
$\mu$	0.275
K [ $10^{-6}$ mm <sup>2</sup> /N]	1.61
HK <sub>0.1/20</sub>	404
Abrasion Aa	298



## P-SF69 723292.293

$n_d = 1.72250$

$v_d = 29.23$

$n_F - n_C = 0.024718$

$n_e = 1.72833$

$v_e = 29.00$

$n_F - n_C = 0.025116$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.67440
$n_{1970.1}$	1970.1	1.68073
$n_{1529.6}$	1529.6	1.68797
$n_{1060.0}$	1060.0	1.69705
$n_t$	1014.0	1.69826
$n_s$	852.1	1.70367
$n_r$	706.5	1.71144
$n_C$	656.3	1.71535
$n_{C'}$	643.8	1.71647
$n_{632.8}$	632.8	1.71752
$n_D$	589.3	1.72229
$n_d$	587.6	1.72250
$n_e$	546.1	1.72833
$n_F$	486.1	1.74007
$n_{F'}$	480.0	1.74158
$n_g$	435.8	1.75502
$n_h$	404.7	1.76840
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.625946470
$B_2$	0.235927609
$B_3$	1.674346230
$C_1$	0.012169668
$C_2$	0.0600710405
$C_3$	145.65190800

### Constants of Formula for $dn/dT$

$D_0$	-2.55E-06
$D_1$	5.68E-09
$D_2$	-2.85E-11
$E_0$	9.50E-07
$E_1$	1.54E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.275

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	0.9	2.5	4.6	-1.4	0.1	2.1
+20/+40	0.6	2.6	5.2	-0.8	1.1	3.6
+60/+80	0.5	2.8	5.6	-0.6	1.6	4.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.800	0.580
2325	0.860	0.680
1970	0.954	0.890
1530	0.993	0.983
1060	0.999	0.998
700	0.998	0.994
660	0.997	0.993
620	0.997	0.993
580	0.998	0.994
546	0.997	0.992
500	0.993	0.983
460	0.985	0.964
436	0.976	0.940
420	0.963	0.910
405	0.930	0.840
400	0.920	0.800
390	0.850	0.660
380	0.690	0.390
370	0.360	0.080
365	0.160	0.010
350	0.000	0.000
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  41/36

### Remarks

suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2188
$P_{C,s}$	0.4727
$P_{d,C}$	0.2893
$P_{e,d}$	0.2360
$P_{g,F}$	0.6050
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2153
$P'_{C,s}$	0.5096
$P'_{d,C'}$	0.2403
$P'_{e,d}$	0.2322
$P'_{g,F'}$	0.5352
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0078
$\Delta P_{C,s}$	0.0016
$\Delta P_{F,e}$	0.0017
$\Delta P_{g,F}$	0.0104
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	11.1
$T_g$ [°C]	508
$T_{10}^{13}$ [°C]	508
$T_{10}^{7.6}$ [°C]	602
$c_p$ [J/(g·K)]	0.820
$\lambda$ [W/(m·K)]	1.120
AT [°C]	547
$\rho$ [g/cm <sup>3</sup> ]	2.93
E [10 <sup>3</sup> N/mm <sup>2</sup> ]	96
$\mu$	0.251
K [10 <sup>-6</sup> mm <sup>2</sup> /N]	2.66
HK <sub>0.1/20</sub>	612
Abrasion Aa	142

## SF1 717295.446

$n_d = 1.71736$   
 $n_e = 1.72310$

$v_d = 29.51$   
 $v_e = 29.29$

$n_F - n_C = 0.024307$   
 $n_{F'} - n_{C'} = 0.024687$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.67352
$n_{1970.1}$	1970.1	1.67855
$n_{1529.6}$	1529.6	1.68449
$n_{1060.0}$	1060.0	1.69258
$n_t$	1014.0	1.69371
$n_s$	852.1	1.69888
$n_r$	706.5	1.70647
$n_C$	656.3	1.71031
$n_{C'}$	643.8	1.71141
$n_{632.8}$	632.8	1.71245
$n_D$	589.3	1.71715
$n_d$	587.6	1.71736
$n_e$	546.1	1.72310
$n_F$	486.1	1.73462
$n_{F'}$	480.0	1.73610
$n_g$	435.8	1.74916
$n_h$	404.7	1.76201
$n_i$	365.0	1.78580
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.559129230
$B_2$	0.284246288
$B_3$	0.968842926
$C_1$	0.012148100
$C_2$	0.0534549042
$C_3$	112.17480900

### Constants of Formula for $dn/dT$

$D_0$	4.84E-06
$D_1$	1.70E-08
$D_2$	-4.52E-11
$E_0$	1.38E-06
$E_1$	1.26E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.259

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.5	7.0	10.1	2.2	4.7	7.7
+20/+40	5.0	7.9	11.3	3.6	6.4	9.8
+60/+80	5.3	8.4	12.1	4.2	7.3	10.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.840	0.650
2325	0.880	0.730
1970	0.959	0.900
1530	0.994	0.985
1060	0.998	0.996
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.996
546	0.998	0.996
500	0.997	0.993
460	0.994	0.984
436	0.990	0.976
420	0.984	0.961
405	0.971	0.930
400	0.967	0.920
390	0.950	0.870
380	0.910	0.790
370	0.840	0.640
365	0.760	0.500
350	0.300	0.030
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  39/34

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2127
$P_{C,s}$	0.4705
$P_{d,C}$	0.2899
$P_{e,d}$	0.2364
$P_{g,F}$	0.5983
$P_{i,h}$	0.9791

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2094
$P'_{C,s}$	0.5078
$P'_{d,C'}$	0.2409
$P'_{e,d}$	0.2327
$P'_{g,F'}$	0.5292
$P'_{i,h}$	0.9640

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0018
$\Delta P_{C,s}$	-0.0012
$\Delta P_{F,e}$	0.0009
$\Delta P_{g,F}$	0.0042
$\Delta P_{i,g}$	0.0307

### Chemical Properties

CR	2
FR	1
SR	3.2
AR	2.3
PR	3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.8
$T_g$ [°C]	417
$T_{10}^{13}$ [°C]	415
$T_{10}^{7.6}$ [°C]	566
$c_p$ [J/(g·K)]	0.430
$\lambda$ [W/(m·K)]	0.660
$\rho$ [g/cm <sup>3</sup> ]	4.46
$E$ [ $10^3$ N/mm <sup>2</sup> ]	56
$\mu$	0.232
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.80
$HK_{0.1/20}$	390
HG	1

## SF2 648339.386

$n_d = 1.64769$

$v_d = 33.85$

$n_F - n_C = 0.019135$

$n_e = 1.65222$

$v_e = 33.60$

$n_F - n_C = 0.019412$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.61003
$n_{1970.1}$	1970.1	1.61494
$n_{1529.6}$	1529.6	1.62055
$n_{1060.0}$	1060.0	1.62766
$n_t$	1014.0	1.62861
$n_s$	852.1	1.63289
$n_r$	706.5	1.63902
$n_C$	656.3	1.64210
$n_{C'}$	643.8	1.64297
$n_{632.8}$	632.8	1.64379
$n_D$	589.3	1.64752
$n_d$	587.6	1.64769
$n_e$	546.1	1.65222
$n_F$	486.1	1.66123
$n_{F'}$	480.0	1.66238
$n_g$	435.8	1.67249
$n_h$	404.7	1.68233
$n_i$	365.0	1.70027
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.403018210
$B_2$	0.231767504
$B_3$	0.939056586
$C_1$	0.010579547
$C_2$	0.0493226978
$C_3$	112.40595500

### Constants of Formula for $dn/dT$

$D_0$	1.10E-06
$D_1$	1.75E-08
$D_2$	-1.29E-11
$E_0$	1.08E-06
$E_1$	1.03E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.249

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.3	4.0	6.0	0.1	1.8	3.7
+20/+40	2.7	4.6	6.9	1.3	3.2	5.4
+60/+80	3.1	5.2	7.6	2.0	4.1	6.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.830	0.620
2325	0.870	0.710
1970	0.950	0.880
1530	0.994	0.985
1060	0.998	0.996
700	0.998	0.996
660	0.998	0.994
620	0.998	0.995
580	0.998	0.995
546	0.998	0.995
500	0.997	0.993
460	0.995	0.988
436	0.993	0.982
420	0.990	0.975
405	0.985	0.962
400	0.981	0.954
390	0.967	0.920
380	0.950	0.870
370	0.910	0.790
365	0.880	0.720
350	0.670	0.370
334	0.110	
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  37/33

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2233
$P_{C,s}$	0.4813
$P_{d,C}$	0.2923
$P_{e,d}$	0.2367
$P_{g,F}$	0.5886
$P_{i,h}$	0.9376

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2201
$P'_{C,s}$	0.5196
$P'_{d,C'}$	0.2430
$P'_{e,d}$	0.2334
$P'_{g,F'}$	0.5209
$P'_{i,h}$	0.9242

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0009
$\Delta P_{C,s}$	-0.0005
$\Delta P_{F,e}$	0.0004
$\Delta P_{g,F}$	0.0017
$\Delta P_{i,g}$	0.0112

### Chemical Properties

CR	1
FR	0
SR	2
AR	2.3
PR	2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.2
$T_g$ [°C]	441
$T_{10}^{13}$ [°C]	428
$T_{10}^{7.6}$ [°C]	600
$c_p$ [J/(g·K)]	0.498
$\lambda$ [W/(m·K)]	0.735
$\rho$ [g/cm <sup>3</sup> ]	3.86
$E$ [ $10^3$ N/mm <sup>2</sup> ]	55
$\mu$	0.227
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.62
$HK_{0.1/20}$	410
HG	2

## SF3 740282.464

$n_d = 1.74000$

$v_d = 28.20$

$n_F - n_C = 0.026244$

$n_e = 1.74620$

$v_e = 27.98$

$n_{F'} - n_{C'} = 0.026667$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.69410
$n_{1970.1}$	1970.1	1.69910
$n_{1529.6}$	1529.6	1.70511
$n_{1060.0}$	1060.0	1.71350
$n_t$	1014.0	1.71469
$n_s$	852.1	1.72017
$n_r$	706.5	1.72829
$n_C$	656.3	1.73242
$n_{C'}$	643.8	1.73360
$n_{632.8}$	632.8	1.73471
$n_D$	589.3	1.73977
$n_d$	587.6	1.74000
$n_e$	546.1	1.74620
$n_F$	486.1	1.75866
$n_{F'}$	480.0	1.76027
$n_g$	435.8	1.77446
$n_h$	404.7	1.78846
$n_i$	365.0	1.81452
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.572305420
$B_2$	0.339661149
$B_3$	1.035937120
$C_1$	0.012038218
$C_2$	0.0531603583
$C_3$	120.00538100

### Constants of Formula for $dn/dT$

$D_0$	3.72E-06
$D_1$	1.74E-08
$D_2$	-3.21E-11
$E_0$	1.49E-06
$E_1$	1.41E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.260

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.0	6.8	10.2	1.7	4.5	7.7
+20/+40	4.6	7.8	11.5	3.1	6.2	10.0
+60/+80	5.0	8.4	12.4	3.8	7.2	11.2

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500		
2325	0.900	0.760
1970	0.963	0.910
1530	0.994	0.986
1060	0.998	0.995
700	0.999	0.998
660	0.999	0.997
620	0.999	0.997
580	0.998	0.995
546	0.997	0.993
500	0.996	0.990
460	0.991	0.977
436	0.984	0.960
420	0.971	0.930
405	0.950	0.880
400	0.940	0.860
390	0.910	0.780
380	0.840	0.650
370	0.730	0.460
365	0.650	0.340
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  40/35

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2090
$P_{C,s}$	0.4665
$P_{d,C}$	0.2890
$P_{e,d}$	0.2362
$P_{g,F}$	0.6020
$P_{i,h}$	0.9929

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2057
$P'_{C,s}$	0.5034
$P'_{d,C'}$	0.2401
$P'_{e,d}$	0.2325
$P'_{g,F'}$	0.5323
$P'_{i,h}$	0.9772

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0032
$\Delta P_{C,s}$	-0.0021
$\Delta P_{F,e}$	0.0012
$\Delta P_{g,F}$	0.0056
$\Delta P_{i,g}$	0.0386

### Chemical Properties

CR	1
FR	2
SR	4.3
AR	2.3
PR	2.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.5
$T_g$ [°C]	415
$T_{10}^{13}$ [°C]	404
$T_{10}^{7.6}$ [°C]	548
$c_p$ [J/(g·K)]	0.423
$\lambda$ [W/(m·K)]	0.706
$\rho$ [g/cm <sup>3</sup> ]	4.64
$E$ [ $10^3$ N/mm <sup>2</sup> ]	56
$\mu$	0.236
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.53
HK <sub>0.1/20</sub>	380

## SF4 755276.479

$n_d = 1.75520$

$v_d = 27.58$

$n_F - n_C = 0.027383$

$n_e = 1.76167$

$v_e = 27.37$

$n_F - n_C = 0.027829$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.70789
$n_{1970.1}$	1970.1	1.71294
$n_{1529.6}$	1529.6	1.71904
$n_{1060.0}$	1060.0	1.72765
$n_t$	1014.0	1.72888
$n_s$	852.1	1.73456
$n_r$	706.5	1.74300
$n_C$	656.3	1.74730
$n_{C'}$	643.8	1.74853
$n_{632.8}$	632.8	1.74969
$n_D$	589.3	1.75496
$n_d$	587.6	1.75520
$n_e$	546.1	1.76167
$n_F$	486.1	1.77468
$n_{F'}$	480.0	1.77636
$n_g$	435.8	1.79121
$n_h$	404.7	1.80589
$n_i$	365.0	1.83330
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.619578260
$B_2$	0.339493189
$B_3$	1.025669310
$C_1$	0.012550210
$C_2$	0.0544559822
$C_3$	117.65222200

### Constants of Formula for $dn/dT$

$D_0$	5.60E-06
$D_1$	1.70E-08
$D_2$	-5.27E-11
$E_0$	1.54E-06
$E_1$	1.46E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.266

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	5.1	8.1	11.8	2.8	5.7	9.4
+20/+40	5.7	9.2	13.3	4.3	7.7	11.8
+60/+80	6.0	9.7	14.2	4.9	8.5	13.0

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.850	0.660
2325	0.890	0.740
1970	0.963	0.910
1530	0.996	0.989
1060	0.998	0.996
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.996
546	0.998	0.996
500	0.996	0.991
460	0.992	0.980
436	0.987	0.967
420	0.980	0.950
405	0.963	0.910
400	0.954	0.890
390	0.920	0.820
380	0.860	0.690
370	0.730	0.450
365	0.600	0.280
350	0.090	
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  40/35

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2076
$P_{C,s}$	0.4650
$P_{d,C}$	0.2886
$P_{e,d}$	0.2361
$P_{g,F}$	0.6036
$P_{i,h}$	1.0012

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2042
$P'_{C,s}$	0.5018
$P'_{d,C'}$	0.2398
$P'_{e,d}$	0.2323
$P'_{g,F'}$	0.5337
$P'_{i,h}$	0.9851

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0032
$\Delta P_{C,s}$	-0.0022
$\Delta P_{F,e}$	0.0014
$\Delta P_{g,F}$	0.0062
$\Delta P_{i,g}$	0.0443

### Chemical Properties

CR	1
FR	2
SR	4.3
AR	2.3
PR	3.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.9
$T_g$ [°C]	420
$T_{10}^{13}$ [°C]	415
$T_{10}^{7.6}$ [°C]	552
$c_p$ [J/(g·K)]	0.410
$\lambda$ [W/(m·K)]	0.650
$\rho$ [g/cm <sup>3</sup> ]	4.79
$E$ [ $10^3$ N/mm <sup>2</sup> ]	56
$\mu$	0.241
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.36
$HK_{0.1/20}$	390
HG	1

## SF5 673322.407

$n_d = 1.67270$

$v_d = 32.21$

$n_F - n_C = 0.020885$

$n_e = 1.67764$

$v_e = 31.97$

$n_F - n_C = 0.021195$

Refractive Indices		
	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.63289
$n_{1970.1}$	1970.1	1.63785
$n_{1529.6}$	1529.6	1.64359
$n_{1060.0}$	1060.0	1.65104
$n_t$	1014.0	1.65206
$n_s$	852.1	1.65664
$n_r$	706.5	1.66327
$n_C$	656.3	1.66661
$n_{C'}$	643.8	1.66756
$n_{632.8}$	632.8	1.66846
$n_D$	589.3	1.67252
$n_d$	587.6	1.67270
$n_e$	546.1	1.67764
$n_F$	486.1	1.68750
$n_{F'}$	480.0	1.68876
$n_g$	435.8	1.69986
$n_h$	404.7	1.71069
$n_i$	365.0	1.73056
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

Constants of Dispersion Formula	
$B_1$	1.461418850
$B_2$	0.247713019
$B_3$	0.949995832
$C_1$	0.011182613
$C_2$	0.0508594669
$C_3$	112.04188800

Constants of Formula for $dn/dT$	
$D_0$	2.59E-06
$D_1$	1.76E-08
$D_2$	-2.03E-11
$E_0$	1.17E-06
$E_1$	1.09E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.255

Temperature Coefficients of the Refractive Index						
[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.1	5.1	7.4	0.9	2.8	5.1
+20/+40	3.5	5.8	8.4	2.1	4.4	6.9
+60/+80	3.9	6.4	9.2	2.8	5.2	8.0

Internal Transmittance $\tau_i$		
$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.85	0.66
2325	0.89	0.74
1970	0.959	0.90
1530	0.995	0.987
1060	0.998	0.996
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.996
546	0.998	0.996
500	0.997	0.993
460	0.995	0.988
436	0.993	0.982
420	0.989	0.973
405	0.983	0.959
400	0.980	0.950
390	0.967	0.92
380	0.950	0.88
370	0.91	0.80
365	0.88	0.73
350	0.63	0.31
334	0.20	
320		
310		
300		
290		
280		
270		
260		
250		

Color Code	
$\lambda_{80} / \lambda_5$	37/33

Remarks
lead containing glass type

Relative Partial Dispersion P	
$P_{s,t}$	0.2194
$P_{C,s}$	0.4775
$P_{d,C}$	0.2915
$P_{e,d}$	0.2366
$P_{g,F}$	0.5919
$P_{i,h}$	0.9513

Relative Partial Dispersion P'	
$P'_{s,t}$	0.2162
$P'_{C,s}$	0.5153
$P'_{d,C'}$	0.2423
$P'_{e,d}$	0.2331
$P'_{g,F'}$	0.5237
$P'_{i,h}$	0.9374

Deviation of Rel. Partial Disp. $\Delta P$ from the normal line	
$\Delta P_{C,t}$	-0.0010
$\Delta P_{C,s}$	-0.0005
$\Delta P_{F,e}$	0.0005
$\Delta P_{g,F}$	0.0023
$\Delta P_{i,g}$	0.0160

Chemical Properties	
CR	1
FR	1
SR	2
AR	2.3
PR	3

Other Properties	
$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.2
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.0
$T_g$ [°C]	425
$T_{10}^{13}$ [°C]	421
$T_{10}^{7.6}$ [°C]	580
$c_p$ [J/(g·K)]	0.470
$\lambda$ [W/(m·K)]	0.690
$\rho$ [g/cm <sup>3</sup> ]	4.07
$E$ [ $10^3$ N/mm <sup>2</sup> ]	56
$\mu$	0.233
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.29
$HK_{0.1/20}$	410
HG	2

## SF6 805254.518

$n_d = 1.80518$

$v_d = 25.43$

$n_F - n_C = 0.031660$

$n_e = 1.81265$

$v_e = 25.24$

$n_F - n_C = 0.032201$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.75302
$n_{1970.1}$	1970.1	1.75813
$n_{1529.6}$	1529.6	1.76444
$n_{1060.0}$	1060.0	1.77380
$n_t$	1014.0	1.77517
$n_s$	852.1	1.78157
$n_r$	706.5	1.79117
$n_C$	656.3	1.79609
$n_{C'}$	643.8	1.79750
$n_{632.8}$	632.8	1.79884
$n_D$	589.3	1.80491
$n_d$	587.6	1.80518
$n_e$	546.1	1.81265
$n_F$	486.1	1.82775
$n_{F'}$	480.0	1.82970
$n_g$	435.8	1.84707
$n_h$	404.7	1.86436
$n_i$	365.0	1.89703
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.724484820
$B_2$	0.390104889
$B_3$	1.045728580
$C_1$	0.013487195
$C_2$	0.0569318095
$C_3$	118.55718500

### Constants of Formula for $dn/dT$

$D_0$	6.69E-06
$D_1$	1.78E-08
$D_2$	-3.36E-11
$E_0$	1.77E-06
$E_1$	1.70E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.269

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.1	9.9	14.5	3.7	7.4	11.9
+20/+40	6.8	11.1	16.2	5.3	9.5	14.6
+60/+80	7.3	11.8	17.4	6.1	10.6	16.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.890	0.740
2325	0.910	0.790
1970	0.971	0.930
1530	0.996	0.991
1060	0.999	0.999
700	0.999	0.997
660	0.998	0.996
620	0.998	0.995
580	0.999	0.996
546	0.998	0.996
500	0.996	0.991
460	0.991	0.978
436	0.982	0.955
420	0.967	0.920
405	0.930	0.840
400	0.920	0.800
390	0.850	0.660
380	0.720	0.440
370	0.440	0.130
365	0.250	0.030
350	0.000	0.000
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  42/36

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2020
$P_{C,s}$	0.4588
$P_{d,C}$	0.2871
$P_{e,d}$	0.2359
$P_{g,F}$	0.6102
$P_{i,h}$	1.0316

### Relative Partial Dispersion P'

$P'_{s,t}$	0.1986
$P'_{C,s}$	0.4950
$P'_{d,C'}$	0.2384
$P'_{e,d}$	0.2319
$P'_{g,F'}$	0.5393
$P'_{i,h}$	1.0143

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0048
$\Delta P_{C,s}$	-0.0033
$\Delta P_{F,e}$	0.0020
$\Delta P_{g,F}$	0.0092
$\Delta P_{i,g}$	0.0669

### Chemical Properties

CR	2
FR	3
SR	51.3
AR	2.3
PR	3.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.0
$T_g$ [°C]	423
$T_{10}^{13}$ [°C]	410
$T_{10}^{7.6}$ [°C]	538
$c_p$ [J/(g·K)]	0.389
$\lambda$ [W/(m·K)]	0.673
$\rho$ [g/cm <sup>3</sup> ]	5.18
$E$ [ $10^3$ N/mm <sup>2</sup> ]	55
$\mu$	0.244
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	0.65
$HK_{0.1/20}$	370
HG	1

## SF6HT 805254.518

$n_d = 1.80518$

$v_d = 25.43$

$n_F - n_C = 0.031660$

$n_e = 1.81265$

$v_e = 25.24$

$n_F - n_C = 0.032201$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.75302
$n_{1970.1}$	1970.1	1.75813
$n_{1529.6}$	1529.6	1.76444
$n_{1060.0}$	1060.0	1.77380
$n_t$	1014.0	1.77517
$n_s$	852.1	1.78157
$n_r$	706.5	1.79117
$n_C$	656.3	1.79609
$n_{C'}$	643.8	1.79750
$n_{632.8}$	632.8	1.79884
$n_D$	589.3	1.80491
$n_d$	587.6	1.80518
$n_e$	546.1	1.81265
$n_F$	486.1	1.82775
$n_{F'}$	480.0	1.82970
$n_g$	435.8	1.84707
$n_h$	404.7	1.86436
$n_i$	365.0	1.89703
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.724484820
$B_2$	0.390104889
$B_3$	1.045728580
$C_1$	0.013487195
$C_2$	0.0569318095
$C_3$	118.55718500

### Constants of Formula for $dn/dT$

$D_0$	6.69E-06
$D_1$	1.78E-08
$D_2$	-3.36E-11
$E_0$	1.77E-06
$E_1$	1.70E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.269

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.1	9.9	14.5	3.7	7.4	11.9
+20/+40	6.8	11.1	16.2	5.3	9.5	14.6
+60/+80	7.3	11.8	17.4	6.1	10.6	16.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.890	0.740
2325	0.910	0.790
1970	0.971	0.930
1530	0.996	0.991
1060	0.999	0.999
700	0.999	0.997
660	0.998	0.996
620	0.998	0.995
580	0.999	0.996
546	0.998	0.996
500	0.996	0.991
460	0.992	0.981
436	0.987	0.967
420	0.977	0.940
405	0.954	0.890
400	0.940	0.860
390	0.890	0.750
380	0.770	0.520
370	0.500	0.180
365	0.300	0.050
350	0.000	0.000
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  41/36

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2020
$P_{C,s}$	0.4588
$P_{d,C}$	0.2871
$P_{e,d}$	0.2359
$P_{g,F}$	0.6102
$P_{i,h}$	1.0316

### Relative Partial Dispersion P'

$P'_{s,t}$	0.1986
$P'_{C,s}$	0.4950
$P'_{d,C'}$	0.2384
$P'_{e,d}$	0.2319
$P'_{g,F'}$	0.5393
$P'_{i,h}$	1.0143

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0048
$\Delta P_{C,s}$	-0.0033
$\Delta P_{F,e}$	0.0020
$\Delta P_{g,F}$	0.0092
$\Delta P_{i,g}$	0.0669

### Chemical Properties

CR	2
FR	3
SR	51.3
AR	2.3
PR	3.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.0
$T_g$ [°C]	423
$T_{10}^{13}$ [°C]	410
$T_{10}^{7.6}$ [°C]	538
$c_p$ [J/(g·K)]	0.389
$\lambda$ [W/(m·K)]	0.673
$\rho$ [g/cm <sup>3</sup> ]	5.18
$E$ [ $10^3$ N/mm <sup>2</sup> ]	55
$\mu$	0.244
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	0.65
$HK_{0.1/20}$	370
HG	1



## SF10 728284.428

$n_d = 1.72825$   
 $n_e = 1.73430$

$v_d = 28.41$   
 $v_e = 28.19$

$n_F - n_C = 0.025633$   
 $n_{F'} - n_{C'} = 0.026051$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.68218
$n_{1970.1}$	1970.1	1.68750
$n_{1529.6}$	1529.6	1.69378
$n_{1060.0}$	1060.0	1.70227
$n_t$	1014.0	1.70345
$n_s$	852.1	1.70887
$n_r$	706.5	1.71681
$n_C$	656.3	1.72085
$n_{C'}$	643.8	1.72200
$n_{632.8}$	632.8	1.72309
$n_D$	589.3	1.72803
$n_d$	587.6	1.72825
$n_e$	546.1	1.73430
$n_F$	486.1	1.74648
$n_{F'}$	480.0	1.74805
$n_g$	435.8	1.76198
$n_h$	404.7	1.77579
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.616259770
$B_2$	0.259229334
$B_3$	1.077623170
$C_1$	0.012753456
$C_2$	0.0581983954
$C_3$	116.60768000

### Constants of Formula for $dn/dT$

$D_0$	5.31E-06
$D_1$	1.59E-08
$D_2$	-4.07E-11
$E_0$	1.28E-06
$E_1$	1.32E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.270

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.8	7.3	10.3	2.5	4.9	7.9
+20/+40	5.3	8.1	11.6	3.8	6.6	10.0
+60/+80	5.6	8.6	12.4	4.4	7.4	11.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.860	0.690
2325	0.900	0.760
1970	0.967	0.920
1530	0.995	0.987
1060	0.999	0.997
700	0.998	0.995
660	0.997	0.993
620	0.997	0.993
580	0.998	0.995
546	0.998	0.995
500	0.996	0.989
460	0.991	0.978
436	0.984	0.961
420	0.967	0.920
405	0.910	0.790
400	0.860	0.690
390	0.670	0.370
380	0.360	0.060
370	0.080	
365	0.020	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  41/37

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2111
$P_{C,s}$	0.4674
$P_{d,C}$	0.2888
$P_{e,d}$	0.2361
$P_{g,F}$	0.6046
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2077
$P'_{C,s}$	0.5042
$P'_{d,C'}$	0.2399
$P'_{e,d}$	0.2323
$P'_{g,F'}$	0.5346
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0012
$\Delta P_{C,s}$	-0.0017
$\Delta P_{F,e}$	0.0017
$\Delta P_{g,F}$	0.0085
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1.2
PR	2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.5
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.4
$T_g$ [°C]	454
$T_{10}^{13}$ [°C]	445
$T_{10}^{7.6}$ [°C]	595
$c_p$ [J/(g·K)]	0.465
$\lambda$ [W/(m·K)]	0.741
$\rho$ [g/cm <sup>3</sup> ]	4.28
$E$ [ $10^3$ N/mm <sup>2</sup> ]	64
$\mu$	0.232
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.95
$HK_{0.1/20}$	430
HG	1

## SF11 785258.474

$n_d = 1.78472$   
 $n_e = 1.79190$

$v_d = 25.76$   
 $v_e = 25.55$

$n_F - n_C = 0.030467$   
 $n_{F'} - n_{C'} = 0.030997$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.73294
$n_{1970.1}$	1970.1	1.73843
$n_{1529.6}$	1529.6	1.74506
$n_{1060.0}$	1060.0	1.75445
$n_t$	1014.0	1.75579
$n_s$	852.1	1.76200
$n_r$	706.5	1.77125
$n_C$	656.3	1.77599
$n_{C'}$	643.8	1.77734
$n_{632.8}$	632.8	1.77862
$n_D$	589.3	1.78446
$n_d$	587.6	1.78472
$n_e$	546.1	1.79190
$n_F$	486.1	1.80645
$n_{F'}$	480.0	1.80834
$n_g$	435.8	1.82518
$n_h$	404.7	1.84208
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.738484030
$B_2$	0.311168974
$B_3$	1.174908710
$C_1$	0.013606860
$C_2$	0.0615960463
$C_3$	121.92271100

### Constants of Formula for $dn/dT$

$D_0$	1.12E-05
$D_1$	1.81E-08
$D_2$	-5.03E-11
$E_0$	1.46E-06
$E_1$	1.58E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.282

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	8.4	11.7	15.8	6.1	9.2	13.3
+20/+40	9.2	12.9	17.6	7.7	11.3	16.0
+60/+80	9.6	13.6	18.7	8.4	12.4	17.4

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.820	0.610
2325	0.870	0.700
1970	0.971	0.930
1530	0.993	0.982
1060	0.999	0.997
700	0.997	0.993
660	0.996	0.991
620	0.996	0.991
580	0.996	0.991
546	0.996	0.989
500	0.990	0.976
460	0.976	0.940
436	0.940	0.860
420	0.870	0.700
405	0.650	0.340
400	0.530	0.200
390	0.180	0.010
380		
370		
365		
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  44/39

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2039
$P_{C,s}$	0.4590
$P_{d,C}$	0.2866
$P_{e,d}$	0.2356
$P_{g,F}$	0.6147
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2004
$P'_{C,s}$	0.4949
$P'_{d,C'}$	0.2380
$P'_{e,d}$	0.2316
$P'_{g,F'}$	0.5433
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0043
$\Delta P_{C,s}$	-0.0040
$\Delta P_{F,e}$	0.0029
$\Delta P_{g,F}$	0.0142
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	0
SR	1
AR	1.2
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.1
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.8
$T_g$ [°C]	503
$T_{10}^{13}$ [°C]	500
$T_{10}^{7.6}$ [°C]	635
$c_p$ [J/(g·K)]	0.431
$\lambda$ [W/(m·K)]	0.737
$\rho$ [g/cm <sup>3</sup> ]	4.74
$E$ [ $10^3$ N/mm <sup>2</sup> ]	66
$\mu$	0.235
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.33
$HK_{0.1/20}$	450
HG	1

## SF56A 785261.492

$n_d = 1.78470$

$v_d = 26.08$

$n_F - n_C = 0.030092$

$n_e = 1.79180$

$v_e = 25.87$

$n_F - n_C = 0.030603$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.73406
$n_{1970.1}$	1970.1	1.73925
$n_{1529.6}$	1529.6	1.74559
$n_{1060.0}$	1060.0	1.75473
$n_t$	1014.0	1.75606
$n_s$	852.1	1.76220
$n_r$	706.5	1.77136
$n_C$	656.3	1.77605
$n_{C'}$	643.8	1.77740
$n_{632.8}$	632.8	1.77866
$n_D$	589.3	1.78444
$n_d$	587.6	1.78470
$n_e$	546.1	1.79180
$n_F$	486.1	1.80615
$n_{F'}$	480.0	1.80800
$n_g$	435.8	1.82449
$n_h$	404.7	1.84092
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.705792590
$B_2$	0.344223052
$B_3$	1.096018280
$C_1$	0.013387470
$C_2$	0.0579561608
$C_3$	121.61602400

### Constants of Formula for $dn/dT$

$D_0$	6.02E-06
$D_1$	1.70E-08
$D_2$	-2.61E-11
$E_0$	1.63E-06
$E_1$	1.59E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.269

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	5.6	9.0	13.1	3.3	6.6	10.6
+20/+40	6.2	10.0	14.7	4.7	8.5	13.1
+60/+80	6.6	10.7	15.8	5.5	9.5	14.5

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.870	0.700
2325	0.900	0.760
1970	0.967	0.920
1530	0.996	0.989
1060	0.999	0.997
700	0.998	0.995
660	0.997	0.993
620	0.998	0.994
580	0.998	0.994
546	0.998	0.994
500	0.996	0.989
460	0.990	0.974
436	0.980	0.950
420	0.959	0.900
405	0.900	0.760
400	0.860	0.680
390	0.700	0.410
380	0.400	0.100
370	0.120	0.010
365	0.040	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  42/37

### Remarks

lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2040
$P_{C,s}$	0.4605
$P_{d,C}$	0.2874
$P_{e,d}$	0.2359
$P_{g,F}$	0.6098
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2006
$P'_{C,s}$	0.4967
$P'_{d,C'}$	0.2387
$P'_{e,d}$	0.2319
$P'_{g,F'}$	0.5390
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0042
$\Delta P_{C,s}$	-0.0032
$\Delta P_{F,e}$	0.0021
$\Delta P_{g,F}$	0.0098
$\Delta P_{i,g}$	

### Chemical Properties

CR	1
FR	1
SR	3.2
AR	2.2
PR	3.2

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.9
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.8
$T_g$ [°C]	429
$T_{10}^{13}$ [°C]	426
$T_{10}^{7.6}$ [°C]	556
$c_p$ [J/(g·K)]	0.400
$\lambda$ [W/(m·K)]	0.690
$\rho$ [g/cm <sup>3</sup> ]	4.92
$E$ [ $10^3$ N/mm <sup>2</sup> ]	57
$\mu$	0.239
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.10
$HK_{0.1/20}$	380
HG	1

## SF57 847238.551

$n_d = 1.84666$

$v_d = 23.83$

$n_F - n_C = 0.035536$

$n_e = 1.85504$

$v_e = 23.64$

$n_F - n_C = 0.036166$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.79026
$n_{1970.1}$	1970.1	1.79539
$n_{1529.6}$	1529.6	1.80187
$n_{1060.0}$	1060.0	1.81185
$n_t$	1014.0	1.81335
$n_s$	852.1	1.82038
$n_r$	706.5	1.83102
$n_C$	656.3	1.83650
$n_{C'}$	643.8	1.83808
$n_{632.8}$	632.8	1.83957
$n_D$	589.3	1.84636
$n_d$	587.6	1.84666
$n_e$	546.1	1.85504
$n_F$	486.1	1.87204
$n_{F'}$	480.0	1.87425
$n_g$	435.8	1.89393
$n_h$	404.7	1.91366
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.816513710
$B_2$	0.428893641
$B_3$	1.071862780
$C_1$	0.014370420
$C_2$	0.0592801172
$C_3$	121.41994200

### Constants of Formula for $dn/dT$

$D_0$	7.26E-06
$D_1$	1.88E-08
$D_2$	-5.14E-11
$E_0$	1.96E-06
$E_1$	1.79E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.276

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.6	11.1	16.7	4.2	8.6	14.1
+20/+40	7.6	12.5	18.9	6.0	10.9	17.2
+60/+80	8.0	13.4	20.1	6.8	12.1	18.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.890	0.750
2325	0.910	0.790
1970	0.971	0.930
1530	0.996	0.991
1060	0.999	0.997
700	0.998	0.996
660	0.998	0.994
620	0.998	0.994
580	0.998	0.994
546	0.998	0.994
500	0.994	0.986
460	0.987	0.968
436	0.971	0.930
420	0.940	0.860
405	0.880	0.730
400	0.850	0.660
390	0.730	0.450
380	0.520	0.200
370	0.160	0.010
365	0.040	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  40/37

### Remarks

lead containing glass type  
suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.1976
$P_{C,s}$	0.4539
$P_{d,C}$	0.2859
$P_{e,d}$	0.2356
$P_{g,F}$	0.6160
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.1942
$P'_{C,s}$	0.4895
$P'_{d,C'}$	0.2373
$P'_{e,d}$	0.2315
$P'_{g,F'}$	0.5443
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0065
$\Delta P_{C,s}$	-0.0046
$\Delta P_{F,e}$	0.0026
$\Delta P_{g,F}$	0.0123
$\Delta P_{i,g}$	

### Chemical Properties

CR	2
FR	5
SR	52.3
AR	2.3
PR	4.3
SR-J	6
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.2
$T_g$ [°C]	414
$T_{10}^{13}$ [°C]	414
$T_{10}^{7.6}$ [°C]	507
$c_p$ [J/(g·K)]	0.360
$\lambda$ [W/(m·K)]	0.620
AT [°C]	449
$\rho$ [g/cm <sup>3</sup> ]	5.51
$E$ [ $10^3$ N/mm <sup>2</sup> ]	54
$\mu$	0.248
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	0.02
HK <sub>0.1/20</sub>	350
HG	1
Abrasion Aa	344

## SF57HTultra 847238.551

$n_d = 1.84666$

$v_d = 23.83$

$n_F - n_C = 0.035536$

$n_e = 1.85504$

$v_e = 23.64$

$n_F - n_C = 0.036166$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.79026
$n_{1970.1}$	1970.1	1.79539
$n_{1529.6}$	1529.6	1.80187
$n_{1060.0}$	1060.0	1.81185
$n_t$	1014.0	1.81335
$n_s$	852.1	1.82038
$n_r$	706.5	1.83102
$n_C$	656.3	1.83650
$n_{C'}$	643.8	1.83808
$n_{632.8}$	632.8	1.83957
$n_D$	589.3	1.84636
$n_d$	587.6	1.84666
$n_e$	546.1	1.85504
$n_F$	486.1	1.87204
$n_{F'}$	480.0	1.87425
$n_g$	435.8	1.89393
$n_h$	404.7	1.91366
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.816513710
$B_2$	0.428893641
$B_3$	1.071862780
$C_1$	0.014370420
$C_2$	0.0592801172
$C_3$	121.41994200

### Constants of Formula for $dn/dT$

$D_0$	7.26E-06
$D_1$	1.88E-08
$D_2$	-5.14E-11
$E_0$	1.96E-06
$E_1$	1.79E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.276

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.6	11.1	16.7	4.2	8.6	14.1
+20/+40	7.6	12.5	18.9	6.0	10.9	17.2
+60/+80	8.0	13.4	20.1	6.8	12.1	18.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.91	0.80
2325	0.93	0.84
1970	0.980	0.951
1530	0.998	0.994
1060	0.999	0.999
700	0.999	0.997
660	0.998	0.996
620	0.998	0.996
580	0.998	0.996
546	0.998	0.995
500	0.996	0.989
460	0.991	0.978
436	0.985	0.962
420	0.971	0.93
405	0.94	0.86
400	0.92	0.82
390	0.83	0.63
380	0.62	0.30
370	0.25	0.03
365	0.10	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{70} / \lambda_{50}$  39/36

### Remarks

lead containing glass type  
suitable for precision molding  
step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.1976
$P_{C,s}$	0.4539
$P_{d,C}$	0.2859
$P_{e,d}$	0.2356
$P_{g,F}$	0.6160
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.1942
$P'_{C,s}$	0.4895
$P'_{d,C'}$	0.2373
$P'_{e,d}$	0.2315
$P'_{g,F'}$	0.5443
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0065
$\Delta P_{C,s}$	-0.0046
$\Delta P_{F,e}$	0.0026
$\Delta P_{g,F}$	0.0123
$\Delta P_{i,g}$	

### Chemical Properties

CR	2
FR	5
SR	52.3
AR	2.3
PR	4.3
SR-J	6
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.2
$T_g$ [°C]	414
$T_{10}^{13}$ [°C]	414
$T_{10}^{7.6}$ [°C]	507
$c_p$ [J/(g·K)]	0.360
$\lambda$ [W/(m·K)]	0.620
AT [°C]	449
$\rho$ [g/cm <sup>3</sup> ]	5.51
E [ $10^3$ N/mm <sup>2</sup> ]	54
$\mu$	0.248
K [ $10^{-6}$ mm <sup>2</sup> /N]	0.02
HK <sub>0.1/20</sub>	350
HG	1
Abrasion Aa	344

## N-KZFS11 638424.320

$n_d = 1.63775$

$v_d = 42.41$

$n_F - n_C = 0.015038$

$n_e = 1.64132$

$v_e = 42.20$

$n_F - n_C = 0.015198$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.59699
$n_{1970.1}$	1970.1	1.60439
$n_{1529.6}$	1529.6	1.61223
$n_{1060.0}$	1060.0	1.62044
$n_t$	1014.0	1.62139
$n_s$	852.1	1.62540
$n_r$	706.5	1.63069
$n_C$	656.3	1.63324
$n_{C'}$	643.8	1.63395
$n_{632.8}$	632.8	1.63462
$n_D$	589.3	1.63762
$n_d$	587.6	1.63775
$n_e$	546.1	1.64132
$n_F$	486.1	1.64828
$n_{F'}$	480.0	1.64915
$n_g$	435.8	1.65670
$n_h$	404.7	1.66385
$n_i$	365.0	1.67636
$n_{334.1}$	334.1	1.69037
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.332224500
$B_2$	0.289241610
$B_3$	1.151617340
$C_1$	0.008402985
$C_2$	0.0344239720
$C_3$	88.43105320

### Constants of Formula for $dn/dT$

$D_0$	3.34E-06
$D_1$	1.16E-08
$D_2$	-1.80E-11
$E_0$	6.32E-07
$E_1$	7.21E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.206

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.5	4.4	5.4	1.3	2.2	3.1
+20/+40	3.5	4.6	5.7	2.1	3.1	4.2
+60/+80	3.6	4.8	6.0	2.5	3.7	4.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.510	0.180
2325	0.780	0.540
1970	0.965	0.910
1530	0.991	0.977
1060	0.999	0.999
700	0.998	0.994
660	0.997	0.992
620	0.997	0.992
580	0.997	0.992
546	0.997	0.993
500	0.996	0.989
460	0.993	0.982
436	0.991	0.978
420	0.990	0.975
405	0.988	0.971
400	0.987	0.968
390	0.983	0.957
380	0.976	0.940
370	0.963	0.910
365	0.950	0.880
350	0.880	0.730
334	0.730	0.450
320	0.470	0.150
310	0.230	0.020
300	0.050	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  36/30

### Remarks

suitable for precision molding

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2664
$P_{C,s}$	0.5212
$P_{d,C}$	0.3000
$P_{e,d}$	0.2377
$P_{g,F}$	0.5605
$P_{i,h}$	0.8319
<b>Relative Partial Dispersion P'</b>	
$P'_{s,t}$	0.2636
$P'_{C,s}$	0.5627
$P'_{d,C'}$	0.2499
$P'_{e,d}$	0.2352
$P'_{g,F'}$	0.4971
$P'_{i,h}$	0.8232

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0415
$\Delta P_{C,s}$	0.0194
$\Delta P_{F,e}$	-0.0039
$\Delta P_{g,F}$	-0.0120
$\Delta P_{i,g}$	-0.0617

### Chemical Properties

CR	1
FR	1
SR	3.4
AR	1
PR	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.6
$T_g$ [°C]	551
$T_{10}^{13}$ [°C]	554
$T_{10}^{7.6}$ [°C]	
$c_p$ [J/(g·K)]	0.690
$\lambda$ [W/(m·K)]	0.810
$\rho$ [g/cm <sup>3</sup> ]	3.20
$E$ [ $10^3$ N/mm <sup>2</sup> ]	79
$\mu$	0.251
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	4.21
$HK_{0.1/20}$	530
HG	3
Abrasion Aa	74

## N-KZFS2 558540.254

$n_d = 1.55836$

$v_d = 54.01$

$n_F - n_C = 0.010338$

$n_e = 1.56082$

$v_e = 53.83$

$n_F - n_C = 0.010418$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.52239
$n_{1970.1}$	1970.1	1.53011
$n_{1529.6}$	1529.6	1.53798
$n_{1060.0}$	1060.0	1.54546
$n_t$	1014.0	1.54625
$n_s$	852.1	1.54944
$n_r$	706.5	1.55337
$n_C$	656.3	1.55519
$n_{C'}$	643.8	1.55570
$n_{632.8}$	632.8	1.55617
$n_D$	589.3	1.55827
$n_d$	587.6	1.55836
$n_e$	546.1	1.56082
$n_F$	486.1	1.56553
$n_{F'}$	480.0	1.56612
$n_g$	435.8	1.57114
$n_h$	404.7	1.57580
$n_i$	365.0	1.58382
$n_{334.1}$	334.1	1.59259
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.236975540
$B_2$	0.153569376
$B_3$	0.903976272
$C_1$	0.007471705
$C_2$	0.0308053556
$C_3$	70.17310840

### Constants of Formula for $dn/dT$

$D_0$	6.77E-06
$D_1$	1.31E-08
$D_2$	-1.23E-11
$E_0$	3.84E-07
$E_1$	5.51E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.196

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.6	5.2	5.7	2.5	3.0	3.5
+20/+40	4.7	5.3	5.9	3.3	3.9	4.5
+60/+80	4.8	5.5	6.2	3.8	4.5	5.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.28	0.04
2325	0.58	0.26
1970	0.91	0.80
1530	0.976	0.94
1060	0.996	0.991
700	0.998	0.996
660	0.998	0.994
620	0.998	0.994
580	0.998	0.994
546	0.998	0.994
500	0.997	0.992
460	0.995	0.987
436	0.992	0.981
420	0.990	0.975
405	0.987	0.967
400	0.985	0.963
390	0.980	0.950
380	0.971	0.93
370	0.963	0.91
365	0.954	0.89
350	0.91	0.80
334	0.81	0.59
320	0.57	0.24
310	0.25	0.03
300	0.01	
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  34/30

### Remarks

suitable for precision molding

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.3080
$P_{C,s}$	0.5568
$P_{d,C}$	0.3061
$P_{e,d}$	0.2383
$P_{g,F}$	0.5419
$P_{i,h}$	0.7758
Relative Partial Dispersion P'	
$P'_{s,t}$	0.3056
$P'_{C,s}$	0.6011
$P'_{d,C'}$	0.2552
$P'_{e,d}$	0.2365
$P'_{g,F'}$	0.4814
$P'_{i,h}$	0.7699

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0636
$\Delta P_{C,s}$	0.0280
$\Delta P_{F,e}$	-0.0044
$\Delta P_{g,F}$	-0.0111
$\Delta P_{i,g}$	-0.0440

### Chemical Properties

CR	1
FR	4
SR	52.3
AR	4.3
PR	4.2
SR-J	6
WR-J	6

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	4.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	5.4
$T_g$ [°C]	482
$T_{10}^{13}$ [°C]	488
$T_{10}^{7.6}$ [°C]	590
$c_p$ [J/(g·K)]	0.830
$\lambda$ [W/(m·K)]	0.810
AT [°C]	533
$\rho$ [g/cm <sup>3</sup> ]	2.54
$E$ [ $10^3$ N/mm <sup>2</sup> ]	66
$\mu$	0.266
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.98
HK <sub>0.1/20</sub>	490
HG	3
Abrasion Aa	70

## N-KZFS4 613445.300

$n_d = 1.61336$   
 $n_e = 1.61664$

$v_d = 44.49$   
 $v_e = 44.27$

$n_F - n_C = 0.013785$   
 $n_{F'} - n_{C'} = 0.013929$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.57535
$n_{1970.1}$	1970.1	1.58233
$n_{1529.6}$	1529.6	1.58971
$n_{1060.0}$	1060.0	1.59739
$n_t$	1014.0	1.59828
$n_s$	852.1	1.60199
$n_r$	706.5	1.60688
$n_C$	656.3	1.60922
$n_{C'}$	643.8	1.60987
$n_{632.8}$	632.8	1.61049
$n_D$	589.3	1.61324
$n_d$	587.6	1.61336
$n_e$	546.1	1.61664
$n_F$	486.1	1.62300
$n_{F'}$	480.0	1.62380
$n_g$	435.8	1.63071
$n_h$	404.7	1.63723
$n_i$	365.0	1.64865
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.350554240
$B_2$	0.197575506
$B_3$	1.099629920
$C_1$	0.008762821
$C_2$	0.0371767201
$C_3$	90.38669940

### Constants of Formula for $dn/dT$

$D_0$	1.81E-06
$D_1$	1.16E-08
$D_2$	-7.99E-12
$E_0$	6.20E-07
$E_1$	7.94E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.205

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.7	3.5	4.4	0.5	1.3	2.2
+20/+40	2.7	3.7	4.7	1.3	2.3	3.2
+60/+80	2.8	3.9	5.0	1.7	2.8	3.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.510	0.190
2325	0.750	0.490
1970	0.951	0.880
1530	0.984	0.961
1060	0.998	0.996
700	0.998	0.994
660	0.997	0.993
620	0.997	0.992
580	0.997	0.993
546	0.997	0.992
500	0.995	0.987
460	0.990	0.976
436	0.987	0.968
420	0.984	0.961
405	0.981	0.952
400	0.979	0.950
390	0.971	0.930
380	0.963	0.910
370	0.940	0.860
365	0.920	0.820
350	0.820	0.600
334	0.470	0.150
320	0.040	
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  36/32

### Remarks

suitable for precision molding

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2694
$P_{C,s}$	0.5240
$P_{d,C}$	0.3006
$P_{e,d}$	0.2378
$P_{g,F}$	0.5590
$P_{i,h}$	0.8284

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2666
$P'_{C,s}$	0.5657
$P'_{d,C'}$	0.2503
$P'_{e,d}$	0.2353
$P'_{g,F'}$	0.4958
$P'_{i,h}$	0.8199

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0373
$\Delta P_{C,s}$	0.0173
$\Delta P_{F,e}$	-0.0033
$\Delta P_{g,F}$	-0.0100
$\Delta P_{i,g}$	-0.0496

### Chemical Properties

CR	1
FR	1
SR	3.4
AR	1.2
PR	1
SR-J	6
WR-J	4

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.2
$T_g$ [°C]	536
$T_{10}^{13}$ [°C]	541
$T_{10}^{7.6}$ [°C]	664
$c_p$ [J/(g·K)]	0.760
$\lambda$ [W/(m·K)]	0.840
AT [°C]	597
$\rho$ [g/cm <sup>3</sup> ]	3.00
$E$ [ $10^3$ N/mm <sup>2</sup> ]	78
$\mu$	0.241
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.90
HK <sub>0.1/20</sub>	520
HG	3
Abrasion Aa	130



## N-KZFS4HT 613445.300

$n_d = 1.61336$

$v_d = 44.49$

$n_F - n_C = 0.013785$

$n_e = 1.61664$

$v_e = 44.27$

$n_F - n_C = 0.013929$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.57535
$n_{1970.1}$	1970.1	1.58233
$n_{1529.6}$	1529.6	1.58971
$n_{1060.0}$	1060.0	1.59739
$n_t$	1014.0	1.59828
$n_s$	852.1	1.60199
$n_r$	706.5	1.60688
$n_C$	656.3	1.60922
$n_{C'}$	643.8	1.60987
$n_{632.8}$	632.8	1.61049
$n_D$	589.3	1.61324
$n_d$	587.6	1.61336
$n_e$	546.1	1.61664
$n_F$	486.1	1.62300
$n_{F'}$	480.0	1.62380
$n_g$	435.8	1.63071
$n_h$	404.7	1.63723
$n_i$	365.0	1.64865
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.350554240
$B_2$	0.197575506
$B_3$	1.099629920
$C_1$	0.008762821
$C_2$	0.0371767201
$C_3$	90.38669940

### Constants of Formula for $dn/dT$

$D_0$	1.81E-06
$D_1$	1.16E-08
$D_2$	-7.99E-12
$E_0$	6.20E-07
$E_1$	7.94E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.205

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.7	3.5	4.4	0.5	1.3	2.2
+20/+40	2.7	3.7	4.7	1.3	2.3	3.2
+60/+80	2.8	3.9	5.0	1.7	2.8	3.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.510	0.190
2325	0.750	0.490
1970	0.951	0.880
1530	0.984	0.961
1060	0.999	0.999
700	0.998	0.994
660	0.997	0.993
620	0.997	0.992
580	0.997	0.993
546	0.997	0.993
500	0.995	0.988
460	0.992	0.980
436	0.990	0.975
420	0.988	0.971
405	0.986	0.966
400	0.985	0.962
390	0.980	0.951
380	0.973	0.930
370	0.959	0.900
365	0.950	0.870
350	0.870	0.700
334	0.550	0.220
320	0.060	0.000
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  36/32

### Remarks

suitable for precision molding

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2694
$P_{C,s}$	0.5240
$P_{d,C}$	0.3006
$P_{e,d}$	0.2378
$P_{g,F}$	0.5590
$P_{i,h}$	0.8284

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2666
$P'_{C,s}$	0.5657
$P'_{d,C'}$	0.2503
$P'_{e,d}$	0.2353
$P'_{g,F'}$	0.4958
$P'_{i,h}$	0.8199

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0373
$\Delta P_{C,s}$	0.0173
$\Delta P_{F,e}$	-0.0033
$\Delta P_{g,F}$	-0.0100
$\Delta P_{i,g}$	-0.0496

### Chemical Properties

CR	1
FR	1
SR	3.4
AR	1.2
PR	1
SR-J	6
WR-J	4

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.2
$T_g$ [°C]	536
$T_{10}^{13}$ [°C]	541
$T_{10}^{7.6}$ [°C]	664
$c_p$ [J/(g·K)]	0.760
$\lambda$ [W/(m·K)]	0.840
AT [°C]	597
$\rho$ [g/cm <sup>3</sup> ]	3.00
$E$ [ $10^3$ N/mm <sup>2</sup> ]	78
$\mu$	0.241
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.90
HK <sub>0.1/20</sub>	520
HG	3
Abrasion Aa	130

## N-KZFS5 654397.304

$n_d = 1.65412$

$v_d = 39.70$

$n_F - n_C = 0.016477$

$n_e = 1.65803$

$v_e = 39.46$

$n_F - n_C = 0.016675$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.61392
$n_{1970.1}$	1970.1	1.62058
$n_{1529.6}$	1529.6	1.62780
$n_{1060.0}$	1060.0	1.63577
$n_t$	1014.0	1.63673
$n_s$	852.1	1.64087
$n_r$	706.5	1.64649
$n_C$	656.3	1.64922
$n_{C'}$	643.8	1.65000
$n_{632.8}$	632.8	1.65072
$n_D$	589.3	1.65398
$n_d$	587.6	1.65412
$n_e$	546.1	1.65803
$n_F$	486.1	1.66570
$n_{F'}$	480.0	1.66667
$n_g$	435.8	1.67511
$n_h$	404.7	1.68318
$n_i$	365.0	1.69756
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.474607890
$B_2$	0.193584488
$B_3$	1.265899740
$C_1$	0.009861438
$C_2$	0.0445477583
$C_3$	106.43625800

### Constants of Formula for $dn/dT$

$D_0$	4.54E-06
$D_1$	1.19E-08
$D_2$	2.93E-12
$E_0$	6.89E-07
$E_1$	8.60E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.230

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	4.2	5.3	6.5	2.0	3.1	4.2
+20/+40	4.2	5.5	6.8	2.8	4.0	5.4
+60/+80	4.4	5.8	7.3	3.3	4.7	6.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.66	0.35
2325	0.83	0.62
1970	0.963	0.91
1530	0.988	0.970
1060	0.999	0.998
700	0.998	0.994
660	0.997	0.992
620	0.997	0.992
580	0.997	0.993
546	0.997	0.992
500	0.994	0.985
460	0.990	0.974
436	0.986	0.965
420	0.983	0.958
405	0.978	0.95
400	0.976	0.94
390	0.967	0.92
380	0.950	0.88
370	0.93	0.83
365	0.91	0.79
350	0.79	0.56
334	0.37	0.08
320	0.02	0.00
310	0.00	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  37/32

### Remarks

suitable for precision molding

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2511
$P_{C,s}$	0.5070
$P_{d,C}$	0.2972
$P_{e,d}$	0.2374
$P_{g,F}$	0.5710
$P_{i,h}$	0.8729

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2481
$P'_{C,s}$	0.5473
$P'_{d,C'}$	0.2474
$P'_{e,d}$	0.2345
$P'_{g,F'}$	0.5060
$P'_{i,h}$	0.8625

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0248
$\Delta P_{C,s}$	0.0115
$\Delta P_{F,e}$	-0.0021
$\Delta P_{g,F}$	-0.0060
$\Delta P_{i,g}$	-0.0286

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1
SR-J	1
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.4
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.4
$T_g$ [°C]	584
$T_{10}^{13}$ [°C]	593
$T_{10}^{7.6}$ [°C]	739
$c_p$ [J/(g·K)]	0.730
$\lambda$ [W/(m·K)]	0.950
AT [°C]	648
$\rho$ [g/cm <sup>3</sup> ]	3.04
$E$ [ $10^3$ N/mm <sup>2</sup> ]	89
$\mu$	0.243
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	3.53
HK <sub>0.1/20</sub>	555
Abrasion Aa	122

## N-KZFS8 720347.320

$n_d = 1.72047$   
 $n_e = 1.72539$

$v_d = 34.70$   
 $v_e = 34.47$

$n_F - n_C = 0.020763$   
 $n_{F'} - n_{C'} = 0.021046$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.67524
$n_{1970.1}$	1970.1	1.68193
$n_{1529.6}$	1529.6	1.68939
$n_{1060.0}$	1060.0	1.69816
$n_t$	1014.0	1.69927
$n_s$	852.1	1.70416
$n_r$	706.5	1.71099
$n_C$	656.3	1.71437
$n_{C'}$	643.8	1.71532
$n_{632.8}$	632.8	1.71622
$n_D$	589.3	1.72029
$n_d$	587.6	1.72047
$n_e$	546.1	1.72539
$n_F$	486.1	1.73513
$n_{F'}$	480.0	1.73637
$n_g$	435.8	1.74724
$n_h$	404.7	1.75777
$n_i$	365.0	1.77690
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.626936510
$B_2$	0.243698760
$B_3$	1.620071410
$C_1$	0.010880863
$C_2$	0.0494207753
$C_3$	131.00916300

### Constants of Formula for $dn/dT$

$D_0$	7.93E-07
$D_1$	6.47E-09
$D_2$	-5.00E-12
$E_0$	7.71E-07
$E_1$	1.01E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.254

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.7	4.1	5.6	0.4	1.7	3.2
+20/+40	2.4	4.0	5.8	0.9	2.5	4.2
+60/+80	2.4	4.1	6.1	1.2	2.9	4.9

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.760	0.510
2325	0.870	0.700
1970	0.967	0.920
1530	0.993	0.983
1060	0.999	0.999
700	0.998	0.996
660	0.998	0.995
620	0.998	0.995
580	0.998	0.995
546	0.997	0.993
500	0.994	0.985
460	0.988	0.971
436	0.982	0.955
420	0.976	0.940
405	0.967	0.920
400	0.963	0.910
390	0.950	0.870
380	0.920	0.820
370	0.890	0.740
365	0.860	0.680
350	0.670	0.360
334	0.140	0.010
320	0.040	0.000
310	0.000	
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  38/33

### Remarks

suitable for precision molding

step 0.5 available

### Relative Partial Dispersion P

$P_{s,t}$	0.2353
$P_{C,s}$	0.4916
$P_{d,C}$	0.2940
$P_{e,d}$	0.2369
$P_{g,F}$	0.5833
$P_{i,h}$	0.9212

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2322
$P'_{C,s}$	0.5305
$P'_{d,C'}$	0.2445
$P'_{e,d}$	0.2337
$P'_{g,F'}$	0.5165
$P'_{i,h}$	0.9088

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0173
$\Delta P_{C,s}$	0.0078
$\Delta P_{F,e}$	-0.0011
$\Delta P_{g,F}$	-0.0021
$\Delta P_{i,g}$	-0.0048

### Chemical Properties

CR	1
FR	0
SR	1
AR	1
PR	1
SR-J	1
WR-J	1

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.4
$T_g$ [°C]	509
$T_{10}^{13}$ [°C]	515
$T_{10}^{7.6}$ [°C]	635
$c_p$ [J/(g·K)]	0.760
$\lambda$ [W/(m·K)]	1.050
AT [°C]	561
$\rho$ [g/cm <sup>3</sup> ]	3.20
E [10 <sup>3</sup> N/mm <sup>2</sup> ]	103
$\mu$	0.248
K [10 <sup>-6</sup> mm <sup>2</sup> /N]	2.94
HK <sub>0.1/20</sub>	570
HG	4
Abrasion Aa	152

## BK7G18 520636.252

$n_d = 1.51975$

$v_d = 63.58$

$n_F - n_C = 0.008174$

$n_e = 1.52170$

$v_e = 63.36$

$n_F - n_C = 0.008233$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.49203
$n_{1970.1}$	1970.1	1.49777
$n_{1529.6}$	1529.6	1.50373
$n_{1060.0}$	1060.0	1.50953
$n_t$	1014.0	1.51015
$n_s$	852.1	1.51267
$n_r$	706.5	1.51579
$n_C$	656.3	1.51724
$n_{C'}$	643.8	1.51764
$n_{632.8}$	632.8	1.51802
$n_D$	589.3	1.51968
$n_d$	587.6	1.51975
$n_e$	546.1	1.52170
$n_F$	486.1	1.52541
$n_{F'}$	480.0	1.52587
$n_g$	435.8	1.52981
$n_h$	404.7	1.53345
$n_i$	365.0	1.53970
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.265385420
$B_2$	0.014419107
$B_3$	1.003230280
$C_1$	0.008131041
$C_2$	0.0543303226
$C_3$	102.82116600

### Constants of Formula for $dn/dT$

$D_0$	1.52E-06
$D_1$	1.37E-08
$D_2$	-1.26E-11
$E_0$	4.36E-07
$E_1$	4.17E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.194

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.2	2.7	3.3	0.2	0.7	1.2
+20/+40	2.2	2.8	3.4	0.9	1.5	2.1
+60/+80	2.4	3.0	3.7	1.4	2.0	2.6

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.630	0.320
2325	0.780	0.540
1970	0.930	0.840
1530	0.992	0.979
1060	0.999	0.998
700	0.997	0.993
660	0.995	0.988
620	0.994	0.984
580	0.992	0.979
546	0.989	0.973
500	0.982	0.957
460	0.970	0.930
436	0.950	0.870
420	0.910	0.780
405	0.820	0.600
400	0.760	0.510
390	0.600	0.280
380	0.360	0.080
370	0.080	
365	0.020	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  41/37

### Remarks

radiation resistant glass

### Relative Partial Dispersion P

$P_{s,t}$	0.3077
$P_{C,s}$	0.5591
$P_{d,C}$	0.3071
$P_{e,d}$	0.2385
$P_{g,F}$	0.5376
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.3055
$P'_{C,s}$	0.6040
$P'_{d,C'}$	0.2561
$P'_{e,d}$	0.2368
$P'_{g,F'}$	0.4777
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	0.0203
$\Delta P_{C,s}$	0.0080
$\Delta P_{F,e}$	-0.0006
$\Delta P_{g,F}$	0.0007
$\Delta P_{i,g}$	

### Chemical Properties

CR	
FR	0
SR	1
AR	2
PR	

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.2
$T_g$ [°C]	585
$T_{10}^{13}$ [°C]	570
$T_{10}^{7.6}$ [°C]	722
$c_p$ [J/(g·K)]	0.820
$\lambda$ [W/(m·K)]	1.190
$\rho$ [g/cm <sup>3</sup> ]	2.52
$E$ [ $10^3$ N/mm <sup>2</sup> ]	82
$\mu$	0.205
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.77
$HK_{0.1/20}$	580

## F2G12 621366.361

$n_d = 1.62072$

$v_d = 36.56$

$n_F - n_C = 0.016979$

$n_e = 1.62474$

$v_e = 36.30$

$n_F - n_C = 0.017212$

Refractive Indices		
	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.58584
$n_{1970.1}$	1970.1	1.59051
$n_{1529.6}$	1529.6	1.59593
$n_{1060.0}$	1060.0	1.60265
$n_t$	1014.0	1.60353
$n_s$	852.1	1.60744
$n_r$	706.5	1.61298
$n_C$	656.3	1.61573
$n_{C'}$	643.8	1.61652
$n_{632.8}$	632.8	1.61725
$n_D$	589.3	1.62057
$n_d$	587.6	1.62072
$n_e$	546.1	1.62474
$n_F$	486.1	1.63271
$n_{F'}$	480.0	1.63373
$n_g$	435.8	1.64261
$n_h$	404.7	1.65121
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

Constants of Dispersion Formula	
$B_1$	1.347022240
$B_2$	0.210037763
$B_3$	19.535076800
$C_1$	0.009808506
$C_2$	0.0471788018
$C_3$	2279.15470000

Constants of Formula for $dn/dT$	
$D_0$	2.19E-06
$D_1$	1.62E-08
$D_2$	-2.20E-11
$E_0$	9.55E-07
$E_1$	8.12E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.250

Temperature Coefficients of the Refractive Index						
[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	2.7	4.3	6.0	0.6	2.1	3.8
+20/+40	3.1	4.8	6.7	1.7	3.3	5.2
+60/+80	3.3	5.2	7.2	2.3	4.1	6.1

Internal Transmittance $\tau_i$		
$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.84	0.65
2325	0.89	0.74
1970	0.959	0.90
1530	0.996	0.989
1060	0.999	0.997
700	0.995	0.988
660	0.994	0.984
620	0.992	0.979
580	0.989	0.972
546	0.981	0.953
500	0.967	0.92
460	0.92	0.81
436	0.80	0.58
420	0.62	0.30
405	0.35	0.07
400	0.25	0.03
390	0.12	0.00
380	0.02	
370	0.00	
365		
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

Color Code	
$\lambda_{80} / \lambda_5$	46/39

Remarks
radiation resistant glass
lead containing glass type

Relative Partial Dispersion P	
$P_{s,t}$	0.2303
$P_{C,s}$	0.4883
$P_{d,C}$	0.2937
$P_{e,d}$	0.2369
$P_{g,F}$	0.5831
$P_{i,h}$	

Relative Partial Dispersion P'	
$P'_{s,t}$	0.2272
$P'_{C,s}$	0.5271
$P'_{d,C'}$	0.2443
$P'_{e,d}$	0.2337
$P'_{g,F'}$	0.5163
$P'_{i,h}$	

Deviation of Rel. Partial Disp. $\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0002
$\Delta P_{C,s}$	0.0002
$\Delta P_{F,e}$	0.0002
$\Delta P_{g,F}$	0.0008
$\Delta P_{i,g}$	

Chemical Properties	
CR	1
FR	0
SR	1
AR	1.3
PR	2.3

Other Properties	
$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.6
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.3
$T_g$ [°C]	435
$T_{10}^{13}$ [°C]	438
$T_{10}^{7.6}$ [°C]	612
$c_p$ [J/(g·K)]	0.530
$\lambda$ [W/(m·K)]	0.820
$\rho$ [g/cm <sup>3</sup> ]	3.61
$E$ [ $10^3$ N/mm <sup>2</sup> ]	58
$\mu$	0.222
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.79
$HK_{0.1/20}$	411

## K5G20 523568.259

$n_d = 1.52344$   
 $n_e = 1.52564$

$v_d = 56.76$   
 $v_e = 56.47$

$n_F - n_C = 0.009222$   
 $n_{F'} - n_{C'} = 0.009308$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.49784
$n_{1970.1}$	1970.1	1.50236
$n_{1529.6}$	1529.6	1.50730
$n_{1060.0}$	1060.0	1.51258
$n_t$	1014.0	1.51319
$n_s$	852.1	1.51573
$n_r$	706.5	1.51906
$n_C$	656.3	1.52065
$n_{C'}$	643.8	1.52109
$n_{632.8}$	632.8	1.52151
$n_D$	589.3	1.52336
$n_d$	587.6	1.52344
$n_e$	546.1	1.52564
$n_F$	486.1	1.52987
$n_{F'}$	480.0	1.53040
$n_g$	435.8	1.53494
$n_h$	404.7	1.53919
$n_i$	365.0	1.54651
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.140943960
$B_2$	0.145001190
$B_3$	37.470578600
$C_1$	0.006949455
$C_2$	0.0310574444
$C_3$	4536.25624000

### Constants of Formula for $dn/dT$

$D_0$	-2.22E-06
$D_1$	8.45E-09
$D_2$	-3.31E-11
$E_0$	5.44E-07
$E_1$	4.95E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.214

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	0.8	1.5	2.2	-1.2	-0.6	0.1
+20/+40	0.6	1.4	2.1	-0.7	0.1	0.8
+60/+80	0.6	1.4	2.2	-0.5	0.3	1.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.630	0.320
2325	0.730	0.460
1970	0.900	0.760
1530	0.990	0.976
1060	0.998	0.995
700	0.997	0.992
660	0.995	0.987
620	0.994	0.985
580	0.993	0.982
546	0.990	0.976
500	0.984	0.961
460	0.971	0.930
436	0.954	0.890
420	0.920	0.820
405	0.860	0.680
400	0.820	0.610
390	0.690	0.390
380	0.440	0.130
370	0.130	0.000
365	0.030	
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_{5}$  41/37

### Remarks

radiation resistant glass  
lead containing glass type

### Relative Partial Dispersion P

$P_{s,t}$	0.2764
$P_{C,s}$	0.5327
$P_{d,C}$	0.3027
$P_{e,d}$	0.2382
$P_{g,F}$	0.5500
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2738
$P'_{C,s}$	0.5755
$P'_{d,C'}$	0.2523
$P'_{e,d}$	0.2360
$P'_{g,F'}$	0.4881
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0051
$\Delta P_{C,s}$	-0.0025
$\Delta P_{F,e}$	0.0005
$\Delta P_{g,F}$	0.0017
$\Delta P_{i,g}$	

### Chemical Properties

CR	
FR	0
SR	1
AR	1
PR	

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	9.0
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.3
$T_g$ [°C]	483
$T_{10}^{13}$ [°C]	501
$T_{10}^{7.6}$ [°C]	679
$c_p$ [J/(g·K)]	0.790
$\lambda$ [W/(m·K)]	1.000
$\rho$ [g/cm <sup>3</sup> ]	2.59
$E$ [ $10^3$ N/mm <sup>2</sup> ]	68
$\mu$	0.222
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	
HK <sub>0.1/20</sub>	510

## LAK9G15 691548.353

$n_d = 1.69064$

$v_d = 54.76$

$n_F - n_C = 0.012612$

$n_e = 1.69364$

$v_e = 54.53$

$n_F - n_C = 0.012721$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.65362
$n_{1970.1}$	1970.1	1.66043
$n_{1529.6}$	1529.6	1.66783
$n_{1060.0}$	1060.0	1.67552
$n_t$	1014.0	1.67639
$n_s$	852.1	1.67999
$n_r$	706.5	1.68462
$n_C$	656.3	1.68680
$n_{C'}$	643.8	1.68741
$n_{632.8}$	632.8	1.68798
$n_D$	589.3	1.69052
$n_d$	587.6	1.69064
$n_e$	546.1	1.69364
$n_F$	486.1	1.69941
$n_{F'}$	480.0	1.70013
$n_g$	435.8	1.70630
$n_h$	404.7	1.71205
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.287736670
$B_2$	0.518244853
$B_3$	26.175610900
$C_1$	0.005575419
$C_2$	0.0223679524
$C_3$	1892.25330000

### Constants of Formula for $dn/dT$

$D_0$	2.19E-06
$D_1$	1.16E-08
$D_2$	-7.71E-12
$E_0$	4.82E-07
$E_1$	4.50E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.193

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	3.0	3.8	4.5	0.7	1.5	2.1
+20/+40	3.0	3.9	4.7	1.5	2.4	3.2
+60/+80	3.2	4.1	5.0	2.0	2.9	3.8

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.480	0.160
2325	0.750	0.490
1970	0.963	0.910
1530	0.995	0.987
1060	0.998	0.996
700	0.994	0.986
660	0.993	0.982
620	0.991	0.978
580	0.989	0.973
546	0.985	0.964
500	0.971	0.930
460	0.920	0.810
436	0.800	0.570
420	0.630	0.320
405	0.380	0.090
400	0.290	0.040
390	0.120	0.010
380	0.030	0.000
370		
365		
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  46/38

### Remarks

lead containing glass type  
total allowable cross section of  
bubbles: 0,1mm<sup>2</sup> per 100 ccm

### Relative Partial Dispersion P

$P_{s,t}$	0.2852
$P_{C,s}$	0.5400
$P_{d,C}$	0.3040
$P_{e,d}$	0.2383
$P_{g,F}$	0.5462
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2828
$P'_{C,s}$	0.5834
$P'_{d,C'}$	0.2533
$P'_{e,d}$	0.2362
$P'_{g,F'}$	0.4849
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

$\Delta P$ from the normal line	
$\Delta P_{C,t}$	0.0205
$\Delta P_{C,s}$	0.0095
$\Delta P_{F,e}$	-0.0018
$\Delta P_{g,F}$	-0.0055
$\Delta P_{i,g}$	

### Chemical Properties

CR	44593
FR	2
SR	53
AR	1.3
PR	4.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	6.3
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.6
$T_g$ [°C]	634
$T_{10}^{13}$ [°C]	635
$T_{10}^{7.6}$ [°C]	710
$c_p$ [J/(g·K)]	0.660
$\lambda$ [W/(m·K)]	0.880
$\rho$ [g/cm <sup>3</sup> ]	3.53
$E$ [ $10^3$ N/mm <sup>2</sup> ]	108
$\mu$	0.288
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	1.86
$HK_{0.1/20}$	721

## LF5G19 597399.330

$n_d = 1.59655$   
 $n_e = 1.60010$

$v_d = 39.89$   
 $v_e = 39.60$

$n_F - n_C = 0.014954$   
 $n_{F'} - n_{C'} = 0.015153$

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.56416
$n_{1970.1}$	1970.1	1.56890
$n_{1529.6}$	1529.6	1.57419
$n_{1060.0}$	1060.0	1.58045
$n_t$	1014.0	1.58125
$n_s$	852.1	1.58477
$n_r$	706.5	1.58970
$n_C$	656.3	1.59214
$n_{C'}$	643.8	1.59284
$n_{632.8}$	632.8	1.59349
$n_D$	589.3	1.59642
$n_d$	587.6	1.59655
$n_e$	546.1	1.60010
$n_F$	486.1	1.60710
$n_{F'}$	480.0	1.60799
$n_g$	435.8	1.61578
$n_h$	404.7	1.62330
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.346113270
$B_2$	0.142428018
$B_3$	0.900477176
$C_1$	0.009717439
$C_2$	0.0501911619
$C_3$	111.95970300

### Constants of Formula for $dn/dT$

$D_0$	-8.15E-06
$D_1$	1.34E-08
$D_2$	-9.22E-12
$E_0$	8.57E-07
$E_1$	8.26E-10
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.243

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	-2.1	-0.9	0.4	-4.2	-3.1	-1.8
+20/+40	-2.0	-0.7	0.8	-3.3	-2.1	-0.6
+60/+80	-1.8	-0.3	1.3	-2.8	-1.4	0.1

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.530	0.200
2325	0.630	0.320
1970	0.870	0.710
1530	0.992	0.979
1060	0.999	0.998
700	0.997	0.993
660	0.995	0.987
620	0.993	0.983
580	0.991	0.977
546	0.986	0.966
500	0.973	0.930
460	0.930	0.830
436	0.820	0.610
420	0.660	0.350
405	0.380	0.090
400	0.280	0.040
390	0.090	
380		
370		
365		
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

$\lambda_{80} / \lambda_5$  45/39

### Remarks

lead containing glass type  
suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2355
$P_{C,s}$	0.4930
$P_{d,C}$	0.2946
$P_{e,d}$	0.2370
$P_{g,F}$	0.5803
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.2324
$P'_{C,s}$	0.5322
$P'_{d,C'}$	0.2451
$P'_{e,d}$	0.2339
$P'_{g,F'}$	0.5139
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0056
$\Delta P_{C,s}$	-0.0028
$\Delta P_{F,e}$	0.0009
$\Delta P_{g,F}$	0.0036
$\Delta P_{i,g}$	

### Chemical Properties

CR	44622
FR	2
SR	3.4
AR	2.2
PR	3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	10.7
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	11.4
$T_g$ [°C]	474
$T_{10}^{13}$ [°C]	462
$T_{10}^{7.6}$ [°C]	606
$c_p$ [J/(g·K)]	0.580
$\lambda$ [W/(m·K)]	0.750
$\rho$ [g/cm <sup>3</sup> ]	3.30
$E$ [ $10^3$ N/mm <sup>2</sup> ]	56
$\mu$	0.242
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	2.80
$HK_{0.1/20}$	410
HG	2



## SF6G05 809253.520

 $n_d = 1.80906$ 
 $v_d = 25.27$ 
 $n_F - n_C = 0.032015$ 
 $n_e = 1.81661$ 
 $v_e = 25.07$ 
 $n_F - n_C = 0.032570$ 

### Refractive Indices

	$\lambda$ [nm]	
$n_{2325.4}$	2325.4	1.75661
$n_{1970.1}$	1970.1	1.76163
$n_{1529.6}$	1529.6	1.76797
$n_{1060.0}$	1060.0	1.77741
$n_t$	1014.0	1.77879
$n_s$	852.1	1.78524
$n_r$	706.5	1.79491
$n_C$	656.3	1.79988
$n_{C'}$	643.8	1.80131
$n_{632.8}$	632.8	1.80265
$n_D$	589.3	1.80878
$n_d$	587.6	1.80906
$n_e$	546.1	1.81661
$n_F$	486.1	1.83190
$n_{F'}$	480.0	1.83387
$n_g$	435.8	
$n_h$	404.7	
$n_i$	365.0	
$n_{334.1}$	334.1	
$n_{312.6}$	312.6	
$n_{296.7}$	296.7	
$n_{280.4}$	280.4	
$n_{248.3}$	248.3	

### Constants of Dispersion Formula

$B_1$	1.621139420
$B_2$	0.506586092
$B_3$	10.403229800
$C_1$	0.011347899
$C_2$	0.0535840223
$C_3$	1118.83658000

### Constants of Formula for $dn/dT$

$D_0$	6.90E-06
$D_1$	1.76E-08
$D_2$	-3.17E-11
$E_0$	1.89E-06
$E_1$	1.50E-09
$\lambda_{TK}$ [ $\mu\text{m}$ ]	0.256

### Temperature Coefficients of the Refractive Index

[°C]	$\Delta n_{rel}/\Delta T$ [ $10^{-6}/K$ ]			$\Delta n_{abs}/\Delta T$ [ $10^{-6}/K$ ]		
	1060.0	e	g	1060.0	e	g
-40/-20	6.4	10.3		4.0	7.8	
+20/+40	7.0	11.4		5.5	9.8	
+60/+80	7.5	12.1		6.3	10.9	

### Internal Transmittance $\tau_i$

$\lambda$ [nm]	$\tau_i$ [10mm]	$\tau_i$ [25mm]
2500	0.850	0.660
2325	0.880	0.720
1970	0.965	0.910
1530	0.995	0.987
1060	0.998	0.994
700	0.985	0.962
660	0.980	0.950
620	0.972	0.930
580	0.958	0.900
546	0.920	0.810
500	0.640	0.330
460	0.090	0.080
436		
420		
405		
400		
390		
380		
370		
365		
350		
334		
320		
310		
300		
290		
280		
270		
260		
250		

### Color Code

 $\lambda_{70} / \lambda_{50} \quad 52/46$ 

### Remarks

lead containing glass type  
suitable for precision molding

### Relative Partial Dispersion P

$P_{s,t}$	0.2013
$P_{C,s}$	0.4574
$P_{d,C}$	0.2866
$P_{e,d}$	0.2358
$P_{g,F}$	0.6121
$P_{i,h}$	

### Relative Partial Dispersion P'

$P'_{s,t}$	0.1979
$P'_{C,s}$	0.4933
$P'_{d,C'}$	0.2380
$P'_{e,d}$	0.2318
$P'_{g,F'}$	0.5409
$P'_{i,h}$	

### Deviation of Rel. Partial Disp.

#### $\Delta P$ from the normal line

$\Delta P_{C,t}$	-0.0062
$\Delta P_{C,s}$	-0.0044
$\Delta P_{F,e}$	0.0025
$\Delta P_{g,F}$	0.0108
$\Delta P_{i,g}$	

### Chemical Properties

CR	4
FR	3
SR	51.3
AR	2.3
PR	3.3

### Other Properties

$\alpha_{-30/+70^\circ\text{C}}$ [ $10^{-6}/K$ ]	7.8
$\alpha_{+20/+300^\circ\text{C}}$ [ $10^{-6}/K$ ]	8.8
$T_g$ [°C]	427
$T_{10}^{13}$ [°C]	
$T_{10}^{7.6}$ [°C]	529
$c_p$ [J/(g·K)]	
$\lambda$ [W/(m·K)]	
$\rho$ [g/cm <sup>3</sup> ]	5.20
$E$ [ $10^3$ N/mm <sup>2</sup> ]	
$\mu$	
$K$ [ $10^{-6}$ mm <sup>2</sup> /N]	
HK <sub>0.1/20</sub>	360

**schott.com**

Hattenbergstrasse 10, 55122 Mainz, Germany  
Phone +49 (0)6131/66-1812, [info.optics@schott.com](mailto:info.optics@schott.com)