# SCHOTT Glass and Glass-Ceramic Sealants for Technical Ceramics in High-Temperature Applications

### **Product Information**

Aluminum oxide, zirconium oxide and silicon carbide have high temperature resistance. Hence, these ceramics are commonly used in high-temperature sensor applications such as in the combustion chamber or exhaust track of automobiles.

SCHOTT has developed special glasses and glass-ceramics for the joining of these technical ceramics. The sealants are stable at elevated temperatures and are chemically resistant, thereby contributing to the stability of the ceramic applications over an extended period of time.

#### **Advantages**

- CTE-matched sealing glasses for Al<sub>2</sub>O<sub>3</sub>, ZrO<sub>2</sub> and SiC substrates
- Sealing glasses are available for operating temperatures in the range 530 1040 °C and CTE in the range  $4.6 10.1 \ 10^{-6}/K$
- Seals can be achieved through conventional heating (in furnace) as well as through laser welding
- Glass sealants have excellent electrical insulation
- Sealants are available in powder, paste and preform formats



Joining of SiC ceramic with SCHOTT sealing glass.

| Sealing Partner                | SCHOTT<br>Glass Number | CTE* (10 <sup>-6</sup> /K for<br>200 – 300 °C) | Т <sub>д</sub> (°С) | Sealing<br>temperature (°C) | Maximum operating<br>temperature (°C) |
|--------------------------------|------------------------|--|---------------------|-----------------------------|---------------------------------------|
| SiC                            | 8253                   | 4.6 (glassy)                                   | 785                 | 1320                        | 735 (glassy)                          |
| Al <sub>2</sub> O <sub>3</sub> | G018-266               | 6.9 (glassy)                                   | 585                 | 770                         | 530 (glassy)                          |
|                                | G018-346               | 7.3 (glassy)                                   | 720                 | 1270                        | 670 (glassy)                          |
|                                | G018-358               | 8.5 (glassy)   8.8 (p.c.)**                    | 658                 | 940                         | 600 (glassy)   1040 (p.c.)**          |
| ZrO <sub>2</sub>               | G018-339               | 9.2 (p.c.)**                                   | 627                 | 990                         | 760 (p.c.)**                          |
|                                | G018-311               | 9.1 (glassy)   9.8 (p.c.)**                    | 622                 | 850                         | 560 (glassy)   880 (p.c.)**           |
|                                | G018-340               | 10.1 (glassy)   10.1 (p.c.)**                  | 602                 | 850                         | 550 (glassy)   920 (p.c.)**           |

\* CTE = coefficient of thermal expansion \*\* p.c. = partially crystalline



## SCHOTT Glass and Glass-Ceramic Sealants for Technical Ceramics in High-Temperature Applications

SCHOTT sealants are available in 2 different states due to differences in the processing method:

#### 1. Glassy seals

Advantage: Short processing time



 Partially crystalline seals through an optimized heating and cooling program allowing for crystallization to take place.
Advantage: Stable at higher operating temperatures





Sealing of the technical ceramic can be achieved through a conventional temperature program in a furnace or through laser welding.

Photo courtesy of Institute for Power Engineering, TU Dresden, Germany

Electronic Packaging SCHOTT AG Christoph-Dorner-Strasse 29 84028 Landshut Germany Phone: +49 (0)871/826-702 Fax: +49 (0)3641/28889090 info.glass@schott.com

www.schott.com/epackaging

