

CONTURAX[®] Pro

Technical Data

Glass Type/Application	Borosilicate glass 3.3 acc. to DIN ISO 3585, chemically highly resistant, high thermal shock resistance. Precision drawn profile tubing on rectangular and non-rectangular shape.		
Physical Data (approx. value)	Coefficient of mean linear thermal expansion $\alpha(20^{\circ}\text{C}; 300^{\circ}\text{C})$ (ISO 7991)	3.3	10^{-6}K^{-1}
	Transformation temperature T_g (ISO 7884-8)	525	$^{\circ}\text{C}$
	Glass temperature at viscosity η in dPa·s		
	10^{13} (annealing point) (ISO 7884-4)	560	$^{\circ}\text{C}$
	$10^{7.6}$ (softening point) (ISO 7884-3)	825	$^{\circ}\text{C}$
	10^4 (working point) (ISO 7884-2)	1260	$^{\circ}\text{C}$
	Stress-optical coefficient K (DIN 52314)	4.0	$10^{-6}\text{mm}^2\cdot\text{N}^{-1}$
	Density ρ at 25°C	2.23	$\text{g}\cdot\text{cm}^{-3}$
	Modulus of elasticity E (Young's modulus)	63	$10^3\text{N}\cdot\text{mm}^{-2}$
	Poisson's ratio μ	0.2	
	Thermal conductivity λ_w at 90°C	1.2	$\text{W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$
	Log of the electric volume resistivity ($\Omega\cdot\text{cm}$)		
	at 250°C	8.0	
	at 350°C	6.5	
	t_{k100} (DIN 52326)	250	$^{\circ}\text{C}$
	Dielectric constant ϵ for 1 MHz at 25°C	4.6	
	Dielectric loss factor $\tan d$ for 1 MHz at 25°C	37	10^{-4}
	Refractive index n_d ($\lambda = 587.6\text{ nm}$)	1.473	
Chemical Resistance	Hydrolytic resistance (ISO 719)	Class	HGB 1
	Acid resistance (DIN 12116)	Class	S1
	Alkali resistance (ISO 695)	Class	A2
	The heavy metal content for the elements lead, cadmium, mercury and hexavalent chromium is below 100 ppm.		

schott.com

CONTURAX[®] is a registered trademark of SCHOTT AG
PT_TTS_1025 EN / index 2 / 04.12.2025
Business Unit Tubing / 02/2025

SCHOTT