# Glass 8230

## Technical Data

| | | | |
|---|---|---|---|
| Glass Type/Application | Intermediate sealing glass.<br>Sealing to glass 8229 and glass 8330. | | |
| Physical Data<br>(approx. value) | Coefficient of mean linear thermal expansion<br>α(20°C; 300°C) (ISO 7991) | 2.7 | $10^{-6}K^{-1}$ |
| | Transformation temperature $T_g$ (ISO 7884-8) | 570 | °C |
| | Glass temperature at viscosity η in dPa·s | | |
| | $10^{13}$ (annealing point) (ISO 7884-4) | 590 | °C |
| | $10^{7.6}$ (softening point) (ISO 7884-3) | 915 | °C |
| | $10^{4}$ (working point) (ISO 7884-2) | 1425 | °C |
| | Stress-optical coefficient K (DIN 52314) | - | $10^{-6}mm^2 \cdot N^{-1}$ |
| | Density ρ at 25°C | 2.19 | $g \cdot cm^{-3}$ |
| | Modulus of elasticity E (Young's modulus) | - | $10^3 N \cdot mm^{-2}$ |
| | Poisson's ratio μ | - | |
| | Thermal conductivity $\lambda_w$ at 90°C | - | $W \cdot m^{-1} \cdot K^{-1}$ |
| | Log of the electric volume resistivity (Ω·cm) | | |
| | at 250°C | - | |
| | at 350°C | - | |
| | $t_{k100}$ (DIN 52326) | 255 | °C |
| | Dielectric constant ε for 1 MHz at 25°C | - | |
| | Dielectric loss factor tan d for 1 MHz at 25°C | - | $10^{-4}$ |
| | Refractive index $n_d$ (λ = 587.6 nm) | - | |
| Chemical Resistance | Hydrolytic resistance (ISO 719) | Class | - |
| | Acid resistance (DIN 12116) | Class | - |
| | Alkali resistance (ISO 695) | Class | - |

The heavy metal content for the elements lead, cadmium, mercury and hexavalent chromium is below 100 ppm.