

DUROBAX® clear

Technical Data

GlassType/Application	Neutral glass tubing, chemically highly resistant Containers, test tubes, pipettes, chemical and technical apparatus		
Physical Data (approx. value)	Coefficient of mean linear thermal expansion $\alpha(20^\circ\text{C}; 300^\circ\text{C})$ (ISO 7991)	4.9	10^{-6}K^{-1}
	Transformation temperature T_g (ISO 7884-8).....	565	°C
	Glass temperature at viscosity η in $\text{dPa}\cdot\text{s}$		
	10^{13} (annealing point) (ISO 7884-4).....	565	°C
	$10^{7.6}$ (softening point) (ISO 7884-3).....	785	°C
	10^4 (working point) (ISO 7884-2).....	1160	°C
	Stress-optical coefficient K (DIN 52314).....	3.4	$10^{-6}\text{mm}^2\cdot\text{N}^{-1}$
	Density ρ at 25°C	2.34	$\text{g}\cdot\text{cm}^{-3}$
	Modulus of elasticity E (Young's modulus)	73	$10^3\text{N}\cdot\text{mm}^{-2}$
	Poisson's ratio μ	0.2	
	Thermal conductivity λ_w at 90°C	1.2	$\text{W}\cdot\text{m}^{-1}\cdot\text{K}^{-1}$
	Log of the electric volume resistivity ($\Omega\cdot\text{cm}$)		
	at 250°C	7.4	
	at 350°C	6.0	
	t_{k100}	215	°C
	Dielectric constant ϵ for 1 MHz at 25°C	5.7	
	Dielectric loss factor $\tan \delta$ for 1 MHz at 25°C	80	10^{-4}
	Refractive index n_d ($\lambda = 587.6\text{ nm}$)	1.492	
Chemical Resistance	Hydrolytic resistance (ISO 719)	Class	HGB 1
	Acid resistance (DIN 12116)	Class	S 1
	Alkali resistance (ISO 695)	Class	A 2

The heavy metal content for the elements lead, cadmium, mercury and hexavalent chromium is below 100 ppm

DUROBAX® is a registered trade mark
of SCHOTT
PT_TTS_1015 GB

Business Unit Tubing / 9/2017

SCHOTT
glass made of ideas